

BS EN 12758:2011



BSI Standards Publication

Glass in building — Glazing and airborne sound insulation — Product descriptions and determination of properties

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 12758:2011. It supersedes BS EN 12758:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/520/4, Properties and glazing methods.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 71030 8

ICS 81.040.20; 91.120.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2011.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 12758

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2011

ICS 81.040.20; 91.120.20

Supersedes EN 12758:2002

English Version

Glass in building - Glazing and airborne sound insulation - Product descriptions and determination of properties

Verre dans la construction - Vitrages et isolement
acoustique - Descriptions de produits et détermination des
propriétés

Glas im Bauwesen - Glas und Luftschalldämmung -
Produktbeschreibungen und Bestimmung der
Eigenschaften

This European Standard was approved by CEN on 11 December 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions and symbols	6
3.1	Terms and definitions	6
3.2	Symbols	7
4	Glass products.....	7
4.1	Basic glasses	7
4.2	Special basic glasses	8
4.3	Processed glasses.....	8
4.3.1	Strengthened glasses	8
4.3.2	Thermally toughened safety glasses.....	8
4.3.3	Laminated glasses.....	8
4.3.4	Coated glasses.....	9
4.3.5	Insulating glass units (IGU)	9
5	Test methods.....	9
5.1	General.....	9
5.2	Reference curves	10
5.2.1	General.....	10
5.2.2	Reference IGU 6(16)6.....	10
5.2.3	Reference IGU 10 (16) 44-2 laminated glass with acoustic interlayer <i>S</i>	10
5.2.4	Maximum standard deviation of repeatability	11
5.3	Extension rules	12
5.3.1	General.....	12
5.3.2	Basic and special basic glasses	12
5.3.3	Laminated/laminated safety glass	13
5.3.4	Coated glasses.....	13
5.3.5	Insulating glass units	13
6	Sound insulation rating and classification	13
6.1	Sound insulation rating.....	13
6.2	Statement of acoustic performance of glass	13
6.3	Specification of glazing requirements.....	14
7	Typical performance data	14
Annex A (normative) Description of Reference Insulating Glass Units		16
Annex B (informative) Glazing recommendations		18
Bibliography		19

Foreword

This document (EN 12758:2011) has been prepared by Technical Committee CEN/TC 129 “Glass in building”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2011, and conflicting national standards shall be withdrawn at the latest by July 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document replaces EN 12758:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard assigns sound insulation values to all transparent, translucent and opaque glass products, described in the European Standards for basic, special basic or processed glass products, when intended to be used in glazed assemblies in buildings, and which exhibit properties of acoustic protection, either as a prime intention or as a supplementary characteristic.

This document outlines the procedure, by which glass products may be rated, according to their acoustic performance which enables assessment of compliance with the acoustic requirements of buildings.

Rigorous technical analysis of measurement data remains an option, but this standard is intended to enable the derivation of simpler indices of performance, which can be adopted with confidence by non-specialists.

By adopting the principles of this standard the formulation of acoustic requirements in Building Codes and for product specification to satisfy particular needs for glazing is simplified.

It is recognised that the acoustic test procedures contained within EN ISO 10140 relate only to glass panes and their combinations. Although the same principles should be followed as closely as possible, it is inevitable that some compromises are necessary, because of the bulkier construction of other glazing types, e.g. glass blocks, paver units, channel-shaped glass, structural glazing and structural sealant glazing. Guidelines on how to adapt the test procedures for these glass products are offered in Clause 4.

All the considerations of this standard relate to panes of glass/glass products alone. Incorporation of them into windows may cause changes in acoustic performance as a result of other influences, e.g. frame design, frame material, glazing material/method, mounting method, air tightness, etc. Measurements of the sound insulation of complete windows (glass and frame) may be undertaken to resolve such issues.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 572-1, *Glass in building — Basic soda lime silicate glass products — Part 1: Definitions and general physical and mechanical properties*

EN 572-2, *Glass in Building — Basic soda lime silicate glass products — Part 2: Float glass*

EN 572-3, *Glass in Building — Basic soda lime silicate glass products — Part 3: Polished wired glass*

EN 572-4, *Glass in building — Basic soda lime silicate glass products — Part 4: Drawn sheet glass*

EN 572-5, *Glass in Building — Basic soda lime silicate glass products — Part 5: Patterned glass*

EN 572-6, *Glass in building — Basic soda lime silicate glass products — Part 6: Wired patterned glass*

EN 572-7, *Glass in Building — Basic soda lime silicate glass products — Part 7: Wired or unwired channel shaped glass*

EN 1051-1, *Glass in building — Glass blocks and glass pavers — Part 1: Definitions and description*

EN 1096-1, *Glass in building — Coated glass — Part 1: Definitions and classification*

EN 1279-1, *Glass in Building — Insulating glass units — Part 1: Generalities, dimensional tolerances and rules for the system description*

EN 1748-1-1, *Glass in building — Special basic products — Borosilicate glasses — Part 1-1: Definition and general physical and mechanical properties*

EN 1748-2-1, *Glass in building — Special basic products — Glass ceramics — Part 2-1: Definitions and general physical and mechanical properties*

EN 1863-1, *Glass in building — Heat strengthened soda lime silicate glass — Part 1: Definition and description*

EN 12150-1, *Glass in building — Thermally toughened soda lime silicate safety glass — Part 1: Definition and description*

EN 12337-1, *Glass in building — Chemically strengthened soda lime silicate glass — Part 1: Definition and description*

EN 13024-1, *Glass in building — Thermally toughened borosilicate safety glass — Part 1: Definition and description*

EN 14178-1, *Glass in building — Basic alkaline earth silicate glass products — Part 1: Float glass*

EN 14179-1, *Glass in building — Heat soaked thermally toughened soda lime silicate safety glass — Part 1: Definition and description*

EN 14321-1, *Glass in building — Thermally toughened alkaline earth silicate safety glass — Part 1: Definition and description*

prEN 15681-1, *Glass in building — Basic alumino silicate glass products — Part 1: Definitions and general physical and mechanical properties*

prEN 15682-1, *Glass in building — Heat soaked thermally toughened alkaline earth silicate safety glass — Part 1: Definition and description*

prEN 15683-1, *Glass in building — Thermally toughened soda lime silicate channel shaped safety glass — Part 1: Definition and description*

EN ISO 10140:2010 (all parts), *Acoustics — Laboratory measurement of sound insulation of building elements*

EN ISO 717-1:1996, *Acoustics — Rating of sound insulation in buildings and of building elements — Part 1: Airborne sound insulation (ISO 717-1:1996)*

EN ISO 12543-1, *Glass in building — Laminated glass and laminated safety glass — Part 1: Definitions and description of component parts (ISO 12543-1:1998)*

EN ISO 12543-2, *Glass in building — Laminated glass and laminated safety glass — Part 2: Laminated safety glass (ISO 12543-2:1998)*

EN ISO 12543-3, *Glass in building — Laminated glass and laminated safety glass — Part 3: Laminated glass (ISO 12543-3:1998)*

ISO 140-2:1991, *Acoustics — Measurement of sound insulation in buildings and of building elements — Part 2: Determination, verification and application of precision data*

ISO 16940, *Glass in building — Glazing and airborne sound insulation — Measurement of the mechanical impedance of laminated glass*

3 Terms and definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 10140:2010, ISO 140-2:1991 and EN ISO 717-1:1996 together with the following apply:

3.1.1

glass product

product manufactured from glass, i.e. basic glass, special basic glass, processed glass, for use in buildings/constructions

NOTE See Clause 4.

3.1.2

glazed assembly

combination of frame/support and glass product used for the determination of the acoustic performance

NOTE 1 The following are examples of such assemblies:

- 1) Glass block walls;
- 2) Paver unit panels;
- 3) Channel shaped glass panels, single or dual glazed;
- 4) Structural sealant glazing;
- 5) Structural assemblies.

NOTE 2 The dimensions of glass blocks, paver units and channel shaped glass do not allow them to be subjected to the standard test regime.

NOTE 3 Structural sealant glazing: is a ‘frameless’ glazing system that uses structural sealant to restrain the glazing. This method of restraint will influence the acoustic performance of the glass product.

NOTE 4 Structural assemblies consist of glass products that are connected by bolted metal fittings to one another and to structural supports, e.g. fin, etc.

3.1.3

single glazing

single pane of glass, that includes annealed, strengthened/toughened (by heat or chemical treatment), laminated/laminated safety and coated glasses, that is glazed into an opening

3.1.4

multiple glazing

two or more panes of glass that are separated by cavities either sealed or unsealed

NOTE 1 Multiple glazing incorporating hermetically sealed cavities, e.g. double glazing, triple glazing, etc., and are known as Insulating Glass Units.

NOTE 2 Multiple glazing with unsealed cavities when in an opening is known as coupled glazing, coupled or double windows. If in a proprietary frame it is known as secondary sash.

NOTE 3 When two panes of channel shaped glass are glazed flange to flange it is known as dual glazed.

3.1.5

insulating glass unit (IGU)

assembly consisting of at least two panes of glass, separated by one or more spacers, hermetically sealed along the periphery, mechanically stable and durable

- NOTE 1 See EN 1279-1.
- NOTE 2 Systems are available where the spacer and hermetic seal are included within a single edge sealing system.
- NOTE 3 The hermetically sealed cavity may contain dry air or a number of other gas types, e.g. argon, xenon, krypton, etc.

3.1.6 laminated/laminated safety glass
assembly consisting of one sheet of glass with one or more sheets of glass and/or plastics glazing sheet material joined together with one or more interlayers

NOTE See EN ISO 12543-1.

3.1.7 interlayer
layer or material acting as an adhesive and separator between plies of glass and/or plastics glazing sheet material

- NOTE 1 It can also give additional performance to the finished product e.g. impact resistance, resistance to fire, solar control, acoustic insulation.
- NOTE 2 There are many types of interlayer. The most common ones are organic. However, for certain products, with resistance to fire performance, the interlayers are inorganic.

3.1.8 acoustic interlayer
interlayer that increases the Sound Reduction Index of the laminated glass

NOTE The interlayer may be evaluated in accordance to ISO 16940.

3.1.9 acoustic interlayer for reference glazing
acoustic interlayer with a measured loss factor of the 1st mode of the beam above or equal to 0,25 when evaluated in accordance to ISO 16940

3.2 Symbols

R	Sound Reduction Index
R_w	Weighted Sound Reduction Index
R_{tr}	Sound Reduction Index for Traffic Noise
C	Spectrum Adaption Term
C_{tr}	Spectrum Adaption Term for Traffic Noise

4 Glass products

4.1 Basic glasses

These are glass products manufactured from soda lime silicate glass in accordance with EN 572-1 and consist of the following:

- Float glass EN 572-2

- Polished wired glass EN 572-3
- Drawn sheet glass EN 572-4
- Patterned glass EN 572-5
- Wired patterned glass EN 572-6
- Wired and unwired channel shaped glass EN 572-7
- Glass blocks and paver units EN 1051-1

4.2 Special basic glasses

These are glass products manufactured from a variety of compositions, which are in accordance with appropriate European standards, and consist of the following:

- Borosilicate glass EN 1748-1-1
- Glass ceramics EN 1748-2-1
- Alkaline earth silicate glass EN 14178-1
- Alumino silicate glass prEN 15681-1

4.3 Processed glasses

4.3.1 Strengthened glasses

These are soda lime silicate glasses that have been strengthened by thermal or chemical means and are as follows:

- Heat strengthened EN 1863-1
- Chemically strengthened EN 12337-1

4.3.2 Thermally toughened safety glasses

These are glasses that have been toughened by thermal treatment and are as follows:

- Thermally toughened soda lime silicate safety glass EN 12150-1
- Thermally toughened borosilicate safety glass EN 13024-1
- Heat soaked thermally toughened soda lime silicate safety glass EN 14179-1
- Thermally toughened alkaline earth silicate safety glass EN 14321-1
- Heat soaked thermally toughened alkaline earth silicate safety glass prEN 15682-1
- Thermally toughened soda lime silicate channel shaped safety glass prEN 15683-1

4.3.3 Laminated glasses

These are glasses that are in accordance with EN ISO 12543-1 and consist of the following:

- Laminated glass EN ISO 12543-3
- Laminated safety glass EN ISO 12543-2

4.3.4 Coated glasses

These are glass panes that have been coated and are in accordance with EN 1096-1.

NOTE Coated glass may be manufactured from any of the glass types referred to in 4.1, 4.2, 4.3.1, 4.3.2 or 4.3.3.

4.3.5 Insulating glass units (IGU)

These are hermetically sealed insulating glass units, containing air or other gas, that are in accordance with EN 1279-1.

NOTE An IGU may be manufactured from any of the glass types or combination of the glass types referred to in 4.1, 4.2, 4.3.1, 4.3.2, 4.3.3 or 4.3.4.

5 Test methods

5.1 General

Acoustic performance data shall be obtained under the conditions specified by EN ISO 10140 and EN ISO 717-1. For laminated glasses, owing to temperature dependency, the specimen temperature shall be $(21 \pm 2)^{\circ}\text{C}$.

NOTE 1 For best reproducibility it is recommended that the test opening for glass panes, as described in EN ISO 10140, be adopted.

Some variation in panel size, etc., to those in EN ISO 10140, may be necessary for the testing of glazed assemblies, i.e. glass blocks, paver units, channel shaped glass, structural sealant glazing and structural assemblies in order to include a valid representation of all their features. Acoustic measurements of the performance of these products shall be made on assemblies or arrays of them, and not on individual elements. Factors which influence testing are size, jointing, etc.

NOTE 2 For large mixed components it may be more appropriate to employ intensity measurement techniques, according to the advice of a specialist.

Test reports on the sound insulation of glazing shall be obtained from measurements made under the conditions specified in EN ISO 10140 or, as closely as possible, for some unconventional glass products or assemblies, as acknowledged above. In all cases, constructional details shall be included, with statements, where appropriate, of:

- a) type of glass;
- b) glass thickness(es);
- c) airspace(s)/cavity width(s);
- d) gas filling - type and concentration;
- e) for laminated glass, glass / plastics glazing sheet materials / interlayer build up - type, thickness(es) and number;
- f) for laminated glass, the specimen temperature;

- g) description of the particular mounting conditions employed for assemblies of glass blocks, pavers units, channel-shaped glass, structural sealant glazing, and structural assemblies due to the necessary deviation from the prescribed conditions of EN ISO 10140.

5.2 Reference curves

5.2.1 General

These shall be determined by measuring two reference Insulating Glass Units (IGU), as defined in 5.2.2 and 5.2.3. Reference curves shall be determined when the test equipment is set up and then checked at least once a year or before each new glazing measurement.

In case of doubt concerning the results obtained using the reference IGUs then a specimen of single glass , i.e. 10 mm float glass in accordance with EN 572-1 and -2, shall be measured to check repeatability.

5.2.2 Reference IGU 6(16)6

The Sound Transmission Loss (STL) of a reference 6(16)6 IGU as described in Annex A; Figure A.1 shall be in the range as given in Table 1:

Table 1 — Sound transmission loss of the reference IGU 6(16)6

frequency (Hz)	min value (dB)	max value (dB)
100	20,0	25,3
125	15,9	21,5
160	17,9	21,1
200	17,3	19,7
250	19,7	22,9
315	23,5	26,4
400	27,2	29,3
500	30,4	32,7
630	33,5	35,6
800	36,9	38,6
1 000	38,4	39,9
1 250	37,8	39,7
1 600	36,6	38,4
2 000	31,7	33,7
2 500	31,5	33,0
3 150	34,9	37,4

When the absolute deviations between the numbers in Table 1 and the measured values are summed then the total deviation cannot exceed 4,0 dB. All calculations shall be undertaken with an accuracy of 0,1.

5.2.3 Reference IGU 10 (16) 44-2 laminated glass with acoustic interlayer S

The STL of a reference IGU made up of 44-2(16)10 shall be in the range as given in Table 2.

The laminated glass being manufactured with an acoustic interlayer *S*. The IGU is described in Annex A; Figure A.2

NOTE 1 A laminated glass make up designated 44-2 means 2 x 4 mm glass and a 0,76 mm interlayer.

Table 2 — Sound transmission loss of the reference IGU 10 (16) 44-2 laminated glass with acoustic interlayer *S*

frequency (Hz)	min value (dB)	max value (dB)
100	25,4	31,5
125	21,2	27,9
160	25,7	29,4
200	27,5	30,4
250	32,4	36,4
315	32,6	35,8
400	37,3	40,4
500	39,7	42,8
630	42,3	45,0
800	43,9	46,4
1 000	43,6	45,8
1 250	43,3	46,2
1 600	45,7	48,1
2 000	47,9	51,0
2 500	48,9	51,9
3 150	49,4	52,0

When the absolute deviations between the numbers in Table 2 and the measured values are summed then the total deviation cannot exceed 4,0 dB. All calculations shall be undertaken with an accuracy of 0,1.

External reproducibility of R_w , R_w+C and R_w+C_{tr} of measurements done following the above rules will be ± 1 dB.

NOTE 2 This data results from a round robin covering 22 laboratories. The values have been obtained by taking the average value \pm one standard deviation.

5.2.4 Maximum standard deviation of repeatability

Maximum repeatability shall be in accordance with ISO 140-2 1991, as reproduced in Table 3.

Table 3 — Maximum standard deviation of repeatability

frequency	$\sigma_{\max.}$
100	1,61
125	1,43
160	1,25
200	1,25
250	0,89
315	0,89
400	0,71
500	0,71
630	0,54
800	0,54
1 000	0,54
1 250	0,54
1 600	0,54
2 000	0,54
2 500	0,54
3 150	0,54

5.3 Extension rules

5.3.1 General

The measured acoustic performance of glass products may be assumed to be unaffected when subjected to specific changes. Application of the following rules removes the necessity of further/extra testing in accordance with EN ISO 10140.

NOTE The use of these rules will ensure that the data used will always be conservative. If more accurate data is required, then the glass product should be measured.

5.3.2 Basic and special basic glasses

- No difference between soda lime silicate glass and other glass compositions;
- No difference between clear, white or body tinted glasses;
- Processing, i.e. heat strengthening, chemical strengthening, thermal toughening, has no effect;
- Surface treatment, i.e. sand blasting, acid etching, has no effect as long as the thickness stays within the allowable tolerance for the specific product;
- Patterned/cast glass can be assumed to be equivalent to the next lowest thickness, i.e. 6 mm patterned glass is described acoustically by the data for 5 mm single glass;
- Wired glass (polished or patterned) is treated as a single glass.

NOTE The wire mesh within wired glass has no influence on the acoustic performance.

5.3.3 Laminated/laminated safety glass

Laminated glass using an inorganic interlayer can be described acoustically by the data for a single glass of the same overall thickness.

NOTE 1 If data for a single glass of the same thickness is not available, then use the data for the next available lower thickness.

- Data for a glass product including laminated glass using organic acoustic interlayer may be adopted for a glass product including laminated glass using another acoustic interlayer as long as the measured loss factor of the 1st mode of the beam of both interlayers are equal to or greater than 0,20, when measured in accordance with ISO 16940.
- Data for a glass product including laminated glass using an interlayer may be taken for a glass product including laminated glass using another interlayer as long as the measured loss factor of the 1st mode of the beam is equal to or greater than that of the initial interlayer measured in accordance with ISO 16940.
- Thicknesses of laminated/laminated safety glasses are given in accordance with EN ISO 12543-5.

NOTE 2 The construction of a laminated glass should be known.

5.3.4 Coated glasses

- The application of a coating, in accordance with EN 1096-1, or thin film, will have no effect on the acoustic description of the glass substrate from which it was manufactured.
- A paint, silver (mirrors) or enamel coating can be treated as any other coating.

5.3.5 Insulating glass units

- The measured data for an air-filled or argon-filled IGU can apply to all IGUs, irrespective of being air-filled or argon-filled, for the same glass composition.
- The data for IGUs including organic sealants can be adopted for any other organic sealants.
- The same rule applies for spacers of the same width.

6 Sound insulation rating and classification

6.1 Sound insulation rating

The octave band values may be derived from third-octave-band data.

The procedures for deriving the values of R , R_w , C and C_{tr} are specified in EN ISO 717-1 and EN ISO 10140.

Proper evaluation of these parameters depends on the corresponding basic sound insulation data, i.e. SRI values, being obtained from measurements, in accordance with EN ISO 10140.

6.2 Statement of acoustic performance of glass

The R_w Index and corresponding spectrum adaptation terms, C and C_{tr} shall be stated, in accordance with EN ISO 717-1. Both spectrum adaptation terms shall be stated in brackets after the basic R_w Index and they shall be separated by a semi-colon as shown below:

$R_w (C ; C_{tr})$

As an example: the acoustic performance of 12 mm single glass as given in Table 4 is:

34 (0 ; -2) .

6.3 Specification of glazing requirements

Performance requirements may be either in terms, of the R_w Index alone, or as the sum of the R_w and the relevant spectrum adaptation term, the latter specification resulting in a closer indication of the required acoustic performance for particular applications:

- for urban road traffic noise, i.e. $R_{A,tr} = R_w + C_{tr}$.

For example, the $R_{A,tr}$ for 12 mm single glass determined from the data in Table 4 is:

34 + (-2) = 32 .

7 Typical performance data

In the absence of specific measured performance data from which to calculate R_w , C and C_{tr} generally accepted values are given.

Table 4 states the generally accepted values of R_w , C and C_{tr} for a range of glass products.

These tabulated values are derived from the mean value minus one standard deviation of typical measured data. As such, they represent conservative values which may be adopted in the absence of specific measured data, in accordance with Clause 5.

When using this table, it is essential to understand the following:

- a) These data refer to float glass or glass products made with float glass
- b) The data for the double glazing units can be adopted for air-, or argon-filled cavities.
- c) Over the cavity width range (6 - 16) mm, the corresponding acoustic data for a given glass combination are regarded as constant.
- d) For patterned glasses, whose thickness varies, the acoustic data, corresponding to the next lower thickness from its nominally assigned thickness, shall be adopted e.g. 6 mm patterned glass is described acoustically by the data for 5 mm single glass.
- e) For laminated glass with a non-plastic interlayer, the acoustic data corresponding to single glass of the same overall thickness shall be adopted. If such a product does not exist, the data corresponding to the next lower thickness is appropriate.
- f) The octave band values have been derived from third-octave-band data.
- g) The laminated glass data relates only to that with plastic interlayers.


For products not covered by Table 4, relevant test data shall be made available from which the corresponding values of R_w , C and C_{tr} may be derived.

Table 4 — Table of standard acoustic performance data

Glass Type and Thickness (mm)	Sound Reduction Index <i>R</i> (dB), at octave-band centre frequency (Hz) 125 250 500 1 000 2 000 4 000						Indices and adaptation terms <i>R</i> _w <i>C</i> <i>C</i> _{tr}		
Single glass:									
3	14	19	25	29	33	25	28	-1	-4
4	17	20	26	32	33	26	29	-2	-3
5	19	22	29	33	29	31	30	-1	-2
6	18	23	30	35	27	32	31	-2	-3
8	20	24	29	34	29	37	32	-2	-3
10	23	26	32	31	32	39	33	-2	-3
12	27	29	31	32	38	47	34	0	-2
Laminated glass ^a :									
6	20	23	29	34	32	38	32	-1	-3
8	20	25	32	35	34	42	33	-1	-3
10	24	26	33	33	35	44	34	-1	-3
12	24	27	33	32	37	46	35	-1	-3
16	26	31	30	35	43	51	36	-1	-3
20	30	32	31	35	46	56	37	-1	-3
24	31	31	31	38	49	56	38	-1	-3
Insulating glass units ^b :									
4/(6-16)/4	21	17	25	35	37	31	29	-1	-4
6/(6-16)/4	21	20	26	38	37	39	32	-2	-4
6/(6-16)/6	20	18	28	38	34	38	31	-1	-4
8/(6-16)/4	22	21	28	38	40	47	33	-1	-4
8/(6-16)/6	20	21	33	40	36	48	35	-2	-6
10/(6-16)/4	24	21	32	37	42	43	35	-2	-5
10/(6-16)/6	24	24	32	37	37	44	35	-1	-3
6/(6-16)/6 Laminated	20	19	30	39	37	46	33	-2	-5
6/(6-16)/10 Laminated	24	25	33	39	40	49	37	-1	-5
^a The data for laminated glasses is for one with an organic interlayer excluding acoustic interlayer.									
^b The construction of IGUs is given by Glass thickness/ Cavity width/ Glass type and thickness, when applicable.									

Annex A
(normative)

Description of Reference Insulating Glass Units




Key

Type 6 – 16 – 6, air filled

- 1 glass pane: float of nominal thickness of 6 mm
- 2 glass pane: float of nominal thickness of 6 mm
- 3 spacer bar: aluminium of nominal thickness of 16 mm
- 4 air space of nominal thickness of 16 mm
- 5 inner seals: butyl
- 6 outer seal: polysulfide

Figure A.1 — Description of reference IGU 6(16)6



Key

Type 10 – 16 –8 laminated with acoustic interlayer *S*, air filled

- 1 glass pane: float of nominal thickness of 10 mm
- 2 laminated glass pane: nominal thickness of 2×4 mm float assembled with acoustic interlayer *S*, nominal thickness of 0,76 mm
- 3 spacer bar: aluminium of nominal thickness of 16 mm
- 4 air space of nominal thickness of 16 mm
- 5 inner seals: butyl
- 6 outer seal: polysulfide

Figure A.2 — Description of reference IGU 10 (16) 44-2 laminated glass with acoustic interlayer *S*

Annex B
(informative)

Glazing recommendations

To maximise acoustic benefits, the laminated component of an insulating glass unit is normally glazed to the warmer side, i.e. usually to the inside of a building.

With insulating glass units incorporating monolithic glass of differing thicknesses there is no preferred way round, i.e. acoustic benefit is not dependent on which glass is outermost.

Bibliography

- [1] EN ISO 12543-5, *Glass in building — Laminated glass and laminated safety glass — Part 5: Dimensions and edge finishing (ISO 12543-5:1998)*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™