

BS EN 14906:2012



BSI Standards Publication

# Leather — Leather for automotive — Test methods and testing parameters

**bsi.**

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 14906:2012. It supersedes DD CEN/TS 14906:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 72630 9

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2012.

Amendments issued since publication

Date	Text affected
<hr/>	



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 14906**

May 2012

ICS 59.140.30

Supersedes CEN/TS 14906:2004

English Version

**Leather - Leather for automotive - Test methods and testing parameters**

Cuir - Cuir pour l'automobile - Méthodes d'essai

Leder - Automobilleleder - Prüfverfahren und Prüfparameter

This European Standard was approved by CEN on 27 April 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	3
Introduction.....	4
1 Scope .....	5
2 Normative references.....	5
3 Terms and definitions .....	6
4 General principles.....	6
5 Sampling.....	6
6 Conditioning and sampling preparation .....	7
7 List of test methods.....	7
8 Test reports .....	9
Bibliography.....	10

## Foreword

This document (EN 14906:2012) has been prepared by Technical Committee CEN/TC 289 “Leather”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2012, and conflicting national standards shall be withdrawn at the latest by November 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 14906:2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **Introduction**

This document was prepared by CEN/TC 289 "Leather" in order to provide the leather and the automotive industries with methods to be used for testing on which sellers and buyers can base their specifications and negotiations.



## 1 Scope

This European Standard gives guidelines to select the test methods to assess the performance of leather for automotive. This document also specifies the sampling and conditioning procedures of specimens.

NOTE Regulations on chemical substances in consumer goods might differ from country to country requiring for any given market a special attention to restricted substances.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15987:2011, *Leather — Terminology — Key definitions for the leather trade*

EN 20105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour (ISO 105-A02)*

EN ISO 105-B06, *Textiles — Tests for colour fastness — Part B06: Colour fastness and ageing to artificial light at high temperatures: Xenon arc fading lamp test (ISO 105-B06)*

EN ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location (ISO 2418)*

EN ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning (ISO 2419)*

EN ISO 2420, *Leather — Physical and mechanical tests — Determination of apparent density (ISO 2420)*

EN ISO 2589, *Leather — Physical and mechanical tests — Determination of thickness (ISO 2589)*

EN ISO 3376, *Leather — Physical and mechanical tests — Determination of tensile strength and percentage extension (ISO 3376)*

EN ISO 3377-1, *Leather — Physical and mechanical tests — Determination of tear load — Part 1: Single edge tear (ISO 3377-1)*

EN ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples (ISO 4044)*

EN ISO 5402-1, *Leather - Determination of flex resistance - Part 1: Flexometer method (ISO 5402-1)*

EN ISO 9237, *Textiles — Determination of permeability of fabrics to air (ISO 9237)*

EN ISO 11640, *Leather — Tests for colour fastness — Colour fastness to cycles of to-and-fro rubbing (ISO 11640)*

EN ISO 11644, *Leather — Test for adhesion of finish (ISO 11644)*

EN ISO 14087, *Leather — Physical and mechanical tests — Determination of bending force (ISO 14087)*

EN ISO 14268, *Leather — Physical and mechanical tests — Determination of water vapour permeability (ISO 14268)*

EN ISO 15700, *Leather — Tests for colour fastness — Colour fastness to water spotting (ISO 15700)*

EN ISO 15701, *Leather — Tests for colour fastness — Colour fastness to migration into plasticized poly(vinyl chloride) (ISO 15701)*





EN ISO 17071, *Leather — Physical and mechanical tests — Determination of fogging characteristics (ISO 17071)*

EN ISO 17074, *Leather — Physical and mechanical tests — Determination of resistance to horizontal spread of flame (ISO 17074)*

EN ISO 17076-2, *Leather — Determination of abrasion resistance — Part 2: Martindale ball plate method (ISO 17076-2)*

EN ISO 17186, *Leather — Physical and mechanical tests — Determination of surface coating thickness (ISO 17186)*

EN ISO 17226-3, *Leather — Chemical determination of formaldehyde content — Part 3: Determination of formaldehyde emissions from leather (ISO 17226-3)*

EN ISO 17227, *Leather — Physical and mechanical tests — Determination of dry heat resistance of leather (ISO 17227)*

EN ISO 17228, *Leather — Tests for colour fastness — Change in colour with accelerated ageing (ISO 17228)*

EN ISO 23910, *Leather — Physical and mechanical tests — Measurement of stitch tear resistance (ISO 23910)*

ISO 2588, *Leather — Sampling — Number of items for a gross sample*

ISO 26082-1, *Leather — Physical and mechanical test methods for the determination of soiling — Part 1: Rubbing (Martindale) method*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 15987:2011 and the following shall apply.

#### **3.1**

##### **upholstery**

seat and headrest

#### **3.2**

##### **trim**

armrest, dashboard, trim-panel, steering-wheel, gear-knob

### **4 General principles**

This document considers different types of leather intended for automotive upholstery, trims, such as steering-wheels/gear-knobs.

### **5 Sampling**

**5.1** Laboratory samples shall be located and identified in accordance with EN ISO 2418.

**5.2** The number of leather samples shall be in accordance with ISO 2588, if not otherwise agreed by the parties.



## 6 Conditioning and sample preparation

Leather samples shall be conditioned and prepared for physical, mechanical and fastness tests in accordance with EN ISO 2419.

Leather samples for chemical tests shall be conditioned and prepared in accordance with EN ISO 4044.

## 7 List of test methods

The following tables define test methods which should be used to test automotive leather. The parameters to be tested are divided in fundamental properties (Table 1) and complementary properties (Table 2).

**Table 1 — List of fundamental properties**

Basic property	Property	Test method	Comments
<b>Basic parameters</b>	Apparent density, mass per unit area	EN ISO 2420	
	Thickness	EN ISO 2589	
	Surface coating thickness	EN ISO 17186	
<b>Tensile properties</b>	Tensile strength	EN ISO 3376	
	Elongation at break	EN ISO 3376	
	Elongation at defined forces	EN ISO 3376	
	Tear load	EN ISO 3377-1	
	Adhesion of finish	EN ISO 11644	
	Stitch tear resistance	EN ISO 23910	
<b>Stiffness in bending</b>			
		EN ISO 14087	
<b>Durability /wear</b>	Flex resistance	EN ISO 5402-1	
	Abrasion	EN ISO 17076-2	
<b>Ageing</b>	Colour change by heat and hydrolytic ageing	EN ISO 17228	Conditions (temperature, humidity, time,...) to be defined by customer requirements
	Dimensional change by heat ageing	EN ISO 17227 (for shrinkage measurement)	Conditions (temperature, humidity, time,...) to be defined by customer requirements
		EN ISO 17228	
		(ageing procedures)	
<b>Light fastness</b>	Colour fastness to artificial light at high temperatures	EN ISO 105-B06	Exposure condition 3 – normal; apparatus type G; filter system BS/SL;



			delta E $4.3 \pm 0.4$ for blue scale 6 for each cycle (exposed blue wool scale 6 shall be supported by a non exposed blue wool scale 6); sample evaluation: exposed region against original sample (without any ageing) according to EN 20105-A02
	Colour fastness and ageing to artificial light at high temperatures	EN ISO 105-B06	Exposure condition 3 – normal; apparatus type C; filter system BS/SL; delta E $4.3 \pm 0.4$ for blue scale 6 for each cycle (exposed blue wool scale 6 shall be supported by a non exposed blue wool scale 6); sample evaluation: exposed region against original sample (without any ageing) according to EN 20105-A02

<b>Fastness</b>	Fastness to and fro rubbing	EN ISO 11640	
	Fastness to water spotting	EN ISO 15700	Test surface to be defined amount of water to be defined

<b>Emission behaviour</b>	Fogging	EN ISO 17071	Gravimetric procedures only drying 7 days minimum
	Volatile organic compounds (VOC)	No EN or ISO standard available at present	See Note 1.
	Odour	No EN or ISO standard available at present	See Note 2.
	Formaldehyde emission	EN ISO 17226-3	

<b>Others</b>	Resistance to horizontal spread of flame	EN ISO 17074	Further requirements according to legislation are discussed with customers
	Soiling and cleanability	ISO 26082-1	
	Loose grain effect	No EN or ISO standard available at present	See Note 3.

NOTE 1 Widely applied test methods for the determination of VOC are described in VDA 277 (*Non-metallic materials in automotive interior trim Determination of emission of organic compounds*) and VDA 278 (*Thermal Desorption Analysis of Organic Emissions for the Characterization of Non-Metallic Materials for Automobiles*).

NOTE 2 A widely applied test method for odour testing is described in VDA 270 (*Determination of the odour characteristics of trim materials in motor vehicles*).

NOTE 3 A widely applied test method for determination of loose grain effect is described in VDA 230-205 (*Automotive leather Determination loose grain effect*).

Table 2 — List of complementary properties

Basic property	Property	Test method	Comments
<b>Fastness</b>	Colour fastness to migration	EN ISO 15701	
	Resistance to insect repellents	EN ISO 11640	10 cycles, 10 % elongation, 0.4 ml DEET (100 %, CAS 134-62-3) on the felt by pipette
	Resistance to sun lotion	No EN or ISO standard available at present	Standardized sun lotion is currently not available
<b>Others</b>	Water vapour permeability	EN ISO 14268	Without pre-treatment
	Stick-slip-behaviour	No EN or ISO standard available at present	See Note.
	Permeability to air	EN ISO 9237	For perforated leather only, (test area 100 cm <sup>2</sup> , pressure drop 100 Pa, leather surface to suction

side, without correction of side effect

NOTE A widely applied test method for determination of stick slip effect is described VDA 230-206-1 (*Examination of the stick-slip behaviour of material pairs — General section*) and VDA 230-206-2 (*Examination of the stick-slip behaviour of material pairs — Specific section Leather: Leather against Leather*).

## 8 Test reports

The test reports shall contain at least the information defined in used standard test methods. The test reports should also include additional information (e.g. special evaluation of specimens) requested in specifications.





## Bibliography

- [1] International glossary of leather terms (English<>French<>German<>Spanish<>Italian), 2<sup>nd</sup> edition, revised, pp.320, 1975 (reprinted with addenda incorporated, 1997)
- [2] VDA 230-205, *Automotive leather*      *Determination of loose grain effect*
- [3] VDA 230-206-1, *Examination of the stick-slip behaviour of material pairs*      *General section*
- [4] VDA 230-206-2, *Examination of the stick-slip behaviour of material pairs*      *Specific section*  
*Leather: Leather against Leather*
- [5] VDA 270, *Determination of the odour characteristics of trim materials in motor vehicles* (currently only available in German language)
- [6] VDA 277, *Non-metallic materials in automotive interior trim*      *Determination of emission of organic compounds* (currently only available in German language)
- [7] VDA 278, *Thermal Desorption Analysis of Organic Emissions for the Characterization of Non-Metallic Materials for Automobiles* (currently only available in German language)





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person

or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs

and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

Tel: +44 845 086 9001

Email (orders): [orders@bsigroup.com](mailto:orders@bsigroup.com)

Email (enquiries): [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

Tel: +44 845 086 9001

Email: [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

Tel: +44 20 8996 7004

Email: [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

Tel: +44 20 8996 7070

Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™