



BSI Standards Publication

Paints and varnishes — Determination of electrical conductivity and resistance

National foreword

This British Standard is the UK implementation of EN ISO 15091:2020. It is identical to ISO 15091:2019. It supersedes [BS EN ISO 15091:2012](#), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 539 05251 0

ICS 87.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2020.

Amendments/corrigenda issued since publication

| Date | Text affected |
|-------|---------------|
| <hr/> | |

English Version

Paints and varnishes — Determination of electrical
conductivity and resistance (ISO 15091:2020)

Peintures et vernis — Détermination
de la conductivité et de la résistance
électriques (ISO 15091:2020)

Beschichtungsstoffe — Bestimmung der
elektrischen Leitfähigkeit und des elektrischen
Widerstandes (ISO 15091:2020)

This European Standard was approved by CEN on 29 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 15091:2020) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2020, and conflicting national standards shall be withdrawn at the latest by July 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15091:2012.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 15091:2019 has been approved by CEN as EN ISO 15091:2020 without any modification.

| Contents | | Page |
|---|---|------|
| Foreword | | iv |
| 1 | Scope | 1 |
| 2 | Normative references | 1 |
| 3 | Terms and definitions | 1 |
| 4 | General | 3 |
| 4.1 | Measurement of the resistance | 3 |
| 4.2 | Avoidance of electrolysis and polarization effects | 4 |
| 5 | Apparatus | 5 |
| 5.1 | Measuring instrument | 5 |
| 5.2 | Measuring cell | 5 |
| 6 | Sampling | 5 |
| 7 | Procedure | 5 |
| 7.1 | Test conditions | 5 |
| 7.2 | Viscosity of test sample | 6 |
| 7.3 | Number of determinations | 6 |
| 7.4 | Measurement of the electrical resistance or the electrical conductivity | 6 |
| 8 | Expression of results | 6 |
| 9 | Precision | 6 |
| 10 | Test report | 7 |
| Annex A (normative) Calibration | | 8 |
| Annex B (informative) Dependence of the conductivity on the measurement temperature | | 10 |
| Bibliography | | 11 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition ([ISO 15091:2012](http://www.iso.org/iso/15091:2012)), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- the conductivity of the aqueous potassium chloride solution with a molality of 0,001 mol/kg has been corrected to 146,71 $\mu\text{S}/\text{cm}$ to correct a mistake in conductivity;
- the text has been editorially revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paints and varnishes — Determination of electrical conductivity and resistance

1 Scope

This document specifies a method for determining the electrical conductivity and the electrical resistance of coating materials. The conductivity is usually measured for water-borne paints and varnishes, including electrodeposition coating materials, and the resistance is usually measured for solvent-borne paints and varnishes. If required, the resistivity of the coating material is calculated from either of these measurements. The method is applicable to products having a conductivity less than 5 µS/cm, corresponding to a resistivity greater than 200 kΩ·cm.

The conductivity of coating materials influences their processability in the presence of an electric field. This is particularly important for electrodeposition paints and coating materials which are processed electrostatically.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 1513](#), *Paints and varnishes — Examination and preparation of test samples*

[ISO 3696](#), *Water for analytical laboratory use — Specification and test methods*

[ISO 4618](#), *Paints and varnishes — Terms and definitions*

[ISO 15528](#), *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in [ISO 4618](#) and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

electrical resistance

R

ratio of the potential difference along a conductor and the current through the conductor

Note 1 to entry: Resistance is given by Ohm's law shown in [Formula \(1\)](#):

$$R = \frac{U}{I} \quad (1)$$

where

3.5
cell constant

c
quotient of the length and the cross-sectional area of a conductor

Note 1 to entry: It is given by [Formula \(5\)](#):

$$c = \frac{l}{A} \tag{5}$$

From [Formula \(2\)](#), it can be seen that it corresponds to the ratio of the resistance to the resistivity of the conductor material.

For the determination of the resistivity by resistance measurement, this geometrical factor, i.e. the cell constant of the measurement assembly, will need to be known.

Cell constants are given in reciprocal centimetres (cm⁻¹).

4 General

4.1 Measurement of the resistance

The resistance may be determined by;

- a) the measurement of the current through a sample and the voltage acting on the sample, or;
- b) comparison of the measured resistance with a reference resistance.

For the current/voltage measurement, usually a constant pre-determined voltage is applied to the sample, and the current is measured with a suitable measuring instrument (e.g. a moving-coil instrument or a digital instrument). The resistance is then calculated from [Formula \(1\)](#). See [Figures 1](#) to [3](#).




Figure 1 — Direct-current measurement




Figure 2 — Alternating-current measurement — Two-electrode cell




Figure 3 — Alternating-current measurement — Four-electrode cell

To compare the resistance of the sample with a reference resistance, a bridge circuit is used in which the resistances are balanced so that the bridge current becomes zero. The resistance of the sample is calculated from the ratio of the resistances of the bridge circuit. Because the bridge current is zero, errors which can result from the existence of a load on the voltage source when the voltage/current measurement method is used are avoided. The only contributions to the overall measurement error are any uncertainty in the reference resistance and any uncertainty in the adjustable resistance. See [Figure 4](#).




Figure 4 — Wheatstone bridge

4.2 Avoidance of electrolysis and polarization effects

In order to avoid electrolysis or polarization effects which would falsify the measurement, measurements of the resistance are usually carried out using alternating current. The frequency of the voltage applied to the measuring cell should, however, be as low as possible in order to minimize the contribution made by the reactance of the measuring cell, which acts as a capacitor.

5 Apparatus


5.1 Measuring instrument

Use a resistance- or conductivity-measuring instrument calibrated as described in [Annex A](#).

5.2 Measuring cell

The measuring cell consists of electrodes insulated from each other, with a known cell constant. The electrodes should preferably consist of a material that is easy to clean and inert (e.g. stainless steel, platinum, graphite, titanium) in order to make sure that the measurement will not be invalidated by changes in the electrodes. For examples of suitable electrodes, see [Figure 5](#). It is important to ensure that the measuring cell is completely immersed in the liquid. The exact depth will depend on the type of electrode.

The cell geometry shall be chosen so that the possibility of contamination by dirt is minimized.



a) Measuring cell with cylinder electrodes

b) Measuring cell with plate electrodes

Figure 5 — Examples of measuring cells

6 Sampling

Take a representative sample of the product to be tested, as described in [ISO 15528](#).

Examine and prepare each sample for testing, as described in [ISO 1513](#).

7 Procedure

7.1 Test conditions

Carry out the test at a temperature of $(25 \pm 1) ^\circ\text{C}$, unless otherwise agreed. The deviation from any agreed temperature shall also be not more than $\pm 1 ^\circ\text{C}$.

The dependence of the conductivity on the measurement temperature is shown in [Annex B](#).

7.2 Viscosity of test sample

The test is usually carried out at the same viscosity as that of the product under test when it is ready for use. The solvent used to adjust the viscosity, if this is necessary, shall be agreed between the interested parties.

7.3 Number of determinations

Make at least three individual measurements on the product under test.

7.4 Measurement of the electrical resistance or the electrical conductivity

Take the required quantity of the paint sample and immerse the electrodes in it, avoiding the formation of bubbles. If required, homogenize the material before doing this.

Prior to the measurement, check the measuring cell for cleanliness and remove any particles of dirt. Connect the measuring cell to the measuring instrument. For measurements using a direct-current measuring instrument, e.g. a Wheatstone bridge, read the value after a waiting time of 10 s in order to allow the electrical potential to become constant. For measurements using an alternating-current measuring instrument, read the value after an agreed waiting time.

When using continuously measuring instruments, the value shall only be read if it is constant for more than 20 s.

Immediately after the test, thoroughly clean the measuring cell.

8 Expression of results

Calculate the mean of the at least three individual measurements made of the resistance or conductivity. If required, calculate the resistivity from this mean value, using [Formula \(2\)](#) if resistance measurements were made or [Formula \(4\)](#) if conductivity measurements were made. Examples of the calculation of the resistivity from the measurements are given below, using typical values.

EXAMPLE 1 Calculation of the resistivity from resistance measurements

| | | |
|-----------------------------------|------------------|-------------------------|
| Mean resistance reading, <i>R</i> | MΩ | 1,22 |
| Mean resistance reading, <i>R</i> | kΩ | 1 220 |
| Cell constant, <i>c</i> | cm ⁻¹ | 7,55 × 10 ⁻³ |
| Resistivity, <i>ρ</i> | MΩ·cm | 161,6 |
| Resistivity, <i>ρ</i> | MΩ·m | 1,62 |

EXAMPLE 2 Calculation of the resistivity from conductivity measurements

| | | |
|-------------------------------------|------------------|----------|
| Mean conductivity reading, <i>γ</i> | μS/cm | 1,375 |
| Mean conductivity reading, <i>γ</i> | nS/cm | 1 375 |
| Cell constant, <i>c</i> | cm ⁻¹ | 0,8 |
| Resistivity, <i>ρ</i> | MΩ·cm | 0,727 |
| Resistivity, <i>ρ</i> | MΩ·m | 0,007 27 |

9 Precision

The precision depends on the method of measurement, the reference materials used for calibration and the product examined. Some typical precision values are given in [Table 1](#). Examples of the conductivity and resistivity to be expected for certain products are given in [Table 2](#).

Annex A
(normative)

Calibration

A.1 Calibration of the electrodes

A.1.1 Method A — Calibration using reference materials

Calibrate using suitable reference materials covering the range of values which are expected for the products to be tested. The uncertainty in the conductivity of the reference materials shall be taken into account. The conductivities of a range of aqueous potassium chloride solutions, which may be used for calibration purposes, are given in [Table A.1](#).

Table A.1 — Conductivity of aqueous potassium chloride solutions

| Molality of potassium chloride solution | Conductivity at 25 °C | Standard measurement uncertainty |
|--|-------------------------|----------------------------------|
| mol·kg ⁻¹ | µS·cm ⁻¹ | % |
| 1,0 | 108 620,00 ^a | ±0,04 ^a |
| 0,1 | 12 824,60 ^a | ±0,04 ^a |
| 0,01 | 1 408,23 ^a | ±0,03 ^a |
| 0,001 | 146,71 ^b | ±0,30 ^b |
| 0,000 1 | 16,00 ^b | ±3,00 ^b |
| ^a As given in Reference [1] . | | |
| ^b Measured at the Physikalisch-Technische Bundesanstalt (PTB) in Braunschweig, Germany. The increased uncertainty at low concentration levels reflects the influence of CO ₂ . | | |

Calibration of plate electrodes and cylinder electrodes shall be carried out using a suitable conductivity-measuring instrument capable of measuring conductivities lying in the range of conductivities stated for the reference materials.

Method A is not suitable for materials having a conductivity which corresponds to a resistance ≤200 kΩ.

A.1.2 Method B — Determination of the cell constant

Determine the cell constant by measuring the cell geometry, i.e. the distance between the plates and the area of each of the plates in the case of a plate electrode and the cylinder diameter and height in the case of a cylinder electrode.

EXAMPLES

Cell constant, c , of a plate electrode:

$$c = \frac{l}{A} \quad (\text{A.1})$$

where

- l is the distance between the plates;
- A is the area of each of the plates.

Cell constant, c , of a cylinder electrode:

$$c = \frac{\ln\left(\frac{r_e}{r_i}\right)}{2\pi h} \quad (\text{A.2})$$

where

- r_e is the internal radius of the exterior cylinder;
- r_i is the radius of the interior cylinder;
- h is the height of the cylinder.

The contribution by this type of calibration to the uncertainty of the measurement is about $\pm 2,5$ %.

A.2 Calibration of the measuring instrument (without the electrodes)

Calibrate the resistance-measuring equipment using reference resistors covering the measurement range or send it to the instrument manufacturer for calibration.

Annex B
(informative)

Dependence of the conductivity on the measurement temperature

The influence of temperature on conductivity measurements is given by [Formula \(B.1\)](#):


$$\gamma_{\theta} = \gamma_T \times \left[1 + \frac{\alpha}{100} \times (\theta - T) \right] \tag{B.1}$$

where

- γ_{θ} is the conductivity measured at temperature θ ;
- T is the reference temperature;
- γ_T is the conductivity at the reference temperature;
- α is the temperature coefficient of conductivity.

[Figure B.1](#) shows an example of this dependence, in which:

- $T = 25\text{ }^{\circ}\text{C}$;
- $\gamma_T = 1\text{ nS/cm}$ at $25\text{ }^{\circ}\text{C}$;
- $\alpha = 5\text{ } \%/^{\circ}\text{C}$.



Key

- θ measurement temperature, in degrees Celsius
- γ conductivity, in nanosiemens per centimetre

Figure B.1 — Dependence of the conductivity, γ_{θ} , on the temperature, θ

Bibliography

- [1] Pure Appl. Chem., Vol. **73**, No. 11, pp. 1783-1793, 2001
- [2] [ISO 7888](#), *Water quality — Determination of electrical conductivity*
- [3] ASTM D4399-05, *Standard Test Method for Measuring Electrical Conductivity of Electrocoat Baths*
- [4] ASTM D5682-18, *Standard Test Methods for Electrical Resistivity of Liquid Paint and Related Materials*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

