

EUROPEAN STANDARD

EN ISO 2746

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2015

ICS 25.220.50

Supersedes EN 14430:2004

English Version

Vitreous and porcelain enamels - High voltage test (ISO 2746:2015)

Emaux vitrifiés - Essai sous haute tension (ISO 2746:2015)

Emails und Emailierungen - Hochspannungsprüfung (ISO 2746:2015)

This European Standard was approved by CEN on 29 August 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 2746:2015) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2016, and conflicting national standards shall be withdrawn at the latest by April 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14430:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 2746:2015 has been approved by CEN as EN ISO 2746:2015 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Specimens	2
7 Test voltage	3
7.1 Test A: Detection of defects (3.1) which extend down to the metal basis (e.g. open pores)	3
7.2 Test B: Detection of defects and weak spots (3.2).....	4
8 Procedure	4
9 Test report	4
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 2746 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings*, in collaboration with Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 2746:1998) which has been technically revised. This edition has also been adopted as a European standard, which supersedes EN 14430:2004.

Introduction

There are two different objectives for high voltage testing of vitreous and porcelain enamels.

Test A is used to detect and locate defects, which extend down to the metal base (e.g. open pores). This is a non-destructive test usually applied to thin enamel coatings. The test serves to monitor either that the parts produced are free from defects at the chosen test voltage, or to count the number of existing defects, e.g. to determine the defect density (defects/m²) of enamelled architecture panels.

Test B is used to detect and locate defects, which extend down to the metal base (e.g. open pores) and to detect weak spots. This is a destructive test, i.e. the test can generate open pores with an electric discharge through weak spots in the enamel coating. This test is usually applied to thick enamel coatings and serves:

- a) to verify that an enamel coating is safe to be used under highly corrosive conditions, e.g. to test the enamel coating of vessels used in the chemical industry, or
- b) to verify that the enamel coating is safe to be used as a dielectric.

Test A and test B require the same test equipment (see [Clause 5](#)) and follow the same test procedure (see [Clause 8](#)). However, for test B the applied voltage is higher than in test A (see [Clause 7](#)).

Vitreous and porcelain enamels — High voltage test

WARNING — This International Standard may not be compliant with some countries' health and safety legislations and calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This International Standard does not address any health hazards, safety or environmental matters and legislations associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health, safety and environmentally acceptable practices and take suitable actions to comply with any national and international regulations. Compliance with this International Standard does not of itself confer immunity from legal obligations.

1 Scope

This International Standard describes two test methods of high voltage testing:

- Test A is used to detect and locate defects in vitreous and porcelain enamels;
- Test B is used to detect and locate defects and weak spots in vitreous and porcelain enamels.

The tests are performed using DC or pulsed DC high voltage.

The tests are applicable to dry surfaces of enamel coatings. In the case of moist surfaces, care should be taken to ensure that the locating of any defects is correctly performed.

Since test voltages depend on the coating thickness, the test method, especially with test A, may not be suitable for test specimens for which the coating thickness varies to a large extent.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 2360, *Non-conductive coatings on non-magnetic electrically conductive basis materials — Measurement of coating thickness — Amplitude-sensitive eddy-current method*

IEC/TS 60479-1, *Effects of current on human beings and livestock — Part 1: General aspects*

IEC/TS 60479-2, *Effects of current on human beings and livestock — Part 2: Special aspects*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 defect

area of an enamel layer where an open path connects the enamel surface with the metal basis

Note 1 to entry: Examples of defects are cracks or pores.

3.2

weak spot

area of an enamel layer where the dielectric strength falls below the required value, as determined by the application of high voltage because of blisters, foreign body inclusions, spalling or cracks

4 Principle

A high voltage electrode is passed over the enamel surface. Defects (Test A) or defects and weak spots (Test B) are indicated by a spark and a simultaneous optical and/or acoustic signal. The applied voltage can be DC or pulsed DC. The test voltage might be different in each case.

At distances smaller than 2 cm of the edges/borders of the enamelled parts, an electrical arc can occur between the test electrode and edges/borders with no or only a limited enamel coating thickness. The high voltage technique may, therefore, not be applicable to such border areas.

5 Apparatus

5.1 High voltage generator.

5.1.1 Direct-current (DC)-voltage generator, conforming to the requirements of IEC/TS 60479-1, able to deliver a DC-voltage corresponding to the testing voltage, adjustable and measurable at the test probe with limiting deviation +5 %/-10 %. The total internal resistance shall be high enough to give the short circuit current of the generator an arithmetical mean from 2 mA to 3 mA maximum. The peak value of the current during a spark discharge shall be between 10 mA and 50 mA and the amount of charge per impulse shall be 25 µC maximum.

The negative pole of the generator shall be earthed (USA: grounded) and the positive pole shall be connected to the test electrode by a screened high voltage cable of suitable length.

5.1.2 Pulsed DC-voltage generator, conforming to the requirements of IEC/TS 60479-2 able to deliver a DC-voltage corresponding to the testing voltage. The voltage shall be adjustable and measurable at the test probe with limiting deviations +20 %/-10 % for test voltage greater than 10 kV and limiting deviations +40 %/-10 % for test voltages less than 10 kV.

5.2 Test electrode, made out of metal wire or conductive rubber that is unaffected by a spark discharge.

NOTE Alternative test electrodes can be used providing they are unaffected by a spark discharge.

5.2.1 Insulated hand-piece, provided externally with an earthed cover for DC-voltage and pulsed DC-voltage devices. Pulsed DC-voltage generators can produce an electric shock to users because of capacitive coupling between cable and hand-piece during operation.

5.2.2 Brush holder, of metal wire (used for the test brush), constructed such that it is completely unaffected by the spark discharge and covers as large an area as possible when sweeping the enamel surface.

5.3 Indicator device, able to give a clear optical and/or acoustic signal at each spark discharge.

5.4 Coating thickness measurement device, such as that described in ISO 2178 or ISO 2360.

6 Specimens

The specimens can be commercial items, parts thereof or test pieces which have been subjected to the same processing, and which for testing purposes are representative of the commercial item.

No special preparation of specimens is required.

7 Test voltage

7.1 Test A: Detection of defects (3.1) which extend down to the metal basis (e.g. open pores)

For a correct determination of these defects, the appropriate test voltage shall be used. This voltage depends on the length of the defect gap, which corresponds to the thickness of the enamel layer. Too low a voltage will not result in the determination of all defects. Too high a voltage will result in a breakdown of thin residual enamel layers (destructive testing). In order to look for defects which extend down to the metal base (e.g. open pores), the test voltage shall be as follows:

- DC-voltages shall be set to the values given in [Table 1](#).
Other voltages may be chosen by mutual agreement between interested parties.
- voltage of pulsed DC-voltage generators shall be agreed between the interested parties.

[Table 1](#) shows the minimum voltage needed to arc through a defect which is open to both the surface and the metal substrate. Note that the dielectric breakdown of air is based on measurement at 23 °C and 60 % maximum relative humidity.

Table 1 — Test voltage^[1]

Layer thickness µm	Test voltage V
100	1 100
110	1 150
120	1 200
130	1 240
140	1 290
150	1 370
160	1 420
170	1 450
180	1 510
190	1 560
200	1 600
210	1 660
220	1 690
230	1 750
240	1 800
250	1 850
260	1 900
270	1 940
280	1 990
290	2 030
300	2 070
400	2 520
500	2 900

Table 1 (continued)

Layer thickness μm	Test voltage V
750	3 820
1 000	4 600
1 500	6 450
2 000	8 000

7.2 Test B: Detection of defects and weak spots (3.2)

Test voltages used to detect defects and weak spots in the enamel layer depend not only on the dielectric strength of air, but also on the dielectric strength of the enamel.

DC-voltages shall be agreed between the interested parties and shall be higher than those given in [Table 1](#). The test voltage of pulsed DC-voltage generators shall be agreed between the interested parties.

8 Procedure

Ensure that the surface of the enamel layer under test is free from impurities and has a temperature of 45 °C maximum.

If possible, the test temperature should not exceed 35 °C as the breakdown voltage appreciably decreases at temperatures higher than 35 °C.

The surface of the enamel shall be dry. This is less important if a pulsed DC generator is used.

The negative pole or earth/return terminal of the generator shall be connected to the substrate (base) of the specimen. The positive pole shall be connected to the test electrode.

Using the pulsed DC-voltage test, a capacitive connection may be used instead of a direct connection. For all-side enamelled components only capacitive earthing is possible.

Switch on the generator, adjust the voltage to the test requirement, place the electrode on the test piece and check the voltage. If the voltage has reduced, remove the cause or adjust as necessary. Move the test electrode systematically over the enamel surface at a speed of 40 cm/s maximum for DC. Pulsed DC may require lower electrode speed.

NOTE If the enamel coating is to be used as a dielectric for electric apparatus, alternative electrodes and conditions (such as time under current) can be used. See for example procedures given in IEC 60335-1, IEC 60335-2-15 and IEC 60335-2-30.

Defects and weak spots are usually indicated by a visible spark and simultaneously by an optical and/or acoustic signal. The visible spark can be influenced by the enamel composition, temperature, humidity and other environmental conditions.

Measure the thickness of the enamel coating where a spark discharge (or discharges) occurs.

9 Test report

The test report shall include the following information:

- a) all information necessary for the identification of the sample tested;
- b) reference to this International Standard, i.e. ISO 2746:2015;
- c) type of test (A or B), the type of test voltage and thickness range of the enamel;
- d) type of test instrument used;

- e) number and position of spark or contact points;
- f) thickness of the enamel coating where a spark discharge (or discharges) occurs;
- g) result(s), including the results of the individual determinations;
- h) any deviations from the procedure specified;
- i) any unusual features observed during the test;
- j) date of the test.

Licensed copy. IP Login, The University of Bath, version correct as of 14/04/2015

Bibliography

- [1] Nix H. Mitteilungen VDEFA - Heft 10 1987 – p 136-139: Schichtdickenmessung mit Geräten nach dem magnetischen und magnet-induktiven Verfahren. Porensuchung mit Hochspannung (Coating thickness measurement using magnetic and magnetic-inductive measurement methods. Pore detection by means of the high voltage method)
- [2] IEC 60335-1, *Household and similar electrical appliances — Safety — Part 1: General requirements*
- [3] IEC 60335-2-15, *Household and similar electrical appliances — Safety — Part 2-15: Particular requirements for appliances for heating liquids*
- [4] IEC 60335-2-30, *Household and similar electrical appliances — Safety — Part 2-30: Particular requirements for room heaters*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com