



BSI Standards Publication

Metallic and other inorganic coatings — Chromate conversion coatings on zinc, cadmium, aluminium-zinc alloys and zinc- aluminium alloys — Test methods

National foreword

This British Standard is the UK implementation of EN ISO 3613:2021. It is identical to ISO 3613:2021. It supersedes BS EN ISO 3613:2010, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/33, Electrodeposited and related coatings.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2021
Published by BSI Standards Limited 2021

ISBN 978 0 539 04564 2

ICS 25.220.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2021.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

**Metallic and other inorganic coatings - Chromate
conversion coatings on zinc, cadmium, aluminium-
zinc alloys and zinc-aluminium alloys - Test methods
(ISO 3613:2021)**

Revêtements métalliques et autres revêtements
inorganiques - Couches de conversion au chromate
sur zinc, cadmium et alliages d'aluminium-zinc et de
zinc-aluminium - Méthodes d'essai (ISO 3613:2021)

Metallische und andere anorganische Überzüge
- Chromatierüberzüge auf Zink, Cadmium,
Aluminium-Zink- und Zink-Aluminium-
Legierungen - Prüfverfahren (ISO 3613:2021)

This European Standard was approved by CEN on 9 May 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 3613:2021) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 3613:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 3613:2021 has been approved by CEN as EN ISO 3613:2021 without any modification.

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Reagents	2
	4.3.1 Test solution C 1	2
	4.3.2 Test solution C 2	2
	4.6 Ammonium persulfate [(NH ₄) ₂ S ₂ O ₈]	3
5	Apparatus	3
6	Test methods	4
	6.1 General	4
	6.2 Test for the presence of a colourless chromate coating on zinc	4
	6.3 Test for the presence of a colourless chromate coating on zinc and cadmium	4
	6.4 Test for the presence of a colourless chromate coating on zinc-aluminium (mass fraction of aluminium: 5 %) alloys	5
	6.5 Test for the presence of hexavalent chromium in both colourless and coloured chromate coatings	5
	6.5.1 General	5
	6.5.2 Test method employing test solution C 1	5
	6.5.3 Test method employing alternative test solution C 2 (destructive)	5
	6.5.4 Expression of results	6
	6.5.5 Calibration of spectrophotometer	7
	6.6 Determination of hexavalent chromium content of coloured chromate coatings	8
	6.6.1 Preparation of calibration graph	8
	6.6.2 Blank test	8
	6.6.3 Determination	8
	6.6.4 Expression of results	8
	6.7 Determination of total chromium content of coloured chromate coatings	8
	6.7.1 Preparation of calibration graph	8
	6.7.2 Blank test	8
	6.7.3 Determination	9
	6.7.4 Expression of results	9
	6.8 Determination of mass per unit area of both colourless and coloured chromate coatings by gravimetric method	9
	6.9 Test for adhesion by abrasion	9
	6.10 Quality evaluation test of chromate layers on zinc and cadmium surfaces	9
7	Test report	10
Bibliography		11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition ([ISO 3613:2010](http://www.iso.org/iso/3613:2010)), which has been technically revised. The main changes compared with the previous edition are as follows:

- [Table 1](#) has been revised;
- analysis method described in [6.5](#) was aligned with the method described in [IEC 62321-7-1](#);
- procedure for the preparation of test solution C 2 in [4.3.2](#) has been revised and a second standard solution has been added;
- limiting time has been amended in [6.1](#);
- procedure for testing with test solution C 2 has been revised in [6.5.2](#);
- description of the calibration of spectrophotometer has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document specifies methods for the qualitative determination of the presence of chromate conversion coatings as well as the total chromium content of chromate conversion coatings.

The application of very thin, colourless, practically invisible chromate conversion coatings is frequently called “passivation”, while the application of thicker, coloured chromate conversion coatings is called “chromating”. The term “passivation” is not correct, as it does not conform to the [ISO 2080](#) designation, and is therefore deprecated.

Chromate conversion coatings are based on a solution containing Cr(VI). Both the process solution and the coating contain hexavalent chromium. The term passivation is nowadays often used for Cr(VI)-free coatings replacing chromate conversion coatings. Products containing Cr(VI) are not allowed within EU and processes using Cr(VI) are strictly regulated.

This page deliberately left blank

Metallic and other inorganic coatings — Chromate conversion coatings on zinc, cadmium, aluminium-zinc alloys and zinc-aluminium alloys — Test methods

WARNING — This document calls for the use of substances and/or procedures that can be injurious to health if adequate safety measures are not taken. This document does not address any health hazards, safety or environmental matters associated with its use. It is the responsibility of the user of this document to establish appropriate health, safety and environmentally acceptable practices and take suitable actions for any national and international regulations.

1 Scope

This document specifies methods for the determination of

- the presence of colourless chromate conversion coatings,
- the presence of hexavalent chromium in colourless and coloured coatings on zinc or cadmium or aluminium-zinc (mass fraction of aluminium: 55 %, within a range of 54 % to 56 % mass fraction) and zinc-aluminium (mass fraction of aluminium: 5 %) alloys,
- the total chromium content per unit area on zinc and cadmium,
- the mass per unit area of both colourless and coloured coatings,
- the satisfactory adhesion of chromate conversion coatings, and
- the quality of chromate coatings.

These methods are applicable to

- colourless and coloured chromate conversion coatings containing trivalent and hexavalent chromium in varying proportions and produced by either chemical or electrochemical processes, and
- chromate coatings that are free from any supplementary coatings, such as oil, water or solvent-based polymers or wax.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 3892](#), *Conversion coatings on metallic materials — Determination of coating mass per unit area — Gravimetric methods*

[ISO 4520](#), *Chromate conversion coatings on electroplated zinc and cadmium coatings*

[IEC 60068-2-30](#), *Environmental testing — Part 2-30: Tests — Test Db: Damp heat, cyclic (12 h + 12 h cycle)*

3 Terms and definitions

No terms and definitions are listed in this document.

For 0,10 µg/ml Cr(VI): Measure 2,5 ml of this solution into a second 1 000 ml volumetric flask and make up to the mark. 1 ml of this standard solution contains 0,10 µg of Cr(VI).

For 0,13 µg/ml Cr(VI): Measure 3,3 ml of this solution into a third 1 000 ml volumetric flask and make up to the mark. 1 ml of this standard solution contains 0,13 µg of Cr(VI).

For the preparation of the comparison solution for 0,10 µg/cm² Cr(VI), add 1 ml of orthophosphoric acid and 1 ml of diphenylcarbazide solution to 50 ml of the standard Cr(VI) solution with 0,10 µg/ml Cr(VI) and mix thoroughly. Then add 2 ml of the diphenylcarbazide solution and mix. Allow the solution to stand for 10 min for the colour reaction to be completed.

For the preparation of the comparison solution for 0,13 µg/cm² Cr(VI), add 1 ml of orthophosphoric acid to 50 ml of the standard Cr(VI) solution with 0,13 µg/ml Cr(VI) and mix thoroughly. Then add 2 ml of the diphenylcarbazide solution and mix. Allow the solution to stand for 10 min for the colour reaction to be completed.

4.4 Test solution D (see 6.6 and 6.7).

Dissolve 0,50 g of diphenylcarbazide in 50 ml of acetone. Dilute slowly, while stirring, with 50 ml of water (rapid mixing can result in precipitation of diphenylcarbazide).

For maximum stability, store the solution under refrigeration in an amber-coloured glass bottle.

4.5 Sulfuric acid, diluted 1 + 3.

Slowly add one volume of concentrated sulfuric acid ($\rho = 1,84 \text{ g/cm}^3$) to three volumes of water.

4.6 Ammonium persulfate [(NH₄)₂S₂O₈].

4.7 Sodium hydroxide (NaOH), 240 g/l solution.

4.8 Silver nitrate (AgNO₃), 17 g/l solution.

4.9 Potassium dichromate (K₂Cr₂O₇), standard solution.

Dilute 2 ml of standard volumetric potassium dichromate solution (4,9 g/l) to 1 000 ml.

4.10 Phosphate buffer solution.

Dissolve 55 g of sodium dihydrogen orthophosphate monohydrate (NaH₂PO₄·H₂O) in 100 ml of water.

5 Apparatus

Use normal laboratory apparatus and the following.

Glassware shall be of grade A. Pipettes shall be calibrated.

Clean all glassware thoroughly. It is recommended that cleaning be done by boiling the glassware with nitric acid (HNO₃) of 30 % mass fraction, and then rinsing thoroughly with distilled water or water of equivalent purity. Adequate cleanliness should be demonstrated through the analysis of method blanks.

5.1 Photoelectric absorptiometer (colorimeter), with a filter having a mean transmission of 520 nm. The absorptiometer shall be used with an absorption cell having an optical path length of 10 mm.

5.2 Spectrophotometer, with wavelength set at 540 nm. The spectrophotometer shall be used with an absorption cell having an optical path length of 10 mm.

5.3 Analytical balance, with an accuracy of 0,10 mg.

6 Test methods

6.1 General

The test surface, prior to the following tests, shall be free of all contaminants, fingerprints and other extraneous stains. If the surface is coated with a thin oil film, this shall be removed prior to the test by degreasing using a suitable solvent at room temperature (not exceeding 35 °C). If it is necessary to store samples, they shall be stored at temperatures not exceeding 40 °C and at a relative humidity below 70 %. For test purposes, the samples shall not be subjected to forced drying at temperatures in excess of 35 °C. Treatment in alkaline solutions shall not be performed as chromate conversion coatings are broken down by alkalis. Spot tests are not always a precise means of determining the presence of chromate coatings.

The test methods for the following are given in [6.2](#) to [6.7](#):

- a) the presence of a colourless chromate coating on zinc, cadmium and aluminium-zinc alloys;
- b) the presence of hexavalent chromium in both coloured and colourless chromate coatings;
- c) the determination of hexavalent chromium content;
- d) the determination of total chromium content.

The test methods for the following are given in [6.8](#), [6.9](#) and [6.10](#), respectively:

- e) the determination of mass per unit area of chromate conversion coatings;
- f) adhesion by abrasion;
- g) the evaluation of the quality of chromate layer.

The tests shall be carried out within the following time limits:

- a minimum of 24 h after the application of the chromate conversion coating for almost all tests ([6.2](#) to [6.4](#), [6.5.2](#) and [6.6](#) to [6.10](#));
- a minimum of 5 d after the application of the chromate conversion coating for the test specified in [6.5.3](#) to [6.5.5](#);
- a maximum of 3 d for the tests specified in [6.2](#) to [6.4](#) and [6.5.2](#);
- a maximum of 30 d for the tests specified in [6.6](#) and [6.7](#). It could be recommendable to apply this limit also to the test specified in [6.5.3](#) to [6.5.5](#).

6.2 Test for the presence of a colourless chromate coating on zinc

Apply one drop of test solution A ([4.1](#)) to the chromated zinc surface. The formation of a red or red-violet colour in the drop shall be deemed to indicate the presence of a chromate film.

6.3 Test for the presence of a colourless chromate coating on zinc and cadmium

Place one drop of test solution B ([4.2](#)) on the surface to be tested.

In the case of a zinc substrate, observe the appearance of the spot for 3 min. The formation of a dark or black stain, at least 1 min after the application of the test solution, shall be deemed to indicate the presence of a colourless chromate conversion coating.

Black stain formation after more than 3 min can be indicative of the presence of supplementary coatings, such as wax or oil.

In the case of a cadmium substrate, observe the appearance of the spot for 1 min. The formation of a dark or black stain at least 5 s after the application of the test solution shall be deemed to indicate the presence of a colourless chromate conversion coating.

Black stain formation after more than 1 min can be indicative of the presence of supplementary coatings, such as wax or oil.

For comparison purposes, test an untreated surface similarly. Untreated zinc and cadmium surfaces, or the surfaces that have been treated for the chromate conversion coating but do not have a continuous coating, will react with the lead acetate solution to form a black stain on the untreated or bare zinc and cadmium surfaces almost immediately, within 2 s to 5 s, after the application of the test solution.

No significance is to be placed upon any differences in the reaction time to black-spot formation between 1 min and 3 min on a zinc substrate, or between 5 s and 60 s on a cadmium substrate, with a colourless chromate conversion treatment. Factors such as substrate surface texture (roughness), chromate film thickness variations (due to processing conditions), variations in the ambient temperature of the test and precise pH control of the lead acetate solution have an influence on the reaction time, and therefore preclude any rating based upon times beyond those already stated. Similarly, the test cannot be used to compare the corrosion protection of chromate conversion coatings made from various types of chromate treatment solutions.

Because of the sensitivity of the method, the test is considered to be a quality control tool for the process. Items with damaged chromate layers should not be tested by this method.

Chromate conversion coatings exposed to temperatures above 60 °C will have considerably reduced resistance to corrosion in the accelerated test method (see [6.10](#)). They will show a black stain in less than 60 s on zinc and less than 5 s on cadmium.

6.4 Test for the presence of a colourless chromate coating on zinc-aluminium (mass fraction of aluminium: 5 %) alloys

Expose the test specimen for 24 h to an accelerated damp heat test in accordance with [IEC 60068-2-30](#).

The formation of a dark grey to black stain over the main part of the area shall be deemed to indicate the absence of a chromate conversion coating.

NOTE This test does not have any significant effect on the surface appearance if a chromate conversion coating is present.

6.5 Test for the presence of hexavalent chromium in both colourless and coloured chromate coatings

6.5.1 General

Carry out the following test methods for the presence of hexavalent chromium.

6.5.2 Test method employing test solution C 1

Place one to five drops of test solution C 1 ([4.3.1](#)) on the surface to be tested. If hexavalent chromium is present, a red to violet colour will appear within a few minutes. Ignore any colour that appears much later, e.g. on drying. For comparison purposes, test an untreated surface similarly.

NOTE The treatment will not have any significant effect on the surface appearance.

6.5.3 Test method employing alternative test solution C 2 (destructive)

In this test method, the Cr(VI) content of a coated part is extracted by boiling in water. The extracted solution is examined according to the colour reaction with 1,5-diphenylcarbazide. Cr(VI) oxidizes

1,5-diphenylcarbazine to 1,5-diphenylcarbazone, which forms a red-violet coloured complex with the developed Cr(III).

The sample to be tested should have a surface area of $(50 \pm 5) \text{ cm}^2$. For fasteners or samples with a smaller surface area, use a suitable number of samples to obtain the total required surface area. In cases where obtaining a total surface area of $(50 \pm 5) \text{ cm}^2$ is not possible, a reduced total sample surface area may be used by reducing the water extraction volume, while maintaining the same surface area to extraction volume ratio ($1 \text{ cm}^2:1 \text{ ml}$). A minimum surface area of 25 cm^2 is recommended. Similarly, a higher sample surface area can be used by keeping the same ratio. The type of adjustment shall be recorded in the final report. Remove any sealing, such as paint or wax, etc., by scraping the surface. The resulting abrasion shall also be analysed.

Fill 50 ml of distilled water or water of equivalent purity with anti-bumping granules into a beaker with volume graduation, cover it with a watch glass and bring it to boiling temperature. Let the water boil for at least 10 min to deoxygenate it. Then totally immerse the sample into the boiling water and cover the beaker again with a watch glass. Extract the sample for $(10 \pm 0,5) \text{ min}$ once boiling is resumed. If necessary, add water to ensure that the sample is totally submerged during the extraction. Remove the sample and allow the beaker content to cool to ambient temperature. The solution should be colourless and free of precipitate. Adjust the volume to 50 ml. If necessary, filter the solution through a $0,45 \text{ }\mu\text{m}$ membrane filter into a dry beaker. Make up the solution to the mark with water (see [Clause 4](#)) or reduce it to the mark by boiling. Add 1 ml of orthophosphoric acid ([4.3.2](#)) per 50 ml volume and mix well. Pour 25 ml of the solution using a graduated cylinder into another dry beaker. Add 1 ml of diphenylcarbazine solution ([4.3.2](#)) and mix well. Allow the solution to stand for 10 min for the colour reaction to be completed. The remaining portion of the extract will serve as the blank.

If there is a colour interference (e.g. from a coating dye), a correction against the blank shall be performed. Transfer a portion of the sample solution to an absorption cell and measure the absorbance at 540 nm against the blank with the spectrophotometer ([5.2](#)). Make three measurements and take the average as the final absorbance of the sample. In some cases, depending on the type of spectrophotometer used, the correction for the blank has to be made manually in the collected data.

Measure the absorbance of the comparison solution for $0,10 \text{ }\mu\text{g/cm}^2 \text{ Cr(VI)}$ ([4.3.2](#)) three times as described above. Take the average of three measurements as the final absorbance of that comparison solution.

Measure the absorbance of the comparison solution for $0,13 \text{ }\mu\text{g/cm}^2 \text{ Cr(VI)}$ ([4.3.2](#)) three times as described above. Take the average of three measurements as the final absorbance of that comparison solution.

6.5.4 Expression of results

The results are expressed as shown in [Table 1](#).

Table 1 — Comparison of solutions

Observation	Resulting Cr(VI) concentration in coating	Definition
The colour intensity of the sample solution (see 6.5.3) is lower than that of the comparison solution for $0,10 \text{ }\mu\text{g/cm}^2 \text{ Cr(VI)}$ (4.3.2).	$<0,10 \text{ }\mu\text{g/cm}^2$	The sample is free from Cr(VI).

Observation	Resulting Cr(VI) concentration in coating	Definition
The colour intensity of the sample solution (see 6.5.3) is not lower than that of the comparison solution for 0,10 µg/cm ² Cr(VI), but not higher than that of the comparison solution for 0,13 µg/cm ² Cr(VI).	≥0,10 µg/cm ² and ≤0,13 µg/cm ²	The result is inconclusive. Unavoidable coating variations can influence the determination. If additional samples are available, perform a total of three trials to increase the sampling surface area. Use the average of the three trials for the final determination.
The colour intensity of the sample solution (6.5.2) is higher than that of the comparison solution for 0,13 µg/cm ² Cr(VI) (4.3.2).	>0,13 µg/cm ²	The sample contains Cr(VI).

In cases where the sample colour after the colorimetric reaction is significantly more intense than the colour of the comparison solution for 0,13 µg/cm² Cr(VI) (4.3.2) such that the result can be clearly determined as positive for Cr(VI), measurement with the spectrophotometer is not necessary. However, the report shall state that the result is significantly above 0,13 µg/cm² Cr(VI) based on visual observation and no colorimetric measurement was performed. A colorimetric measurement shall always be performed if the Cr(VI) is not clearly above 0,13 µg/cm².

6.5.5 Calibration of spectrophotometer

The spectrophotometer shall be calibrated using a blank and three standard solutions at a minimum. The standard solution concentrations shall bracket 0,10 µg/ml Cr(VI) and 0,13 µg/ml Cr(VI).

Zero the spectrophotometer with the 0,0 µg/ml blank standard and save this solution to re-zero the instrument before reading samples and standards.

Read the standard solutions. Construct a calibration curve and determine a line equation by plotting absorbance values against µg/ml of Cr(VI) for each standard including the 0,0 µg/ml standard. The calibration curve (linear fit with zero intercept) shall have a correlation coefficient ≥0,995 or a new curve shall be built.

Calibration curves can be used for up to one month from initial generation.

Colorimetric instruments designed specifically for hexavalent chromium detection at 540 nm can have a permanent calibration provided by the manufacturer and no further calibration is needed. Refer to the manufacturer’s instructions to ensure that the instrument is functioning properly and its working range is appropriate for this analysis.

Regardless of the instrument type, a performance verification using the two comparison solutions (see 4.3.2) shall be carried out prior to sample measurements and at the end of each sample sequence to ensure the instrument is functioning properly.

In the event that either of the comparison solutions measured prior to sample measurements result in concentrations that differ from the expected values (0,10 µg/ml and 0,13 µg/ml) by more than 15 %, the calibration shall be re-measured.

In the event that either of the comparison solutions measured at the end of the instrumental sequence result in concentrations that differ from the expected values by more than 15 %, the calibration and all of the samples in the sequence shall be re-measured.

6.6 Determination of hexavalent chromium content of coloured chromate coatings

6.6.1 Preparation of calibration graph

6.6.1.1 To a series of five 250 ml volumetric flasks, add respectively 0 ml (i.e. the compensation solution), 10 ml, 20 ml, 30 ml and 40 ml of standard potassium dichromate solution (4.9). Add to each flask 100 ml of water and 3 ml of dilute sulfuric acid (4.5). To one flask, add 3 ml of test solution D (4.4) and mix well. Exactly 2 min after the addition of test solution D, add 25 ml of phosphate buffer solution (4.10), dilute to the mark and mix. Repeat this procedure with the other four flasks.

6.6.1.2 Transfer a portion of each solution to an absorption cell and measure the absorbance in the absorptiometer (5.1) or spectrophotometer (5.2). Complete each reading within 25 min of adding test solution D (4.4) as the colour is not stable. Subtract the compensation solution (see 6.6.1.1) from each reading and plot the differences against micrograms of chromium per 250 ml.

6.6.2 Blank test

Carry out a blank test in accordance with 6.6.3 and record the result.

Prepare the test sample for the blank test as follows: pour 0 ml of standard potassium dichromate solution (4.9) in a flask, and add the reagents and test solution as described in 6.6.1.1.

6.6.3 Determination

6.6.3.1 Cut a test piece measuring about 50 mm × 100 mm from the coated item. Bring to the boil 50 ml of distilled water in a suitable vessel and totally immerse the test specimen in this. Leach for exactly 5 min while the water continues to boil, remove the specimen and rinse over the vessel. Cool the vessel and its contents to room temperature, add 3 ml of dilute sulfuric acid (4.5) and mix. Transfer the contents to a 250 ml volumetric flask. Rinse the vessel twice into the flask with 10 ml to 15 ml of distilled water, add 3 ml of test solution D (4.4) and mix. Exactly 2 min after the addition of test solution D, add 25 ml of phosphate buffer solution (4.10), dilute to the mark and mix.

6.6.3.2 Transfer a portion of the solution to an absorption cell and measure the absorbance in the absorptiometer (5.1) or spectrophotometer (5.2). Complete the reading within 25 min of adding test solution D (4.4) as the colour is not stable. Subtract the blank test reading (see 6.6.2) from the instrument reading and, using the calibration graph (see 6.6.1), convert the result into micrograms per 250 ml.

6.6.3.3 If the reading obtained falls within the portion of the calibration graph below 10 µg, repeat the determination using a larger test piece (1,5 times to 2 times the dimensions given in 6.6.3.1).

6.6.4 Expression of results

Determine the total surface area of coating on the test specimen, in square centimetres. Divide the hexavalent chromium content, obtained in accordance with 6.6.3, by the surface area of the coating. The hexavalent chromium content shall be expressed in micrograms per square centimetre.

6.7 Determination of total chromium content of coloured chromate coatings

6.7.1 Preparation of calibration graph

Prepare a calibration graph in accordance with 6.6.1.

6.7.2 Blank test

Carry out a blank test in accordance with 6.6.2.

6.7.3 Determination

6.7.3.1 Cut a test piece measuring about 50 mm × 100 mm from the coated item. Heat 25 ml of dilute sulfuric acid (4.5) to 40 °C to 50 °C and pour into a suitable vessel containing the test specimen. Swirl continuously so that all surfaces are exposed to the acid for 10 s to 15 s. Remove the test specimen and rinse it over the vessel. Dilute to about 175 ml, add about 0,1 g of ammonium persulfate (4.6) and 3 ml of silver nitrate solution (4.8). Then add anti-bumping granules and boil for 30 min. Cool and adjust the pH to 1,5 to 1,8 using about 20 ml of sodium hydroxide solution (4.7). To measure the pH, transfer a drop to the pH paper; do not immerse the paper in the solution. Transfer to a 250 ml one-mark volumetric flask. Rinse the vessel twice into the flask with 10 ml to 15 ml of water, add 3 ml of test solution D (4.4) and mix. Exactly 2 min after the addition of test solution D, add 25 ml of phosphate buffer solution (4.10), dilute to the mark and mix.

WARNING — For health and safety reasons, sodium hydroxide shall not be added directly to sulfuric acid.

6.7.3.2 Transfer a portion of the solution to an absorption cell and measure the absorbance in the absorptiometer (5.1) or spectrophotometer (5.2). Complete the reading within 25 min of adding test solution D (4.4) as the colour is not stable. Subtract the blank test reading (see 6.7.2) from the instrument reading and, using the calibration graph (see 6.7.1), convert the result into micrograms per 250 ml.

6.7.4 Expression of results

Determine the total surface area of coating on the test specimen, in square centimetres. Divide the total chromium content obtained in accordance with 6.7.3 by the surface area of the coating. The total chromium content shall be expressed in micrograms per square centimetre.

6.8 Determination of mass per unit area of both colourless and coloured chromate coatings by gravimetric method

The mass per unit area shall be determined in accordance with [ISO 3892](#). The mass per unit area shall be expressed in milligrams per square centimetre.

6.9 Test for adhesion by abrasion

Test the adhesion of the chromate by lightly rubbing the surface for about 10 strokes with white paper, such as a No. 40 Whatman filter paper¹⁾ or a gritless, soft gum eraser. The adhesion of the coating shall be deemed satisfactory if no more than the faintest stain is visible on the paper and there is no sign of the underlying metal surface due to the removal of the coating.

NOTE This test method is not quantifiable.

6.10 Quality evaluation test of chromate layers on zinc and cadmium surfaces

Carry out the neutral salt spray (fog) test (see [ISO 9227](#) and ASTM B117) to evaluate the quality of chromate layers on zinc and cadmium surfaces.

The time for formation of white corrosion products on chromated cadmium or zinc coatings shall be not less than the values given in [ISO 4520](#).

The requirements of this method are primarily for quality acceptance and for the qualification programme. The duration and results of artificial atmospheric deterioration of coatings for quality control tests can bear little relationship to the service life of the coated article and, therefore, the results obtained are not to be regarded as a direct guide to the corrosion resistance of the tested coatings in all environments where these coatings can be used.

1) No. 40 Whatman filter paper is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

7 Test report

The test report shall contain the following information:

- a) a reference to this document, i.e. ISO 3613:2021;
- b) detailed information concerning the test method, including the test solutions used;
- c) the number of samples tested;
- d) the results of the test, including the results of the individual determinations and their mean values;
- e) any deviations from the procedures specified;
- f) any unusual features (anomalies) observed during the test;
- g) the date of the test and that of the report.

Bibliography

- [1] [ISO 2080](#), *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*
- [2] [ISO 9227](#), *Corrosion tests in artificial atmospheres — Salt spray tests*
- [3] [IEC 62321-7-1](#), *Determination of certain substances in electrotechnical products – Part 7.1: Hexavalent chromium – Presence of hexavalent chromium (Cr(VI)) in colourless and coloured corrosion-protected coatings on metals by the colorimetric method*
- [4] ASTM B117, *Standard Practice for Operating Salt Spray (Fog) Apparatus*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

- Standards purchased in soft copy format:
- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
 - The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
 - A single paper copy may be printed for personal or internal company use only.

- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
 - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services
Tel: +44 345 086 9001
Email: cservices@bsigroup.com

Subscriptions
Tel: +44 345 086 9001
Email: subscriptions@bsigroup.com

Knowledge Centre
Tel: +44 20 8996 7004
Email: knowledgecentre@bsigroup.com

Copyright & Licensing
Tel: +44 20 8996 7070
Email: copyright@bsigroup.com

BSI Group Headquarters
389 Chiswick High Road London W4 4AL UK

