



BSI Standards Publication

**Leather - Chemical tests - Determination  
of pH and difference figure**

---

EUROPEAN STANDARD

**EN ISO 4045**

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2018

ICS 59.140.30

Supersedes EN ISO 4045:2008

English Version

## Leather - Chemical tests - Determination of pH and difference figure (ISO 4045:2018)

Cuir - Essais chimiques - Détermination du pH et de l'indice de différence (ISO 4045:2018)

Leder - Chemische Prüfungen - Bestimmung des pH und der Differenzzahl (ISO 4045:2018)

This European Standard was approved by CEN on 5 May 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## **European foreword**

This document (EN ISO 4045:2018) has been prepared by Technical Committee IULTCS "International Union of Leather Technologists and Chemists Societies" in collaboration with Technical Committee CEN/TC 289 "Leather" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2018, and conflicting national standards shall be withdrawn at the latest by December 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4045:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

The text of ISO 4045:2018 has been approved by CEN as EN ISO 4045:2018 without any modification.

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>1</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Sampling and preparation of the samples</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>2</b>
8.1 Preparation of the extract .....	<b>2</b>
8.2 Calibration of the pH meter .....	<b>3</b>
8.3 Determination of the pH value .....	<b>3</b>
8.4 Determination of the difference figure .....	<b>3</b>
<b>9 Test report</b> .....	<b>3</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html)

This document was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUC 11 published in *J. Soc. Leather Tech. Chem.*, **49**, pp. 25–29, 1965, and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This third edition cancels and replaces the second edition (ISO 4045:2008), which has been technically revised as follows:

- change in title to include “and difference figure”;
- [5.1](#) and [6.1](#) have been revised;
- [Clause 7](#) has been revised: two samples are only prepared when there is enough leather;
- [8.1](#) has been revised to more clearly explain the procedure;
- [8.2](#) has been added (previously part of the next clause);
- [8.3](#) and [8.4](#) (previously [8.2](#) and [8.3](#)) have been revised and the previous title of [8.4](#) deleted;
- [Clause 9](#) b) and d) have been revised.

# Leather - Chemical tests - Determination of pH and difference figure

## 1 Scope

This document specifies a method for determining the pH value and the difference figure of an aqueous leather extract. It is applicable to all types of leather.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 2418](#), *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

[ISO 3696](#), *Water for analytical laboratory use — Specification and test methods*

[ISO 4044](#), *Leather — Chemical tests — Preparation of chemical test samples*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **difference figure**

difference between the pH value of a solution and that of its tenfold dilution

Note 1 to entry: The difference figure is a measure of the strength of acids and bases and can never exceed a value of 1. The difference figure amounts to 0,70 to 1,00 when a solution contains a free strong acid (or a free strong base). The ionization of weak acids and bases increases with greater dilution, and therefore the difference figure can only act as a criterion for the presence of free strong acid or base in aqueous extracts with pH values below 4 or above 10.

## 4 Principle

Preparation of an aqueous extract from a test portion of the leather and measurement of the pH of the extract, using a pH meter. In cases where the pH value obtained is below 4,00 or above 10,00, the pH value of a tenfold dilution of the aqueous extract is also determined.

## 5 Reagents

**5.1 Water**, minimum grade 3 in accordance with [ISO 3696](#).

## 5.2 Buffer solution, for calibrating the electrode system.

It is preferable to purchase a commercially available standard buffer solution for measurement as recommended by the pH meter manufacturer. The length of time for which buffer solutions will keep depends on their composition and the method of use. Control of the accuracy of the buffer solution is therefore indispensable. Used buffer solution shall be discarded.

## 6 Apparatus

**6.1 Suitable shaker**, rotating shaker with a frequency of  $(50 \pm 10)$  r/min or other suitable shaker after validation.

**6.2 pH meter**, with glass electrode, with a measuring range of 0 pH units to 14 pH units, graduated in 0,01 pH units. The electrode system shall be calibrated prior to each series of measurements against the buffer solution (5.2).

Aqueous extracts of heavily fat-liquored leather may in time make the electrode membrane dirty. In such cases, the membrane shall be lightly rubbed with a piece of cotton wool dipped in acetone or the electrode should be suspended in a 1:1 water:acetone mixture. After cleaning, the membrane should again be thoroughly soaked in water.

**6.3 Analytical balance**, capable of weighing to an accuracy of 0,01 g.

**6.4 Wide mouthed flask**, with leak-proof stopper, capacity 250 ml.

**6.5 Measuring cylinder**, capacity 100 ml, graduated in 1 ml divisions.

**6.6 Volumetric flask**, capacity 100 ml.

**6.7 Pipette**, capacity 10 ml.

## 7 Sampling and preparation of the samples

Sample in accordance with [ISO 2418](#). If sampling in accordance with [ISO 2418](#) is not possible, then details about sampling shall be given in the test report. Prepare the leather sample in accordance with [ISO 4044](#).

Samples should be analysed in duplicate, if it is possible.

## 8 Procedure

### 8.1 Preparation of the extract

Weigh  $(5,0 \pm 0,1)$  g of the test sample into the wide-mouthed flask (6.4) and using the measuring cylinder (6.5) add  $(100 \pm 1)$  ml of water (5.1) at  $(20 \pm 2)$  °C. Shake well by hand for about 30 s so that the test portion is uniformly wet. Shake mechanically in the shaker (6.1) for between 6,0 h and 6,5 h. Allow the extract to settle. Decant and take the liquid phase for pH measurement, ensuring that there are no suspended solids.

If difficulty is experienced in decanting the extract from the slurry, it may be strained through a clean, dry, non-absorbent mesh (for example, nylon cloth or a coarse sintered glass filter) or centrifuged.

## 8.2 Calibration of the pH meter

Calibrate the pH meter with a minimum of two buffer solutions: at least one below the expected value and at least one above the expected value. Both these buffer readings shall be within 0,02 pH units of the correct reading when the pH meter is standardized.

## 8.3 Determination of the pH value

Ensure that the extract (8.1) is at  $(20 \pm 2)$  °C. Immediately after stirring, immerse the electrode in the extract solution and determine the pH value with the pH meter (6.2), to the nearest 0,05 pH unit, as soon as a steady reading has been reached. The reading should be taken within 30 s to 60 s.

The result of the pH value is either

- the mean value of the two individual determinations, or
- the value for a single sample.

The figures shall be given to the nearest 0,05 pH unit.

## 8.4 Determination of the difference figure

If the pH value is below 4,00 or over 10,00, the difference figure shall be determined, except if precluded by the client or specification. For this determination, using the pipette (6.7), transfer 10 ml of the extract solution into the volumetric flask (6.6) and fill up to the mark with water (5.1). Rinse the electrodes with approximately 20 ml of the diluted solution and then measure the pH value, as in 8.3.

The result of the difference figure value is either

- the mean value of the two individual determinations, or
- the value for a single sample.

The figures shall be given to the nearest 0,05 pH unit.

The difference figure is calculated by subtracting the pH value obtained in 8.4 from that obtained in 8.3. The difference figure result is quoted to the nearest 0,05 pH unit.

## 9 Test report

The test report shall include the following:

- a) a reference to this document (i.e. ISO 4045);
- b) a description of the sample;
- c) a reference to any instability of the pH reading of the extract which prevents an unequivocal statement of the pH value or difference figure;
- d) pH and, if requested, difference figures as measured in 8.3 and 8.4;
- e) details of any deviations from the prescribed test conditions.

# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
  - The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
  - A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
  - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK