



BSI Standards Publication

**Metallic powders – Determination of
flow rate by means of a calibrated funnel
(Hall flowmeter) (ISO 4490:2018)**

National foreword

This British Standard is the UK implementation of EN ISO 4490:2018. It supersedes BS EN ISO 4490:2014, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/65, Sintered metal components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 90964 1

ICS 77.160

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2018.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

English Version

**Metallic powders - Determination of flow rate by means
of a calibrated funnel (Hall flowmeter) (ISO 4490:2018)**

Poudres métalliques - Détermination du
temps d'écoulement au moyen d'un entonnoir
calibré (appareil de Hall) (ISO 4490:2018)

Metallpulver - Bestimmung der Durchflussrate
mit Hilfe eines kalibrierten Trichters
(Hall flowmeter) (ISO 4490:2018)

This European Standard was approved by CEN on 23 March 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 4490:2018) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2018, and conflicting national standards shall be withdrawn at the latest by November 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4490:2014.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4490:2018 has been approved by CEN as EN ISO 4490:2018 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Calibration of the funnel	3
6.1 Calibration by the manufacturer of the funnel	3
6.2 Calibration by the user of the funnel	3
7 Sampling	4
7.1 General	4
7.2 Test sample weight	4
7.3 Test portion weight	4
7.4 Number of test portions	4
8 Procedure	4
9 Expression of results	4
10 Precision	5
11 Test report	5
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 2, *Sampling and testing methods for powders (including powders for hardmetals)*.

This fifth edition, which cancels and replaces the fourth edition ([ISO 4490:2014](http://www.iso.org/iso/4490:2014)), has been revised to include a precision statement together with some other minor clarifications.

Metallic powders – Determination of flow rate by means of a calibrated funnel (Hall flowmeter)

1 Scope

This document specifies a method for determining the flow rate of metallic powders, including powders for hard metals, by means of a calibrated funnel (Hall flowmeter).

The method is applicable only to powders which flow freely through the specified test orifice.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Measurement of the time required for 50 g of a metallic powder to flow through the orifice of a calibrated funnel of standardized dimensions.

5 Apparatus

5.1 Calibrated funnel, the dimensions of which are shown in [Figure 1](#). The funnel shall be made of a non-magnetic, corrosion-resistant metallic material with sufficient wall thickness and hardness to withstand distortion and excessive wear.

5.2 Stand and horizontal vibration-free base, which shall support the funnel rigidly. An example is shown in [Figure 2](#).


5.3 Balance of sufficient capacity, capable of weighing the test portion to an accuracy of $\pm 0,05$ g.

5.4 Timing device, capable of measuring the elapsed time to an accuracy of $\pm 0,1$ s.

5.5 Reference grit, a reference powder¹⁾ used for calibration of the funnel, shall be used.

1) Material complying with [5.5](#) can be purchased as “Chinese emery grit” from ACuPowder International, LLC, 901 Lehigh Avenue, Union, NJ 07083, USA. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the company named above. Equivalent products may be used if they can be shown to lead to the same results.

Dimensions in millimetres



- Key**
- 1 polished to $R_a \leq 0,4 \mu\text{m}$
 - a $D = 2,5 + 0,4 \begin{smallmatrix} . \\ 0 \end{smallmatrix}$

Figure 1 — Calibrated funnel (Hall flowmeter)




Figure 2 — Arrangement of calibrated funnel and stand

6 Calibration of the funnel

6.1 Calibration by the manufacturer of the funnel

The manufacturer shall supply the flowmeter calibrated as follows.

- Dry the reference grit ([5.5](#)) in an open and clean glass jar at 110 °C for 60 min in air.
- Cool the reference grit to room temperature in a desiccator.
- Weigh out $50 \text{ g} \pm 0,1 \text{ g}$ of the reference grit.
- Follow the procedure outlined in [Clause 8](#).
- Repeat the procedure with the same 50 g mass of reference grit, until there are five determinations within 0,4 s.
- The average of these five determinations is stamped on the bottom of the funnel and the duration of flow shall be within $40,0 \text{ s} \pm 0,5 \text{ s}$.

6.2 Calibration by the user of the funnel

It is recommended that the users periodically verify whether a correction is needed or not.

The flow rate of the reference sample shall be determined by the above method. If the flow rate has changed to be outside $40,0 \text{ s} \pm 0,5 \text{ s}/50 \text{ g}$, a correction factor shall be used when measuring different powders. This correction factor is obtained by dividing 40,0 by the value obtained above.

It is recommended that, before a correction factor is adopted, the cause of the change be investigated. If the flow rate has decreased, it is probable that repeated use has burnished the orifice and a (new) correction factor is justified. An increase in flow rate may indicate a coating of soft powder on the orifice. This coating should be carefully removed and the calibration test repeated.

It is recommended that the use of a funnel be discontinued after the duration of flow of the reference sample has decreased to less than 37 s.

7 Sampling

7.1 General

In general, the powder shall be tested in the as-received condition. In certain cases, and after agreement between the supplier and user, the powder may be dried. However, if the powder is susceptible to oxidation, the drying shall take place in a vacuum or in inert gas. If the powder contains volatile substances, it shall not be dried.

7.2 Test sample weight

The mass of the test sample shall be at least 200 g.

7.3 Test portion weight

Immediately before the test, weigh out a $50 \text{ g} \pm 0,1 \text{ g}$ test portion.

7.4 Number of test portions

The determination shall be carried out on three test portions.

8 Procedure

- a) Transfer the test portion to the funnel, keeping the discharge orifice properly closed, for example with a dry finger or a mechanical shutter. Take care that the stem of the funnel is filled with powder.
- b) Start the timing device ([5.4](#)) when the orifice is opened and stop it at the instant when the last of the powder leaves the orifice.
- c) Record the elapsed time measured to the nearest 0,1 s.

Alternatively, the orifice can be kept open when the test portion is transferred to the funnel, with the rest of the procedure being the same.

If the powder does not begin to flow when the orifice is opened, one slight tap on the funnel to start the flow is permitted. If this has no effect, or if the flow stops during the test, the powder is considered to possess no flowability according to the test method described in this document.

9 Expression of results

Calculate the arithmetic mean of the results of the three determinations and report the value in seconds per 50 g, rounded to the nearest second. If a correction factor (see [6.2](#)) is used, the average shall be multiplied by this correction factor.

10 Precision

Three iron powders, see [Table 1](#), were included in the inter-laboratory study to develop this precision statement.

Table 1 — Types of powders included in the inter laboratory study

Type of powder
Plain atomized iron powder
Plain sponge iron powder
Stainless steel powder

In [Table 2](#) the repeatability and reproducibility are presented as one standard deviation.

Table 2 — Repeatability and reproducibility as standard deviations

Tested powder	Level Average flow time s	Repeatability (s_r) Standard deviation s	Reproducibility (s_R) Standard deviation s
Plain atomized iron powder	25	0,4	1,1
Plain sponge iron powder	33	0,3	1,1
Stainless steel powder	32	0,2	1,2

The difference between two test results found on identical test material by one operator using the same apparatus within the shortest feasible time interval will exceed the repeatability limit (r), see [Table 3](#), on average not more than once in 20 cases in the normal and correct operation of the method.

Test results on identical test material reported by two laboratories will differ by more than the reproducibility limit (R), see [Table 3](#), on average not more than once in 20 cases in the normal and correct operation of the method.

Table 3 — Repeatability and reproducibility, difference between two tests at 95 % probability level

Tested powder	Level Average flow time s	Repeatability (r) Limit s	Reproducibility (R) Limit s
Plain atomized iron powder	25	1,1	3,1
Plain sponge iron powder	33	0,7	3,0
Stainless steel powder	32	0,6	3,2

The accuracy data were determined from an experiment organized and analysed in accordance with [ISO 5725-2\[1\]](#) in 2014 involving 14 laboratories and three levels. Data from two of the laboratories contained outliers for the stainless steel powder. These data points were excluded in the calculations of the precision statement.

The repeatability and reproducibility are valid for powders similar to the powders evaluated for the precision statement. Other types of metal powders, with properties different from the evaluated powders, may have repeatability and reproducibility that are different from what is reported in this precision statement.

11 Test report

The test report shall include the following information:

- a reference to this document (i.e. ISO 4490);

- b) all details for identification of the test sample;
- c) the result obtained expressed in s/50 g;
- d) the use of an open orifice;
- e) all operations not specified by this document, or regarded as optional (e.g. the drying procedure applied and whether flow has been induced by tapping the funnel);
- f) details of any occurrence which may have affected the result.

Bibliography

- [1] [ISO 5725-2](#), *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions. With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member. PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email:

knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

This page deliberately left blank