

BS EN ISO 4630:2015



BSI Standards Publication

Clear liquids — Estimation of colour by the Gardner colour scale

bsi.

...making excellence a habit.™

EUROPEAN STANDARD

EN ISO 4630

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 87.060.20

Supersedes EN ISO 4630-1:2004, EN ISO 4630-2:2004

English Version

Clear liquids - Estimation of colour by the Gardner colour scale (ISO 4630:2015)

Liquides clairs - Évaluation de la couleur au moyen de l'échelle de couleur Gardner (ISO 4630:2015)

Klare Flüssigkeiten - Bestimmung der Farbe nach der Gardner-Farbskala (ISO 4630:2015)

This European Standard was approved by CEN on 1 November 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 4630:2015) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4630-1:2004, EN ISO 4630-2:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4630:2015 has been approved by CEN as EN ISO 4630:2015 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus and materials	1
5 Sampling	2
6 Procedure	2
7 Expression of results	2
8 Precision	2
8.1 General.....	2
8.2 Repeatability limit, <i>r</i>	2
8.3 Reproducibility limit, <i>R</i>	3
8.4 Bias.....	3
9 Test report	3
Annex A (normative) Gardner colour standards	4
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 4630 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*, in collaboration with ASTM D 01.34, *Naval stores*. It has been harmonized with ASTM D 1544-04, *Standard test Method for Color of Transparent Liquids (Gardner Color Scale)* and ASTM D 6166-12, *Standard Test Method for Color of Naval Stores and Related Products (Instrumental Determination of Gardner Color)*.

This third edition of ISO 4630 cancels and replaces ISO 4630-1:2004 and ISO 4630-2:2004, which have been technically revised. The main changes are:

- a) both standards have been combined into one standard;
- b) the spectrophotometric method (formerly described in ISO 4630-2:2004) is the only one standardized now;
- c) the original visual comparison of colours (formerly described in ISO 4630-1:2004) has been deleted, and the description of manufacture of the original Gardner colour standards has been moved to [Annex A](#).

Clear liquids — Estimation of colour by the Gardner colour scale

1 Scope

This International Standard specifies a method for estimating the colour of optically clear, yellow/brownish coloured liquid products by means of the Gardner colour scale using colour-measuring instruments. The method uses the Gardner colour scale described in [Annex A](#).

It is applicable to drying oils, varnishes and solutions of fatty acids, polymerized fatty acids, resins, tall oil, tall oil fatty acids, rosin and related products. The results might be invalid if other products are tested.

The method described provides a more precise way of measuring Gardner colour than a visual sample comparison using human eyes. It is applicable to products having colours from Gardner 1 to Gardner 18. The Gardner scale is not applicable to products with colours darker than 18. For products with colours lighter than Gardner 1 the method specified in ISO 6271 applies.

2 Normative references

The following referenced documents, in whole or in part, are normally referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

ISO 13632, *Binders for paints and varnishes — Rosin — Sampling and sample preparation for colour measurement*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

CIE Publication No. 15:2004, *Colorimetry*

3 Principle

The colour of a liquid sample is measured using an instrument capable of measuring transmitted colour and reporting in Gardner colours or in a colour system that can be converted into Gardner colours.

4 Apparatus and materials

4.1 Colour-measuring instrument, spectrophotometer capable of measuring transmitted colour ($0^\circ/180^\circ$ geometry) and reporting the results in the Gardner colour scale. If such an instrument is not available, one may be used which is capable of measuring transmitted colour and reporting in tristimulus values using standard illuminant C and the 2° observer, described in CIE Publication No. 15:2004.

4.2 Absorption cells, 10 mm light path length recommended, unless a different path length is specified by the instrument manufacturer or

4.3 Glass tubes, 11 mm path length. Glass test tubes designed for a specific instrument may be used.

5 Sampling

Take a representative sample of the product to be tested, as described in ISO 15528.

In the case of rosin, take a representative sample, as specified in ISO 13632.

6 Procedure

Baseline calibration of the instrument shall be performed following the instrument manufacturer's recommendations.

If the material to be tested is cloudy, first filter it (see Note). Then, using the same type of glass tube or absorption cell as used for the baseline calibration, fill the glass tube or absorption cell with the product. Take care not to touch the measurement area of the glass tube or absorption cell.

If the material shows any visual haziness, remove the haze e.g. by filtration, centrifugation, heating, ultrasonic treatment or any other suitable means (see Note).

If the haziness cannot be removed, the measured value will be unreliable.

Then, using the same type of glass tube or absorption cell as used for the baseline calibration, fill the glass tube or absorption cell with the product. Take care not to touch the measurement area of the glass tube or absorption cell.

Avoid creating air bubbles when filling the glass tube or absorption cell. If air bubbles are formed and remain trapped, remove them by heating, vacuum, ultrasonic treatment or any other suitable means (see Note).

NOTE Some sample pre-treatments can change the colour.

Insert the glass tube or absorption cell in the instrument and measure the Gardner colour, following the instrument manufacturer's recommended procedure.

Regular checks as per the instrument manufacturer's recommendations should be carried out. These will normally be in the form of checks with certified reference materials.

7 Expression of results

Report the colour in Gardner colour units to the nearest tenth of a Gardner unit as given by the instrument.

8 Precision

8.1 General

The precision of the test method was determined by interlaboratory testing in accordance with ISO 5725-2.

Three different materials were tested by 13 laboratories.

8.2 Repeatability limit, r

The repeatability limit r is the value below which the absolute difference between two single test results, each the mean of duplicates, obtained on identical material by one operator in one laboratory within a short interval of time using the standardized test method can be expected to lie with a probability of 95 %.

The repeatability for three repeated measurements, made in accordance with this International Standard and expressed as the repeatability limit r , is 0,1 Gardner units.

The repeatability standard deviation among test results, related to the above number by the factor 2,8, is 0,02 Gardner units.

8.3 Reproducibility limit, R

The reproducibility limit R is the value below which the absolute difference between two test results, each the mean of duplicates, obtained on identical material by operators in different laboratories using the standardized test method can be expected to lie with a probability of 95 %.

The reproducibility for three repeated measurements, made in accordance with this International Standard and expressed as the reproducibility limit R , is 0,5 Gardner units.

The reproducibility standard deviation among test results, related to the above number by the factor 2,8, is 0,18 Gardner units.

8.4 Bias

Since there is no accepted reference material suitable for determining the bias of the procedure in this test method, bias has not been determined.

9 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product examined;
- b) a reference to this International Standard (ISO 4630);
- c) any type of pretreatment of the test sample;
- d) the result of the test as indicated in [Clause 7](#);
- e) any deviation from the test method specified;
- f) any unusual features (anomalies) observed during the test;
- g) the date of the test.

Annex A (normative)

Gardner colour standards

A.1 Reagents

In preparing these standards, use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

A.1.1 Hydrochloric acid, diluted 1 + 17

Mix 1 volume of concentrated hydrochloric acid, 38 % (by mass), $\rho = 1,19$ g/ml, with 17 volumes of water.

A.1.2 Potassium hexachloroplatinate solution

Dissolve 790 mg of potassium hexachloroplatinate (K_2PtCl_6) in diluted hydrochloric acid (A.1.1) in a 100 ml one-mark volumetric flask. Warm the solution until all the potassium hexachloroplatinate has dissolved. Cool to 20 °C, dilute to the mark with the same hydrochloric acid and mix well.

The stock solution A.1.2 prepared in this way shall have tristimulus values which lie within the limits specified in Table A.1 when measured in accordance with 4.1 and 4.2 (10 mm optical path length) in the spectrophotometer.

Table A.1 — Tristimulus tolerance limits for potassium hexachloroplatinate stock solution (A.1.2)

X	Y	Z
80,9 ± 0,5	87,1 ± 0,5	24,5 ± 1,5

A.1.3 Cobalt(II) chloride solution

Dissolve 40 g of cobalt(II) chloride hexahydrate ($CoCl_2 \cdot 6H_2O$) in 120 g of diluted hydrochloric acid (A.1.1).

A.1.4 Iron(III) chloride solution

Dissolve 1 000 g of iron(III) chloride hexahydrate ($FeCl_3 \cdot 6H_2O$) in 240 g of diluted hydrochloric acid (A.1.1), heating gently if necessary. Adjust the concentration so that the solution has exactly the same colour (visually assessed) as a freshly prepared 30 g/l solution of potassium dichromate ($K_2Cr_2O_7$) in concentrated sulfuric acid ($\rho = 1,84$ g/ml).

The stock solution A.1.4 prepared in this way shall have tristimulus values X, Y, Z which lie within the limits specified in Table A.2 when measured in accordance with to 4.1 and 4.2 (10 mm optical path length) in the spectrophotometer.

Table A.2 — Tristimulus tolerance limits for iron(III) chloride stock solution (A.1.4)

X	Y	Z
10,0 ± 2,5	5,3 ± 1,5	0,0 + 0,2

A.2 Preparation of liquid colour standards

A.2.1 Gardner colour standards 1 to 8

Into each of a series of one-mark volumetric flasks of the capacities indicated in [Table A.3](#), transfer from a microburette the volume of potassium hexachloroplatinate solution ([A.1.2](#)) shown in [Table A.3](#), make each up to the mark with diluted hydrochloric acid ([A.1.1](#)) and mix well.

Table A.3 — Composition of Gardner colour standards 1 to 8

Gardner colour standard number	Volume of potassium hexachloroplatinate solution ml	Volume of volumetric flask ml
1	3,48	50
2	5,47	50
3	8,42	50
4	6,58	25
5	9,60	25
6	5,35	10
7	8,10	10
8	10,00	10

A.2.2 Gardner colour standards 9 to 18

Into a series of 100 ml one-mark volumetric flasks, introduce from burettes the volumes of iron(III) chloride solution ([A.1.4](#)) and cobalt(II) chloride solution ([A.1.3](#)) shown in [Table A.4](#). Make each up to the mark with diluted hydrochloric acid ([A.1.1](#)) and mix well.

Table A.4 — Composition of Gardner colour standards 9 to 18

Gardner colour standard number	Volume of iron(III) chloride solution ml	Volume of cobalt(II) chloride solution ml	Volume of hydrochloric acid ml
9	3,8	3,0	93,2
10	5,1	3,6	91,3
11	7,5	5,3	87,2
12	10,8	7,6	81,6
13	16,6	10,0	73,4
14	22,2	13,3	64,5
15	29,4	17,6	53,0
16	37,8	22,8	39,4
17	51,3	25,6	23,1
18	100,0	0,0	0,0

A.2.3 Storage

Gardner colour standards are stable for 6 months when stored in the dark but should preferably be prepared immediately before use.

Bibliography

- [1] ISO 6271, *Clear liquids — Estimation of colour by the platinum-cobalt colour scale*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com