



BSI Standards Publication

Adhesives — Determination of shear behaviour of structural adhesives

Part 1: Torsion test method using butt-bonded hollow cylinders

National foreword

This British Standard is the UK implementation of [ISO 11003-1:2019](#).

The UK participation in its preparation was entrusted to Technical Committee PRI/52, Adhesives.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 539 00359 8

ICS 83.180

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
11003-1

Third edition
2019-04-30

**Adhesives — Determination of shear
behaviour of structural adhesives —**

Part 1:
**Torsion test method using butt-
bonded hollow cylinders**

*Adhésifs — Détermination du comportement en cisaillement
d'adhésifs structuraux —*

*Partie 1: Méthode d'essai en torsion de cylindres creux
collés bout à bout*



Reference number
ISO 11003-1:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Test specimen	4
6.1 Preparation.....	4
6.1.1 Substrate material.....	4
6.1.2 Preparation of the surface.....	4
6.1.3 Bonding.....	4
6.1.4 Adhesive bond.....	4
6.1.5 Dimensions.....	4
6.2 Number of specimens.....	7
7 Test conditions	7
7.1 Temperature.....	7
7.2 Shear rate.....	7
8 Procedure	7
9 Calculations	8
10 Precision	8
11 Test report	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This third edition cancels and replaces the second edition ([ISO 11003-1:2001](http://www.iso.org/iso/11003-1:2001)), which has been technically revised. The main changes compared to the previous edition are as follows:

- correction of the formula for angular displacement in [7.2](#);
- updated references.

A list of all parts in the ISO 11003 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Adhesives — Determination of shear behaviour of structural adhesives —

Part 1:

Torsion test method using butt-bonded hollow cylinders

1 Scope

This document specifies a shear test for the characterization of adhesives in a bond. The shear stress/strain properties of the adhesive (including the shear modulus) are useful for advanced design work, such as in finite element analysis methods.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 291](#), *Plastics — Standard atmospheres for conditioning and testing*

[ISO 10365](#), *Adhesives — Designation of main failure patterns*

ISO 17212, *Structural adhesives — Guidelines for the surface preparation of metals and plastics prior to adhesive bonding*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:


- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The shear deformation of the adhesive in an annular bond between two hollow cylinders, and the corresponding torque, are measured and recorded up to failure of the joint.

5 Apparatus

5.1 Torsion-testing machine, with a capacity of at least 300 N·m and preferably of 1 000 N·m. Alternatively, a suitably adapted tensile-testing machine may be used. The machine shall include equipment for recording the torque instantaneously with an error of less than 1 %. The gripping heads shall be accurately aligned and, if no hydraulic gripping mechanism is available, all bolts and holes shall be precisely machined so that the specimens are mounted in the apparatus and tested free of uncontrolled loads. The machine shall be equipped with an adequately thermostatted chamber if tests are to be carried out at temperatures different from the ambient temperature.



Key

- 1 adherends
- 2 target support (on upper adherend)
- 3 butt joint
- 4 transducer support (on lower adherend)
- 5 displacement transducer
- 6 target

Figure 1 — Adhesive-layer specimen with displacement transducer mounted in the test apparatus

6 Test specimen

6.1 Preparation

6.1.1 Substrate material

Aluminium alloy or steel are suitable materials for the adherends. Other materials are acceptable provided the material (including pre-treated surface layers) has a shear modulus at least 10 times higher than that of the adhesive.

6.1.2 Preparation of the surface

The surfaces to be bonded shall be prepared in accordance with ISO 17212 or by any method leading to a cohesive failure within the adhesive layer.

6.1.3 Bonding

Prepare the specimens in accordance with the instructions of the manufacturer of the adhesive. Information about conditioning of the specimen shall be included in the test report.

A joint completely filled with adhesive is essential for the reliability of the test. The two adherends shall be bonded coaxially, with a maximum lateral displacement between their two axes of $0,002 r_o$ (r_o = outer radius), and a maximum angular deviation so that the bond line thickness varies by no more than 5 % of the recommended thickness. The joining device shall prevent the adhesive from running out of the joint and any displacement of the two adherends during curing.

NOTE To achieve this, the two hollow cylinders are aligned with the help of a plug made of polytetrafluoroethylene (PTFE) or any other suitable device. A temperature-resistant O-ring, inserted into the PTFE plug and placed just below the bond, stops the adhesive from running out of the joint. At the other ends of the adherends, two plates fastened to a threaded rod passing through the PTFE plug prevent any displacement during curing (see [Figure 2](#)).

6.1.4 Adhesive bond

The preferred thickness of the bond is 0,2 mm.

For special adhesives, a thickness in the range from 0,05 mm to 0,5 mm may be used.

The thickness of the bond is defined by a rim which is machined along the outer perimeter of one adherend. The rim acts as spacer between the two adherends. The adhesive is applied to the machined adherend to fill the space adjacent to the rim, prior to joining the two adherends. The rim is removed on the lathe after the adhesive is cured (see [Figure 3](#)). The resulting adhesive layer shall have a width at least 10 times its thickness.


6.1.5 Dimensions

Three sizes of specimen (A, B, C) are recommended (see [Table 1](#)), although intermediate sizes are acceptable provided that [see [Formula \(1\)](#)]:

$$r_i \geq 0,8r_o \quad (1)$$

where

- r_i is the inner radius of each cylinder;
- r_o is the outer radius of each cylinder.




Key

- 1 top plate
- 2 polytetrafluoroethylene plug
- 3 adhesive layer
- 4 o-ring
- 5 rod with screw thread
- 6 bottom plate

Figure 2 — Coaxially aligned hollow cylinders in a suitable joining device

Dimensions in millimetres



Key

- 1 adherends
- 2 adhesive
- 3 bolt
- 4 fixture

NOTE The rim spacer that controls the thickness of the bond is shown in the upper detail view. Before testing, the spacer is removed, as shown in the lower detail view.

Figure 3 — Dimensions of the specimen and specimen holders

The width ($r_i - r_o$) of the bond zone may be reduced to a minimum of $0,1 r_o$ if the available torque is not sufficient to produce failure of the specimen.

Suitable values for the length of the specimen and the dimensions of the specimen holders are given in [Figure 3](#).

The thickness of the bond is controlled by a spacer (see [6.1.4](#) and [Figure 3](#)).

Table 1 — Recommended specimen sizes

Specimen	Radii	
	r_o mm	r_i mm
A	36	30
B	24	20
C	12	10

6.2 Number of specimens

At least five specimens shall be tested for a given adhesive.

7 Test conditions

7.1 Temperature

The temperature of the test shall be one of the standard temperatures specified in [ISO 291](#). The temperature of the specimen shall be measured at the outer surface of the hollow cylinder, close to the bond (e.g. with thermocouples). Agreement to within ± 1 °C is required.

7.2 Shear rate

The rate of shear, $\dot{\gamma}$, of the adhesive shall lie within the range from $0,000\ 5\ \text{s}^{-1}$ to $0,02\ \text{s}^{-1}$.

NOTE The preferred rate of shear is $0,01\ \text{s}^{-1}$.

The corresponding rate of angular displacement α , to be set on the torsion-testing machine is given by [Formula \(2\)](#):

$$\alpha = \frac{\dot{\gamma}t}{r_o} \quad (2)$$

where

t is the thickness of the adhesive bond, expressed in millimetres;

r_o is the outer radius of the specimen, expressed in millimetres (see [Table 1](#)).

8 Procedure

Fix the specimens in the test apparatus, equipped with a temperature cabinet if required. Adjust the apparatus so that the joint is free from any load.

While increasing the shear deformation continuously up to the requested maximum value, record the torque-displacement curve. If the specimen fails, check the surfaces of the bonded parts and reject any specimens with incompletely filled adhesive bonds (due e.g. to the presence of bubbles or voids). Sometimes the adhesive layer will not fail after reaching the maximum shear deformation, especially when loading with a low shear rate. If this happens, repeat the test with an increasing torque rate until the specimen fails. As before, check the adhesive layer for defects of fabrication. Ensure that cohesive failure is achieved.

Suitable values for the length of the specimen and the dimensions of the specimen holders are given in [Figure 3](#).

The thickness of the bond is controlled by a spacer (see [6.1.4](#) and [Figure 3](#)).

Table 1 — Recommended specimen sizes

Specimen	Radii	
	r_o mm	r_i mm
A	36	30
B	24	20
C	12	10

6.2 Number of specimens

At least five specimens shall be tested for a given adhesive.

7 Test conditions

7.1 Temperature

The temperature of the test shall be one of the standard temperatures specified in [ISO 291](#). The temperature of the specimen shall be measured at the outer surface of the hollow cylinder, close to the bond (e.g. with thermocouples). Agreement to within ± 1 °C is required.

7.2 Shear rate

The rate of shear, $\dot{\gamma}$, of the adhesive shall lie within the range from $0,000\ 5\ \text{s}^{-1}$ to $0,02\ \text{s}^{-1}$.

NOTE The preferred rate of shear is $0,01\ \text{s}^{-1}$.

The corresponding rate of angular displacement α , to be set on the torsion-testing machine is given by [Formula \(2\)](#):

$$\alpha = \frac{\dot{\gamma}t}{r_o} \quad (2)$$

where

t is the thickness of the adhesive bond, expressed in millimetres;

r_o is the outer radius of the specimen, expressed in millimetres (see [Table 1](#)).

8 Procedure

Fix the specimens in the test apparatus, equipped with a temperature cabinet if required. Adjust the apparatus so that the joint is free from any load.

While increasing the shear deformation continuously up to the requested maximum value, record the torque-displacement curve. If the specimen fails, check the surfaces of the bonded parts and reject any specimens with incompletely filled adhesive bonds (due e.g. to the presence of bubbles or voids). Sometimes the adhesive layer will not fail after reaching the maximum shear deformation, especially when loading with a low shear rate. If this happens, repeat the test with an increasing torque rate until the specimen fails. As before, check the adhesive layer for defects of fabrication. Ensure that cohesive failure is achieved.

Suitable values for the length of the specimen and the dimensions of the specimen holders are given in [Figure 3](#).

The thickness of the bond is controlled by a spacer (see [6.1.4](#) and [Figure 3](#)).

Table 1 — Recommended specimen sizes

Specimen	Radii	
	r_o mm	r_i mm
A	36	30
B	24	20
C	12	10

6.2 Number of specimens

At least five specimens shall be tested for a given adhesive.

7 Test conditions

7.1 Temperature

The temperature of the test shall be one of the standard temperatures specified in [ISO 291](#). The temperature of the specimen shall be measured at the outer surface of the hollow cylinder, close to the bond (e.g. with thermocouples). Agreement to within ± 1 °C is required.

7.2 Shear rate

The rate of shear, $\dot{\gamma}$, of the adhesive shall lie within the range from $0,000\ 5\ \text{s}^{-1}$ to $0,02\ \text{s}^{-1}$.

NOTE The preferred rate of shear is $0,01\ \text{s}^{-1}$.

The corresponding rate of angular displacement α , to be set on the torsion-testing machine is given by [Formula \(2\)](#):

$$\alpha = \frac{\dot{\gamma}t}{r_o} \quad (2)$$

where

t is the thickness of the adhesive bond, expressed in millimetres;

r_o is the outer radius of the specimen, expressed in millimetres (see [Table 1](#)).

8 Procedure

Fix the specimens in the test apparatus, equipped with a temperature cabinet if required. Adjust the apparatus so that the joint is free from any load.

While increasing the shear deformation continuously up to the requested maximum value, record the torque-displacement curve. If the specimen fails, check the surfaces of the bonded parts and reject any specimens with incompletely filled adhesive bonds (due e.g. to the presence of bubbles or voids). Sometimes the adhesive layer will not fail after reaching the maximum shear deformation, especially when loading with a low shear rate. If this happens, repeat the test with an increasing torque rate until the specimen fails. As before, check the adhesive layer for defects of fabrication. Ensure that cohesive failure is achieved.

- h) the test temperature;
- i) the number of specimens tested and used for the calculation;
- j) the individual results for the shear modulus, the highest shear stress and corresponding shear strain, and additionally, if applicable, the shear stress and shear strain at failure;
- k) the ranges of torque and displacement used;
- l) the averaged results, including the standard deviation;
- m) the stress-strain curve obtained;
- n) observations concerning the debonded surfaces in accordance with [ISO 10365](#);
- o) any deviation from the specified procedure which may have influenced the results;
- p) the date of the test.

