

BS ISO 11972:2015



BSI Standards Publication

Corrosion-resistant cast steels for general applications

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 11972:2015.

The UK participation in its preparation was entrusted to Technical Committee ISE/111, Steel Castings and Forgings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 76498 1

ICS 77.140.20; 77.140.80

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 11972:2015

ISO
11972

Second edition
2015-09-15

**Corrosion-resistant cast steels for
general applications**

Aciers moulés résistant à la corrosion pour applications courantes



Reference number
ISO 11972:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva,
Switzerland
Tel. +41 22 749 01 11 Fax
+41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
1	Scope	1
2	Normative reference	1
3	General conditions for delivery	1
4	Chemical composition	1
5	Mechanical properties	1
6	Heat treatment	1
7	Supplementary requirements	5
Annex A (informative) UNS cast grades similar to ISO cast grades		6
Bibliography		7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC17, *Steel*, Subcommittee SC11, *Steel castings*.

This second edition cancels and replaces the first edition (ISO 11972:1998), which has been technically revised with the following changes:

- [Clause 7](#) revised;
- [Table 1](#) composition limits modified — various grades;
- [Tables 1, 2, and 3](#) — grade numbers added;
- [Annex A](#) added.

Corrosion-resistant cast steels for general applications

1 Scope

This International Standard specifies cast steels for general corrosion-resistant applications. The grades covered by this International Standard represent types of alloy steel castings suitable for broad ranges of application which are intended for a wide variety of corrosion applications.

NOTE [Annex A](#) gives information on ISO grade designation and available UNS numbers which are similar to the ISO grade designation.

2 Normative reference

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4990, *Steel castings — General technical delivery conditions*

3 General conditions for delivery

Materials furnished according to this International Standard shall conform to the applicable requirements of ISO 4990 including the supplementary requirements that are indicated on the inquiry and purchase order.

4 Chemical composition

The steel shall conform to the requirements for chemical composition specified in [Table 1](#).

5 Mechanical properties

Steel used for castings shall conform to the mechanical property requirements given in [Table 2](#) up to the maximum ruling thickness. Verification of impact tests is not required except when indicated by the customer. Test blocks used to verify mechanical properties shall not have a thickness exceeding 150 mm. For samples removed from castings, the mechanical properties required shall be agreed between the manufacturer and purchaser.

6 Heat treatment

Castings shall be heat treated in accordance with the requirements in [Table 3](#).

Table 1 — Chemical composition, % (m/m)

Grade designation		Chemical composition								
Name	Number	C	Si	Mn	P	S	Cr	Mo	Ni	Others
GX12Cr12	1.4011	0,15	1,0	1,0	0,035	0,025	11,5 to 13,5	0,50	1,0	
GX7CrNiMo12-1	1.4008	0,10	1,0	1,0	0,035	0,025	12,0 to 13,5	0,20 to 0,50	1,0 to 2,0	
GX4CrNi13-4 (QT1) GX4CrNi13-4 (QT2)	1.4317	0,06	1,0	1,0	0,035	0,025	12,0 to 13,5	0,70	3,5 to 5,0	
GX4CrNiMo16-5-1	1.4405	0,06	0,8	1,0	0,035	0,025	15,0 to 17,0	0,70 to 1,50	4,0 to 6,0	
GX2CrNi19-11	1.4309	0,03	1,5	2,0	0,035	0,025	18,0 to 20,0	–	9,0 to 12,0	N 0,20
GX2CrNi19-11	1.4487	0,03	1,5	1,5	0,040	0,030	18,0 to 20,0	–	9,0 to 12,0	N 0,12 to 0,20
GX5CrNi19-10	1.4308	0,07	1,5	1,5	0,040	0,030	18,0 to 20,0	–	8,0 to 11,0	
GX5CrNiNb19-11	1.4552	0,07	1,5	1,5	0,040	0,030	18,0 to 20,0	–	9,0 to 12,0	8 × C ≤ Nb ≤ 1,00
GX2CrNiMo19-11-2	1.4409	0,03	1,5	2,0	0,035	0,025	18,0 to 20,0	2,00 to 2,50	9,0 to 12,0	N 0,20
GX2CrNiMoN19-11-2	1.4490	0,03	1,5	2,0	0,035	0,030	18,0 to 20,0	2,00 to 2,50	9,0 to 12,0	N 0,12 to 0,20
GX4CrNiMoN26-5-2	1.4474	0,05	1,0	2,0	0,035	0,025	25,0 to 27,0	1,30 to 2,00	4,5 to 6,5	N 0,12 to 0,20
GX5CrNiMo19-11-2	1.4408	0,07	1,5	1,5	0,040	0,030	18,0 to 20,0	2,00 to 2,50	9,0 to 12,0	
GX5CrNiMoNb19-11-2	1.4581	0,07	1,5	1,5	0,040	0,030	18,0 to 20,0	2,00 to 2,50	9,0 to 12,0	8 × C ≤ Nb ≤ 1,00
GX2CrNiMo19-11-3	1.4518	0,03	1,5	1,5	0,040	0,030	18,0 to 20,0	3,00 to 3,50	9,0 to 12,0	
GX2CrNiMoN19-11-3	1.4508	0,03	1,5	1,5	0,040	0,030	18,0 to 20,0	3,00 to 3,50	9,0 to 12,0	N 0,10 to 0,20
GX2CrNiMoN22-5-3	1.4470	0,03	1,0	2,0	0,035	0,025	21,0 to 23,0	2,50 to 3,50	4,5 to 6,5	N 0,12 to 0,20
GX2CrNiMoN25-7-3	1.4417	0,03	1,0	1,5	0,030	0,020	24,0 to 26,0	3,00 to 4,00	6,0 to 8,5	Cu 1,00 N 0,15 to 0,25 W 1,00
GX2CrNiMoN26-7-4	1.4469	0,03	1,0	1,0	0,035	0,025	25,0 to 27,0	3,00 to 5,00	6,0 to 8,0	N 0,12 to 0,22 Cu 1,30
GX5CrNiMo19-11-3	1.4412	0,07	1,5	1,5	0,040	0,030	18,0 to 20,0	3,00 to 3,50	10,0 to 13,0	
GX2NiCrMo- CuN25-20-6	1.4588	0,02	1,0	2,00	0,035	0,020	19,0 to 21,0	6,00 to 7,00	24,0 to 26,0	N 0,10 to 0,25 Cu 0,50 to 1,50
GX2CrNiMo- CuN20-18-6	1.4557	0,02	1,0	1,20	0,030	0,010	19,5 to 20,5	6,00 to 7,00	17,5 to 19,5	N 0,18 to 0,24 Cu 0,50 to 1,00
GX2CrNiMo- CuN25-6-3-3	1.4517	0,03	1,0	1,50	0,035	0,025	24,5 to 26,5	2,50 to 3,50	5,0 to 7,0	N: 0,12 to 0,22 Cu: 2,75 to 3,50
GX3CrNiMoCuN26-6-3	1.4515	0,03	1,0	2,00	0,030	0,020	24,5 to 26,5	2,50 to 3,50	5,5 to 7,0	N 0,12 to 0,25 Cu: 0,80 to 1,30
GX2CrNiMoN25-6-3	1.4468	0,03	1,0	2,0	0,035	0,025	24,5 to 26,5	2,50 to 3,50	5,5 to 7,0	N 0,12 to 0,25

NOTE A single value in the table indicates the maximum limit.

Table 2 — Mechanical properties at room temperature^b

Grade designation		$R_{p0,2}$ min MPa	R_m min. MPa	A min. %	KV min. J	Maximum ruling thickness mm
Name	Number					
GX12Cr12	1.4011	450	620	15	20	150
GX7CrNiMo12-1	1.4008	440	590	15	27	300
GX4CrNi13-4 (QT1)	1.4317	550	750	15	50	300
GX4CrNi13-4 (QT2)		830	900	12	35	300
GX4CrNiMo16-5-1	1.4405	540	760	15	60	300
GX2CrNi19-11	1.4309	185	440	30	80	150
GX2CrNiN19-11	1.4487	230 ^a	510	30	80	150
GX5CrNi19-10	1.4308	175 ^a	440	30	60	150
GX5CrNiNb19-11	1.4552	175 ^a	440	25	40	150
GX2CrNiMo19-11-2	1.4409	195 ^a	440	30	80	150
GX2CrNiMoN19-11-2	1.4490	230 ^a	510	30	80	150
GX4CrNiMoN26-5-2	1.4474	420	600	20	30	150
GX5CrNiMo19-11-2	1.4408	185 ^a	440	30	60	150
GX5CrNiMoNb19-11-2	1.4581	185 ^a	440	25	40	150
GX2CrNiMo19-11-3	1.4518	180 ^a	440	30	80	150
GX2CrNiMoN19-11-3	1.4508	230 ^a	510	30	80	150
GX2CrNiMoN22-5-3	1.4470	420	600	20	30	150
GX2CrNiMoN25-7-3	1.4417	480	650	22	50	150
GX2CrNiMoN26-7-4	1.4469	480	650	22	50	150
GX5CrNiMo19-11-3	1.4412	205 ^a	440	30	60	150
GX2NiCrMoCuN25-20-6	1.4588	210	480	30	60	50
GX2CrNiMoCuN20-18-6	1.4557	260	500	35	50	50
GX2CrNiMoCuN25-6-3-3	1.4517	480	650	22	50	150
GX3CrNiMoCuN26-6-3	1.4515	480	650	22	60	200
GX2CrNiMoN25-6-3	1.4468	480	650	22	50	150

^a The minimum $R_{p1,0}$ value is 25 MPa higher.

^b 1 MPa = 1 N/mm²

Table 3 — Heat treatment

Grade designation		Treatment
Name	Number	
GX12Cr12	1.4011	Austenitize at 950 °C to 1 050 °C; air cool. Temper at 650 °C to 750 °C; air cool.
GX7CrNiMo12-1	1.4008	Austenitize at 1 000 °C to 1 050 °C; air cool. Temper at 620 °C to 720 °C; air or furnace cool.
GX4CrNi13-4 (QT1)	1.4317	Austenitize at 1 000 °C to 1 050 °C; air cool. Temper at 570 °C to 620 °C; air or furnace cool.
GX4CrNi13-4 (QT2)	1.4317	Austenitize at 1 000 °C to 1 050 °C; air cool. Temper at 500 °C to 530 °C; air or furnace cool.
GX4CrNiMo16-5-1	1.4405	Austenitize at 1 020 °C to 1 070 °C; air cool. Temper at 580 °C to 630 °C; air or furnace cool.
GX2CrNi19-11	1.4309	Solution treat at 1 050 to 1 150 °C; quench. Depending on thickness, accelerated air cooling.
GX2CrNi19-11	1.4487	Solution treat at 1 050 °C; quench. Depending on thickness, accelerated air cooling.
GX5CrNi19-10	1.4308	Solution treat at 1 050 °C to 1 150 °C ; quench. Depending on thickness, accelerated air cooling.
GX5CrNiNb19-11	1.4552	Solution treat at 1 050 to 1 150 °C; quench. Depending on thickness, accelerated air cooling.
GX2CrNiMo19-11-2	1.4409	Solution treat at 1 080 °C to 1 150 °C ; quench. Depending on thickness, accelerated air cooling
GX2CrNiMoN19-11-2	1.4490	Solution treat at 1 080 °C; quench. Depending on thickness, accelerated air cooling.
GX4CrNiMoN26-5-2	1.4474	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX5CrNiMo19-11-2	1.4408	Solution treat at 1 080 °C to 1 150 °C; quench. Depending on thickness, accelerated air cooling.
GX5CrNiMoNb19-11-2	1.4581	Solution treat at 1 080 to 1 150 °C; quench. Depending on thickness, accelerated air cooling.
GX2CrNiMo19-11-3	1.4518	Solution treat at 1 120 °C min.; quench. Depending on thickness, accelerated air cooling.
GX2CrNiMoN19-11-3	1.4508	Solution treat at 1 120 °C min.; quench. Depending on thickness, accelerated air cooling.
GX2CrNiMoN22-5-3	1.4470	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX2CrNiMoN25-7-3	1.4417	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX2CrNiMoN26-7-4	1.4469	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX5CrNiMo19-11-3	1.4412	Solution treat at 1 120 to 1 180 °C; quench. Depending on thickness, accelerated air cooling.
GX2NiCrMoCuN25-20-6	1.4588	Solution treat at 1 200 °C to 1 240 °C for 4 h minimum, quench in water.

Table 3 (continued)

Grade designation		Treatment
Name	Number	
GX2CrNiMoCuN20-18-6	1.4557	Solution treat at 1 200 °C to 1 240 °C for 4 h minimum, quench in water.
GX2CrNiMoCuN25-6-3-3	1.4517	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX3CrNiMoCuN26-6-3	1.4515	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.
GX2CrNiMoN25-6-3	1.4468	Solution treat at 1 120 °C to 1 150 °C; quench in water. After solution annealing at high temperature, castings may be cooled to 1 040 °C to 1 010°C prior to water quenching in order to prevent cracks in complex shapes.

7 Supplementary requirements

A list of standardized supplementary requirements for use at the option of the purchaser is included in ISO 4990. Others, whether or not in ISO 4990, may be used with this International Standard upon agreement by the manufacturer and purchaser.

Annex A (informative)

UNS cast grades similar¹⁾ to ISO cast grades

Table A.1 — UNS cast grades similar to ISO cast grades

Grade designation		UNS number (similar grade)
Name	Number	
GX12Cr12	1.4011	J91150
GX7CrNiMo12-1	1.4008	—
GX4CrNi13-4 (QT1)	1.4317	J91540 (CA6NM)
GX4CrNi13-4 (QT2)	1.4317	J91540 (CA6NM)
GX4CrNiMo16-5-1	1.4405	—
GX2CrNi19-11	1.4309	J92500 (CF3)
GX2CrNiN19-11	1.4487	—
GX5CrNi19-10	1.4308	J92600 (CF8)
GX5CrNiNb19-11	1.4552	(CF8Cb)
GX2CrNiMo19-11-2	1.4409	J92800 (CF3M)
GX2CrNiMoN19-11-2	1.4490	—
GX4CrNiMoN26-5-2	1.4474	J 93371
GX5CrNiMo19-11-2	1.4408	—
GX5CrNiMoNb19-11-2	1.4581	(CF8MCb)
GX2CrNiMo19-11-3	1.4518	—
GX2CrNiMoN19-11-3	1.4508	—
GX2CrNiMoN22-5-3	1.4470	J 92205
GX2CrNiMoN25-7-3	1.4417	J 93380
GX2CrNiMoN26-7-4	1.4469	J 93404
GX5CrNiMo19-11-3	1.4412	J93000 (CG8M)
GX2NiCrMoCuN25-20-6	1.4588	J 94651
GX2CrNiMoCuN20-18-6	1.4557	J 93254
GX2CrNiMoCuN25-6-3-3	1.4517	J 93372
GX3CrNiMoCuN26-6-3	1.4515	—
GX2CrNiMoN25-6-3	1.4468	

NOTE The grade designations including the names and the numbers follow the rules of EN 10027-1 and EN 10027-2.

1) The similar UNS (Unified Numbering System) grades may not be equivalent to the grades in this International Standard.

Bibliography

- [1] EN 10027-1, *Designation system for steels — Part 1: Steel names*
- [2] EN 10027-2, *Designation system for steels — Part 2: Steel numbers*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person

or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs

and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™