

BS ISO 16132:2016



BSI Standards Publication

Ductile iron pipes and fittings — Seal coats for cement mortar linings

bsi.

National foreword

This British Standard is the UK implementation of ISO 16132:2016. It supersedes BS ISO 16132:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PSE/10, Iron pipes and fittings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 90826 2

ICS 23.040.10; 77.140.75

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2016.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

INTERNATIONAL STANDARD

BS ISO 16132:2016

ISO
16132

Second edition
2016-05-01

Ductile iron pipes and fittings — Seal coats for cement mortar linings

*Tuyaux et raccords en fonte ductile — Seal coats pour les revêtements
de mortier de ciment*



Reference number
ISO 16132:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO’s member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Performance test requirements	2
4.1	Short-term sealing efficiency	2
4.2	Long-term sealing efficiency	2
4.3	Cyclic pressure	2
5	Routine test requirements	3
5.1	General	3
5.2	Visual appearance	3
5.3	Coating thickness	3
5.4	Adhesion	3
6	Marking	3
Annex A (normative) Short-term sealing efficiency		4
Annex B (normative) Long-term sealing efficiency		6
Annex C (normative) Cyclic pressure test		10
Annex D (normative) Coating thickness measurement using test film		12
Annex E (normative) Adhesion test		14
Bibliography		16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 5, *Ferrous metal pipes and metallic fittings*, Subcommittee SC 2, *Cast iron pipes, fittings and their joints*.

This second edition cancels and replaces the first edition (ISO 16132:2004), of which it constitutes a minor revision.

Introduction

The intended purpose of a seal coat is to reduce the contact between a cement mortar lining and the contents of a water main, thereby restricting the leaching of inorganic materials into the water supply.

Seal coats are usually specified where the pipeline is to convey soft waters and/or where residence times are very long. Supply water quality data for such pipelines should be discussed between the prospective client and the seal coated pipe supplier to ensure the suitability of the product for use.

Attention is drawn to the fact that seal coated cement mortar lined surfaces in contact with, or likely to come into contact with, potable water need to conform to the requirements of national or international water supply or water quality regulations. Approval may be required for the individual components of the system, or for the combined system, depending upon the requirements of those national or international water supply or water quality regulations when used

- in accordance with the product manufacturer's instructions for use, and
- under any other appropriate conditions defined for that product within any published list of substances, products and processes approved to those water supply or water quality regulations.

Ductile iron pipes and fittings — Seal coats for cement mortar linings

1 Scope

This International Standard specifies the requirements for seal coatings for factory application to the surfaces of cement mortar linings, which are factory applied to the interior of ductile iron pipes and fittings.

It provides the performance requirements for short-term sealing efficiency, long-term durability and cyclic pressure, as well as the routine testing requirements for visual appearance, coating thickness and adhesion.

This International Standard is applicable to products for potable and other water applications.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2439, *Flexible cellular polymeric materials — Determination of hardness (indentation technique)*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 10523, *Water quality — Determination of pH*

ASTM D 3330, *Standard Test Method for Peel Adhesion of Pressure-Sensitive Tape*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 ductile iron

type of cast iron used for pipes, fittings and accessories in which graphite is present primarily in spheroidal form

3.2 fitting

casting other than a pipe, which allows pipeline deviation or change of direction or bore

Note 1 to entry: Flanged sockets, flanged spigots and collars are also classified as fittings.

3.3 test film

film of consistent thickness and density, morphologically stable at the temperature of the substrate during seal coat application, used as a surrogate surface for the measurement of coating thicknesses

3.4 pipe

casting of uniform bore, with straight axis, having either socket, spigot or flanged ends

Note 1 to entry: This does not apply to flanged sockets or flanged spigots and collars, which are classified as fittings.

3.5

product

seal coated, cement mortar lined iron pipe or fitting

3.6

seal coat

coating applied over a cement mortar lining to control the interactions between the lining and the contents of the conduit

3.7

performance test

proof of design test, done once and repeated only after a relevant change of material or supplier of the seal coat or lining, or relevant change in process design

4 Performance test requirements

4.1 Short-term sealing efficiency

When tested in accordance with [Annex A](#), the pH of the test water shall not exceed 9,5.

By agreement between the manufacturer of the product and the customer, other performance tests with other exposure periods, test waters and/or limits of pH value may be undertaken to suit particular national or customer requirements.

4.2 Long-term sealing efficiency

When tested in accordance with [Annex B](#), the pH of the test water shall not exceed 9,5 for each of the test samples.

By agreement between the manufacturer of the product and the customer, other performance tests with other exposure periods, test waters and/or limits of pH value may be undertaken to suit particular national or customer requirements.

Note that if the seal coat has been documented by the manufacturer to a National Standard and successfully used for a minimum of 5 years, the performance of the type test in accordance with [Annex B](#) is only required for significant changes in the coating material, type or formulation which could adversely affect the performance of the seal coat.

4.3 Cyclic pressure

When tested in accordance with [Annex C](#), visual inspection shall display no peeling of the seal coat or cracking with a width in excess of 0,8 mm. It is permissible to have some precipitation of white alkaline deposit.

At the conclusion of the visual inspection, the pipe samples shall immediately be tested for sealing efficiency in accordance with [Annex A](#). When tested in accordance with [Annex A](#), the pH of the test water shall not exceed 9,5 in either of the pipe samples.

Note that if the seal coat has been tested and successfully used for a minimum of 10 years, the performance of the type test in accordance with [Annex C](#) is only required for significant changes in the coating material, type, or formulation which could adversely affect the performance of the seal coat.

5 Routine test requirements

5.1 General

Coating and re-work procedures (e.g. drying regimes for solvent-based coatings and mixing and curing regimes for multi-component materials) shall be defined by the manufacturer of the product in agreement with the seal coat supplier, if necessary, so as to enable the product to conform to the requirements of this International Standard.

The tests specified in [5.2](#) to [5.4](#) shall be carried out on factory seal coated pipes or fittings as opposed to separately prepared samples.

Sampling plans for the tests specified in [5.2](#) to [5.4](#), specific to the seal coating material used, the size of the batch and the storage conditions, shall be specified by the manufacturer of the product for each batch of product.

Where a non-conforming product is identified, the product shall either be re-worked, so that it meets the requirements of this International Standard, or be rejected.

5.2 Visual appearance

When examined visually, the seal coat shall be free from any coating irregularities likely to be detrimental to the performance of the seal coat (as required by the performance tests in this International Standard). The manufacturer shall define those coating irregularities (e.g. hairline cracks or pinholes) which are considered not to be detrimental to the performance of the seal coat (as required by the performance tests in this International Standard), taking into account the nature of the seal coat material.

5.3 Coating thickness

When tested in accordance with [Annex D](#) or any appropriate method defined in ISO 2808, the wet or dry coating thickness shall be within the limits specified by the manufacturer of the product in conjunction with the seal coat supplier, if necessary.

5.4 Adhesion

When tested in accordance with [Annex E](#), one of the following requirements shall be met:

- where a cross cut is made in the seal coat, the adhesive strength shall fall within the range of 1 to 3;
- where no cross cut is used, the area of disbonded coating shall be less than 10 % of the test area.

Any area damaged during testing shall be repaired in accordance with a procedure defined by the manufacturer of the product in agreement with the seal coat supplier.

6 Marking

Each seal coated pipe or fitting shall be identified with the pipe manufacturer's name or mark.

In addition, seal coated pipes shall be indelibly and legibly marked on the external surface with the number and year of this International Standard.

Where pipes are bundled, the required markings may be applied to the bundle rather than to individual pipes.

Annex A (normative)

Short-term sealing efficiency

A.1 Principle

The initial or short-term sealing efficiency of a seal coat applied to a cement mortar lined surface that is exposed to a given test water is determined by measuring the pH of test water after three successive 24 h periods of exposure within a seal coated pipe sample.

A.2 Materials and apparatus

A.2.1 Paraffin wax, solventless epoxy, silicone resin, or other suitable sealing material that does not affect the pH of the water.

A.2.2 Test water, having a bicarbonate alkalinity of approximately 26 mg/l as CaCO_3 , at equilibrium with the atmosphere (i.e. no artificially induced carbon dioxide level), and with a stable pH of $8,0 \pm 0,1$.

A.2.3 Petroleum jelly.

This water shall be produced by dissolving $(0,027\ 8 \pm 0,000\ 5)$ g of CaCl_2 (calcium chloride) and $(0,042\ 8 \pm 0,000\ 5)$ g of NaHCO_3 (sodium bicarbonate) in 1 l of distilled water.

A.3 Apparatus

A.3.1 Clear glass or plastic plate.

A.3.2 pH meter, having capacity to measure pH 0 to pH 14, with discrimination of a pH of 0,01 or better.

A.4 Preparation of test samples

The test shall be carried out using a DN 150 seal coated and cement mortar lined pipe, 500 mm in nominal length, with a double spigot. The sample(s) shall be cut from pipe taken from normal production. Ensure any bare exposed cement mortar at pipe ends (resulting from cutting the pipe) has the seal coat applied.

A.5 Procedure

A.5.1 Seal the pipe at its lower end in a shallow pan of molten paraffin wax, or with a solventless epoxy, silicone resin or other suitable sealing material ([A.2.1](#)). Allow the material to harden/cure.

A.5.2 Fill the pipe to the brim with test water ([A.2.2](#)) at ambient temperature.

A.5.3 Cover the top of the pipe with a glass plate ([A.3.1](#)) and seal it with petroleum jelly ([A.2.3](#)).

A.5.4 After (24 ± 1) h, dispose of the water, rinse and refill with test water ([A.5.2](#) and [A.5.3](#)).

A.5.5 Repeat [A.5.4](#) twice, sampling the water after the third 24 h exposure period.

A.5.6 Determine the pH of the water sample using the pH meter ([A.3.2](#)) in accordance with ISO 10523.

Annex B (normative)

Long-term sealing efficiency

B.1 Principle

The long-term durability of a seal coat, applied to a cement mortar lining, is determined by measuring the sealing efficiency of the seal coat, after exposure to a cycle of swabbing, high velocity flowing water, pressurization and de-pressurization for a period of 3 months.

B.2 Materials

B.2.1 Test water, shall be the same as that defined for test water in [Annex A](#).

B.3 Apparatus

All the materials and components of the test pipeline shall be selected so that they do not impact on the performance of the seal coating.

B.3.1 Soft foam swab, bullet shaped, with a nominal density of 25 kg/m³ to 35 kg/m³, and an indentation hardness index (method A of ISO 2439) of (200 ± 50) N. When placed inside the test pipe, the swab shall be of a diameter such that a compression of 15 % to 25 % is achieved.

B.3.2 Pump, capable of pumping to produce a flow velocity of 2 m/s in the test pipes.

B.3.3 Pressure gauge, capable of measuring pressure of at least 6 bar with a minimum readability of 0,5 bar.

B.3.4 Flowmeter or other suitable device, to enable the measurement of a flow velocity of at least 2 m/s with a minimum readability of 0,2 m/s.

B.3.5 Hand pump or other suitable device, to enable pressurization of the test pipeline.

B.3.6 Flow control valve, e.g. gate valve or other suitable device, to enable setting of the flow velocity.

B.3.7 Air bleed valve, to enable the removal of air from the pipeline.

B.3.8 Outlet/inlet valve, to allow the pipeline to be filled with water and drained of water.

B.3.9 Connecting pipeline components, to enable the assembly and restraint of the pipeline.

B.3.10 DN 150 flow development pipes (FDP), a minimum of 500 mm long, to establish uniform flow in the pipeline after a bend.

B.3.11 Accumulator, (optional device) to reduce pressure variations during the test.

B.3.12 Pressure relief valve, (optional device) to prevent over pressurization during the test.


B.3.13 Water cooler, (optional device) to prevent overheating of the water during the test.

B.4 Preparation of test samples

The test shall be carried out using two nominally 500 mm long, DN 150 seal coated, cement mortar lined, ductile iron pipe samples. These samples shall be cut from two ductile iron pipes taken from normal production batches. Prior to the test, the seal coat and the swab shall be wetted and the swab shall be passed through each of the test samples once.

B.5 Procedure

B.5.1 Assemble the pipeline to allow water to be re-circulated, under pressure, through the samples in accordance with [Figure B.1](#). Note that the pipe components will need to be held in place to withstand the forces generated by the internal water pressure.



- Key**
- 1 inlet/outlet valve
 - 2 flow control valve
 - 3 pump
 - 4 water cooler (optional)
 - 5,6 flow development pipe to assist in developing constant flow
 - 7,8 pipe sample
 - 9 accumulator (optional)
 - 10 pressure relief valve (optional)
 - 11 pressure gauge
 - 12 air bleed valve
 - 13 hand pressure pump
 - 14 water meter
 - a Direction of flow.

Figure B.1 — Schematic diagram of durability pipeline

B.5.2 Fill the pipeline with the test water and bleed out any entrapped air.

B.5.3 Pump the water in the pipeline up to a minimum pressure of 6 bar ± 1 bar and maintain the pressure for the duration of the test. Note that at the start of the test, small amounts of additional water may need to be added to the pipeline in order to maintain the pressure. The use of an optional accumulator will reduce pressure variations.

B.5.4 Start the pump and increase the flow velocity up to a minimum velocity of 2 m/s ± 0,2 m/s for the duration of the test. The flowmeter may be used to determine the flow velocity by noting the volume of water passing through the pipeline in a set period of time, together with the knowledge of the internal diameter of the test samples. The test is to be conducted at ambient temperature. The temperature of the

water in the pipeline may increase significantly due to the heat from the pump. To prevent this some of the water can be passed through a cooler (as shown in [Figure B.1](#)).

B.5.5 After one month of operation stop the flow, de-pressurize the pipeline, drain and discard the water, and remove the test samples. Wet the seal coat and the swab, then pass the swab once through each of the test samples.

B.5.6 Repeat steps [B.5.1](#) to [B.5.5](#) a further two times to complete 3 months of exposure.

B.5.7 Assess the sealing efficiency of the test samples, after the 3-month exposure, by testing each sample in accordance with [Annex A](#).

Annex C (normative)

Cyclic pressure test

C.1 Principle

The cyclic pressure test is determined as a measure of the durability of a seal coat, applied to a cement mortar lining, when subjected to water contact and cyclic pressurization and de-pressurization.

C.2 Apparatus and material

C.2.1 Test media, tap water.

C.2.2 Hand pump or alternative device, to enable pressurization of the test pipe.

C.2.3 Inlet valve, to allow the pipe to be filled with water and pressurization.

C.2.4 Air bleed valve, to enable the removal of air from the pipe and de-pressurization.

C.2.5 Pressure gauge, capable of measuring pressure of at least 25 bar with a minimum discrimination of 0,5 bar.

C.2.6 Connecting pipe components, to enable the assembly and restraint of the pipe. For example, socket plug, spigot plug and support structure for restrain the pipe during pressurization.

C.3 Sample preparation

The test shall be carried out using two nominally 500 mm long, DN 150 seal coated, cement mortar lined, ductile iron pipe samples. These samples shall be cut from two ductile iron pipes taken from normal production batches ensuring that the seal coat is completely dry/cured before test.

C.4 Procedure

C.4.1 Test temperature, the test shall be carried out at ambient temperature.

C.4.2 Assembly, assemble test components in accordance with [Figure C.1](#).

NOTE The pipe components need to be held in place to withstand the forces generated by the internal water pressure.


C.4.3 Preparation, fill the pipe with tap water and bleed out any entrapped air, and soak for 24 h.

C.4.4 Pressurization and retention, pump the water pressure up to 16 bar to 18 bar, and maintain it in that range for 2 h. During the maintenance period, continuously monitor the pressure in the pipes, and re-pressure as required.

C.4.5 De-pressurization, after 2 h, de-pressurize the pipe to 0 bar at a rate within the range of 0,5 bar to 1,0 bar/s and maintain at 0 bar for 2 h.

C.4.6 Cycle, [C.4.4](#) to [C.4.5](#) is one cycle. Repeat that cycle to achieve a total of 25 cycles.

C.4.7 Inspection, after 25 cycles, disassemble the components and visually inspect the seal coat immediately using a light source to illuminate the seal coat along the full length of the sample to determine if there is any peeling of the seal coat or cracking in excess of 0,8 mm in width.



Key

- 1 end caps
- 2 pipe samples
- 3 pipe joiner
- 4 inlet valve
- 5 pressure gauge
- 6 outlet valve/air bleed

Figure C.1 — Schematic diagram of cyclic pressure test assembly

Annex D (normative)

Coating thickness measurement using test film

D.1 Principle

The average thickness of dry coating on a test film is determined to within 5 µm either by using a micrometer or by using a weight and area method.

D.2 Apparatus

D.2.1 Test film, of known thickness and mass/unit area, and having a minimum area of 5 000 mm² (0,005 0 m²).

D.2.2 Micrometer, having the capacity to measure to at least 10 mm, with a resolution of 5 µm or less.

D.2.3 Tape measure, at least 1m in length, with a resolution of 1 mm or less.

D.2.4 Analytical balance, having at least 200 g capacity and a resolution of 0,01 g or less.

D.3 Preparation of test samples

D.3.1 Immediately prior to applying the seal coating, attach the piece of test film to the surface of the lining using self-adhesive tape.

The test film may be attached to the surface by applying tape to two edges of the film.

D.3.2 After applying the seal coating, remove the test film. Allow the coating on the film to dry/cure.

D.3.3 When the coating on the film is dry/cured, determine the dry film thickness using one or both of the methods [D.4](#) or [D.5](#).

D.4 Micrometer measurement method

D.4.1 Procedure

D.4.1.1 Select positions on the test film, where readings are to be taken, which are free from surface irregularities and are not less than 20 mm from the coated test film edge and not less than 20 mm apart.

For large areas of coated test film, select the number and distribution of the test areas to give a representative indication of the coated film thickness.

D.4.1.2 Position the micrometer ([D.2.2](#)) with its fixed jaw in contact with the coated side of the coated test film at the first test area. Gently screw home its movable jaw until a resistance is felt and no further movement of the jaw occurs on turning the ratchet.

Note the reading on the micrometer. Record the reading on a test sheet.

D.4.1.3 Release the micrometer and repeat the whole procedure in [D.4.1.2](#), at each of the other test positions.

D.4.2 Calculation

D.4.2.1 Calculate the film thickness at each point by subtracting the mean thickness of the test film from each thickness reading.

The mean thickness of the test film, if unknown, may be determined in accordance with [D.4.1.2](#), using an un-coated test film sample, taking the average of at least 10 readings.

D.4.2.2 Calculate the mean value for the thickness of the coating to the nearest multiple of 5 µm or less (depending upon the accuracy of the micrometer).

D.5 Weight and area method — Procedure

D.5.1 In order to produce a rectangular sample, cut away areas of the coated test film which have adhesive tape attached.

D.5.2 Using a tape measure ([D.2.3](#)), measure the width and length of the test film to an accuracy of ±1 mm, and then calculate the film area, A , in square metres (m²) to five decimal places.

D.5.3 Record the weight of the uncoated test film, W , in grams (g) to four significant figures using the balance ([D.2.4](#)).

D.5.4 Record the weight of the coated test film, G , in grams (g) to four significant figures using the balance ([D.2.4](#)).

D.5.5 Determine the coating thickness, T , in micrometres (µm), using Formula (D.1):

$$T = (G - W) / (D \times A) \quad (D.1)$$

where D is the density of the dried/cured coating in grams per cubic centimetre (g/cm³).

Annex E (normative)

Adhesion test

E.1 Principle

The adhesion of a seal coat to a cement mortar substrate is assessed by applying and removing adhesive tape. For seal coats with a specified minimum thickness of greater than 100 µm, a cross cut is made in the film before application of the adhesive tape. For seal coats with a specified minimum thickness of less than or equal to 100 µm, the adhesive tape is applied directly to the seal coat.

E.2 Apparatus

E.2.1 Cutting tool, e.g. sharp bladed knife, scalpel, high-speed micro-abrasive disc, or other cutting device.

E.2.2 Cutting guide, e.g. steel or other hard metal straight edge to ensure straight cuts.

E.2.3 Soft brush, for removing debris from the cut area.

E.2.4 Light Source, to assist in determining whether the cuts have been made through the film to the substrate.

E.2.5 Adhesive Tape, 25 mm to 50 mm wide with a minimum peel adhesion strength of 0,35 N/mm width when measured in accordance with ASTM D3330, Test method A.

E.3 Procedure

E.3.1 Select an area of seal coated surface and ensure that it is clean and dry.

E.3.2 Where applicable (see [E.1](#)) using the cutting tool ([E.2.1](#)) with the straight edge ([E.2.2](#)) as a guide, in one steady motion, make two cuts in the film, each approximately 50 mm long, which intersect near their middle with a smaller angle of between 30° and 45°. Remove any cutting debris using a soft brush ([E.2.3](#)). Using the light source ([E.2.4](#)), inspect the incisions to establish that the coating film has been penetrated. If not, repeat [E.3.2](#).

E.3.3 Remove a length of adhesive tape ([E.2.5](#)) at least 75 mm long from the roll. Smooth the tape into place using finger pressure. Where a cross cut is used, place the centre of the tape at the intersection of the cuts in the same direction as the smaller angles. Smooth the tape into place using finger pressure in the area of the incisions.

E.3.4 Within (60 ± 30) s of application, remove the tape by grasping the free end and slowly pull it back on itself, without jerking, at an angle of approximately 180° to the plane of the seal coated lining.

E.3.5 Inspect the area of the tape for removal of seal coat from the mortar substrate. Only coating removed by adhesive failure of the bond between the seal coat and the mortar shall be considered in the assessment. Coating removed by cohesive failure, either within the seal coat or within the mortar (shown by a white/grey layer on the underside of the tape), shall not be considered in the assessment.

E.3.6 If a cross cut is used, determine the adhesion in terms of the following scale:

- 1) no peeling or removal of seal coat;
- 2) traces of peeling or removal along incisions or at the intersection;
- 3) jagged removal of seal coat along incisions up to 2 mm either side;
- 4) jagged removal of seal coat along incisions up to 4 mm either side;
- 5) removal of most of the area of the X on to the tape;
- 6) removal beyond the area of the X.

E.3.7 If no cross cut is used, determine the total area of disbonded coating as a percentage of the total area of coating originally covered by the adhesive tape.

Bibliography

[1] ISO 2531, *Ductile iron pipes, fittings, accessories and their joints for water applications*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

