



BSI Standards Publication

Thermal insulation products — Sheep wool mat and board — Specification

National foreword

This British Standard is the UK implementation of ISO 17749:2018.

The UK participation in its preparation was entrusted to Technical Committee B/540/8, Mirror committee for ISO/TC 163 - Thermal Performance and Energy use in the built Environment.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 85193 3

ICS 91.100.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2018.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
17749

First edition
2018-05-01

Thermal insulation products — Sheep wool mat and board — Specification

*Produits d'isolation thermique — Panneaux et tapis en laine de
mouton — Spécifications*



Reference number
ISO 17749:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviated terms	2
4.1 Symbols.....	2
4.2 Abbreviated terms.....	3
5 Requirements	3
5.1 General.....	3
5.2 Material properties.....	3
5.2.1 Thermal resistance and thermal conductivity.....	3
5.2.2 Length and width.....	4
5.2.3 Thickness.....	4
5.2.4 Reaction to fire.....	5
5.2.5 Moisture content.....	5
5.3 Specific requirements.....	5
5.3.1 Apparent density.....	5
5.3.2 Sound absorption.....	5
5.3.3 Formaldehyde release.....	5
5.3.4 Thickness recovery ratio.....	5
6 Test methods	6
6.1 Sampling.....	6
6.2 Conditioning.....	6
6.3 Procedure.....	6
6.3.1 General.....	6
6.3.2 Thermal resistance and thermal conductivity.....	7
7 Designation code	7
8 Product conformity	7
8.1 General.....	7
8.2 Initial type testing.....	8
8.3 Factory production control.....	8
9 Marking and labelling	8
Annex A (normative) Determination of the declared values of thermal resistance and thermal conductivity	9
Annex B (normative) Factory production control	11
Annex C (normative) Determination of the thermal conductivity in relation to moisture content	12
Annex D (normative) Thickness-recovery ratio test method	14
Annex E (informative) Evaluation of conformity	16
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products*.

Thermal insulation products — Sheep wool mat and board — Specification

1 Scope

This document specifies requirements for factory-made products of sheep wool, which are used for the thermal insulation of buildings. This document applies to material containing more than 50 % (by mass) natural sheep wool, with the balance being polymeric material. The products are delivered as a mat or board with or without facings.

This document describes product characteristics and testing methods, marking, labelling and packaging.

Products covered in this document are also used in prefabricated thermal insulation systems and composite panels; the performance of systems incorporating these products is not covered.

The sheep wool mat and board thermal insulation is not to be used when the continuous service temperature of the substrate is outside the range of $-60\text{ }^{\circ}\text{C}$ to $+80\text{ }^{\circ}\text{C}$.

The use of mothproof agent residues is outside the scope of this document.

This document does not address all the health and safety aspects associated with its use. It is the responsibility of the user of this document to establish appropriate health and safety practices.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 354](#), *Acoustics — Measurement of sound absorption in a reverberation room*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

[ISO 9229](#), *Thermal insulation — Vocabulary*

[ISO 11654](#), *Acoustics — Sound absorbers for use in buildings — Rating of sound absorption*

[ISO 11925-2](#), *Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test*

ISO 12460-1, *Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the 1-cubic-metre chamber method*

[ISO 12570](#), *Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature*

ISO 12576-1, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products*

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

ISO 29466, *Thermal insulating products for building applications — Determination of thickness*

k	factor related to the number of test results available
R_D	declared thermal resistance, $m^2 \cdot K/W$
R_i	one test result of thermal resistance, $m^2 \cdot K/W$
$R_{90/90}$	90 % fractile with a confidence level of 90 % for the thermal resistance, $m^2 \cdot K/W$
ρ_a	apparent density, kg/m^3
r	thickness recovery ratio, %
L	declared class or level for length tolerances
T	declared class or level for thickness tolerances
W	declared class or level for width tolerances

4.2 Abbreviated terms

SWM	sheep wool mat
SWB	sheep wool board
ITT	initial type test
FPC	factory production control

5 Requirements

5.1 General

Product properties shall be determined in accordance with [Clause 6](#).

The test methods to be used for determination of each property are given in [Table 4](#), which also shows the required test specimen dimensions and the minimum number of test specimens required to give one test result.

One test result for a product property is the average of the measured values on the number of test specimens given in [Table 4](#).

NOTE For FPC, see [Annex B](#).

5.2 Material properties

5.2.1 Thermal resistance and thermal conductivity

For thermal conductivity testing, the specimen shall be conditioned according to the following: $(80 \pm 2)^\circ C$ to constant mass.

Thermal resistance and thermal conductivity shall be based upon measurements carried out in accordance with ISO 8302 or ISO 8301 for thick products.

The thermal resistance and thermal conductivity shall be determined in accordance with the procedures given in [Annex A](#) and declared by the manufacturer according to the following.

- The reference mean temperature shall be $10^\circ C$ and/or $23^\circ C$.
- The measured values shall be expressed with three significant figures.

- For products of uniform thickness, the thermal resistance, R_D , shall always be declared. The thermal conductivity, λ_D , shall be declared where possible. Where appropriate, for products of non-uniform thickness (i.e. for sloped and tapered products), only the thermal conductivity, λ_D , shall be declared.
- The declared thermal resistance, R_D , and the declared thermal conductivity, λ_D , shall be given as limit values representing at least 90 % of the production, determined with a confidence level of 90 %.
- The value of the thermal conductivity, $\lambda_{D\ 90/90}$, shall be rounded up to the nearest 0,001 W/(m·K) and declared as λ_D in levels with steps of 0,001 W/(m·K).
- The declared thermal resistance, R_D , shall be calculated from the nominal thickness, d_N , and the corresponding thermal conductivity, $\lambda_{90/90}$.
- The value of the thermal resistance, $R_{90/90}$ (when calculated from the nominal thickness, d_N , and the corresponding thermal conductivity, $\lambda_{D90/90}$), shall be rounded down to the nearest 0,05 m²·K/W and declared as R_D in levels with steps of 0,05 m²·K/W.
- The value of $R_{90/90}$, for those products for which only the thermal resistance is measured directly, shall be rounded down to the nearest 0,05 m²·K/W and declared as R_D in levels with steps of 0,05 m²·K/W.

Examples of the determination of declared values of thermal resistance, R_D , and thermal conductivity, λ_D , are given in [Annex A](#).

Examples of the determination of declared values of thermal conductivity in relation to moisture content λ are given in [Annex C](#).

5.2.2 Length and width

The length, l , and width, b , shall be determined in accordance with ISO 29465. No test result shall deviate from the nominal values by more than the tolerances given in [Table 1](#) and [Table 2](#).

Table 1 — Products for length tolerances

Product	Tolerances mm
SWM	± 5 or ± 0,4 % ^a
SWB	± 3 or ± 0,4 % ^a
^a Whichever gives the greatest numerical tolerance.	

Table 2 — Products for width tolerances

Product	Tolerances mm
SWM	± 2 or ± 0,4 % ^a
SWB	± 2 or ± 0,4 % ^a
^a Whichever gives the greatest numerical tolerance.	

5.2.3 Thickness

The thickness, d , shall be determined in accordance with ISO 29466, under a pressure of 50 Pa. No test result shall deviate from the nominal thickness, d_N , by more than the tolerances given in [Table 3](#).

Table 3 — Products for thickness tolerances

Product	Tolerances
	mm
SWM	+5
	0
SWB	+3
	-2

5.2.4 Reaction to fire

The reaction to fire characteristics of the product as placed on the market shall be measured according to [ISO 11925-2](#).

5.2.5 Moisture content

Moisture content, H , shall be determined in accordance with [ISO 12570](#) (80 ± 2 °C). No test result shall exceed a mass fraction of 30 %.

5.3 Specific requirements

5.3.1 Apparent density

Apparent density, ρ_a , is a useful identification parameter. Apparent density of mat and board shall be determined in accordance with [ISO 29470](#). No mean value of a product shall deviate by more than ± 15 % from the declared value given in the manufacturer's literature.

5.3.2 Sound absorption

Sound absorption coefficient shall be determined in accordance with [ISO 354](#). The sound absorption characteristics shall be calculated in accordance with [ISO 11654](#) using the values for the practical sound absorption coefficient, α_p , at the frequencies 125 Hz, 250 Hz, 500 Hz, 1 000 Hz, 2 000 Hz and 4 000 Hz and the single number value for the weighted sound absorption coefficient, α_w . α_p and α_w shall be rounded to the nearest 0,05 (α_p larger than 1 shall be expressed as $\alpha_p = 1$) and declared in levels with steps of 0,05.

The weighted sound absorption coefficient, α_w , shall be declared. No result of α_w shall be lower than the declared level.

5.3.3 Formaldehyde release

The formaldehyde release amount shall be measured and declared according to ISO 12460-1. The formaldehyde release shall be declared.

5.3.4 Thickness recovery ratio

Determine the thickness recovery ratio in accordance with [Annex D](#). The thickness recovery ratio of the mat shall not be less than 100 %.

NOTE For the mat, the buyer needs the thickness recovery ratio data to ensure the thermal performance in the application.

6 Test methods

6.1 Sampling

Test specimens shall be taken from the same sample with a total area not less than 1 m² and sufficient to cover the needed tests. The shorter side of the sample shall not be less than 300 mm or full size of the product, whichever is the smaller.

6.2 Conditioning

Condition the test specimen at (23 ± 2) °C and (50 ± 10) % relative humidity or (27 ± 5) °C and (65 ± 10) % relative humidity for 6 h.

For thermal conductivity testing, the conditioning shall be according to [5.2.1](#).

6.3 Procedure

6.3.1 General

[Table 4](#) gives the dimensions of the test specimens, the minimum number of measurements required to get one test result and any specific conditions which are necessary.

The test may be performed on the unfaced product, if the facing is known to have no relevance to the test result.

Table 4 — Test methods, test specimens and specific conditions

Sub-clause	Test method		Test specimen length and width (mm)	Minimum number of specimens for one test result	Specific conditions	Material requirements
No.	Title					
5.2.1	Thermal resistance and thermal conductivity	ISO 8301 or ISO 8302	Required in ISO 8301 or ISO 8302	3	(80 ± 2) °C to constant mass	Declared
5.2.2	Length and width	ISO 29465	Full-size	3	—	Table 1 and Table 2
5.2.3	Thickness	ISO 29466	Full size	3	Method in Annex B ; pressure at 50 Pa	Table 3
5.2.4	Reaction to fire	ISO 11925-2	250 × 90	6	—	Declared
5.2.5	Moisture content	ISO 12570	200 × 200	3	(80 ± 2) °C to constant mass	30 % maximum
5.3.1	Apparent density	ISO 29470	Full size	3	(23 ± 2) °C and (50 ± 5) % RH to constant mass	Declared
5.3.2	Sound absorption	ISO 354	10 m ² minimum	3	—	Declared in steps of 0,05
5.3.3	Formaldehyde release	ISO 12460-1	Required in ISO 12460-1	3	—	Declared
5.3.4	Thickness recovery ratio	Annex D	Full size	3	—	100 % recovery

6.3.2 Thermal resistance and thermal conductivity

For thermal conductivity testing, the specimen shall be conditioned according to: (80 ± 2) °C to constant mass.

Thermal resistance and thermal conductivity shall be determined in accordance with ISO 8301 or ISO 8302 for thick products and under the following conditions:

- at a mean temperature of $(10 \pm 0,30)$ °C or at a mean temperature of $(23 \pm 0,30)$ °C.

Thermal resistance and thermal conductivity can also be measured at other mean temperatures, providing that the accuracy of the relationship between temperature and thermal properties is well documented.

Thermal resistance and thermal conductivity shall be determined directly at measured thickness. In the event that this is not possible, they shall be determined by measurements on other thicknesses of the product providing that

- the product is of similar chemical and physical characteristics and is produced on the same production unit, and;
- it can be demonstrated that the thermal conductivity, λ , does not vary more than 2 % over the range of thicknesses where the calculation is applied.

When measured thickness is used for testing of thermal resistance and thermal conductivity, the test thickness shall be the smallest of the measured points on the test specimen (and not the mean) as far as possible to avoid any air gaps during testing.

Examples of the determination of declared values of thermal conductivity in relation to moisture content λ are given in [Annex C](#).

7 Designation code

A designation code for the product shall be given by the manufacturer. The following shall be included except when there is no requirement for a property described in [5.3](#):

- the sheep wool mat and sheep wool board abbreviated term, SWM and SWB;
- a reference to this document, i.e. ISO 17749;
- the thickness, d_N ;
- the width and length, b and l ;
- the thermal resistance and/or thermal conductivity, λ_D and/or R_D .

The designation code for an SWM product is illustrated by the following example.

EXAMPLE SWM — ISO 17749 — d_N90 - $b395$ - $l8500$, $\lambda_D 0,042$ W/(m·K), $R_D 2,15$ m²·K/W

NOTE The characteristics determined in [5.2](#) are not included in the designation code if a limit value (threshold value) is given for the product.

8 Product conformity

8.1 General

The manufacturer shall be responsible for the conformity of their product with the requirements of this document.

The manufacturer or their authorized representative shall make available, in response to a request, a certificate or declaration of conformity as appropriate. [Annex E](#) contains information on evaluation of product conformity.

8.2 Initial type testing

All characteristics defined in [Clause 5](#), if declared, shall be subject to initial type testing in accordance with [Annex B](#).

8.3 Factory production control

The minimum frequencies of tests in the factory production control shall be in accordance with [Annex B](#). When indirect testing is used, the correlation to direct testing shall be established in accordance with ISO 12576-1.

9 Marking and labelling

Products which refer to this document shall be marked clearly on the product, label or packaging, with the following information:

- product name or other identifying characteristic;
- name or identifying mark and address of the manufacturer or their authorized representative;
- shift or time of production or traceability code;
- reaction to fire performance of the product as placed on the market in accordance with the test methods specified in [5.2.4](#) and any additionally required national or regional test and classification methods;
- declared thermal resistance (R_D);
- declared thermal conductivity (λ_D);
- nominal thickness (d_N);
- designation code as given in [Clause 7](#);
- nominal length;
- nominal width;
- type of facing, if any;
- number of pieces and area in the package, as appropriate;
- that the products shall be protected from rain during storage.

Annex A (normative)

Determination of the declared values of thermal resistance and thermal conductivity

A.1 General

It is the responsibility of the manufacturer to determine the declared values of thermal resistance and thermal conductivity. The manufacturer shall demonstrate conformity of the product to its declared values. The declared values of thermal resistance and thermal conductivity of a product shall be the expected values of these properties during an economically-reasonable working life under normal conditions, assessed through measured data from properly conditioned specimens.

A.2 Input data

In order to calculate the declared values, the manufacturer shall have at least 10 test results for thermal resistance or thermal conductivity, obtained from internal or external direct measurements. These measurements shall be carried out at regular intervals, spread over a period of the last 12 months. If fewer than 10 test results are available, that period may be extended until 10 results are obtained, but in a maximum period of three years, within which the product and production conditions have not changed significantly.

For new products, the 10 thermal resistance or thermal conductivity test results shall be obtained spread over a minimum period of 10 days.

The declared values shall be calculated according to the method given in [A.3](#) and shall be recalculated at intervals not exceeding three months of production.

A.3 Declared values

The derivation of the declared values, R_D and λ_D , from the calculated values, $R_{90/90}$ and $\lambda_{90/90}$, shall use the rules given in [5.2.1](#) which include the rounding conditions.

A.3.1 Case where both thermal resistance and thermal conductivity are declared

The declared values, R_D and λ_D , shall be derived from the calculated values, $R_{90/90}$ and $\lambda_{90/90}$, which are determined using [Formula \(A.1\)](#), [Formula \(A.2\)](#) and [Formula \(A.3\)](#).

$$\lambda_{90/90} = \lambda_{\text{mean}} + k \times s_{\lambda} \quad (\text{A.1})$$

$$s_{\lambda} = \sqrt{\frac{\sum_{i=1}^n (\lambda_i - \lambda_{\text{mean}})^2}{n-1}} \quad (\text{A.2})$$

$$R_{90/90} = d_N / \lambda_{90/90} \quad (\text{A.3})$$

Values for k shall be taken from [Table A.1](#).

A.3.2 Case where only thermal resistance is declared

The declared value, R_D , shall be derived from the calculated value, $R_{90/90}$, which is determined using [Formula \(A.4\)](#) and [Formula \(A.5\)](#).

$$R_{90/90} = R_{\text{mean}} - k \times s_R \tag{A.4}$$

$$s_R = \sqrt{\frac{\sum_{i=1}^n (R_i - R_{\text{mean}})^2}{n-1}} \tag{A.5}$$

Values for k shall be taken from [Table A.1](#).

Table A.1 — Values for k for a one-sided 90 % tolerance interval with a confidence level of 90 %

Number of test results	k^a
10	2,07
11	2,01
12	1,97
13	1,93
14	1,90
15	1,87
16	1,84
17	1,82
18	1,80
19	1,78
20	1,77
22	1,74
24	1,71
25	1,70
30	1,66
35	1,62
40	1,60
45	1,58
50	1,56
100	1,47
300	1,39
500	1,36
2 000	1,32

^a For other values of test results, use ISO 12491 or linear interpolation.

Licensed copy: Imperial College, Imperial College London, Version correct as of 16/05/2018

Annex B (normative)

Factory production control

Table B.1 — Minimum product testing frequencies

Subclause		Minimum testing frequencies ^a		
No.	Title	Direct testing	Indirect test method	Testing frequency
5.2.1	Thermal resistance and thermal conductivity	1 per 3 months and indirect testing	Apparent density	1 per 2 h
5.2.2	Length and width	1 per 2 h	—	— ^b
5.2.3	Thickness	1 per 2 h	—	— ^b
5.2.4	Reaction to fire	ISO 11925-2 , 1 per week; EN 13823 , 1 per 2 years and indirect testing	Manufacturer's method	1 per day
5.2.5	Moisture content	1 per week and indirect testing	Manufacturer's method	1 per day
5.3.1	Apparent density	Once per production batch	—	— ^b
5.3.2	Sound absorption	1 per 5 years	Apparent density and thickness	1 per 2 h
5.3.3	Thickness recovery ratio	1 per 3 months	Manufacturer's method	1 per batch

^a The minimum testing frequencies, expressed in test results, shall be understood as the minimum for each production unit/line under stable conditions. In addition to the testing frequencies given above, testing of the relevant properties of the product shall be repeated when changes or modifications are made that are likely to affect the conformity of the product.
For mechanical properties, the testing frequencies given are independent of the change of the product. In addition, the manufacturer shall establish rules for process adjustments related to these properties when changing the product.

^b Frequencies are not given, as test methods are not available.

Annex C (normative)

Determination of the thermal conductivity in relation to moisture content

The thermal conductivity corresponding to a conditioning atmosphere of (23 ± 2) °C and (50 ± 5) % relative humidity shall be calculated using [Formula \(C.1\)](#):

$$\lambda = \lambda_{23,\text{dry}} \times [1 + a (u_{23,50})] \quad (\text{C.1})$$

where

- $\lambda_{23,\text{dry}}$ is the thermal conductivity measured in accordance with ISO 8301 or ISO 8302 after conditioning at a dry reference state [[ISO 12570](#) (80 ± 2 °C)];
- $u_{23,50}$ is the moisture content of the specimen measured in accordance [ISO 12571](#);
- a is a coefficient obtained by regression.

The coefficient a shall be determined using the measurements of λ made in accordance with ISO 8301 or ISO 8302 under the following procedure for conditioned test specimens:

- in the dry reference state [[ISO 12570](#) (80 ± 2 °C)];
- at (23 ± 2) °C and (50 ± 5) % relative humidity;
- under another set of conditions, preferably (23 ± 2) °C and (80 ± 5) % relative humidity.

For the determination of a , at least five specimens shall be taken from different runs.

NOTE The coefficient a can be represented on a graph, as shown in [Figure C.1](#).


During measurement of λ , precautions shall be taken to avoid moisture absorption by the specimen. It is acceptable, for instance, to put the test specimen into a thin plastic bag.

The relative change in weight of the specimen, before and after measurement of λ , shall not exceed 0,1 %, when weighed with an accuracy of 0,5 g.

The determination of a and $u_{23,50}$ shall be made only once, except in the case where noticeable change of product properties occurs.

Thermal properties shall be measured directly at the nominal thickness of the test specimen. In the event that this is not possible they shall be determined by measurements on other thicknesses of the material providing that:

- the material is of similar chemical and physical characteristics and is produced on the same production line;
- and it can be demonstrated that λ does not vary more than 2 % over the range of thicknesses where the calculation is applied.



Key

X moisture content (kg/kg)

Y $\frac{\lambda}{\lambda_{23, \text{dry}}} - 1$

Figure C.1 — Example of a graphic representation of “a”
 ($a = 0,0362/0,0348 - 1 = 0,04$ in this example)

Annex D (normative)

Thickness-recovery ratio test method

D.1 General

For the mat, sometimes the buyer needs the thickness recovery ratio data to make sure the thermal performance in application.

D.2 Test procedure

Open the package of sheep wool mat.

Put the full-sized mat on a flat plate and measure the thickness after at least 48 h and before 72 h. In case of dispute, the testing shall be performed at (23 ± 2) °C and (50 ± 5) % relative humidity.

Measure the thickness (t_1) of the full-sized mat in accordance with ISO 29466.

D.3 Calculation

Calculate the thickness recovery ratio (r) using [Formula \(D.1\)](#):

$$r = \frac{t_1}{d_N} \quad (\text{D.1})$$

where

t_1 is the thickness of the mat 48 h after opening package, expressed in millimetres;
 d_N is the nominal thickness of the mat, expressed in millimetres.

D.4 Report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 17749:2018;
- b) the product identification:
 - 1) product designation code, factory, manufacturer or supplier;
 - 2) packaging;
 - 3) form in which the product arrived at the laboratory;
 - 4) other information as appropriate;
- c) the test procedure:
 - 1) pre-test history and sampling (name of person taking the samples and sampling site);
 - 2) conditioning;
 - 3) deviations from ISO 29466, if any;

- 4) conditioning and testing conditions in tropical countries, if applicable;
- 5) date of test;
- 6) general information relating to the test including the pressure;
- 7) any occurrences that can have affected the results;

NOTE It is expected that information about the apparatus and identity of the technician be available in the laboratory, but it is not necessary that it be recorded in the report.

- d) the result.

Annex E (informative)

Evaluation of conformity

The evaluation of conformity should be carried out in accordance with the most appropriate system in ISO 12576-1 and should be based on initial type testing (ITT) and factory production control (FPC) by the manufacturer, including product assessment and tests on samples taken at the factory.

Grouping products is possible if a valid demonstration of the relation between products is given.

Bibliography

- [1] ISO 12491, *Statistical methods for quality control of building materials and components*
- [2] [ISO 13787](#), *Thermal insulation products for building equipment and industrial installations — Determination of declared thermal conductivity*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
 - The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
 - A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
 - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK