



bsi.

National foreword

This British Standard is the UK implementation of [ISO 19427:2019](#).

The UK participation in its preparation was entrusted to Technical Committee MHE/2, Wire ropes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 96850 1

ICS 93.040; 77.140.65

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2019.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

INTERNATIONAL STANDARD

ISO
19427

First edition
2019-01-04

Steel wire ropes — Pre-fabricated parallel wire strands for suspension bridge main cable — Specifications

*Câbles en acier — Câbles à fils parallèles préfabriqués pour câble
porteur de pont suspendu — Spécifications*



Reference number
ISO 19427:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Designation of product	5
5 Requirements	5
5.1 Traceability	5
5.2 Lengths and fabrication tolerances	5
5.3 Material and manufacture	6
5.4 Mechanical property	7
5.4.1 Tensile property	7
5.4.2 Modulus of elasticity	7
5.4.3 Fatigue property	7
6 Test methods	8
6.1 Material test	8
6.2 Tensile test of PPWS	8
6.3 Modulus of elasticity	8
6.4 The test of socketing process	9
6.5 Fatigue test	9
7 Inspection	9
7.1 Inspection and inspection documents	9
7.2 Acceptance unit, number of samples and test pieces	9
7.3 Evaluation of test results for mechanical, chemical, and coating properties	10
7.4 Sorting and reprocessing	10
8 Identification and marking	10
9 Storage and handling	11
10 Transportation	11
Annex A (normative) Cross-sectional layout of PPWS	12
Annex B (informative) Sectional dimensions, nominal length mass of PPWS	13
Annex C (informative) Nominal breaking force	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 105, *Steel wire ropes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Steel wire ropes — Pre-fabricated parallel wire strands for suspension bridge main cable — Specifications

1 Scope

This document specifies the production methods, specifications, requirements, test methods, inspection rules, marks, packing, transportation and storage for pre-fabricated parallel wire strand (PPWS), which are made of hot-dip galvanized or zinc-aluminium coated high tensile steel wires described in [ISO 19203](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 148-1](#), *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

[ISO 4986](#), *Steel casting — Magnetic particle inspection*

[ISO 4992-2](#), *Steel castings — Ultrasonic examination — Part 2: Steel castings for highly stressed components*

[ISO 6892-1](#), *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

[ISO 10474:2013](#), *Steel and steel products — Inspection documents*

ISO 17558:2006, *Steel wire ropes — Socketing procedures — Molten metal and resin socketing*

[ISO 19203](#), *Steel wire rod and wire products — Hot-dip galvanized and zinc-aluminium coated steel wires for bridge cables — Specifications*

[EN 1774](#), *Zinc and zinc alloys — Alloys for foundry purposes — Ingot and liquid*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>


3.1

pre-fabricated parallel wire strand

PPWS

strand factory pre-fabricated by assembling a group of wires laid parallel in a hexagonal (regular or irregular) shape, bound together at intervals by binding tape, and fitted with *sockets* ([3.3](#)) at each end

Note 1 to entry: The section and the structure of PPWS is shown in [Figure 1](#).



Key

- 1 socket
- 2 binding tape
- 3 PPWS
- 4 gauge wire
- 5 coloured wire (red)

- d_{s1} hexagon diagonal distance (across corners), in mm
- d_{s2} hexagon width distance (across flats), in mm
- a Cross-section of strand (without binding tape).
- b Cross-section of strand (with binding tape).

Figure 1 — Diagram of structure of PPWS


3.2
binding tape

plastic tape reinforced by plastic fibres

Note 1 to entry: The tapes are bound at intervals to keep the shape of strand tight and can permit the wires to open or spread sufficiently to adjust the stresses in the strand during reeling and unreeling.

3.3
socket

PPWS (3.1) termination incorporating a *socket basket* (3.5), see [Figure 2](#)



Key

- 1 overall basket length [tapered portion plus parallel portion(s), if applicable, plus radius at rope entry]
- 2 tapered portion of socket basket
- 3 parallel portion of socket basket and any radius at strand entry
- 4 angle of tapered basket
- 5 diameter at strand entry

Figure 2 — Typical socket basket

Note 1 to entry: Length adjusting system shall be provided at connection between PPWS socket and anchorage structure.

3.4

socketing medium

molten metal alloy or resin

3.5

socket basket

tapered portion of a *socket* (3.3) within which the evenly splayed out wires are secured

3.6

PPWS grade

R_m

level of requirement of nominal tensile strength grade which is designated by a number

EXAMPLE 1 770, 1 960.

Note 1 to entry: PPWS (3.1) strength grade correspond to the strength grades of the wires in the PPWS. It is expressed in MPa.

3.7

nominal wire diameter

d

nominal diameter of the perpendicular cross-section of the steel wire after coating

Note 1 to entry: It is expressed in millimetres.

3.8**nominal metallic cross-sectional area***A*

design value obtained from the sum of the metallic cross-sectional areas of the wires in the *PPWS* (3.1) based on their nominal diameters:

$$A = \frac{\pi}{4} d^2 \times n$$

where *n* is the number of steel wires composing *PPWS*

Note 1 to entry: It is expressed in mm².

3.9**nominal breaking force***F_n*

value of minimum breaking force based on the nominal wire sizes, wire tensile strength grades for the *PPWS* (3.1) class or construction as given in the manufacturer's design, which is obtained as follows:

$$F_n = R_m \times A / 1\,000$$

Note 1 to entry: It is expressed in kN.

3.10**measured breaking force***F_m*

breaking force obtained using a prescribed method

Note 1 to entry: It is expressed in kN.

3.11**nominal *PPWS* length mass***m*

mass of unit length of *PPWS* (3.1) obtained from the product of the *nominal metallic cross-sectional area* (3.8) and density of steel wires after coating and calculated as follows:

$$m = A \times \gamma_w$$

where γ_w is the density of coated steel wire

Note 1 to entry: It is expressed in kg/m.

Note 2 to entry: γ_w is expressed in kg/m³ (see [ISO 19203:2018](#), Annex C).

3.12**unstressed length**

length which corresponds to the actual length without load supplied using a prescribed method

3.13**free length***L₀*

cable length excluding *socket* (3.3) lengths, which is the length between the front faces of sockets

Note 1 to entry: It is expressed in m.

3.14**gauge wire**

wire used to control the length of the *PPWS* (3.1) during manufacturing, which is measured and marked under specific marking load while temperature is uniform

3.15

coloured wire

wire used to check twist condition of *PPWS* (3.1) during construction, which is painted with distinct colour on its total length

3.16

unit of product

set of 20 pieces of *PPWSs* (3.1) subsequently produced

4 Designation of product

The *PPWS* shall be ordered in accordance with this document and be designated as follows:

- a) [ISO 19427](#);
- b) *PPWS*;
- c) nominal diameter of steel wire, in millimetres;
- d) number of steel wires composing *PPWS*;
- e) *PPWS* grade;
- f) coating type:

EXAMPLE 1 A *PPWS* made up of 91 pieces of zinc coated steel wires with diameter of 5 mm and grade of 1770, is designated:

ISO 19427-PPWS-5,00-91-1770-Zn

where Zn is hot-dip zinc coated.

EXAMPLE 2 A *PPWS* made up of 127 pieces of zinc-aluminium alloy coated steel wires with diameter of 7 mm and grade of 1860, is designated:

ISO 19427-PPWS-7,00-127-1860-ZnAl

where ZnAl is zinc-aluminium alloy coated.

5 Requirements

5.1 Traceability

The traceability shall be done from the beginning to the end of manufacturing. The manufacturer shall use suitable means to ensure the conformity of products and identify the status of products with respect to monitoring and measurement requirements throughout production and delivery.

The manufacturer shall control the unique identification of the products, and shall retain the documented information necessary to enable traceability.

5.2 Lengths and fabrication tolerances

5.2.1 The gauge wire shall be in the outside of the *PPWS*. The total length of the *PPWS* and all measuring points for the sockets, saddles and the key point such as main span middle point and side span middle point shall be marked on the gauge wire under specific marking load while temperature is uniform. The length of gauge wire shall take into account elongation, sag correction and temperature correction based on unstressed length of the cable.

The tension load shall be varied according to the wire diameter. For 5 mm diameter wires, the load shall be more than 50 kg. For 7 mm diameter wires, the load shall be more than 100 kg.

5.2.2 The gauge wire tolerance of the total length shall be within $(L_0 / 15\,000)$ for lengths more than 30 m. The tolerance shall be within 2 mm for total lengths less than or equal to 30 m. The length tolerance between the marks of the gauge wire shall be within $(L_0 / 15\,000)$ or 2 mm, whichever is greater.

5.2.3 The coloured wire shall be in the outside of the PPWS to check the twist condition of the PPWS during the erection process. The coloured wire shall also be made by covering the steel wire with colour paint, such as red, along the total length.

5.2.4 The mark of the total length of the PPWS and all measuring points for the sockets, saddles and the key points such as the main span middle point and side span middle point shall be transferred and marked according to the mark of the gauge wire.

5.2.5 Tolerance for the total length of the PPWS is composed of allowances associated with manufacturing of gauge wire and socketing. The allowance for gauge wire is $\pm(1/15\,000 L_0)$ or 2 mm, whichever is greater. The allowance for socketing is ± 5 mm.

NOTE In case of using Zn alloy as a filler material, the alloy shrinks at ambient temperature. As a result, this shrink causes initial cone draw when PPWS are loaded. The manufacturer needs to minimize this initial cone draw in an appropriate way, such as pre-compression from a back face of a socket cone.

5.3 Material and manufacture

5.3.1 The wires of PPWS shall conform to [ISO 19203](#). Welds are not allowed in the wires in PPWS.

5.3.2 When placing the order, the purchaser may nominate the material of sockets. Socket material shall be agreed between the purchaser and manufacturer. The chemical composition and mechanical properties, such as tensile and Charpy properties, shall be agreed between the purchaser and manufacturer.

5.3.3 The socket castings shall be subject to visual, magnetic particle and ultrasonic inspection. The other non-destructive examinations (such as liquid penetration, radiographic etc.) shall be done in conditions agreed at the time of enquiry and order. The severity levels for every method, areas of the socket to be tested, percentage and/or frequency of testing shall be agreed between the manufacturer and purchaser. The acceptance criteria (severity level) shall be agreed between the manufacturer and purchaser.

5.3.4 For each socket, wherever transitions cause stress concentrations, transitions shall generally be rounded and machined. Edges on the sockets shall be rounded to make them suitable for zinc coating or painting. Specification for corrosion protection of socket shall be specified by the purchaser.

5.3.5 The socketing medium is as follows:

- Zinc-copper alloy: ZnCu2, which contains $(98 \pm 0,2)$ % Zn, $(2,0 \pm 0,2)$ % Cu.
- Zinc-aluminum-copper alloy: ZnAl6Cu1 in accordance with [EN 1774](#), which contains $(5,8 \pm 0,2)$ % Al, $(1,4 \pm 0,2)$ % Cu and the rest, of Zn.
- The resin compound material may be used in the socketing medium of PPWS. The physical property of resin shall meet the requirements of ISO 17558:2006, Annex C.
- The manufacturer may use other socketing medium if the purchaser agrees.

5.3.6 Bundles of steel wires shall be wrapped by binding tape to form the shape in hexagon as in [Annex A](#). The binding tape interval distance is 1,5 m to 2,5 m. Typical sectional dimensions are given in [Annex B](#).

5.3.7 The binding tape shall have sufficient strength to confine the wires of the PPWS during reeling but it shall permit the wires to open or spread sufficiently to adjust for the stresses in the PPWS during reeling.

5.3.8 During socketing, the following requirements shall be met:

- The individual steel wires of each PPWS shall be splayed out and cleaned.
- Inserting the PPWS bundle end into the socket. Concentricity of the PPWS and the socket shall be optimized by positioning and alignment of PPWS axis and socket axis.
- The wires shall be evenly distributed within the cone.
- The wires shall be securely clamped together so that the wires do not slip during socketing.

5.3.9 After socketing, the following requirements shall be met:

- The socket basket is filled to the top with the socketing medium.
- The back of the molten metal cone shall be pressed into the socket with a load of not less than 50 % of the nominal breaking force or 1,1 times the service load of the PPWS applied by a suitable diameter jacking head, the pressure being maintained for 5 min.
- Initial cone draw in the resin socket assembly shall be removed by proof loading or alternative means.
- The axis of the PPWS and the front surface of the socket shall be at a right angle in any direction. The angle deviation shall be no more than 0,5°.

5.3.10 The PPWS shall be coiled or reeled on a drum or frame. The coiling or reeling diameter shall meet the following requirements:

- The coil or reel diameter shall be larger than 1,8 m for PPWS of 5 mm diameter wires.
- The coil or reel diameter shall be larger than 2,1 m for PPWS of 7 mm diameter wires.

NOTE The PPWS is composed of wires: an inner diameter of a coiled or reeled PPWS can be changed by considering the diameter of wire.

5.4 Mechanical property

5.4.1 Tensile property

The measured breaking force of the PPWS shall be equal to or greater than the nominal breaking force of the PPWS. The typical nominal breaking force are given in [Annex C](#).

5.4.2 Modulus of elasticity

The modulus of elasticity shall be (200 ± 10) GPa.

5.4.3 Fatigue property

If requested, the fatigue property of the PPWS shall meet the following requirements.

- The load cycle is 2×10^6 , the upper load is $0,45 \times F_n$, the stress range shall be 150 MPa according to the PPWS strength.
- Break is allowed in a maximum of 5 % of the total number of wires.
- After the fatigue test, the PPWS shall be taken to tensile failure and the failure load shall be not less than 95 % of F_n or as agreed between manufacturer and purchaser.

NOTE The PPWS is generally used for the main cables of suspension bridges. The ratio of live loads which work to the main cable is small because most loads are dead loads consisting of the weight of the cable wires themselves and the deck. Therefore, the fatigue test is not required for the materials of the main cable. The fatigue test is a special requirement.

6 Test methods

6.1 Material test

The socket shall be tested as below:

- Chemical testing shall be done to verify steel composition per the specified casting standard agreed between the manufacturer and purchaser.
- Material tests of socket shall be tested in accordance with the requirements and the following testing methods: [ISO 6892-1](#) for tensile testing and [ISO 148-1](#) for Charpy-V impact testing.
- The ultrasonic tests and magnetic particle tests shall be done according to [ISO 4992-2](#) and [ISO 4986](#).
- The socket appearance shall be inspected by visual means.
- The other non-destructive examination shall be done according to the agreement between the manufacturer and purchaser.

6.2 Tensile test of PPWS

6.2.1 A sample from each PPWS unit of product shall be fixed to the sockets and subjected to the tensile test.

6.2.2 Tensile test shall be loaded until 5 % wire breakage (including wire pulled out from the socketing medium) at least or socket broken/socketing medium broken occurs. The load at which the wires, socket or socket medium break is F_m . The test force shall be applied steadily during the test. After 80 % of F_n has been achieved, the force shall be applied at a rate of not more than 0,5 % of F_n per second.

6.2.3 If required tensile load has not been reached when a single wire breaks, allow test to continue until the required load is met or multiple breaks occur, confirming maximum load possible has been reached. The broken wire number should be less than 5 % of wires of PPWS. The maximum load should not be less than nominal breaking force of PPWS.

6.2.4 If the breaking of more than 5 % of wires of PPWS occurs at a force less than the nominal breaking force, the PPWS is rejected.

The tensile test shall be performed on three samples taken from the same unit of production from the same steel wire coils. The remaining PPWSs are accepted only when all the measured breaking force of three tests achieve no less than the nominal breaking force.

6.3 Modulus of elasticity

The modulus of elasticity shall be determined from the slope of the linear portion of the force-extension diagram in the range between 0,2 F_n and 0,6 F_n , divided by the nominal cross-sectional area of the test piece. The interval for determining the modulus of elasticity shall be 0,05 F_n .


The slope may be calculated either by a linear regression of the measured data stored in a data storage facility or by a best-fit visual technique over the above-defined portion of the registered curve.

The gauge length of the extensometer used in the test shall be at least 2 m.

6.4 The test of socketing process

The following items shall be checked:

- The socket basket is filled to the top with the socketing medium.
- The axis of the PPWS and the front surface of the socket shall be checked by angle ruler.
- Measure the distance between socket and socket mark (L_s in [Figure 3](#)) by ruler after socket cone pressing.



Key

- 1 socket mark
- L_s length tolerance of socketing
- a Total length of PPWS L_0 ($1 \pm 1\,500$).

Figure 3 — Measure length

6.5 Fatigue test

6.5.1 Testing shall be carried out on the completed PPWS, including original sockets and socket medium. The free length of test specimen shall be minimum 3,0 m.

6.5.2 The specimen is mounted in the testing machine. The test specimen shall then be loaded to a maximum force of $0,45 F_n$. Subsequently, the specimen is subjected to a fatigue test with two million load cycles, and an axial stress range 150 MPa. After the fatigue test, the PPWS shall be tensioned to 95 % of F_n or as agreed between manufacturer and purchaser.

7 Inspection

7.1 Inspection and inspection documents

Inspection shall be carried out by manufacturer in accordance with [Clause 6](#) before delivery. The inspection documents shall be based on inspection certificate 3.1 or 3.2 of [ISO 10474:2013](#). A type of the inspection certificate shall be agreed between the manufacturer and purchaser.

7.2 Acceptance unit, number of samples and test pieces

The finished PPWS products shall be sampled and tested in accordance with [Table 1](#).

Table 1 — Frequency of sampling and testing of PPWS

Property		Frequency of sampling and testing
Socket	Dimension	100 %
	Appearance	100 %
	Mechanical test	1 per heat treatment charge and casting
	Chemical test	1 per casting charge
	Magnet particle inspection	Agreed between manufacturer and purchaser
	Ultrasonic test	Agreed between manufacturer and purchaser
	Coating	10 %
Length	Gauge wire length	each gauge wire
	Socketing length	each socket
Tensile property		1 per 20 pieces
Modulus of elasticity		1 per 20 pieces
Fatigue test		Agreed between manufacturer and purchaser
Socketing medium quantity		Every socket
Perpendicularity of socket and PPWS		Every socket

7.3 Evaluation of test results for mechanical, chemical, and coating properties

The material shall be deemed to conform to the requirements of this document if all the results of the tests comply. If these conditions are not met, then the following procedures shall apply:

- When results for the properties specified by a minimum and or maximum value do not conform to the requirements, then two additional samples shall be taken from the unit of product concerned by each failed result and these shall be tested for the property concerned.
- If the two additional results conform to the requirements of this document, then the unit of product shall be deemed to conform to this document.
- If one or more of these additional tests does not conform to the specifications, the unit of product concerned shall be rejected. In addition, all units of product from the last good result until the next good result shall be tested for the defective properties.

All units of product with non-conforming results shall be rejected and the manufacturer shall immediately take measures to determine the reason and rectify the fault.

7.4 Sorting and reprocessing

The manufacturer has the right to carry out sorting or reprocessing of non-conforming products, either before or after retests, and to submit these products as a new test unit in accordance with 7.2. Manufacturer shall report non-conforming products to the purchaser before sorting or reprocessing. If the inspection results conform to this document and is agreed by the purchaser, these products can be delivered as qualified products. If requested, the manufacturer shall inform the purchaser which method of sorting or reprocessing is used. The manufacturer shall state such manner of the sorting and reprocessing in the method statement and get the approval from the purchaser.

8 Identification and marking

8.1 Each PPWS shall be legibly and permanently marked with the PPWS serial number. The marking detail shall be in accordance with agreement between the purchaser and manufacturer.

8.2 Each socket shall be permanently marked with marks or symbols that provide identification with the manufacturer's certificate of test.

8.3 The identification marking shall not affect the performance of the socket and PPWS.

8.4 Each PPWS shall be delivered with metal or plastic labels attached on which is shown the relationship between the internal production number of the PPWSs and the identification number of the sockets, enabling to trace all the information of the cable wire to be used and of the test results, and are stamped.

9 Storage and handling

9.1 The PPWS shall be delivered and stored in a wrapped condition, so that both PPWS and socket are protected against mechanical wear and tear, precipitation and similar.

9.2 During storage, the PPWS shall be protected against rain and long-term exposure to hot-humid environments. Storage condition and inspection interval shall be agreed between manufacturer and purchaser.



9.3 Each PPWS shall be handled with utmost care during storage and handling.


10 Transportation

Transportation of the PPWS in connection with reloading shall take place in such a way that the PPWS is not damaged. In this respect, it is important to take into account the capacity of cranes and lifting equipment and possible loading restrictions on quays, roads, bridges, etc., and the shape of such elements. In addition, it shall be ensured that the PPWS cannot be displaced or start rolling during transportation and storage.

Annex A
(normative)

Cross-sectional layout of PPWS

Number of wires	61	91
Sectional area		

Number of wires	127
Sectional area	

Annex B (informative)

Sectional dimensions, nominal length mass of PPWS

The nominal dimensions of PPWS complying with this document are as specified in [Table B.1](#). The nominal PPWS length mass is calculated with [Formula \(B.1\)](#):

$$m = A \cdot \gamma_w \quad (\text{B.1})$$

where

- m is the nominal PPWS length mass;
- A is the nominal metallic cross-sectional area;
- γ_w is the density of coated steel wire.

Table B.1 — Sectional dimension and area of PPWS

Products	Nominal hexagon diagonal distance (across corners) d_{s1} mm	Nominal hexagon width distance (across flats) d_{s2} mm	Nominal sectional area of PPWS A mm ²
ISO 19427-PPWS-5,00-61	45	40	1 197,7
ISO 19427-PPWS-5,00-91	55	48	1 786,8
ISO 19427-PPWS-5,00-127	65	57	2 493,6
ISO 19427-PPWS-7,00-61	63	56	2 347,6
ISO 19427-PPWS-7,00-91	77	68	3 502,1
ISO 19427-PPWS-7,00-127	91	80	4 887,5

NOTE The nominal length mass of PPWS includes the steel wire coating weight.

Annex C
(informative)

Nominal breaking force

Products	Nominal breaking force, F_n				
	kN				
	PPWS grade 1 570	PPWS grade 1 670	PPWS grade 1 770	PPWS grade 1 860	PPWS grade 1 960
ISO 19427-PPWS-5,00-61	1 880,4	2 000,2	2 120,0	2 227,8	2 347,6
ISO 19427-PPWS-5,00-91	2 805,2	2 983,9	3 162,6	3 323,4	3 502,1
ISO 19427-PPWS-5,00-127	3 915,0	4 164,4	4 413,7	4 638,2	4 887,5
ISO 19427-PPWS-7,00-61	3 685,7	3 920,4	4 155,2	4 366,5	4 601,2
ISO 19427-PPWS-7,00-91	5 498,3	5 848,5	6 198,7	6 513,9	6 864,1
ISO 19427-PPWS-7,00-127	7 673,4	8 162,2	8 650,9	9 090,8	9 579,6

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK