



BSI Standards Publication

**Paints and varnishes — Determination of  
the resistance to rubbing using a linear  
abrasion tester (crockmeter)**

---

National foreword

This British Standard is the UK implementation of ISO 21546:2019.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019  
Published by BSI Standards Limited 2019

ISBN 978 0 580 98749 6

ICS 87.040

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2019.

Amendments/corrigenda issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

# INTERNATIONAL STANDARD

**ISO**  
**21546**

First edition  
2019-02

---

---

## **Paints and varnishes — Determination of the resistance to rubbing using a linear abrasion tester (crockmeter)**

*Peintures et vernis — Détermination de la résistance à la rayure avec  
un abrasimètre linéaire*



Reference number  
ISO 21546:2019(E)

© ISO 2019





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|  |           |
|--|-----------|
| <b>Foreword</b>  | <b>iv</b> |
| <b>1 Scope</b>   | <b>1</b>  |
| <b>2 Normative references</b>                                      | <b>1</b>  |
| <b>3 Terms and definitions</b>                                     | <b>1</b>  |
| <b>4 Principle</b>   | <b>2</b>  |
| <b>5 Apparatus and ancillary materials</b>                         | <b>2</b>  |
| 5.1 Linear abrasion tester (crockmeter)                            | 2         |
| 5.2 Abrasion tool  | 3         |
| 5.3 Felt cloth   | 7         |
| 5.4 Abrasive material, for lining the abrasion tool                | 7         |
| 5.5 Abrasive medium  | 7         |
| 5.6 Tools for assessing the friction marks                         | 7         |
| <b>6 Test specimens</b>  | <b>7</b>  |
| 6.1 Test specimens   | 7         |
| 6.2 Film thickness   | 7         |
| 6.3 Conditioning   | 8         |
| <b>7 Procedure</b>   | <b>8</b>  |
| 7.1 Test conditions subject to agreement                           | 8         |
| 7.2 Test environment   | 8         |
| 7.3 Testing process  | 8         |
| <b>8 Evaluation</b>  | <b>9</b>  |
| <b>9 Precision</b>   | <b>9</b>  |
| 9.1 Repeatability limit, $r$                                       | 9         |
| 9.2 Reproducibility limit, $R$                                     | 9         |
| <b>10 Test report</b>  | <b>10</b> |
| <b>Annex A (informative) Usual test conditions</b>                 | <b>11</b> |
| <b>Annex B (informative) Measuring template</b>                    | <b>12</b> |
| <b>Annex C (informative) Evaluation of gloss as test criterion</b> | <b>13</b> |
| <b>Annex D (informative) Details on precision</b>                  | <b>14</b> |
| <b>Bibliography</b>  | <b>18</b> |



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



# Paints and varnishes — Determination of the resistance to rubbing using a linear abrasion tester (crockmeter)

## 1 Scope

This document specifies a method for determining the resistance of a coating to rubbing by means of a loaded abrasive material which is linearly moved over the surface to be tested.

The method can also be applied to different material surfaces, such as plastics and metals.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-F09, *Textiles — Tests for colour fastness — Part F09: Specification for cotton rubbing cloth*

ISO 845, *Cellular plastics and rubbers — Determination of apparent density*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 23321, *Solvents for paints and varnishes — Demineralized water for industrial applications — Specification and test methods*<sup>1)</sup>

ASTM D2240, *Standard Test Method for Rubber Property — Durometer Hardness*

FEPA-Standard 43-2<sup>2)</sup>, *Grains of fused aluminium oxide, silicon carbide and other abrasive materials for coated abrasives microgrits P 240 to P 2500*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

1) Under preparation. Stage at the time of publication: ISO/FDIS 23321:2019.

2) Federation of European Producers of Abrasives (FEPA). Reference source for FEPA standards: Staatliche Materialprüfungsanstalt Darmstadt, Dr. Ing. P. Hof, Grafenstraße 2, 64283 Darmstadt, Germany, Tel.: +49-6151-16 65 82, Fax: +49-6151-16 60 46, E-Mail: [hof@mpa-ifw.tu-darmstadt.de](mailto:hof@mpa-ifw.tu-darmstadt.de).



## 4 Principle

A loaded abrasion tool, lined with agreed abrasive material and influenced by an agreed abrasive medium, is moved over the coating using a linear abrasion tester (crockmeter). There are three procedure variations, depending on the agreement and application (see [Table 1](#)).

**Table 1 — Procedure variations**

| Abrasion tool | Geometry of abrasion tool | Contact surface to test specimen               | Test load      | Application                   |
|---------------|---------------------------|--|----------------|-------------------------------|
| A             | Cuboid                    | Base surface (22 mm × 22 mm)                   | (22,0 ± 0,5) N | flat test panels              |
| B             | Cylinder                  | Front surface (Ø 16 mm)                        | (9,0 ± 0,2) N  | flat test panels <sup>a</sup> |
| C             |                           | Lateral surface (Ø 44 mm × 25 mm) <sup>b</sup> |                | flat and curved test specimen |

<sup>a</sup> With limitations: Abrasion tool B is the original procedure variation; in most cases abrasion tool A is preferred also for flat test specimen.

<sup>b</sup> The contact surface is a part of the lateral surface, which depends on different parameters, see [5.2.3](#), Note 3.

The assessment of the friction mark shall be agreed and can be carried out e.g. visually or by means of measuring the change in gloss, haze or brightness.

## 5 Apparatus and ancillary materials

### 5.1 Linear abrasion tester (crockmeter)

Linear abrasion tester in accordance with [Figure 1](#), which is specified by the following properties.

**5.1.1** The mechanism can be manual (as illustrated in [Figure 1](#)) or (electro) motor driven.

**5.1.2** For the motoric version, an operation counter for pre-setting the number of double-strokes shall be integrated and the mechanism shall have a stroke frequency of (1,0 ± 0,1) Hz and shall have a constant velocity within the 70 mm measurement area.

**5.1.3** The test load with which the abrasion tool ([5.2](#)) is pressed onto the test specimen shall be (9,0 ± 0,2) N (for abrasion tool B and C) and (22,0 ± 0,5) N (for abrasion tool A).


**NOTE** Test devices intended for a test load of 9,0 N can be converted to a test load of 22,0 N by means of an additional load of 13,0 N (corresponding to an additional weight with a mass of 1,33 kg).

**5.1.4** The stroke length shall be selected in such a way that the length of the assessable friction mark is (100 ± 30) mm.

**NOTE 1** The assessable friction mark equals the total friction mark, less the expansion of the contact surface of the abrasion tool in the direction of the stroke on both ends (see [7.3.1](#)). Consequently, the stroke length is at least 70 mm + 2 × expansion, in millimetres, of the contact surface of the abrasion tool in the direction of the stroke. For the dimensions of the abrasion tools, see [5.2](#).

**NOTE 2** Some devices exist with a length of the assessable surface less than 70 mm due to technical reasons.





#### Key

- 1 crank mechanism (crank handle)
- 2 abrasion tool B – see 5.2.2
- 3 test specimen
- a Direction of stroke motion.

**Figure 1 — Crockmeter (example with manual crank mechanism)**

## 5.2 Abrasion tool

**5.2.1 Abrasion tool A**, e.g. as shown in Figure 2 a). The felt insert shall have the dimensions  $(22,0 \pm 0,2)$  mm  $\times$   $(22,0 \pm 0,2)$  mm  $\times$  6 mm and a bulk density of 0,44 g/cm<sup>3</sup>. The coupling with the crockmeter (5.1) is rigid.

**NOTE** Despite the rigid coupling a tilting of the front face of the abrasion tool A against the test specimen is impossible due to the elastic felt insert.

**5.2.2 Abrasion tool B**, designed as a cylinder with a diameter of  $(16,0 \pm 0,1)$  mm, the front surface of which is facing the test specimen. The coupling with the crockmeter (5.1) is rigid.

**NOTE 1** Due to the rigid coupling a tilting of the front surface of the abrasion tool B against the test specimen is generally possible.

**NOTE 2** Unlike abrasion tools A and C, abrasion tool B cannot be lined with abrasive material without wrinkling.

**5.2.3 Abrasion tool C**, e.g. as shown in Figure 2 b). The radius of the tool shall be  $(19,0 \pm 0,5)$  mm and a width of  $(25,0 \pm 0,3)$  mm. In the contact area to the test specimen, the lateral surface of the tool shall be covered with a layer of EPDM rubber<sup>3)</sup>, e.g. DIM ZK EPDM 21606<sup>4)</sup>, with a thickness of  $(3,0 \pm 0,3)$  mm and a width of  $(25,0 \pm 0,3)$  mm, and which has the hardness of  $(60 \pm 5)$  Shore-00 in accordance with ASTM D2240 and a bulk density of  $(0,16 \pm 0,02)$  g/cm<sup>3</sup> in accordance with ISO 845. The coupling with the crockmeter (5.1) can be moved across the direction of the stroke [see view II in Figure 2 b)].

When lining the abrasion tool with the abrasive material (5.3), the latter is attached tightly to the abrasion tool by means of roll pins which are elastically interconnected by the rubber strips (see view III in Figure 2 b)).

**NOTE 1** Due to the EPDM rubber cover the effective diameter of the tool is 44 mm.



3) EPDM: Ethylene-propylene-dien-monomer.

4) DIM ZK EPDM 21606 is the trade name of a product supplied by DIMER. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.




NOTE 2 Due to the geometry of the abrasion tool and the movable coupling with the crockmeter, tests can be carried out on curved test specimens by means of abrasion tool C.

NOTE 3 Unlike abrasion tools A and B, the contact surface with the test specimen is geometrically unspecified for abrasion tool C; it is rather defined by the radius of the tool, the elastomer hardness, the test load, and, if applicable, by the properties of the abrasive material.



a) Abrasion tool A





**b) Abrasion tool C**


**Key**

- 1 felt insert
- 2 o-ring for attaching abrasive material
- 3 adapter shaft
- 4 axial pin (swivel axis)
- 5 rubber strips
- 6 roll pins (locked in the base 5)
- 7 base with cylindrical outer contour (radius 19 mm)
- 8 cellular rubber (20 mm × 25 mm × 3 mm)
- 9 swivelling range (approximately 60°)
- 10 abrasive material

**Figure 2 — Abrasion tool**



**5.2.4 Selection of the abrasion tool.** The selection of the suitable abrasion tool depends on the type of the sample. [Figure 3](#) shows examples for abrasion tools and the corresponding friction marks.




**Figure 3 — Examples for abrasion tools and the corresponding friction marks**

For flat test panels, abrasion tool A is most suitable, because it produces a uniform, homogeneous friction mark which can be assessed easily.

The original abrasion tool B can also be used on flat test panels, nevertheless it produces a transversal inhomogeneous friction mark [see [Figure 3 b\)](#)] which is difficult to assess. Therefore the abrasion tool A should be preferred.

For curved test specimen, abrasion tool C shall be used in any case. Care shall be taken to ensure that the strokes are located parallel to the curvature of the sample to obtain a maximum contact area and a friction mark that can be assessed clearly (see [Figure 4](#)).



**Figure 4 — Position of abrasion tool C on a curved sample surface**



### 5.3 Felt cloth

Felt cloth with a thickness of 1,5 mm and a bulk density of 0,28 g/cm<sup>3</sup>, corresponding to the felt hardness DIN 61200 — M5.

The abrasion tool can be lined with the felt cloth beneath the abrasive material. The felt cloth works as a compensating material and ensures that the abrasive material is pressed onto the coating evenly and over the entire surface. By agreement, a different cloth can be used which fulfils the same function.

### 5.4 Abrasive material, for lining the abrasion tool

**5.4.1 Cotton rubbing cloth**, in accordance with ISO 105-F09 with a mass per unit area of  $(110 \pm 5)$  g/m<sup>2</sup> and 36 threads/cm in both directions.

**5.4.2 Abrasive paper**, with agreed grain size in accordance with FEPA standard 43-2 and preferably self-adhesive.

**5.4.3 Abrasive material**, with agreed grain size in accordance with FEPA standard 43-2, attached to a soft supporting material.

**5.4.4 Felt**, made of a material with agreed properties (e.g. bulk density and felt hardness according to DIN 61200).

### 5.5 Abrasive medium

Abrasive paste, abrasive powder, etc. of agreed type and/or water in accordance with ISO 23321, for sprinkling/wetting the abrasive material and/or the coating prior to rubbing.

### 5.6 Tools for assessing the friction marks

Depending on the agreed evaluation method, e.g. a measuring device for determining the gloss (see [Annex C](#)), the haze, or the brightness, is necessary, in combination with a measuring template (see [Annex B](#)) or a set of comparison pictures.

## 6 Test specimens

### 6.1 Test specimens

The test specimens shall be plane and prepared, coated, and dried/hardened in accordance with ISO 1514. The width of the test specimens shall allow for the possibility that three tests can be carried out next to each other without edge influence; the lengths of the test specimens depend on the construction of the test device.

NOTE Normal test specimen dimensions are 100 mm × 150 mm.

The surface of the test specimen shall be clean. Clean the surface with a soft, lint-free cloth and, if necessary, use a solvent which does not attack the coating.

### 6.2 Film thickness

Determine the dry film thickness of the coating, in micrometres, in accordance with one of the methods given in ISO 2808.



## 6.3 Conditioning

Prior to testing, condition the coated test specimens at a temperature of  $(23 \pm 2)$  °C and a relative humidity of  $(50 \pm 5)$  % in accordance with ISO 3270, if not otherwise agreed, for a minimum of 16 h.

## 7 Procedure

### 7.1 Test conditions subject to agreement

For the test procedure and the evaluation of the test the following shall be agreed:

- the abrasion tool in accordance with [5.2](#);
- the abrasive material in accordance with [5.4](#);
- the abrasive medium in accordance with [5.5](#);
- the number of double-strokes;
- the evaluation criterion, e.g. measurements of gloss, haze or brightness, visual comparison with reference pictures, etc.;
- the time interval between abrasion and evaluation of the friction marks.

Examples of usual test conditions are given in [Annex A](#).

### 7.2 Test environment

Carry out the test at a temperature of  $(23 \pm 2)$  °C. Measure the relative humidity during the test and record in the test report. In case of high relative humidity, be careful that no condensation water forms on the test specimen due to falling below the dew point.

Carry out the test as quick as possible, however, not later than 30 min after the conditioning phase.

### 7.3 Testing process

**7.3.1** If the friction marks are assessed by agreement using optical measurements, e.g. gloss, haze or brightness, determine — preferably using the measuring template (see [Annex B](#)) — on the test panel at least three linearly spread measurement points and mark them.

The measurement points shall be determined such that:

- the measuring areas do not overlap;
- they are spread evenly on the (expected) friction mark;
- at the ends of the (expected) friction marks, an area corresponding to the agreed abrasion tool is left blank.

**7.3.2** **Align** the agreed abrasion tool ([5.2](#)) with the agreed abrasive material ([5.4](#)), if necessary in combination with felt cloth ([5.5](#)).

**7.3.3** Mount the test specimen on the test device. Where appropriate, consider the markings in accordance with [7.3.1](#), so that the position of the intended friction mark corresponds with the specified measurement points.

**7.3.4** If applicable, apply the agreed abrasive medium ([5.5](#)) on the abrasive material and/or the coating.



**7.3.5** Lower the abrasion tool prepared in accordance with [7.3.2](#) onto the coating with the specified test load (see [Table 1](#) and [5.1.3](#)) and carry out the agreed number of double-strokes with a frequency of 1 double-stroke/s.

**7.3.6** Clean the area of the friction mark in the direction of the marking by means of a soft, lint-free cloth and, if necessary, use a solvent which does not attack the coating. After the agreed period of time, assess the friction mark in accordance with the method specified.

**7.3.7** If the friction marks are assessed by agreement using optical measurements, e.g. gloss, haze or brightness, repeat the measurements in accordance with [7.3.1](#) using the same measuring direction.

**7.3.8** Only uniform and continuous friction marks shall be evaluated.

**7.3.9** If it is agreed to assess several friction marks, repeat the procedure described in [7.3.1](#) to [7.3.7](#) accordingly.

## 8 Evaluation

The evaluation method of the friction marks shall be agreed between the interested parties.

## 9 Precision

### 9.1 Repeatability limit, $r$

The repeatability limit,  $r$ , is the value less than or equal to which the absolute difference between two test results obtained under repeatability conditions may be expected to be with a probability of 95 % (see ISO 5725-1:1994, 3.16). For gloss measurements as an example for a test criterion the repeatability limit,  $r$ , in accordance with this document, calculated with a probability of 95 %, is given in [Table 2](#).

**Table 2 — Repeatability limit,  $r$ , for gloss measurements**

| Measurement angle<br>abrasion tool | $r$ |
|------------------------------------|-----|
|                                    | GU  |
| A20-A                              | 8   |
| A20-B                              | 8   |
| A20-C                              | 9   |
| A60-A                              | 8   |
| A60-B                              | 7   |
| A60-C                              | 8   |

### 9.2 Reproducibility limit, $R$

The reproducibility limit,  $R$ , is the value less than or equal to which the absolute difference between two test results obtained under reproducibility conditions may be expected to be with a probability of 95 % (see ISO 5725-1:1994, 3.20). For gloss measurements as an example for a test criterion the reproducibility limit,  $R$ , in accordance with this document, calculated with a probability of 95 %, is given in [Table 3](#).



**Table 3 — Reproducibility limit,  $R$ , for gloss measurements**

| Measurement angle<br>abrasion tool | $R$<br>GU |
|------------------------------------|-----------|
| A20-A                              | 14        |
| A20-B                              | 11        |
| A20-C                              | 15        |
| A60-A                              | 13        |
| A60-B                              | 10        |
| A60-C                              | 11        |

For more details on precision, see [Annex D](#).

## 10 Test report

The test report shall contain at least the following information:

- all details necessary to identify and characterize the test specimen;
- the film thickness, in micrometres, in accordance with [6.2](#);
- a reference to this document (i.e. ISO 21546);
- the relative humidity during testing, as percentage;
- the abrasion tool (A, B, or C) used;
- the agreed abrasive material in accordance with [5.4](#) and information whether the felt cloth ([5.3](#)) was used;
- the agreed abrasive medium in accordance with [5.5](#) (type of abrasive paste, abrasive powder, etc. and/or quantity and type of water);
- the agreed number of double-strokes;
- the stroke length, in millimetres;
- the agreed test criterion;
- the agreed time interval between abrasion and assessment of the friction mark;
- the test result for the agreed test criterion;
- any deviation from the test method specified;
- any unusual observation (deviation) during testing;
- the name of the operator and the testing laboratory;
- the date of the test.



## Annex A (informative)

### Usual test conditions

Usual test conditions are given in [Table A.1](#).

**Table A.1 — Usual test conditions**

| Coating system                       | Compensating material                             | Abrasive material  | Abrasive medium                                 |
|--------------------------------------|---|--|---|
| Automobile clear coating material    | Felt cloth in accordance with <a href="#">5.3</a> | Abrasive material in accordance with <a href="#">5.4.3</a>   | —   |
| Automobile interior coating material | —   | Cotton rubbing cloth in accordance with <a href="#">5.4.1</a> or felt in accordance with <a href="#">5.4.4</a> | Without abrasive medium or various test liquids |
| Interior wall coating                | —   | Cotton rubbing cloth in accordance with <a href="#">5.4.1</a>  | Without abrasive medium or water                |
| Industrial coating material          | —   | Abrasive paper in accordance with <a href="#">5.4.2</a>  | —   |


## Annex B (informative)

### Measuring template

If the friction marks are assessed by agreement using optical measurements, e.g. gloss, haze or brightness, it shall be ensured that:

- the measuring surface of the measuring device considering the measuring direction lies within the intended friction mark;
- the measurement points are in the same position prior to and after abrading.

For these purposes, it can be helpful to use a measuring template (see [Figure B.1](#)) in order to carry out process steps [7.3.1](#), [7.3.3](#) and [7.3.7](#) correctly.



#### Key

- 1 friction mark
- 2 test specimen
- 3 measuring template (mask)
- 4 cross marking on the mask
- 5 cross marking on the test specimen
- 6 longitudinal marking on the test specimen
- 7 longitudinal marking on the mask


**Figure B.1 — Measuring template (example)**



## Annex C (informative)

### Evaluation of gloss as test criterion

The evaluation of gloss as test criterion is influenced by the width of the friction mark. In most cases, the measuring spot of the 60° geometry is larger than the width of the friction mark. See [Figure C.1](#).



#### Key

- 1 abrasion tool A
- 2 abrasion tool B
- 3 abrasion tool C
- 4 friction mark obtained with abrasion tool A
- 5 friction mark obtained with abrasion tool B
- 6 friction mark obtained with abrasion tool C
- 7 test panel
- 8 measuring spot for gloss measurements with 20° geometry
- 9 measuring spot for gloss measurements with 60° geometry
- 10 gloss measurements perpendicularly to the friction mark

**Figure C.1 — Gloss measurements on friction marks**



## Annex D (informative)

### Details on precision

#### D.1 General

An interlaboratory comparison test has been carried out for the determination of precision using linear abrasion tester (crockmeter) and three different types of abrasion tools (see [Table D.1](#)).

The friction marks were assessed by measuring the gloss.

#### D.2 Crockmeter and abrasion tool

Ten laboratories participated in the interlaboratory test with their own linear abrasion testers (crockmeters).

The different types of abrasion tools ([5.2](#)) were used with the crockmeters.

##### Abrasion tool A

The abrasion tool A has been specifically developed for use with this document. It has a square shape with a square contact area of 22 mm × 22 mm. Thus, the rubbed area is large enough to use the portable glossmeter with the measurement angles of 20° and 60°. Nevertheless, this area is not large enough for gloss measurements of matt areas using the measurement angle of 85°.

##### Abrasion tool B

The cylindrical abrasion tool B with a diameter of 16 mm was implemented from ISO 105-X12. This tool is mainly used for textiles, but also used for other material surfaces.

This small diameter of the cylinder results in a small friction mark which can hardly be measured with a measurement angle of 20°. It is not possible to measure with the angle of 60° or 85°. All measurements will include the non-rubbed edge area and will give erroneously high gloss values.

##### Abrasion tool C

The abrasion tool C is a new development with the movable transverse cylindrical abrading the surface. This construction can also be used for curved samples. Only a small area of the cylinder is touching the surface.

The purpose of the interlaboratory comparison was to clarify the following:

- are the three abrasion tools A, B and C comparable;
- advantage and disadvantage of the different abrasion tools;
- applicability of gloss measurements to the evaluation of rubs;
- precision of the test method including the differences between spatially resolved and non-spatially resolved measurements.



**Table D.1 — Crockmeter and test conditions**

| Crockmeter-ID | Crockmeter   | Abrasion tool A<br>N | Abrasion tool B<br>N | Abrasion tool C<br>N |
|---------------|--------------|----------------------|----------------------|----------------------|
| C01           | Crockmeter A | 22,4                 | 9,0                  | 9,6                  |
| C02           | Crockmeter A | 22,8                 | 9,0                  | 8,9                  |
| C03           | Crockmeter A | 22,8                 | 9,4                  | 9,8                  |
| C04           | Crockmeter A | 22,2                 | 8,8                  | 9,0                  |
| C05           | Crockmeter A | 22,8                 | 8,7                  | 9,0                  |
| C06           | Crockmeter B | 22,4                 | 9,0                  | 8,8                  |
| C07           | Crockmeter C | 22,0                 | 9,0                  | 9,0                  |
| C08           | Crockmeter A | 22,4                 | 9,0                  | 9,2                  |
| C09           | Crockmeter A | 22,2                 | 8,8                  | 8,8                  |
| C10           | Crockmeter A | 22,0                 | 9,0                  | 9,0                  |

### D.3 Samples and abrasion materials

Four different coatings on three different substrates were tested in the interlaboratory comparison (see [Table D.2](#)).

For three samples, polishing paper 9 µm was used as abrasion material and for the coated plastic substrate the felt cloth was used for abrasion ([5.3](#) and [5.4](#)).

**Table D.2 — Samples**

| Sample number | Substrate     | Coating   | Abrasion material    | Double strokes | Angle   |
|---------------|---------------|---|----------------------|----------------|---------|
| P01           | polycarbonate | red automotive coating with reflow effect, measurement after 10 min | polishing paper 9 µm | 10             | 20°/60° |
| P02           | steel         | black automotive coating +2 component clear coat                    | polishing paper 9 µm | 10             | 20°     |
| P03           | plastics      | mat soft coat   | dry felt cloth       | 100            | 60°/85° |
| P04           | steel         | black powder coating, high gloss                                    | polishing paper 9 µm | 10             | 20°/60° |

Two friction marks were produced on each sample.

### D.4 Determination of the abrasion using gloss measurements

Only one glossmeter was used for all measurements.

For samples P01 and P04 measurements with 20° and 60° were made, to determine which measurement angle is the most suitable for high changes in gloss after abrasion.

Gloss measurements were taken perpendicularly to the tracks.

### D.5 Multiple determinations

All gloss measurements, before and after abrasion were taken using a measurement template for defining the three measurement points on each of the two friction marks.



D.6 Evaluation

Test results were evaluated in accordance with ISO 5725-2 and ISO/TR 22971.

The evaluation was done for each abrasion tool and each measurement angle. The repeatability and reproducibility limits are given in [Table D.3](#).

Table D.3 — Repeatability and reproducibility limits

| Measurement angle<br>abrasion tool | <i>r</i> | <i>R</i> |
|------------------------------------|----------|----------|
|                                    | GU       | GU       |
| 20-A                               | 8        | 14       |
| 20-B                               | 8        | 11       |
| 20-C                               | 9        | 15       |
| 60-A                               | 8        | 13       |
| 60-B                               | 7        | 10       |
| 60-C                               | 8        | 11       |

[Figures D.1](#) and [D.2](#) illustrate the results obtained for samples P01, P02 and P04, and for P01 and P04, respectively.

Sample P03 was eliminated as an outlier.





Figure D.1 — Comparison of abrasion tools on samples P01, P02 and P04 measured at 20°





**Key**

- X crockmeter (see [Table D.1](#))
- Y gloss unit after abrasion
- 1 abrasion tool C
- 2 abrasion tool B
- 3 abrasion tool A

**Figure D.2 — Comparison of abrasion tools on samples P01 and P04 measured at 60°**



## Bibliography

- [1] ISO 105-X12, *Textiles — Tests for colour fastness — Part X12: Colour fastness to rubbing*
- [2] ISO 5725-1:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*
- [3] ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*
- [4] ISO 20566, *Paints and varnishes — Determination of the scratch resistance of a coating system using a laboratory-scale car-wash*
- [5] ISO/TR 22971, *Accuracy (trueness and precision) of measurement methods and results — Practical guidance for the use of ISO 5725-2:1994 in designing, implementing and statistically analysing interlaboratory repeatability and reproducibility results*
- [6] ASTM D 6037, *Standard Test Methods for Dry Abrasion Mar Resistance of High Gloss Coatings*
- [7] ASTM D 6279, *Test Methods for Rub Abrasion Mar Resistance of High Gloss Coatings*
- [8] DIN 61200, *Felts — Hardness*







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
  - The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
  - A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
  - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK