



BSI Standards Publication

Assessment of the effectiveness of cathodic protection based on coupon measurements

National foreword

This British Standard is the UK implementation of [ISO 22426:2020](#).

The UK participation in its preparation was entrusted to Technical Committee ISE/NFE/8, Corrosion of metals and alloys.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 580 98766 3

ICS 77.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
22426

First edition
2020-02-10

Assessment of the effectiveness of cathodic protection based on coupon measurements

*Evaluation de l'efficacité de la protection cathodique par
mesurages sur coupon*



Reference number
ISO 22426:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO’s member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Assessment of CP effectiveness	3
5	Application principles	4
5.1	IR-free potential measurements	4
5.2	DC and AC currents and current densities	4
5.3	Spread resistance	5
5.4	Corrosion rate measurements	5
6	Design considerations	5
6.1	General	5
6.2	Geometry of the defect	5
6.3	Dimension of the coupon base plate	6
6.4	Surface area of the coupon	7
6.5	Other types of coupon geometries	7
7	Monitoring purpose — Selection of installation sites	7
7.1	General	7
7.2	Detailed and comprehensive assessment of CP effectiveness	7
7.3	Assessment of CP effectiveness under DC interference conditions	8
7.4	Assessment of CP effectiveness under AC interference conditions	9
8	Installation procedures	9
9	Commissioning of coupons	10
9.1	Preliminary checking	10
9.2	Start up	10
9.3	Measurement of the settled parameters	11
9.4	Installation and commissioning documents	11
9.5	Frequency of coupon measurement	11
Annex A (informative) Special types and procedures of coupons and probes		12
Annex B (informative) Assessment of the effectiveness of CP under any conditions including DC and/or AC interferences		15
Annex C (informative) Examples of instant-off and current density measurements on coupons — Remote monitoring and remote control		17
Bibliography		22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Assessment of the effectiveness of cathodic protection based on coupon measurements

1 Scope

This document specifies requirements for the design, installation, positioning, sizing, use and maintenance of coupons for the assessment of the effectiveness of cathodic protection (CP) of buried and immersed metallic structures, such as pipelines, in the case of normal operation as well as AC and DC interference conditions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 15589-1](#), *Petroleum, petrochemical and natural gas industries — Cathodic protection of pipeline systems — Part 1: On-land pipelines*

[EN 50162](#), *Protection against corrosion by stray current from direct current systems*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

complex structure

system comprising the *structure* (3.13) to be protected connected to one or more foreign electrodes and/or crossing multiple connected electrodes or passing close or through steel-reinforced concrete

3.2

electrolyte

medium in which an electric current is transported by ions

Note 1 to entry: Electrolyte is synonymous with soil, backfill and water.

3.3

polarization

change of an electrode [e.g. *structure* (3.13) and/or *coupon* (3.14)] potential caused by current flow

Note 1 to entry: Current flow results in *concentration polarization* (3.4) and *activation polarization* (3.5).

3.4

concentration polarization

portion of an electrode [*structure* (3.13) and/or *coupon* (3.14)] *polarization* (3.3) produced by electrolyte concentration changes resulting from the passage of a current through an *electrolyte* (3.2)

3.13

structure

metallic structure intended to receive cathodic protection

3.14

coupon

metal sample of defined dimensions and shape made of a metal equivalent to the metal of the *structure* (3.13)

Note 1 to entry: For the purpose of this document, the coupon is connected to the external surface of, and immersed in the *electrolyte* (3.2) adjacent to, the structure being protected by cathodic protection.

Note 2 to entry: Special kinds of *probes* (3.15) and coupons (examples of which are given in the annexes) are also considered part of the coupon definition (hence covered by this document) to the extent that they are intended to reflect structure coating defects, and thus act as a representative metal sample used to quantify the extent of corrosion or the effectiveness of applied cathodic protection.

3.15

probe

device incorporating a *coupon* (3.14) that provides measurements of parameters to assess the effectiveness of cathodic protection

Note 1 to entry: In this document, the term “coupon” is used as a synonym for both coupons and probes.

3.16

electrical resistance probe

ER probe

device that provides measurements of metal loss by comparison of the calibrated resistance value of a piece of metal with known physical characteristics

Note 1 to entry: Refer to [Annex A](#) for information on ER probes.

3.17

stray current

current flowing through paths other than the intended circuits

[SOURCE: ISO 8044:2020, 4.14, modified — “corrosion” has been deleted from the end of the term, and “impressed current corrosion caused by” has been deleted from the start of the definition.]

4 Assessment of CP effectiveness

The assessment of the effectiveness of CP in accordance with [ISO 15589-1](#) is based on an IR-free potential measurement. The determination of the IR-free potential on the cathodically protected structure is only possible based on combined direct current voltage gradient and close-interval potential survey measurements. This method is called “intensive measurement” and is described in [EN 13509](#). This method requires, however, significant measurable voltage gradients associated with individual coating defects in order to allow for a reliable assessment of their IR-free potential and demonstrating conformity to [ISO 15589-1](#). As a consequence, the determination of IR-free potential and demonstrating conformity to [ISO 15589-1](#) is no longer possible on today’s structures with high-quality coating systems. While it is still possible to determine instant-off potentials on many structures and use this reading as an approximation to the IR-free potential in certain cases, the increasing level of AC interference is preventing the separation of the earthing systems connected through decoupling devices from the cathodically protected structures for safety reasons. Similarly, in the presence of DC interference conditions, the determination of both IR-free potentials and instant-off potentials is not possible. As a consequence, on an increasing number of structures neither IR-free potentials nor instant-off potentials can be determined in order to demonstrate conformity to [ISO 15589-1](#). The only remaining technology for demonstrating effectiveness is the use of coupons that are connected to the structure under investigation. The use of coupons is further required by [ISO 18086](#). The determination of the effectiveness of CP under AC interference is only possible based on a current density measurement

on coupons. The validity and accuracy of data obtained on coupons depend on a number of factors, such as location, geometry and bedding conditions. This document provides guidance on these aspects.

5 Application principles

5.1 IR-free potential measurements

The traditional coupon measurement technique has been used to demonstrate conformity of the coupon polarization, which is taken to be representative of the structure coating defects in accordance with the requirements of [ISO 15589-1](#). There are several situations where the use of coupons is a feasible alternative to IR-free potential measurements directly on the structure. In particular, when accurate measurements directly on the structure itself are problematic. Examples include:

- in areas affected by traction stray currents and telluric currents;
- when dealing with the CP of complex structures;
- interference caused by two or more cathodically protected structures crossing or sharing the same right-of-way;
- interference between both parts of an isolating joint for a structure protected by two different CP systems one on each side of the joint;
- effects from equalizing currents from adjacent coating defects: the coupon may be regarded as one single coating defect exposed in the chemistry of the soil exactly where the coupon has been buried, whereas measurements on the structure may include a range of coating defects exposed in varying individual soil chemistries leading to the formation of potential differences and varying current demand;
- in areas where the CP is applied using several CP sources, and it is not possible or economically practical to synchronously turn off these CP sources.

[EN 13509](#), [EN 50162](#), [ISO 18086](#) and [ISO 15589-1](#) allow for the use of coupons in such instances.

5.2 DC and AC currents and current densities

The use of coupons allows for an assessment of current densities in order to demonstrate conformity to [ISO 18086](#) and [EN 50162](#).

The DC current consumed by a coupon is primarily used for assessing the significance of DC stray current interference. [EN 50162](#) describes a procedure for the demonstration of effectiveness of CP based on current density. This involves measuring the DC current throughout a period of typically 24 h. From these measurements, a period is defined in which no interference is present (e.g. hours during the night when trains do not operate). This period is used as the reference value and the measure of the reference current under normal CP. Based on the analysis of these currents, an assessment of the effectiveness of CP under DC interference is performed.

Apart from the risk of corrosion due to DC stray current interference, the DC current density is also important in the evaluation of effectiveness of CP under AC interference in accordance with [ISO 18086](#). Excessive cathodic DC current can produce alkalinity near a coating defect to the extent where this electrolysis (leading to the production of current conducting OH⁻ ions) considerably increases the conductivity of the soil adjacent to the coating defect, thus lowering the spread resistance of this coating defect and increasing the corrosion rate under AC interference.

The AC current density has become a significant tool in the determination of the effectiveness of CP under AC interference in accordance with [ISO 18086](#). Essentially, the AC current density associated with a coating defect with given surface is the result of the AC voltage on the structure at the position of the coating defect divided by the spread resistance of the coating defect. As the spread resistance and the AC current density cannot be measured directly at coating defects on structures, [ISO 18086](#) requires

a 1 cm² coupon for measuring the coupon current and calculating the current density for evaluation of the effectiveness of CP under AC interference.

5.3 Spread resistance

In relation to coupons, the spread resistance is the ohmic resistance from the exposed metallic surface of the coupon towards remote earth. This is the resistance that controls the DC or AC current through a coating defect for a given DC or AC voltage. Determining the spread resistance on coupons allows for assessing acceptable on-potentials (DC) and AC voltages.

5.4 Corrosion rate measurements

Various types of coupons and probes have been designed for the purpose of quantifying corrosion and the corrosion rate. Examples are weight loss coupons, perforation probes and ER probes. Refer to [Annex A](#) for more details.

6 Design considerations

6.1 General

The coupon design should reflect the purpose of the coupon measurement. The purpose may be:

- a detailed and comprehensive assessment of the CP effectiveness;
- an assessment of the effectiveness of CP under DC interference;
- an assessment of the effectiveness of CP under AC interference.

The information obtained with coupons depends on the geometry and size of the coupon. In the case of assessing the effectiveness of CP, the critical aspects are associated with insufficient cathodic current. In that case, a coupon with a design that results in a highest relative spread resistance, e.g. [Figure 1 a\)](#), represents a worst case. In contrast, the most critical conditions in the case of AC and DC interference occur on small coating defects with a design that results in lowest spread resistance, e.g. [Figure 1 c\)](#). As a consequence, these influencing parameters shall be considered. The fundamental concept of a coupon is the mimicking of a coating defect on the structure. These coating defects can have various shapes and sizes. Therefore, the coupon geometry should be adapted to an assumed coating defect geometry and size present on the structure. The relevant parameters are discussed in the following clauses.

6.2 Geometry of the defect

The case of a coating defect with vertical side walls is shown in [Figure 1 a\)](#). This represents the case where the coating was locally damaged resulting in parallel walls going through the coating. The resistance of the electrolyte within the defect gives a contribution to the spread resistance and results in a homogeneous current distribution on the metal surface. This type of coupon, see [Figure 1 a\)](#), is least sensitive to the total surface area in the case of large values of z/y . The value y represents the diameter of the coating defect and z represents the coating thickness. The reason for this is the parallel current distribution caused by the constrained electrical field. The calculated average current density is identical to the current density on the edges of the coupon. This configuration represents a conservative assessment of the effectiveness of CP, since typical coating defects do not have vertical parallel sides and permit higher average current densities on the steel within the coating defect.

In [Figure 1 c\)](#), another extreme case of a coating defect represented by a coupon is shown. In this case, the coupon was constructed with the metal surface flush with the encapsulating coating surface. A large increase of the current density is observed at the edges next to the coating. This edge effect can result in a local increase of the current density of up to a factor of 10, compared to the average current density. This is a result of the non-parallel current distribution and the absence of a constrained electrical field.

When high current densities are associated with high corrosion rates (in the case of DC and/or AC interference), locally increased metal loss is observed resulting in a heterogeneous metal loss. The corrosion rate is significantly higher with the type of coupon indicated in [Figure 1 c\)](#) compared to the one shown in [Figure 1 a\)](#). The calculated average current density in [Figure 1 c\)](#) underestimates the maximum current densities present at the edges of the metal surface. Similarly, using probes that permit the determination of the average metal loss underestimates the maximum corrosion rate taking place in the case of [Figure 1 c\)](#) on the edges. If the structure coating thickness is low (e.g. fusion bonded epoxy coatings), the coupon type in [Figure 1 c\)](#) is relatively representative of structure coating defects.

The case in [Figure 1 a\)](#) is conservative for conventional E_{off} measurements for the assessment of the effectiveness of CP (measured values may be less negative than in reality). In contrast, the case in [Figure 1 c\)](#) is conservative for AC corrosion investigations, since it results in the lowest possible spread resistance and highest local current densities; the coupon geometry in [Figure 1 c\)](#) will indicate higher AC corrosion rates than expected on a coating defect of the same size on the structure.

[Figure 1 b\)](#) illustrates a compromise that may be used in all cases based on the avoidance of excessively conservative data of the geometry in [Figure 1 c\)](#) in the case of AC and/or DC interference. Similarly, in the case of an assessment of CP effectiveness, the [Figure 1 a\)](#) geometry is excessively conservative.




Figure 1 — Examples of different coupon geometries and the corresponding current density distribution

6.3 Dimension of the coupon base plate

The lateral dimension of the coupon non-metallic encapsulation mimicking the structure coating is relevant for the spread resistance and correspondingly for the current density. This is because the encapsulation (such as the coated structure) restricts the CP current flow in the electrolyte. In [Figure 1 a\)](#) to [c\)](#), x represents the width of insulated coupon surface adjacent to the bare steel surface and y represents the coating defect diameter. In the case of a defect on a structure, this width x would correspond to the coating extending around the defect. This value is typically quite large. Detailed analysis has shown^[5] that the effect of the width x is negligible when x is at least three times y (the

diameter of the steel surface of the coupon). If x is smaller, the current density on the coupon will be increased compared to that of an identical coating defect on the structure.

6.4 Surface area of the coupon

Generally, increasing the coupon size results in smaller average current density since the spread resistance decreases linearly with increasing y and the current density decreases linearly with the surface area (i.e. $0,25 \cdot \pi \cdot y^2$). As a consequence, the current density is typically underestimated when the coupon surface area is chosen larger than the maximum defect size present on the structure. For this reason, in the case of AC corrosion, the use of 1 cm^2 has been established as a standard dimension in [ISO 18086](#). Contrarily, the use of 1 cm^2 to 100 cm^2 coupon surfaces may be indicated for investigating the effectiveness of CP. The size of the coupon shall be adapted to the coating defects expected on a given structure. It is important to note that it is not possible to prove the effectiveness of CP on a poorly coated structure with large coating defects based on a measurement on a 1 cm^2 coupon with a defect geometry represented in [Figure 1 c](#)), since the current density and the polarization will be significantly increased compared to the one on larger coating defects on the structure.

When using a coupon for a specific application, these effects shall be taken into account. They significantly affect the spread resistance, the resulting current density and the level of polarization. Depending on whether the coupon is used to demonstrate the effectiveness of CP, protection against interference from DC traction systems or AC corrosion, different designs are required. With respect to the effectiveness of CP, the design should reflect the highest possible spread resistances as obtained with the geometry in [Figure 1 a](#)) or [Figure 1 b](#)) in conjunction with a value for x that is larger than three times y . In contrast, the assessment with respect to AC and/or DC interference conditions low spread resistances are more critical corresponding to the geometry in [Figure 1 c](#)).

6.5 Other types of coupon geometries

The above description highlights the effects associated with plate-shaped coupons. However, the same basic principles apply to other geometries, such as rod-shaped coupons. Values of x that are significantly smaller than y will result in decreased spread resistance and typically increased current densities.

7 Monitoring purpose — Selection of installation sites

7.1 General

The selection of the installation sites shall include the following aspects:

- a detailed and comprehensive assessment of the CP effectiveness;
- an assessment of the effectiveness of CP under DC interference;
- an assessment of the effectiveness of CP under AC interference.

7.2 Detailed and comprehensive assessment of CP effectiveness

For a detailed and comprehensive assessment of CP effectiveness, the coupons may be installed in locations along the structure that may vary in soil resistivity, soil chemistry, moisture content, current density, coating condition and temperature. Examples of such locations are:

- the top of a dry, rocky hill;
- a low-lying wet valley;
- a mid-span between CP current sources;
- the suction and discharge of compressor stations;
- the casings.

The coupon should be located close to the structure to ensure that the soil conditions are similar at the coupon surface and at the nearby structure surface. The design of the coupon shall be adopted according to the coating system and coating condition of the structure. For the CP assessment, coupons shall be electrically connected to the structure. In order to ensure that the protection criterion is met, it can be useful to install coupons in locations where the access of CP current could be difficult. Typically, these are areas where the protection criterion can be difficult to obtain. Examples of such conditions with compromised CP effectiveness are:

- in high or very low soil resistivity;
- within casings;
- in the presence of high DC stray current.

In conditions and locations where it is not possible to place coupons close to the structure in the same backfill, it may be acceptable to place coupons somewhat remote from the structure, in a selected backfill.

To demonstrate a detailed and comprehensive effectiveness of CP in accordance with [ISO 15589-1](#), IR-free potentials shall be measured. This is possible based on the following requirements.

- Measuring the off-potential immediately after disconnecting the coupon from the structure. For demonstrating the effectiveness of CP, taking measurements after 0,3 s in accordance with [ISO 15589-1](#). However, to minimize depolarization effects causing the measured IR-free potential to become more positive, it can be necessary to commence measurements within a shorter period after the disconnection of the coupon. The measurement period shall be at least the time period of the AC cycle measured locally on the structure caused by various interference sources. This typically corresponds to 16,7 ms in the case of 60 Hz, 20 ms in the case of 50 Hz, and 60 ms in the case of 16,7 Hz interference. Optimum coupon IR-free potential measurements shall commence within 0,1 s after interrupting the current and shall measure for at least one AC cycle. This type of measurement allows for assessing concentration polarization.
- For demonstrating the absence of over-polarization, [ISO 15589-1](#) requires measurements using a “fast data logger or oscilloscope”. The data logger shall be sufficiently “fast” in the range of 1 ms to permit the measurements as detailed above. Similarly, such a high time resolution is required for the assessment of the effects of AC interference on the IR-free potential. These high data acquisition rates allow for the assessment of concentration polarization and activation polarization. Inductance and capacitance of the measurement circuit needs careful evaluation to ensure plausible data in the case of such fast measurements. This typically includes the use of shielded cables and high precision switching devices.
- Calculation of the IR-free potential based on the determined spread resistance and the on-potential. This measurement allows for an assessment of the polarization caused by concentration polarization and activation polarization in absence of AC interference. In the case of AC interference, the assessment of the contribution of the activation polarization requires the use of the fast-measured IR-free potential.
- Placing the reference electrode very close to the coupon surface thereby minimizing contributions of the spread resistance and stray currents in the soil to the IR-error. This allows for the direct assessment of the IR-free potential and eliminates all contributions from other voltage gradients in the ground caused by foreign constant and time-variant interferences.

An installation example for the assessment of the effectiveness of CP is given in [B.1](#).

7.3 Assessment of CP effectiveness under DC interference conditions

For the evaluation of the risk of DC stray current corrosion, the coupons shall be placed at any location where DC stray current causes unacceptable levels of interference. In the presence of stray currents created by DC traction systems, the influences produced along the structure can significantly change during the design life. To avoid any corrosion at cathodically protected structures caused by stray

currents, the requirements of [ISO 15589-1](#) and [EN 50162](#) with respect to IR-free potentials shall be permanently met. To demonstrate this requirement, the measurements shall be performed during a representative period of time. The sufficient period of time shall cover all normal variations created by time-variant DC interference. For this purpose, a data logger shall be installed for measuring IR-free potentials according to [7.2](#).

Additionally, [EN 50162](#) allows the assessment of effectiveness of CP under DC interference conditions based on current measurements. Examples for the assessment of effectiveness of CP under DC interference conditions are given in [Annex C](#). An example of using coupons for mitigating DC interference is shown in [C.2](#).

NOTE [EN 50162](#) provides guidance on the assessment of DC stray current interference.

7.4 Assessment of CP effectiveness under AC interference conditions

For the evaluation of the effectiveness of CP under AC interference, the coupons shall be installed wherever the criteria for AC corrosion likelihood are expected to be exceeded, as indicated by increased AC voltages, low soil resistivities and possible over-polarization. The areas with low soil resistivity and more negative on-potentials result in an increased AC corrosion risk based on [ISO 18086](#), since they contribute to low-spread resistances and high-current densities. The current densities typically increase with decreasing defect size. For coupons used to assess AC corrosion, the defect surface area is typically 1 cm², since larger defects will exhibit lower current densities and can overestimate the effectiveness of corrosion protection under AC interference. Additionally, the access of the current to a small defect is influenced by its geometry. The adjacent coating, its thickness and the geometry of the coupon shall reflect the expected defect geometry on the structure to obtain the most representative results. Wherever possible, the coupon should be installed on the lower part of the structure, since there the humidity of the soil is higher and, therefore, the soil resistivity is naturally lower. Further guidance for the assessment of effectiveness of CP under AC interference conditions is given in [B.2](#). Examples of concepts for addressing combined interference conditions are given in [Annex C](#).

NOTE [ISO 18086](#) provides guidance on the assessment of AC interference.

8 Installation procedures

The installation of coupons should be made in such a manner that the representative behaviour is maintained to the greatest possible extent. The following aspects shall be considered in this context:

- a) the coupon should be permanently installed, ideally in the same soil or backfill as the structure itself; if this is not possible, a replacement soil with conservative behaviour can be used;
- b) the coupon geometry and associated spread resistance should reflect the purpose of the monitoring;
- c) the coupon should not cause or receive any electrical interference from adjacent coupons or coating defects, unless this is part of the purpose of monitoring;
- d) the coupon should have and maintain an intimate contact to the surrounding soil, unless a lack of contact and poor bedding condition is part of the purpose of monitoring;
- e) if a permanent installation of the coupon is not possible, the effect of a limited polarization time on the obtained data with respect to corrosion protection, over-polarization and AC corrosion should be assessed; it shall be ensured that the temporary coupon is sufficiently polarized during the limited exposure time in order to demonstrate effectiveness of CP.

Intimate contact shall be maintained between the coupon surface and the surrounding environment. During the installation process, the soil around the coupon shall be compacted to prevent settlement and air voids forming around the coupon. These voids could result in loss of full contact between the coupon surface and the surrounding soil. The possible loss of contact because of soil movement caused by freezing or subsidence of the backfill material around the coupon shall be considered and minimized during installation, unless a lack of contact/poor bedding condition is part of the purpose of monitoring.

A loss of contact between soil and coupon can usually be excluded when the coupon's surface is oriented upward. In contrast, a loss of contact can be mimicked by orienting the coupon surface downward.

Coupons may be installed by a number of different methods, including:

- excavation activities during the structure investigation;
- installation of the coupon during construction of the structure under investigation;
- hand digging;
- auguring;
- vacuum excavation;
- use of an underground access box to limit excavation work for easier installation and later removal of coupon.

NOTE Access boxes usually consist of cement or plastic rings that allow direct access to the soil. They are usually closed and exhibit direct cable connections.

The installation method selected depends on the site access, type of soil to be excavated, cost involved and availability of an electrical connection to the structure.

9 Commissioning of coupons

9.1 Preliminary checking

Before connecting the coupon to the structure, the following measurements should be performed:

- corrosion potential of the coupon;
- potential of the permanent reference electrode (if present) against a portable reference electrode;
- spread resistance of the coupon (e.g. by measuring the resistance between coupon and pipe with a AC resistance meter);
- in cases of ER probes, the initial values of the electrical resistance of the built-in metal elements shall be recorded;
- soil resistivity near the coupon, if possible (e.g. with a soil box during installation or a resistivity calculation based on the spread resistance).

9.2 Start up

After connecting the coupon to the structure, the following measurements should be performed:

- coupon AC current;
- coupon DC current;
- on-potential;
- coupon IR-free potential;
- in cases of ER probes, the initial values of the electrical resistance of the build-in metal elements, under the influence of the AC current;
- checking of the remote monitoring system, if present.

In addition, the spread resistance of the coupon (e.g. by measuring the resistance between the coupon and pipe with an AC resistance meter) can be assessed.

9.3 Measurement of the settled parameters

Once the coupon has sufficient ground contact and after a suitable polarization period, the coupon parameters (see [9.2](#)) should be checked.

9.4 Installation and commissioning documents

After the successful installation of the coupon, the following documents can be prepared:

- installation date, as well as documents detailing the type of coupon and the dimensions of the coupon parameters;
- as-built layout documents showing the position of the coupon; additionally, other information can be collected such as the orientation of the coupon (e.g. upward by 45° or horizontally downward), the precise relative position to the pipe (vertical and lateral) and, if possible, the position relative to the position within the original backfill (e.g. in the backfill, 10 cm from native soil);

NOTE When the location of the coupon can be readily assessed in the field (e.g. due to an underground access box), the as-built layout documents are not required.

- results of all measurements carried out before and after commissioning;
- description of the installation with details and references to materials as well as information useful for the correct operation and maintenance, e.g. frequency of system checks.

The final data are the basis for subsequent system checks to be performed on the coupon arrangement. Results of relevant measurements carried out before, during and after commissioning shall be filed and retained. The relevant data are the parameters listed above.

9.5 Frequency of coupon measurement

The frequency of the measurement depends on the requirements with respect to a detailed and comprehensive assessment, i.e. typically every three years in accordance with [ISO 15589-1](#). [Annex C](#) gives examples of continuous coupon measurements based on remote monitoring and control systems.

Annex A
(informative)


Special types and procedures of coupons and probes

A.1 Coupons for determination of weight loss and pitting

The coupons are produced from steel plates that are marked, degreased and weighed. After the connection of the cable, the surface is coated except for the area simulating the coating defect. Until installed, it should be stored in a sealed plastic bag containing a drying agent. For cable connections, precautions shall be taken to prevent any contributions of cable connection and disconnection to the mass loss measurement. Typical solutions include a thread in the coupon in combination with a screwed cable connection.

When the coupon is excavated for evaluation, it is advised to collect a sample of the surrounding soil for determination of soil type and resistivity by means of a soil box. Before cleaning the exposed steel surface, a photo should be taken. The coupon is cleaned with fresh water, dried and placed in a plastic bag with a drying agent.

The coating is removed and the cable disassembled. The weight loss is determined by pickling in Clarke's solution (20 g Sb_2O_3 and 60 g $\text{SnCl}_2 \times 2\text{H}_2\text{O}$ per litre concentrated HCl), in accordance with [ISO 8407](#). The pickling is performed in several steps with weighing in-between. The mass loss for each pickling is transferred to a graph, see [Figure A.1](#).



Key
X pickling time
Y mass loss

Figure A.1 — Mass loss curve

The line AB represents the removal of corrosion products. The pickling is repeated until three points on or close to the horizontal line BC are achieved. Until point B, corrosion products still remain on the surface. At point B, the surface is clean from corrosion products and the points between B and C represent the attack on the base metal. The mass loss is extrapolated to the point D on the y-axis, which

represents the mass loss due to corrosion. The difference in mass loss between the points D and C is a compensation for the mass loss of the base metal during the pickling.

After each pickling, the coupons are rinsed in water, dipped in ethanol and dried in warm air. When the coupons are dry and have achieved room temperature, they are weighed. The pickling is performed at room temperature at periods between 1 min and 10 min depending on how heavily the coupons have been attacked.

The deepest pit within the exposed area should be determined using an optical microscope.

A.2 Perforation probes

The perforation probe can be used as a conventional coupon for regular measurements, but its primary purpose is to give a warning when the deepest corrosion pit reaches a predestined value. The key advantage is the simple handling and especially the information with respect to the corrosion depth. Hence, information about the depth of the corrosion is provided independent of the corroding surface. This is especially important in cases of very local corrosion that penetrates rapidly, but with little mass loss. The monitoring of the perforation probe can be readily integrated into the conventional inspection routine and also remotely controlled.

There are different types of perforation probes, but they are built on the same principle idea. When corrosion penetrates a thin steel plate with a thickness of typically 0,5 mm to 2 mm, this can be detected by a physical measurement, as described below.

The conductive type consists of a thin steel plate and an internal electrode. When corrosion perforates this steel plate, humidity will penetrate into the gas tight coupon and form a conductive electrolyte between the electrode and the thin plate. By a resistance measurement between the electrode and the thin plate, the perforation of the coupon can be detected by means of conventional resistance measurement devices.

The pressurized perforation probe based on pressure surveillance consists of a steel tube connected to a flexible copper tube. Both tubes are covered with a heat shrinkable tube, except for the defect on the steel tube. The copper tube is fitted into a junction box. To the same box, a valve and a manometer are connected, enabling pressurization of the copper/steel tube as well as monitoring the pressure. This measuring device is placed within a plastic container, which is mounted within the test post. When the deepest pit penetrates the wall of the exposed steel surface, the pressure falls, and this is indicated on the manometer.


A.3 ER probes

The ER probe technique can be applied for corrosion rate assessment as an alternative to the weight loss coupon. Unlike the weight loss coupon, the ER coupon technique does not require excavation for thickness measurement during normal operating conditions and weighing procedures since a mass loss is assessed by electronic means. Other coupon quantities, such as AC current, DC current, spread resistance, etc., can also be measured on ER coupons.

The ER technique consists of measuring the change of the resistance of a metal element formed as a coupon. When the metal element suffers from metal loss due to corrosion, the electrical resistance of the element increases. Since the resistance of the element also changes due to temperature variations, a second element, which is coated in order to protect it from corrosion, is used for temperature compensation. The element exposed to the corrosive environment constitutes the coupon part element, whereas the element protected from corrosion by the coating constitutes a reference element (see [Figure A.2](#)).

When current is exchanged between the exposed element and the soil, the ER technique should provide a means for temperature compensation due to heating of the exposed element by the current exchange.

The resistance values of the two individual elements are usually measured by passing an excitation current through the elements and measuring the voltage generated over the element length caused by the excitation current.



- Key**
Rr reference element
Rc coupon element
Ie excitation current
- VR voltmeter for reference element
VC voltmeter for coupon element

Figure A.2 — Principle of ER probe with excitation current and voltage measurement

The thickness of the coupon element at time *t* can be assessed throughout time using the sketched circuit principle. The coupon element thickness at time *t* is then quantified using a mathematical algorithm.

Annex B (informative)


Assessment of the effectiveness of CP under any conditions including DC and/or AC interferences

B.1 CP criteria based on the IR-free potentials

Under any conditions, including DC and/or AC interferences, as a first step, CP criteria based on the protection potentials and limiting critical potential provided by [ISO 15589-1](#) shall be met. As these potentials are polarized ones without IR errors, the effectiveness of CP for steel structures can be assessed by coupon instant-off (IR-free) potential measurements.

The measurements shall be taken immediately after the coupon is disconnected from the pipe without interrupting all sources of CP current to the structure. Accurate coupon instant-off potentials can be acquired by placing the reference electrode as close to the coupon as possible to minimize the IR drop due to stray currents. [Figure B.1](#) shows an example of a measuring system for coupon on-potential, coupon instant-off potential, and coupon DC and AC currents on a permanent coupon. A coupon should be installed so as not to shield CP current flowing into the structure. [Figure B.1](#) shows an example of an upwards oriented coupon with the surface area of 1 cm² that is installed in a 9 o'clock position of the structure. An on or off-status between the coupon and the pipe is created by operating a solid state relay[6].

It is relatively simple to measure on-potential at each measuring point and AC voltage along the entire structure. On-potential and AC voltage measurements detect the areas of positive (anodic interference) and negative (cathodic interference) potential shifts indicating the risks of stray current interference and over-polarization, respectively, and the point of highest AC interference. At the detected critical points, coupon measurements (instant-off potential and DC and AC currents) can be taken for demonstrating the effectiveness of CP.



Key	
1	structure (ex. pipeline)
2	high resistivity coating
3	CP current and DC/AC stray current
4	coupon
5	reference electrode
6	voltmeter
7	ammeter shunt
8	solid state relay
9	soil

Figure B.1 — Example of a measuring system for coupon on-potential, coupon instant-off potential, and coupon DC and AC currents

B.2 AC interference

Based on [ISO 18086](#), increased AC and DC current densities cause increased AC corrosion rates. These increased current densities are associated with higher AC voltages and more negative on-potentials. Hydroxides and carbonates of earth alkali cations produce solid precipitates with sometimes increased resistivity, leading to a higher spread resistance and a correspondingly lower AC corrosion rate at the coating defect.

The installation of coupons allows for a direct assessment of these complex interactions and demonstration of effective corrosion protection.

B.3 Real time remote monitoring and control of the rectifiers based on coupon data

In cases of a strong variation of AC and/or DC interferences over time, it can be difficult to control interference phenomena with a fixed setting of the rectifiers. The application of an impressed current cathodic protection (ICCP) system with remote monitoring and remote control of the rectifier based on coupon measurements, such as coupon on-potential, coupon instant-off potential or coupon AC and DC current, can be an effective way of assessing and ensuring effective corrosion protection.

Annex C (informative)

Examples of instant-off and current density measurements on coupons — Remote monitoring and remote control

C.1 Real-time remote monitoring and control of the rectifier based on IR-free potential measurements in cases of DC interference

The amount of change in coupon instant-off potential readings measured with a reference electrode in the direct vicinity of the coupon is less than that of on-potentials under stray current interference conditions. Therefore, continuous remote monitoring and remote control over the rectifier based on coupon instant-off potential measurements in accordance with [EN 50162](#) can improve the efficiency of the operation of the ICCP system due to the optimized output current of the rectifier[7].

In cases where it is hard to make a clear distinction between anaerobic (immunity environment) and aerobic soils (passivity environment), a coupon instant-off potential of $-0,95 V_{CSE}$ or more negative could be required to control the rectifiers.

Under homogeneous soil conditions that have very high resistivity and are well-aerated, IR-free potentials more positive than $-0,85 V_{CSE}$ could be sufficient. [ISO 15589-1](#) offers the following criteria for aerated soil:

- $-0,75 V_{CSE}$ where soil resistivity is between $100 \Omega m$ and $1000 \Omega m$;
- $-0,65 V_{CSE}$ where soil resistivity is greater than $1\,000 \Omega m$.


C.2 Real-time remote monitoring and control of the rectifier based on current density measurements in cases of DC interference

The CP level can be evaluated by placing a steel coupon at a critical point, then determining the coupon DC current, which shows entering (protection) and leaving (corrosion) directions as shown in [Figure C.1](#).

With this set up, the constant DC current density averaged over a representative period of time (e.g. 24 h) on the coupon should always be maintained so that the effectiveness of CP is maintained. After confirming the AC interference level is acceptable as defined in [ISO 18086](#), the calculated average DC current density of the coupon is adjusted to the predetermined value. Any decrease in the average coupon DC current density below the preset value will cause the transformer-rectifier current output to increase automatically until a balance is regained. Likewise, any increase in the average DC current density above the predetermined value will cut the current output until a balance is regained.

This approach is only feasible using very rapid response control-circuits and is particularly effective for a structure buried in a stray current exposure area showing the possibly very marked and quick stray current variations.

When a structure is buried under a railroad crossing, and when required during the CP design step, the installation of a coupon should be implemented at the stage of structure laying in the casing pipe. The location of the coupon is very important, particularly when used to control the system. The coupon should be placed just under a railroad crossing where the most intense risks of corrosion and over-polarization are possible. Since the area of influence surrounding the track at the railroad crossing is limited, it is applicable for the installation of shallow groundbed anodes and smaller CP currents, which can result in minimization of the interference effect on foreign metallic structures and AC corrosion risk.



Key			
1	structure	6	soil
2	groundbed anode	7	train equipped with regenerative braking
3	coupon	8	transformer-rectifier
4	casing pipe	9	equipotential line
5	electrolyte		

Figure C.1 — Coupon DC current density controlled impressed current cathodic protection system[8]

The structure should be evaluated to determine if its CP system is operating properly. The application of a remote monitoring system is very effectual. Items of this remote monitoring system are coupon current density, voltage and current outputs, and the total circuit resistance (= (average voltage output) / (average current output)).

A DC power source with automatic control should be used to maintain a constant coupon DC current density that should be set (e.g. 1 A/m²).


The DC power source should be able to deliver a sufficient output current instantly when the coupon DC current density becomes below the set value.

This type of DC power source should also be able to cut the output current instantly to mitigate the over-polarization risk when leakage current enters the coupon, with the result that the cathodic current becomes greater than the preset value at the coupon location.

The DC power source shall be equipped with a smoothing circuit (filters), which limits the magnitude of ripple to a value as low as possible. Thereby, the DC power source can maintain a preset constant coupon DC current density very accurately.

The DC power source with output current limitation circuits has an effective shut-down in the event of an external short circuit.

A typical block diagram for a constant coupon DC current density controlled ICCP system is shown in [Figure C.2](#).



Key

- | | |
|---------------------------------------|-----------------------------------|
| 1 structure | 11 switching circuit |
| 2 coupon | 12 transforming circuit |
| 3 casing pipe | 13 12-bit SAR A/D converter |
| 4 electrolyte | 14 comparator circuit |
| 5 groundbed | 15 pulse width modulation circuit |
| 6 diode | 16 isolation amplifier |
| 7 ammeter shunt for output current | 17 control of output voltage |
| 8 ammeter shunt for coupon DC current | 18 DC power source |
| 9 rectifying circuit | 19 remote monitoring device |
| 10 smoothing circuit | 20 soil |

Figure C.2 — A typical block diagram for constant coupon DC current density controlled impressed current cathodic protection system[8]

Figure C.3 is an example of a measurement of controlled DC current density of 1 A/m².





Figure C.3 — An example of a measurement of controlled DC current density of 1 A/m²[8]

C.3 Real-time remote monitoring and control of the rectifier based on on-potential measurements in case of AC interference

Time-variant DC stray currents are manifested by a fluctuation in on-potentials. The on-potentials can simply be measured at each measuring point and any change in on-potential more positive or negative than the preset value will cause the rectifier current output to increase or decrease easily using remote monitoring and control of the rectifier in an ICCP system.

A setup of remote monitoring and control of the rectifier based on on-potentials and coupon verification at selected measuring points is shown in Figure C.4. The remote monitoring on-potential data are sent to a server via connection 8. The server calculates the optimal CP set value, then sends the parameters via connection 9 to the rectifier, thereby CP is always maintained in optimum condition from the point of view of sufficient CP and minimized over-polarization.



Key

- | | | | |
|---|---------------------|----|---|
| 1 | structure | 8 | transformer-rectifier |
| 2 | coating | 9 | server |
| 3 | groundbed | 10 | soil |
| 4 | coupon | 11 | railway crossing |
| 5 | reference electrode | 12 | connection between a measuring point and a server |
| 6 | volt meter | 13 | connection between a transformer-rectifier and a server |
| 7 | CP current | | |

Figure C.4 — Setup of remote monitoring and control of rectifier based on coupon on-potential measurements[9]

Bibliography

- [1] ISO 8044:2020, *Corrosion of metals and alloys — Vocabulary*
- [2] [ISO 8407](#), *Corrosion of metals and alloys — Removal of corrosion products from corrosion test specimens*
- [3] [ISO 18086](#), *Corrosion of metals and alloys — Determination of AC corrosion — Protection criteria*
- [4] [EN 13509](#), *Cathodic protection measurement techniques*
- [5] NIELSEN L.V., PETERSEN M.B., BORTELS L., PARLONGUE J. *Effect of coating defect size, coating defect geometry, and cathodic polarisation on spread resistance: Consequences in relation to AC corrosion monitoring*. CEOCOR International Congress, 2010
- [6] KAJIYAMA F. *Alternating current corrosion likelihood of cathodically protected steel pipelines by analysing coupon current for a single period*, CEOCOR International Congress Paper 2014-10, 2014
- [7] MAGNIFICO I., DOMBARD C. *Instant off measurements on coupons: Practical advantages of a continuous remote monitoring and rectifier remote control based on Eoff, improving effects on cathodic efficiency evaluation and maintenance operations*. CEOCOR International Congress Paper 2016-17, 2016
- [8] KAJIYAMA F. *Challenges in developing coupon DC current density-controlled impressed current cathodic protection system on buried steel pipelines*. CEOCOR International Congress Paper 2018-07, 2018
- [9] JOOS D., BÜCHLER M. *Real time remote monitoring and control of the cathodic protection for mitigation of interference*. CEOCOR International Congress Paper 2016-23, 2016

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

