



BSI Standards Publication

Corrosion of metals and alloys — Measurement of the electrochemical critical localized corrosion temperature (E-CLCT) for Ti alloys fabricated via the additive manufacturing method

National foreword

This British Standard is the UK implementation of [ISO 22910:2020](#).

The UK participation in its preparation was entrusted to Technical Committee ISE/NFE/8, Corrosion of metals and alloys.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 580 51724 2

ICS 77.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
22910

First edition
2020-08-06

Corrosion of metals and alloys — Measurement of the electrochemical critical localized corrosion temperature (E-CLCT) for Ti alloys fabricated via the additive manufacturing method

*Corrosion des métaux et alliages — Mesurage de la température
critique de la corrosion localisée électrochimique pour les alliages de
Ti fabriqués à l'aide d'une méthode de fabrication additive*



Reference number
ISO 22910:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO’s member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Main contents and limitations of existing standards	1
4.1	Application coverage of ISO 17864	1
4.2	Limitations of ISO 17864	1
4.3	Scope of ISO 18089	2
4.4	Limitations of ISO 18089	2
5	Principle	2
6	Apparatus	4
6.1	Potentiostat	4
6.2	Recirculating heating bath with temperature controller	4
6.3	Specimen holder and connections	4
6.4	Test cell	5
6.5	Auxiliary electrode and reference electrode	5
7	Test solutions	6
8	Test specimens	6
9	Procedure	6
9.1	Preparation of reference electrodes	6
9.2	Preparation of Ti alloy specimen	6
9.3	Preparation of solution	6
9.4	Setting up the E-CLCT test	6
9.5	Ending test	7
10	Evaluation of test results	7
11	Test report	7
Annex A (informative) Relationship between applied potential and localized corrosion of AM Ti-alloys with temperature		8
Bibliography		9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Ti alloys such as Ti-6Al-4V are considered the most promising engineering materials. Due to a unique combination of high strength-to-density ratio and increased mechanical and corrosion resistance, their applications are growing in a wide range of industries, e.g. aerospace, automobile, marine and biomedical fields.

Ti alloys are conventionally produced by wrought or cast processes, which are subtractive manufacturing (SM) methods. The recent emergence of a new additive manufacturing (AM) method known as “3D printing” has gained worldwide attention as a way to cut costs and improve efficiency for small quantity, batch productions.

Additively manufactured Ti alloys are extensively investigated for their usage in aerospace and medical applications. When AM is compared with conventional manufacturing, the buy-to-fly ratio is known to be around 15:1 (conventional). In terms of mechanical viewpoints, both the strength and ductility of Ti alloys such as Ti-6Al-4V fabricated via AM are comparable to or superior to those developed via conventional manufacturing methods, because of their unique microstructure based on laser or electron beam technologies. However, the characteristics of additively manufactured alloys are highly dependent upon the geometric and processing conditions (and there are over 130 variables) such as layer formation (imbedded or sprayed), size and quality of powder or wire, dimension, input energy, layer orientation and surface conditions, and tolerance in the CAD process, which converts the data into additive layers for building parts. The differences in layer orientation and the porosity generated by crossing hatches during the layer-by-layer fabrication process can result in differences in both mechanical and electrochemical properties in AM materials. Heat treatment controls the porosity or the microstructure derived from rapid melting and quenching; however, it cannot eliminate interlayers, which contribute to the differences in the mechanism of localized corrosion in AM materials. The resistance to corrosion of Ti alloys produced via AM is similar to that of conventionally manufactured Ti alloys. The mechanisms of corrosion also differ. Therefore, since the conventional testing methods have shown limited ability for evaluation of those properties, the new test method measuring electrochemical critical localized corrosion temperature (E-CLCT) has been developed to evaluate pitting and crevice corrosion in alloys generated via AM. E-CLCT is defined as the lowest temperature on the surface of the AM specimen on which localized corrosion to both pitting and crevice corrosion is initiated under specified test conditions.

This document specifies a procedure for evaluation of the resistance to localized corrosion on the AM alloys by measuring their E-CLCT, providing an efficient method for a qualitative evaluation or comparison of corrosion properties between AM materials or their heats with altered process variables. This test method demonstrates the quality of heat treatment, bonding integrities between layers, and effective control of variables for AM materials, providing a qualitative tool for long-term application. Furthermore, this document can extend its use from AM Ti-alloys to other AM alloys, such as Ni alloys by modifying the concentration of test solutions or the applied potentials. This document also provides important clues to evaluate other types of localized corrosion such as corrosion cracking and erosion-corrosion. Related documents can be developed and followed up based on the results of this test.

Corrosion of metals and alloys — Measurement of the electrochemical critical localized corrosion temperature (E-CLCT) for Ti alloys fabricated via the additive manufacturing method

1 Scope

This document specifies procedures for testing the resistance to localized corrosion of Ti alloys fabricated via additive manufacturing (AM) method. This document regulates the electrochemical critical localized corrosion temperature (E-CLCT) of the AM Ti materials for a comparative evaluation of resistance to localized corrosion.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

electrochemical critical localized corrosion temperature

E-CLCT

lowest temperature on the surface of the AM Ti alloy specimen at which stable localized corrosion, including both pitting and crevice corrosion, occurs under specified test conditions

3.2

temperature ramp rate

rate at which the surface temperature of the specimen increases during the test

4 Main contents and limitations of existing standards

4.1 Application coverage of ISO 17864

The test method in [ISO 17864](#) determines the critical pitting temperature (CPT) using a potentiostatic technique with a temperature scan. The current is monitored during the temperature scan, and CPT is defined as the temperature at which the current increases rapidly, which for practical reasons is defined as the temperature at which the current density exceeds $100 \mu\text{A}/\text{cm}^2$ for 60 s. Pitting on the specimen is confirmed visually after the test.

4.2 Limitations of ISO 17864

[ISO 17864](#) is useful to measure the resistance of pitting corrosion for stainless steel and related alloys. This method applies to wrought or cast products. However, this method cannot be used for Ti alloys





Figure 1 — Determination of E-CLCT values of Ti-6Al-4V, CP-Ti, and Ni718 for the side edge parallel to the AM direction produced by additive manufacturing, according to applied potentials of 2,8 V with respect to saturated calomel electrode in the concentrated sodium chloride (mass fraction of 25 %) solution



a) Subtractive-manufactured Ti-6Al-4V alloys



b) Additive-manufactured Ti-6Al-4V alloys

Figure 2 — Two different shapes of crevice corrosion on Ti-6Al-4V alloys

6 Apparatus

6.1 Potentiostat.

The potentiostat shall be capable of controlling the electrode potential to within ± 1 mV of a preset value.

This potentiostat should have the electrode potential-measuring instrument with a high impedance of the order $10^{11} \Omega$ to $10^{14} \Omega$ and the current-measuring instruments capable of measuring current to within 2 % of the actual value.


6.2 Recirculating heating bath with temperature controller.

The recirculating heating bath is a vessel capable of generating temperatures between 0 °C and 100 °C \pm 1 °C.

The temperature controller should facilitate increase in the surface temperature of the specimen from 0 °C to 100 °C with the temperature ramp rate of 1 °C/min.

6.3 Specimen holder and connections.

Figure 3 shows the schematic design on the specimen holder and connection. Any part of the specimen holder or the connection of the electrode shall be designed to avoid corrosion in the connecting point with resin seal or a similar coating.



Key


- 1 line of solution
- 2 electric connection

The crevice former shall not be placed.

Figure 3 — Schematic diagram of a specimen

6.4 Test cell.

The test cell shall contain the test specimen, a Luggin capillary probe connected to an external reference electrode to measure the electrode potential, an auxiliary electrode, a port for insertion of a temperature-measuring device and a facility for stirring the solution by bubbling gas through the solution, as shown in [Figure 4](#).



Key

- | | |
|-----------------------|---------------------|
| 1 reference electrode | 4 counter electrode |
| 2 double wall | 5 specimen |
| 3 electrolyte | |

Figure 4 — Schematic diagram of CLCT cell

6.5 Auxiliary electrode and reference electrode.

The auxiliary electrode is prepared from high-purity platinum. The reference electrode shall be maintained at ambient temperature external to the test cell and connected to the test cell via a Luggin capillary probe. The commonly used reference electrode is the saturated calomel electrode.

7 Test solutions

For the test, 250 g of reagent-grade sodium chloride (NaCl) is dissolved in 750 ml of reagent water, producing an aqueous solution containing 25 % NaCl by mass. The ratio of the volume of solution in the test cell to the specimen area shall be at least 100 ml/cm².

8 Test specimens

Any specimen geometry compatible with the specimen holder may be used. Two different test surfaces of the specimen are used, which are made by the layers perpendicular to or parallel to the stacking direction, depending on the stacking direction via AM. A minimum test volume of 10 mm × 10 mm × 1 mm or higher shall be used. A less than 20 % ratio of edge area to total area is desirable.

9 Procedure

9.1 Preparation of reference electrodes

The difference in potential between the reference electrode and two other validation electrodes shall be measured. If the potential difference is greater than 3 mV, the test electrodes shall be rejected.

9.2 Preparation of Ti alloy specimen

The specimen shall be prepared to ensure a reproducible surface finish.

The specimen shall be cleaned immediately prior to immersion in the solution by degreasing, rinsing in high-purity water, followed by ethanol or a similar solvent, and air drying. After degreasing, care shall be taken not to contaminate the test surface of the specimen.

9.3 Preparation of solution

The solution shall be prepared using reagent-grade chemicals and reagent-grade water purified to 20 µS/cm by distillation equivalent to type I grade (see [ISO 3696](#)).

9.4 Setting up the E-CLCT test

The exposed surface area of the specimen shall be measured. Two different test surfaces of the specimen are prepared, comprising layers perpendicular to or parallel to the stacking direction, depending on the stacking direction via AM.

The specimen, counter electrode and salt bridge shall be placed in the test cell. The test cell shall be filled with the solution. It is important to ensure that the specimen is immersed and exposed in the solution. The salt bridge is filled with test solution and is free of air bubbles.

The solution shall be stirred continuously throughout the test by bubbling an inert gas through the solution at a controlled rate.

The electrodes shall be connected to the potentiostat and the data-recording device. The connections for temperature measurement and control shall be made.

The open-circuit potential of the test specimen shall be recorded and the desired anodic potential shall be applied to the specimen. The recommended applied potential for Ti alloys (e.g. Ti-6Al-4V) in the concentrated sodium chloride (25 %) solution is 2,8 V with respect to the saturated calomel electrode (SCE) (25 °C). If uncertainty exists concerning whether 2,8 V_{SCE} is sufficiently high to obtain the potential independent E-CLCT, a test at 2,9 V with respect to SCE (25 °C) may be performed. A significant deviation between the E-CLCT obtained at 2,8 V_{SCE} and 2,9 V_{SCE} indicates the need for re-evaluation and new choice of potential (for information, refer to [Annex A](#)). Following application of potential for 60 s or longer, the specimen temperature shall be increased at a controlled rate.

The current and solution temperature shall be monitored throughout the test.

The E-CLCT is defined as the temperature at which a sharp increase in current density occurs during the temperature ramp at 1 °C/min.

9.5 Ending test

The test shall be terminated when the E-CLCT is determined.

The specimen shall be removed from the solution and rinsed in water, cleaned with ethanol, rinsed with high-purity water, cleaned with ethanol or a similar solvent, and dried in air.

The specimen shall be inspected using an optical microscope to determine pitting and crevice corrosion. The ending current density may be higher than 1 mA/cm² (e.g. 5 mA/cm²) if the surface is evaluated after testing.

10 Evaluation of test results

The E-CLCT shall not be compared with values obtained using a different procedure. The E-CLCT of AM Ti alloys is specific to the test method used and should only be used as a comparative measure of performance.

Localized corrosion is generally of random nature, and thus the number of specimens required for experimental condition is preferably greater than three considering data scatter and analysis.

11 Test report


The test report shall include the following information:

- a) a reference to the document used (including its year of publication);
- b) the test solution and its volume;
- c) a full description of the test materials from which the specimens were taken, including composition and structural condition, type of product and section thickness;
- d) the orientation and size of test specimens;
- e) the surface finish of specimens, including the storage time between carrying out the final surface finish and testing;
- f) the test area and the minimum thickness;
- g) the electrode potential;
- h) the temperature ramp rate;
- i) a description of the specimen surface after testing;
- j) the electrochemical critical localized corrosion temperature (E-CLCT);
- k) ending current density;
- l) deviation of test results from the procedure;
- m) unusual features observed;
- n) a reference to explain the calculation of the results;
- o) the date of the test.

Annex A
(informative)

Relationship between applied potential and localized corrosion of
AM Ti-alloys with temperature

The potential for localized corrosion at a given temperature varies because of the random nature of the localized corrosion initiation. Therefore, the characteristic localized corrosion potential is best described as a range shown by the shaded area in [Figure A.1](#). Generally, the localized corrosion potential decreases with increasing temperature. The occurrence of localized corrosion on AM Ti-alloys as a function of temperature and potential is shown in [Figure A.1](#).



Key	
X	temperature
Y	potential
1	transpassive corrosion
2	localized corrosion
3	localized corrosion potential range
4	no localized corrosion
a	High potential.
b	Low potential.
c	E-CLCT potential <u>independent</u> .
d	E-CLCT potential <u>dependent</u> .

Figure A.1 — Principles of potential and temperature effects on the localized corrosion of
AM Ti-alloys

As shown in [Figure A.1](#), the potential independent E-CLCT represents the temperature limit of only passive or transpassive corrosion on an AM Ti-alloy below a certain temperature, whereas the potential dependent E-CLCT is defined by the temperature under localized corrosion depending on the potential at temperatures above the potential independent E-CLCT. Thus, the localized corrosion can occur at potentials within the localized potential range if the temperature is sufficiently high. In this case, the E-CLCT depends on the specific potential and variation in the localized corrosion potential. Therefore, the optimum localized corrosion potential selected should be the potential independent E-CLCT. [Figure A.1](#) also shows the potential dependent E-CLCT range for a specific low potential. Principally, the low temperature limit of the potential dependent E-CLCT is the potential independent E-CLCT. At potentials within the localized corrosion potential range, localized corrosion can occur if the temperature is sufficiently high. In this case, the E-CLCT depends on the specific potential. At potentials above the localized corrosion potential range and below the transpassive potential, localized corrosion can occur virtually instantaneously. However, at potentials below the localized corrosion potential range, no localized corrosion occurs.

Bibliography

- [1] [ISO 3696](#), *Water for analytical laboratory use — Specification and test methods*
- [2] [ISO 17864](#), *Corrosion of metals and alloys — Determination of the critical pitting temperature under potentiostatic control*
- [3] [ISO 18089](#), *Corrosion of metals and alloys — Determination of the critical crevice temperature (CCT) for stainless steels under potentiostatic control*
- [4] DONG-IL SEO and JAE-BONG LEE. Corrosion characteristics of additive-manufactured Ti-6Al-4V using microdroplet cell and critical pitting temperature techniques. *Journal of the Electrochemical Society*. 2019, 166(13), pp. C428–C433
- [5] JAE-BONG LEE, DONG-IL SEO and HYUN-YOUNG CHANG. Evaluating corrosion resistance of additive-manufactured Ti-6Al-4V using electrochemical critical localized corrosion temperature. *Metals and Materials International*. 2020, 26(1), pp. 39–45

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

