



BSI Standards Publication

Rubber — Determination of ash

Part 2: Thermogravimetric analysis (TGA)

National foreword

This British Standard is the UK implementation of ISO 247-2:2018.

The UK participation in its preparation was entrusted to Technical Committee PRI/22, Testing and analysis of rubber.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 96310 0

ICS 83.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2018.

Amendments/corrigenda issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

INTERNATIONAL
STANDARD

ISO
247-2

First edition
2018-07-31

Rubber — Determination of ash —
Part 2:
Thermogravimetric analysis (TGA)

Caoutchouc — Détermination du taux de cendres —
Partie 2: Analyse thermogravimétrique (TGA)



Reference number
ISO 247-2:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

| Contents | | Page |
|----------------------------------------------|---------------------------------------------|-----------|
| Foreword | | iv |
| 1 | Scope | 1 |
| 2 | Normative references | 1 |
| 3 | Terms and definitions | 1 |
| 4 | Principle | 2 |
| 5 | Reagents | 2 |
| 6 | Apparatus | 2 |
| 7 | Preparation of the test sample | 2 |
| 8 | Calibration | 2 |
| 9 | Procedure | 3 |
| | 9.1 Method A | 3 |
| | 9.2 Method B | 3 |
| 10 | Expression of results | 3 |
| 11 | Precision | 4 |
| 12 | Test report | 4 |
| Annex A (informative) Precision | | 5 |
| Bibliography | | 7 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

A list of all parts in the ISO 247 series can be found on the ISO website.

Rubber — Determination of ash —

Part 2: Thermogravimetric analysis (TGA)

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies two methods for the determination of ash from raw rubbers, compounded rubbers and vulcanizates using a thermogravimetric analyser (TGA).

The methods are applicable to raw, compounded or vulcanized rubbers of the M, O, R and U families described in [ISO 1629](#):

- Method A is applicable for the determination of the ash from raw rubbers.
- Method B is applicable for the determination of the ash from compounded or vulcanized rubbers.

The methods are not applicable for the determination of the ash from raw rubbers, compounded or vulcanized rubbers containing chlorine, bromine or iodine.

This document does not cover the interpretation of the ash results from the inorganic chemical contents of compounded or vulcanized rubbers.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 248-1](#), *Rubber, raw — Determination of volatile-matter content — Part 1: Hot-mill method and oven method*

[ISO 1795](#), *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

9 Procedure

9.1 Method A

9.1.1 Switch on and stabilize the instrument, set the temperature of furnace to 30 °C.

9.1.2 Place an empty sample pan on the platform and tare the sample pan.

9.1.3 Take about 10 mg to 20 mg from the test portion of raw rubber (see 7.1) and weigh to the nearest 0,1 mg. Place it in the sample pan. Position the sample pan on the sample platform and load the sample pan onto the thermo-balance.

9.1.4 Set the flow rate according to the manufacturer's instructions. Raise the temperature to 500 °C at a rate of 20 °C/min or 30 °C/min under an atmosphere of nitrogen. Maintain at this temperature for 1 min.

9.1.5 Switch from the stream of nitrogen to a stream of oxygen or air. Raise the temperature to 550 °C. Maintain the temperature at 550 °C for 5 min or until the mass is constant.

9.1.6 Calculate the ash using the apparatus micro-processor.

9.2 Method B

9.2.1 Switch on and stabilize the instrument, set the temperature of furnace to 30 °C.

9.2.2 Place an empty sample pan on the platform and tare the sample pan.

9.2.3 Take a test portion of about 10 mg to 20 mg from the test sample of compounded or vulcanized rubbers (see 7.2 or 7.3) and weigh to the nearest 0,1 mg. Place it in the sample pan. Position the sample pan on the sample platform and load the sample pan onto the thermo-balance.

9.2.4 Set the flow rate according to the manufacturer's instructions. Raise the temperature to 550 °C at a rate of 20 °C/min or 30 °C/min under an atmosphere of nitrogen. Maintain at this temperature for 1 min.

9.2.5 Switch from the stream of nitrogen to a stream of oxygen or air. Raise the temperature to 650 °C. Maintain the temperature at 650 °C for 5 min or until the mass is constant.

For compounded or vulcanized rubbers containing inorganic fillers such as calcium carbonate, a temperature of 850 °C should be used.

9.2.6 Calculate the ash using the apparatus micro-processor.

10 Expression of results

The ash content, w , is given, as a percentage mass fraction, by [Formula \(1\)](#):

$$w = \frac{m_1}{m_0} \times 100 \quad (1)$$

where

m_0 is the mass of the test portion, in milligrams;

m_1 is the mass of the ash, in milligrams.

11 Precision

See [Annex A](#).

12 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 247-2:2018;
- b) all details necessary for identification of the sample tested;
- c) the method employed — method A or method B;
- d) the heating rate and the final temperature reached;
- e) the type of apparatus used;
- f) the result of the test;
- g) details of any procedures not specified in this document as well as details of any incidents which could have influenced the results;
- h) the date of the test.

Annex A (informative)

Precision

A.1 General

An interlaboratory test programme (ITP) to determine the precision of the two test methods specified in this document was conducted using thermogravimetric analysers in April 2017. The precision evaluated was a type 1 precision in accordance with Method B in ISO 19983. Precision concepts and nomenclature are also given in ISO 19983.

Nine laboratories participated in the ITP and four different materials (Raw rubber: NR and NBR, compounded SBR, vulcanized NR) were used. A test result was taken to be the average value of two measurements. Test results were obtained on two different days at intervals of one week. Two measurements were repeated for each day.

A.2 Precision results

The precision results are given in [Table A.1](#) for method A and [Table A.2](#) for method B. These results were obtained using outlier deletion procedures as described in ISO 19983.

Repeatability: The difference between two day test (value) averages, found on nominally identical material samples under correct operation of this test method, exceed the tabulated day-to-day repeatability on average not more than once in 20 cases.

Reproducibility: The difference between two independently measured test (value) averages, found in two laboratories using correct operation of this test method on nominally identical material samples, exceed the tabulated reproducibility not more than once in 20 cases.

Table A.1 — Precision data for Method A

| Material | Mean content | Within lab | | | Between labs | | | No. of labs ^a |
|----------|--------------|------------|-------|---------|--------------|-------|-------|--------------------------|
| | | s_{rD} | r_D | (r_D) | s_R | R | (R) | |
| NR | 0,29 | 0,039 | 0,110 | 37,9 | 0,100 | 0,283 | 97,6 | 8 |
| NBR | 0,55 | 0,067 | 0,190 | 34,5 | 0,096 | 0,272 | 49,5 | 9 |

The symbols used in this table are defined as follows:

s_{rD} is the day-to-day repeatability standard deviation;

r_D is the day-to-day repeatability, in measurement units;

(r_D) is the relative day-to-day repeatability, in percent;

s_R is the reproducibility standard deviation;

R is the reproducibility, in measurement units;

(R) is the relative reproducibility, in percent.

^a The final number of laboratories in the ITP after deletion of outliers.

Table A.2 — Precision data for Method B

| Material | Mean content | Within lab | | | Between labs | | | No. of labs ^a |
|----------|--------------|------------|-------|---------|--------------|-------|-------|--------------------------|
| | | s_{rD} | r_D | (r_D) | s_R | R | (R) | |
| SBR | 2,06 | 0,057 | 0,161 | 7,81 | 0,289 | 0,818 | 39,7 | 8 |
| NR | 5,12 | 0,107 | 0,303 | 5,92 | 0,239 | 0,676 | 13,2 | 7 |

For the meanings of the symbols used in this table, see [Table A.1](#).

^a The final number of laboratories in the ITP after deletion of outliers.

Bibliography

- [1] [ISO 1629](#), *Rubber and latices — Nomenclature*
- [2] ISO 19983, *Rubber — Determination of precision of test methods*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK