



BSI Standards Publication

Magnesium and magnesium alloys — Wrought magnesium and magnesium alloys

National foreword

This British Standard is the UK implementation of [ISO 3116:2019](#). It supersedes [BS ISO 3116:2007](#), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee NFE/35, Light metals and their alloys.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 539 02398 5

ICS 77.120.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2019.

Amendments/corrigenda issued since publication

Date	Text affected

Fifth edition
2019-05-23

**Magnesium and magnesium
alloys — Wrought magnesium and
magnesium alloys**

*Magnésium et alliages de magnésium — Magnésium et alliages de
magnésium corroyés*



Reference number
ISO 3116:2019(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Designation	1
4.1 Material	1
4.2 Temper designation	2
4.3 Designations of product form	3
4.4 Designation for ordering	3
5 Requirements	3
5.1 Chemical composition	3
5.2 Mechanical properties	3
5.3 Frequency of testing	3
6 Sampling	3
7 Test pieces	3
8 Test methods	4
8.1 Chemical composition	4
8.2 Tensile test	4
9 Retests	4
10 Rounding of results	4
Annex A (informative) List of national designations corresponding to the ISO designation	24
Annex B (informative) Physical properties of wrought magnesium alloys	26
Annex C (informative) Heat-treatment schedules for wrought magnesium alloys	28
Bibliography	30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

This fifth edition cancels and replaces the fourth edition ([ISO 3116:2007](http://www.iso.org/iso/standard/100000/100000)), which has been technically revised to include wrought magnesium alloys that have been developed in the past few years.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document classifies the commercially available magnesium alloys into a number of grades suitable for the application to which they might be put.

Some of the alloys referenced in this document can be the subject of a patent or of patent applications and their listing herein is not to be construed in any way as the granting of a licence under such patent rights.

This page deliberately left blank

Magnesium and magnesium alloys — Wrought magnesium and magnesium alloys

1 Scope

This document specifies the chemical composition and mechanical properties of magnesium and magnesium alloys for wrought products in the form of bars and solid sections, tubes and hollow sections, forgings, and plate and sheet.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 80000-1:2009, Quantities and units — Part 1: General](#)

[ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature](#)

[EN 515, Aluminium and aluminium alloys — Wrought products — Temper designations](#)

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Designation

4.1 Material

The material shall be designated by symbols as given in [Tables 1 to 47](#).

The designation for alloys shall consist of a prefix character “M”, which represents magnesium, and not more than three capital letters representing the alloying elements specified in the greatest amount, arranged in order of decreasing percentages, or in alphabetical order if of equal percentages, followed by the respective percentages rounded off to whole numbers and a serial letter in lower case.

The letters used to represent the alloying elements shall be those in [Table 1](#). The third letter is used when the third largest amount of element is above or equal to 1 wt.%. If the third and fourth largest amount of elements are above or equal to 1, the higher amount of elements is taken; if of equal percentage, the third letter is decided by the producer who developed the alloy.

Table 1 — Letters representing alloying elements

Letters	Element	Name of element	Letters	Element	Name of element
A	Al	Aluminium	N	Ni	Nickel

Details of heat treatments are given in [Annex C](#).

4.3 Designations of product form

The following symbols shall be used for product form:

- B: bars and solid sections;
- T: tubes and hollow sections;
- F: forgings;
- P: plate and sheet.

4.4 Designation for ordering

EXAMPLE

An order for magnesium bars, conforming to this document, of magnesium alloy MAZ31a, delivered in the as-fabricated condition (F) is as follows:

ISO 3116 - ISO-MgAl3Zn1 (A) (or MAZ31a) - F - B

Tonnage and dimensions shall be specified in addition.

5 Requirements

5.1 Chemical composition

The chemical composition of wrought magnesium alloys, taken as cast analysis at the time the material is cast, shall conform to the requirements for the appropriate material given in [Table 2](#).

5.2 Mechanical properties

The minimum values of the mechanical properties of wrought products in magnesium alloys in the defined temper conditions shall be as given in [Tables 3 to 48](#).

5.3 Frequency of testing

The frequency of testing shall be subject to an agreement between the manufacturer and the purchaser.

6 Sampling

Conditions for sampling, formation of batches and frequency of verification shall be subject to an agreement between the manufacturer and the purchaser.

7 Test pieces

Test pieces shall be taken in the longitudinal direction. For rolled flat products of thickness > 0,6 mm, test pieces may be taken in the long transverse direction.

8 Test methods

8.1 Chemical composition

The determination of the alloying elements given in [Table 2](#) shall be performed in accordance with the relevant International Standards, or other standards as agreed between the supplier and the customer.

8.2 Tensile test

Tensile tests shall be carried out in accordance with [ISO 6892-1](#).

9 Retests

Conditions for retests shall be subject to an agreement between the manufacturer and the purchaser.

10 Rounding of results

The number representing the result for any value specified in this document shall be expressed to the same number of decimal places as the corresponding number in this document. The rounding of numbers shall meet the requirements of [ISO 80000-1:2009](#), B.3, rule A or B. The choice shall be left to the discretion of the manufacturer, unless the use of one of the rules is agreed by the time of acceptance of the order.

Table 2 — Chemical composition of wrought magnesium and magnesium alloys

Alloy group	Symbol	Number	Material designation	Product form	Composition % (mass fraction)															
					Designation	Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Si	Fe	Cu	Ni	Others each
Mg	ISO-Mg99,99	ISO-WD11000	MG9999	B	min. max.	99,99	0,002	0,003	0,002	—	—	—	—	—	—	0,002	0,002	0,00 0,03	0,002	0,01
MgAlAg	ISO-MgAl8Ag	ISO-WD25110	MAQ80	F,P	min. max.	Rem. ^a	7,5	0,35	0,15	—	0,01	—	—	—	0,001	0,02	—	—	—	—
	ISO-MgAl5Ca1	ISO-WD25120	MAX51	B,T	min. max.	Rem.	4,5	—	0,15	—	—	—	—	—	0,7	—	—	—	—	—
MgAlCa	ISO-MgAl6Ca1	ISO-WD25130	MAX61	B,T,P	min. max.	Rem.	5,5	—	0,15	—	—	—	—	—	0,10	0,005	0,05	0,005	0,05	0,30
	ISO-MgAl6Ca2	ISO-WD25140	MAX62	B,T,P	min. max.	Rem.	5,5	—	0,15	—	—	—	—	—	1,6	—	—	—	—	—
	ISO-MgAl3Li2	ISO-WD26110	MAL32	P	min. max.	Rem.	2,5	0,50	0,20	—	1,0	—	—	—	2,5	—	0,10	0,005	0,05	0,30
MgAlLi	ISO-MgAl6Mn	ISO-WD21240	MAM60	B,T,P	min. max.	Rem.	5,5	—	0,15	—	—	—	—	—	3,0	—	—	0,01	0,005	0,00 0,05
	ISO-MgAl1Sn1	ISO-WD25150	MAT11	B,P	min. max.	Rem.	0,50	—	0,10	—	—	—	—	—	0,6	—	0,004	—	—	—
MgAlSn	ISO-MgAl6Sn1	ISO-WD25160	MAT61	B,P	min. max.	Rem.	6,0	—	0,2	—	—	—	—	—	1,2Sn	0,01	—	0,01	0,15	
	ISO-MgAl3Sr1	ISO-WD21450	MAJ31	B	min. max.	Rem.	2,5	0	0,6	—	—	—	—	—	0,7	—	—	—	—	—
MgAlSr							3,5	0,25	0,8	—	—	—	—	—	1,3Sn	0,025	0,005	—	0,05	0,15

Key

B = bars and solid sections

T = tubes and hollow sections

F = forgings

P = plate and sheet

RE = neodymium and other heavy rare earth metals

^a RemAlnder.

^b Zn+Ag.

Table 2 (continued)

Alloy group	Symbol	Number	Material designation	Product form	Composition % (mass fraction)											Other-s each	Other-s total				
					Designa-tion	Ele-ment	Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Si	Fe	Cu	Ni	Other-s each
	ISO-MgAl3Zn1(A)	ISO-WD21150	MAZ31a	B,T,F,P	min.	Rem.	2,4	0,50	0,15	—	—	—	—	—	—	—	—	—	—	—	—
	ISO-MgAl3Zn1(B)	ISO-WD21151	MAZ31b	B,T,F,P	min.	Rem.	2,4	0,5	0,05	—	—	—	—	—	—	—	—	—	—	—	0,30
	ISO-MgAl3Zn1(C)	ISO-WD21153	MAZ31c	B, P	min.	Rem.	2,5	0,50	0,20	—	—	—	—	—	—	—	—	—	—	—	0,30
MgAlZn	ISO-MgAl6Zn1	ISO-WD21160	MAZ61	B,T,F, P	min.	Rem.	5,5	0,50	0,15	—	—	—	—	—	—	—	—	—	—	—	0,15
	ISO-MgAl8Zn	ISO-WD21170	MAZ80	B,T,F	min.	Rem.	7,8	0,20	0,12	—	—	—	—	—	—	—	—	—	—	—	0,30
	ISO-MgAl9Zn1	ISO-WD21180	MAZ91	B,T	min.	Rem.	8,6	0,35	0,15	—	—	—	—	—	—	—	—	—	—	—	0,30

Key

B = bars and solid sections

T = tubes and hollow sections

F = forgings

P = plate and sheet

RE = neodymium and other heavy rare earth metals

^a RemAnder.^b Zn+Ag

Table 2 (continued)

Alloy group	Symbol	Number	Designation	Material designation												Composition % (mass fraction)					
				Product form	Element	Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Si	Fe	Cu	Ni	Others each	Others total
MgAlCa-Zn	ISO-MgAl3Ca-1Zn1	ISO-WD22110	MAXZ311	B,T	min. max.	2,4 —	0,5 3,6	0,15 1,0	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl6Ca-1Zn1	ISO-WD22120	MAXZ611	B,T,P	min. max.	5,5 6,5	0,5 1,0	0,15 0,40	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl6Ca-2Zn1	ISO-WD22130	MAXZ621	B,T,P	min. max.	5,5 6,5	0,5 1,0	0,15 0,40	—	—	—	—	—	1,6 2,5	—	—	—	—	—	—	
	ISO-MgAl8Ca-1Zn1	ISO-WD22140	MAXZ811	B,P	min. max.	7,5 8,5	0,5 1,5	0,15 0,40	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl9Ca-1Zn1	ISO-WD22150	MAXZ911	B,T	min. max.	8,6 9,5	0,35 1,0	0,15 0,50	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl9Ca-2Zn1	ISO-WD22160	MAXZ921	B,T	min. max.	8,6 9,5	0,35 1,0	0,15 0,50	—	—	—	—	—	1,6 2,5	—	—	—	—	—	—	
	ISO-MgGd6Y4Zn1	ISO-WD69120	MVWZ641	F,P	min. max.	— —	0,3 1,0	— —	5,5 6,5	— —	— —	— —	— —	0,3 0,7	3,0 4,5	0,002 0,020	0,2 1,0Ag	—	—	—	
	ISO-MgGd7Y5RE1	ISO-WD69130	MVWE751	B	min. max.	— —	— —	— —	6,5 7,5	— 1,5	— —	— —	— —	0,3 1,0	0,005 0,020	0,05 0,05	—	—	—	—	
	ISO-MgGd7Y6	ISO-WD69140	MVW76	B	min. max.	— —	— —	— 0,03	6,5 7,5	— —	— 0,2	— 0,5	— 6,5	— —	— —	— —	— 0,01	0,010 0,02	0,005 0,02	—	—
	ISO-MgGd8Y3	ISO-WD69150	MVW83	B,F,P	min. max.	— 0,02	— 0,10	— 0,05	8,0 9,0	— —	— —	— —	— —	— —	— —	— —	— —	— —	— —	—	
	ISO-MgGd8Y4Zn2	ISO-WD69160	MVWZ842	B,F,P	min. max.	— —	— 2,0	— 1,0	0,6 9,0	— —	— —	— —	— —	— —	— —	— —	— —	— —	— —	—	

Key

B = bars and solid sections

T = tubes and hollow sections

F = forgings

P = plate and sheet

RE = neodymium and other heavy rare earth metals

a RemAnder.

b Zn+Ag

Table 2 (continued)

Alloy group	Symbol	Number	Designation	Material designation												Composition % (mass fraction)					
				Product form	Element	Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Si	Fe	Cu	Ni	Others each	Others total
MgAlCa-Zn	ISO-MgAl3Ca-1Zn1	ISO-WD22110	MAXZ311	B,T	min. max.	2,4 —	0,5 3,6	0,15 1,0	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl6Ca-1Zn1	ISO-WD22120	MAXZ611	B,T,P	min. max.	5,5 6,5	0,5 1,0	0,15 0,40	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl6Ca-2Zn1	ISO-WD22130	MAXZ621	B,T,P	min. max.	5,5 6,5	0,5 1,0	0,15 0,40	—	—	—	—	—	1,6 2,5	—	—	—	—	—	—	
	ISO-MgAl8Ca-1Zn1	ISO-WD22140	MAXZ811	B,P	min. max.	7,5 8,5	0,5 1,5	0,15 0,40	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl9Ca-1Zn1	ISO-WD22150	MAXZ911	B,T	min. max.	8,6 9,5	0,35 1,0	0,15 0,50	—	—	—	—	—	0,7 1,5	—	—	—	—	—	—	
	ISO-MgAl9Ca-2Zn1	ISO-WD22160	MAXZ921	B,T	min. max.	8,6 9,5	0,35 1,0	0,15 0,50	—	—	—	—	—	1,6 2,5	—	—	—	—	—	—	
	ISO-MgGd6Y4Zn1	ISO-WD69120	MVWZ641	F,P	min. max.	— —	0,3 1,0	— —	5,5 6,5	— —	— —	— —	— —	0,3 0,7	3,0 4,5	0,002 0,020	0,2 1,0Ag	—	—	—	
	ISO-MgGd7Y5RE1	ISO-WD69130	MVWE751	B	min. max.	— —	— —	— —	6,5 7,5	— 1,5	— —	— —	— —	0,3 1,0	0,005 0,020	0,05 0,05	—	—	—	—	
	ISO-MgGd7Y6	ISO-WD69140	MVW76	B	min. max.	— —	— —	— 0,03	6,5 7,5	— —	— 0,2	— 0,5	— 6,5	— —	— —	— —	— 0,01	0,010 0,02	0,005 0,02	—	—
	ISO-MgGd8Y3	ISO-WD69150	MVW83	B,F,P	min. max.	— 0,02	— 0,10	— 0,05	8,0 9,0	— —	— —	— —	— —	— —	— —	— —	— —	— —	— —	—	
	ISO-MgGd8Y4Zn2	ISO-WD69160	MVWZ842	B,F,P	min. max.	— —	— 2,0	— 1,0	0,6 9,0	— —	— —	— —	— —	— —	— —	— —	— —	— —	— —	—	

Key

B = bars and solid sections

T = tubes and hollow sections

F = forgings

P = plate and sheet

RE = neodymium and other heavy rare earth metals

a RemAnder.

b Zn+Ag

Table 2 (continued)

Alloy group	Symbol	Material designation		Product form	Element	Composition % (mass fraction)										Others each	Others total		
		Number	Designation			Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Si	Fe	Cu	Ni
MgYZn	ISO-MgY7Zn3	ISO-WD96110	MWZ73	B,T,P	min. max.	—	2,0 —	—	—	—	—	—	6,2 —	—	—	—	—	—	—
	ISO-MgY7Zn5	ISO-WD96120	MWZ75	B,T,P	min. max.	—	4,5 —	—	—	—	—	—	6,2 —	—	—	—	—	—	—
MgZnAl	ISO-MgZn8Al-1Cu1	ISO-WD32110	MZAC811	B	min. max.	0,5 —	6,0 1,5	0,30 8,0	—	—	—	—	—	—	—	0,5 0,01	1,0 0,01	—	—
	ISO-MgZn2Cu	ISO-WD32120	MZC20	P	min. max.	—	1,5 2,5	—	—	0,2 0,6Ce	—	—	—	—	—	0,30 0,02	0,6 0,6	—	0,01 0,05
MgZn-CuMn	ISO-MgZn-7Cu1Mn1	ISO-WD32150	MZCM711	B	min. max.	—	6,0 0,2	0,5 7,0	—	—	—	—	—	—	—	1,0 0,05	—	—	—
	ISO-MgZn2Mn1	ISO-WD32350	MZM21	B,T,F,P	min. max.	—	0,1 0,1	1,75 2,3	0,6 1,3	—	—	—	—	—	—	0,01 0,01	1,5 0,01	0,05 0,30	—
MgZnMn	ISO-MgZn2Mn-1RE	ISO-WD32351	MZME210	B,T,P	min. max.	—	1,8 0,02	0,50 2,4	0,10 0,9	—	—	—	—	—	—	0,1 0,01	0,06 0,008	0,1 0,006	0,05 0,01 0,20
	ISO-MgZn5Mn1	ISO-WD32360	MZM51	B	min. max.	—	4,5 6,0	0,5 2,0	—	—	—	—	—	—	—	0,01 0,01	0,005 0,004	—	—
MgZnZr	ISO-MgZn3Zr	ISO-WD32250	MZK30	B,T,F	min. max.	—	2,5 —	—	—	—	—	—	0,45 0,8	—	—	—	—	—	—
	ISO-MgZn6Zr	ISO-WD32260	MZK60	B,T,F	min. max.	—	4,8 —	—	—	—	—	—	0,45 0,8	—	—	—	—	—	0,05 0,30

Key

B = bars and solid sections

T = tubes and hollow sections

F = forgings

P = plate and sheet

RE = neodymium and other heavy rare earth metals

^a RemAnder.

^b Zn+Ag.

Table 3 — ISO-Mg 99.99 (MG9999)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 10	185	95	22
	10 < t ≤ 40	180	90	21

Table 4 — Alloy ISO-MgAl8Ag (MAQ80)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Forgings				
F	All	320	210	4
Plate and sheet				
F	10 < t ≤ 30	370	250	6

Values for separately forged test pieces shall be agreed between the manufacturer and the customer.

Table 5 — Alloy ISO-MgAl5Ca1 (MAX51)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	240	100	8
Tubes and hollow sections				
F	1 ≤ t ≤ 10	240	100	8

Table 6 — Alloy ISO-MgAl6Ca1 (MAX61)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	250	120	6
Tubes and hollow sections				
F	1 ≤ t ≤ 10	250	120	6
Plate and sheet				
H112	0,5 ≤ t ≤ 3	260	200	4

Table 3 — ISO-Mg 99.99 (MG9999)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 10	185	95	22
	10 < t ≤ 40	180	90	21

Table 4 — Alloy ISO-MgAl8Ag (MAQ80)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Forgings				
F	All	320	210	4
Plate and sheet				
F	10 < t ≤ 30	370	250	6

Values for separately forged test pieces shall be agreed between the manufacturer and the customer.

Table 5 — Alloy ISO-MgAl5Ca1 (MAX51)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	240	100	8
Tubes and hollow sections				
F	1 ≤ t ≤ 10	240	100	8

Table 6 — Alloy ISO-MgAl6Ca1 (MAX61)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	250	120	6
Tubes and hollow sections				
F	1 ≤ t ≤ 10	250	120	6
Plate and sheet				
H112	0,5 ≤ t ≤ 3	260	200	4

Table 11 — Alloy ISO-MgAl6Sn1 (MAT61)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 16$	300	200	13
Plate and sheet				
F	$1 < t \leq 3$	280	140	22
F	$t \leq 1$	300	230	6
O	$t \leq 1$	310	220	23

Table 12 — Alloy ISO-MgAl3Sr1 (MAJ31)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
H8	$t \leq 16$	340	220	13

Table 13 — Alloy ISO-MgAl3Zn1 (MAZ31)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 10$	220	140	10
	$10 < t \leq 65$	240	150	10
Tubes and hollow sections				
F	$1 \leq t \leq 10$	220	140	10
Forgings				
F	All	235	130	8
Plate and sheet				
O	$0,5 \leq t \leq 6$	220	105	11
	$6 < t \leq 25$	210	105	9
H × 2	$0,5 \leq t \leq 6$	250	160	5
	$6 < t \leq 25$	220	120	8
H × 4	$0,5 \leq t \leq 6$	260	200	4
	$6 < t \leq 25$	250	160	6
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 14 — Alloy ISO-MgAl3Zn1(C) (MAZ31c)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 16$	290	240	17
Plate and sheet				
0	$t \leq 3$	280	230	9

Table 15 — Alloy ISO-MgAl6Zn1 (MAZ61)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 10$	260	160	6
	$10 < t \leq 40$	270	180	10
	$40 < t \leq 65$	260	160	10
Tubes and hollow sections				
F	$1 < t \leq 10$	260	150	10
Forgings				
F	All	270	152	6
Plate and sheet				
0	$0,25 \leq t \leq 6$	240	140	11
	$6 < t \leq 25$	170	120	3
H112	$0,5 \leq t \leq 6$	260	160	4
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 16 — Alloy ISO-MgAl8Zn (MAZ80)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 40$	295	195	10
	$40 < t \leq 60$	295	195	8
	$60 < t \leq 130$	290	185	8
T5	$t \leq 6$	325	205	4
	$6 < t \leq 60$	330	230	4
	$60 < t \leq 130$	310	205	2
Tubes and hollow sections				
F	$t \leq 10$	295	195	7
Forgings				
F	All	290	200	6
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 17 — Alloy ISO- MgAl9Zn1 (MAZ91)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 65$	280	180	8
Tubes and hollow sections				
F	$1 \leq t \leq 10$	280	180	8

Table 18 — Alloy ISO- MgAl3Ca1Zn1 (MAXZ311)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 65$	220	140	10
Tubes and hollow sections				
F	$1 \leq t \leq 10$	220	140	10

Table 19 — Alloy ISO- MgAl6Ca1Zn1 (MAXZ611)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 65$	250	120	8

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Tubes and hollow sections				
F	1 ≤ t ≤ 10	250	120	8
Plate and sheet				
O	0,5 ≤ t ≤ 6	240	160	8
	6 < t ≤ 25	200	140	4
H112	0,5 ≤ t ≤ 3	260	160	4

Table 20 — Alloy ISO- MgAl6Ca2Zn1 (MAXZ621)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	250	120	6
Tubes and hollow sections				
F	1 ≤ t ≤ 10	250	120	6
Plate and sheet				
O	0,5 ≤ t ≤ 6	240	140	6
	6 < t ≤ 25	140	120	2
H112	0,5 ≤ t ≤ 3	260	160	4

Table 21 — Alloy ISO- MgAl8Ca1Zn1 (MAXZ811)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	260	150	6
Plate and sheet				
O	0,5 ≤ t ≤ 6	250	200	6
H112	0,5 ≤ t ≤ 6	300	220	4

Table 22 — Alloy ISO- MgAl9Ca1Zn1 (MAXZ911)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	1 ≤ t ≤ 65	280	180	6
Tubes and hollow sections				
F	1 ≤ t ≤ 10	280	180	6

Table 23 — Alloy ISO- MgAl9Ca2Zn1 (MAXZ921)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 65$	280	180	6
Tubes and hollow sections				
F	$1 \leq t \leq 10$	280	180	6

Table 24 — Alloy ISO-MgGd6Y4Zn1 (MVWZ641)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Forgings				
F	All	350	260	4
Plate and sheet				
F	$20 < t \leq 30$	380	280	5

Values for separately forged test pieces shall be agreed between the manufacturer and the customer.

Table 25 — Alloy ISO-MgGd7Y5RE1 (MVWE751)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$t \leq 20$	450	355	6

Table 26 — Alloy ISO- MgGd7Y6 (MVW76)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
T5A	$t \leq 100$	350	230	5
T5B	$t \leq 100$	400	260	1

Table 27 — Alloy ISO-MgGd8Y3 (MVW83)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation <i>A</i> % min.
Bars and solid sections $t = D$ for solid round bars				
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
T5	$t \leq 100$	420	320	8
Forgings				
T5	$t \leq 100$	380	280	5
Plate and sheet				
T5	$t \leq 100$	400	320	6
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 28 — Alloy ISO-MgGd8Y4Zn2 (MVWZ842)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$10 \leq t \leq 65$	350	250	11
T6	$10 \leq t \leq 65$	500	350	8
Forgings				
F	All	350	280	12
Plate and sheet				
O	$6 \leq t \leq 25$	350	260	9
T6	$6 \leq t \leq 25$	450	350	4
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 29 — Alloy ISO-MgGd4Zr1 (MVK41)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 10$	205	140	44
	$10 < t \leq 16$	200	130	50

Table 30 — Alloy ISO- MgLi9Zn1 (MLZ91)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 10$	110	90	20
Tubes and hollow sections				
F	$1 \leq t \leq 10$	110	90	20
Plate and sheet				

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
0	$0,25 \leq t \leq 3$	130	90	20

Table 31 — Alloy ISO-MgLi4Al3Zn3 (MLAZ433)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Plate and sheet				
F	$t \geq 20$	230	140	10

Table 32 — Alloy ISO-MgLi10Al3Zn3 (MLAZ1033)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Plate and sheet				
F	$t \geq 20$	140	120	18

Table 33 — Alloy ISO-MgMn2 (MM2)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 10$	230	120	3
	$10 < t \leq 50$	230	120	3
	$50 < t \leq 100$	200	120	3
Tubes and hollow sections				
F	$t \leq 2$	225	165	2
	$t > 2$	200	145	1,5

Table 34 — Alloy ISO-MgY4RE3Zr1(B) (MWEK431b)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$10 \leq t \leq 50$	230	140	5
	$50 < t \leq 100$	220	130	5

Values for separately forged test pieces shall be agreed between the manufacturer and the customer.

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
T6	$10 \leq t \leq 50$	220	130	6
	$50 < t \leq 100$	220	130	6
Forgings				
T5	All	280	150	6
T6	All	255	160	6
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 35 — Alloy ISO- MgY4RE3Zr1(C) (MWEK431c)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	All	305	195	6
Plate and sheet				
T5	All	303	227	12

Table 36 — Alloy ISO-MgY5RE4Zr1 (MWEK541)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$10 \leq t \leq 50$	250	170	6
	$50 < t \leq 100$	250	160	6
T6	$10 \leq t \leq 50$	250	160	6
	$50 < t \leq 100$	250	160	6
Forgings				
T5	All	290	155	6
T6	All	260	165	6
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 37 — Alloy ISO- MgY7RE1Zr1 (MWEK711)

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$t \leq 70$	365	275	8

Table 38 — Alloy ISO- MgY9RE1Zr1 (MWEK911)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$t \leq 50$	410	340	6

Table 39 — Alloy ISO- MgY7Zn3 (MWZ73)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 80$	320	240	5
Tubes and hollow sections				
F	$2 \leq t \leq 10$	320	240	5
Plate and sheet				
H112	$1 \leq t \leq 6$	320	240	5

Table 40 — Alloy ISO- MgY7Zn5 (MWZ75)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$1 \leq t \leq 80$	330	250	5
Tubes and hollow sections				
F	$1 \leq t \leq 10$	330	250	5
Plate and sheet				
H112	$1 \leq t \leq 6$	330	250	5

Table 41 — Alloy ISO-MgZn8Al1Cu1 (MZAC811)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
T6	$10 < t \leq 65$	335	290	12

Table 42 — Alloy ISO-MgZn2Cu (MZC20)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Plate and sheet				
F	0,5 ≤ t ≤ 3	320	250	22

Table 43 — Alloy ISO-MgZn7Cu1Mn1 (MZCM711)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	10 ≤ t ≤ 130	250	160	7
T6	10 ≤ t ≤ 130	325	300	3

Table 44 — Alloy ISO-MgZn2Mn1 (MZM21)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 10$	230	150	8
	$10 < t \leq 75$	245	160	10
Tubes and hollow sections				
F	$t \leq 10$	230	150	8
	$10 < t \leq 75$	245	160	10
Forgings				
F	All	200	125	9
Plate and sheet				
O	$6 \leq t \leq 25$	220	120	8
H × 4	$6 \leq t \leq 25$	250	165	5
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 45 — Alloy ISO-MgZn2Mn1RE (MZME210)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F (340 °C)	$t \leq 16$	310	280	19
F (370 °C)	$t \leq 16$	300	260	21
F (400 °C)	$t \leq 16$	290	250	21
F (430 °C)	$t \leq 16$	290	230	19

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Tubes and hollow sections				
F	$t \leq 16$	250	170	18
Plate and sheet				
F	$t \leq 16$	260	180	22

Table 46 — Alloy ISO- MgZn5Mn1 (MZM51)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
T5	$t \leq 100$	315	235	10

Table 47 — Alloy ISO-MgZn3Zr (MZK30)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 10$	280	200	8
	$10 < t \leq 100$	300	225	8
T5	All	275	255	4
Tubes and hollow sections				
T5	All	275	255	4
Forgings				
F	All	290	205	7
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Table 48 — Alloy ISO-MgZn6Zr (MZK60)

Temper	Thickness mm	Tensile strength R_m N/mm ² min.	0,2 % Proof stress $R_{p0,2}$ N/mm ² min.	Elongation A % min.
Bars and solid sections $t = D$ for solid round bars				
F	$t \leq 50$	300	210	5
T5	$t \leq 50$	310	230	5
Tubes and hollow sections				
F	All	275	195	5
T5	All	315	260	4
Forgings				
Values for separately forged test pieces shall be agreed between the manufacturer and the customer.				

Temper	Thickness mm	Tensile strength	0,2 % Proof stress	Elongation
		R_m N/mm ² min.	$R_{p0,2}$ N/mm ² min.	A % min.
T5	$t \leq 75$	290	180	7
T6	$t \leq 75$	295	220	4

Values for separately forged test pieces shall be agreed between the manufacturer and the customer.

Annex A (informative)

List of national designations corresponding to the ISO designation

Table A.1 — List of national designations corresponding to the ISO designation

Material designation in accordance with ISO 2092	Material designation in accordance with this document	USA ASTM	China GB	Japan JIS	Germany DIN Number	United Kingdom BS Series	France NF
ISO-Mg99.99	MG9999	—	—	—	—	—	—
ISO-MgAl8Ag	MAQ80	—	AQ80M	—	—	—	—
ISO-MgAl5Ca1	MAX51	—	—	AXM510	—	—	—
ISO-MgAl6Ca1	MAX61	—	—	AXM610	—	—	—
ISO-MgAl6Ca2	MAX62	—	—	AXM620	—	—	—
ISO-MgAl3Li2	MAL32	—	AL32M	—	—	—	—
ISO-MgAl6Mn	MAM60	AM60A	—	AM60	—	—	—
ISO-MgAl1Sn1	MAT11	—	AT11M	—	—	—	—
ISO-MgAl6Sn1	MAT61	—	AT61M	—	—	—	—
ISO-MgAl3Sr1	MAJ31	—	AJ31M	—	—	—	—
ISO-MgAl3Zn1(B)	MAZ31b	AZ31B	AZ31S	—	3.5312	MAG 110	G-A3Z1
ISO-MgAl3Zn1(C)	MAZ31c	AZ31D	AZ31N	—	—	—	—
ISO-MgAl6Zn1	MAZ61	AZ61A	AZ61M	AZ61	3.5612	MAG 121	G-A6Z1
ISO-MgAl8Zn	MAZ80	AZ80A	AZ80M	—	3.5812	—	—
ISO-MgAl9Zn1	MAZ91	AZ91A	AZ91M	AZ91	—	—	—
ISO-MgAl3Ca1Zn1	MAXZ311	—	—	AZX311	—	—	—
ISO-MgAl6Ca1Zn1	MAXZ611	—	—	AZX611	—	—	—
ISO-MgAl6Ca2Zn1	MAXZ621	—	—	AZX612	—	—	—
ISO-MgAl8Ca1Zn1	MAXZ811	—	—	AZX811	—	—	—
ISO-MgAl9Ca1Zn1	MAXZ911	—	—	AZX911	—	—	—
ISO-MgAl9Ca2Zn1	MAXZ921	—	—	AZX912	—	—	—
ISO-MgGd6Y4Zn1	MVWZ641	—	VW64M	—	—	—	—
ISO-MgGd7Y5RE1	MVWE751	—	VW75M	—	—	—	—
ISO-MgGd7Y6	MVW76	—	—	—	—	—	—
ISO-MgGd8Y3	MVW83	—	VW83M	—	—	—	—
ISO-MgGd8Y4Zn2	MVWZ842	—	VW84M	—	—	—	—
ISO-MgGd4Zr1	MVK41	—	VK41M	—	—	—	—
ISO-MgLi9Zn1	MLZ91	—	—	LZ91	—	—	—
ISO-MgLi4Al3Zn3	MLAZ433	—	LA43M	—	—	—	—
ISO-MgLi10Al3Zn3	MLAZ1033	—	LA103M	—	—	—	—
ISO-MgMn2	MM2	—	M2M	—	—	—	—
ISO-MgY4RE3Zr1b	MWEK431b	WE43B	—	—	—	—	—
ISO-MgY4RE3Zr1c	MWEK431c	WE43C	—	—	—	—	—
ISO-MgY5RE4Zr1	MWEK541	WE54A	WE54A	—	—	—	—

Material designation in accordance with ISO 2092	Material designation in accordance with this document	USA ASTM	China GB	Japan JIS	Germany DIN Number	United Kingdom BS Series	France NF
ISO-MgY7RE1Zr1	MWEK711	—	WE71M	—	—	—	—
ISO-MgY9RE1Zr1	MWEK911	—	WE91M	—	—	—	—
ISO-MgY7Zn3	MWZ73	—	—	WZ73	—	—	—
ISO-MgY7Zn5	MWZ75	—	—	WZ75	—	—	—
ISO-MgZn8Al1Cu1	MZAC811	—	—	—	—	—	—
ISO-MgZn2Cu	MZC20	—	ZC20M	—	—	—	—
ISO-MgZn7Cu1Mn1	MZCM711	—	—	—	—	—	—
ISO-MgZn2Mn1	MZM21	—	ZM21M	—	—	MAG 131	—
ISO-MgZn2Mn1RE	MZME210	—	ZE20M	—	—	—	—
ISO-MgZn5Mn1	MZM51	—	ZM51M	—	—	—	—
ISO-MgZn3Zr	MZK30	—	—	—	—	MAG 151	—
ISO-MgZn6Zr	MZK60	ZK60A	ZK61S	—	—	—	—

Annex B

(informative)

Physical properties of wrought magnesium alloys

Table B.1 — Physical properties of wrought magnesium alloys

Alloy	Specific gravity (20 °C)	Coefficient of thermal expansion 10 ⁻⁶ K ⁻¹ (20 °C to 200 °C)	Thermal conductivity Wm ⁻¹ K ⁻¹ (20 °C)	Electrical resistivity nΩm (20 °C)	Specific heat Jkg ⁻¹ K ⁻¹ (20 °C to 100 °C)
ISO-Mg99,99	1,74	—	—	—	—
ISO-MgAl8Ag	1,80	27,9	58	—	1 100
ISO-MgAl5Ca1	1,76	—	—	—	1 000
ISO-MgAl6Ca1	1,77	—	—	—	1 000
ISO-MgAl6Ca2	1,77	—	—	—	1 000
ISO-MgAl3Li2	1,73	—	—	—	—
ISO-MgAl6Mn	1,78	26,0	61	—	1 000
ISO-MgAl1Sn1	1,76	—	—	—	—
ISO-MgAl6Sn1	1,84	—	—	—	—
ISO-MgAl3Sr1	1,77	—	—	—	—
ISO-MgAl3Zn1	1,77	26,0	96	100	1 040
ISO-MgAl6Zn1	1,80	27,3	79	143	1 000
ISO-MgAl8Zn	1,80	26,0	78	145	1 050
ISO-MgAl9Zn1	1,83	27,0	72	145	1 000
ISO-MgAl3Ca1Zn1	1,78	—	—	—	—
ISO-MgAl6Ca1Zn1	1,81	26,7	70	—	1 030
ISO-MgAl6Ca2Zn1	1,81	—	77	—	950
ISO-MgAl8Ca1Zn1	1,81	30,0	51	127	980
ISO-MgAl9Ca1Zn1	1,83	—	—	—	—
ISO-MgAl9Ca2Zn1	1,83	—	—	—	—
ISO-MgGd6Y4	1,93	26,7	36	—	900
ISO-MgGd7Y5RE1	1,93	—	≤ 40	—	—
ISO-MgGd7Y6	1,95	27,4	76	—	—
ISO-MgGd8Y3	1,88	27,5	31	182	868
ISO-MgGd8Y4Zn2	1,9	—	—	—	—
ISO-MgGd4Zr1	1,95	—	—	—	—
ISO-MgLi9Zn1	1,47	31,0	50	100	1 000
ISO-MgLi4Al3Zn3	1,65	—	—	—	—
ISO-MgLi10Al3Zn3	1,52	—	—	—	—
ISO-MgMn2	—	—	—	—	—
ISO-MgY4RE3Zr1	1,84	26,7	51	148	966
ISO-MgY5RE4Zr1	1,85	24,6	52	173	960
ISO-MgY7RE1Zr1	1,82	—	≤ 55	—	—

Alloy	Specific gravity (20 °C)	Coefficient of thermal expansion 10^{-6}K^{-1} (20 °C to 200 °C)	Thermal conductivity $\text{Wm}^{-1}\text{K}^{-1}$ (20 °C)	Electrical resistivity $\text{n}\Omega\text{m}$ (20 °C)	Specific heat $\text{Jkg}^{-1}\text{K}^{-1}$ (20 °C to 100 °C)
ISO-MgY9RE1Zr1	1,85	—	≤ 50	—	—
ISO-MgY7Zn3	1,89	27,3	56	—	—
ISO-MgY7Zn5	1,93	27,3	56	—	—
ISO-MgZn8Al1Cu1	1,89	—	—	—	—
ISO-MgZn2Cu	1,78	—	—	—	—
ISO-MgZn7Cu1Mn1	1,87	26,0	123	54	960
ISO-MgZn2Mn1	1,78	26,0	125	70	1 040
ISO-MgZn2Mn1RE	1,80	67,82	—	—	1 029
ISO-MgZn5Mn1	1,83	—	120	—	—
ISO-MgZn3Zr	1,80	27,1	125	70	960
ISO-MgZn6Zr	—	—	—	—	—

Annex C

(informative)

Heat-treatment schedules for wrought magnesium alloys

Table C.1 — Heat-treatment schedules for wrought magnesium alloys

Alloy	Condition	Solution treatment	Quench	Age
ISO-Mg99.99	F	—	—	—
ISO-MgAl8Ag	F	—	—	—
ISO-MgAl5Ca1	F	—	—	—
ISO-MgAl6Ca1	F	—	—	—
ISO-MgAl6Ca1	H112	—	—	—
ISO-MgAl6Ca2	F	—	—	—
ISO-MgAl6Ca2	H112	—	—	—
ISO-MgAl3Li2	F	—	—	—
ISO-MgAl6Mn	O	—	—	—
ISO-MgAl6Mn	H112	—	—	—
ISO-MgAl1Sn1	F	—	—	—
ISO-MgAl1Sn1	T5	—	—	30 min at 250 °C
ISO-MgAl6Sn1	F	—	—	—
ISO-MgAl6Sn1	T5	—	—	30 min at 250 °C
ISO-MgAl3Zn1	F	—	—	—
ISO-MgAl6Zn1	F	—	—	—
ISO-MgAl8Zn	F	—	—	—
ISO-MgAl8Zn	T5	—	—	16 h at 180 °C
ISO-MgAl9Zn1	F	—	—	—
ISO-MgAl3Ca1Zn1	F	—	—	—
ISO-MgAl6Ca1Zn1	F	—	—	—
ISO-MgAl6Ca1Zn1	O	—	—	—
ISO-MgAl6Ca1Zn1	H112	—	—	—
ISO-MgAl6Ca2Zn1	F	—	—	—
ISO-MgAl6Ca2Zn1	O	—	—	—
ISO-MgAl6Ca2Zn1	H112	—	—	—
ISO-MgAl8Ca1Zn1	O	—	—	—
ISO-MgAl8Ca1Zn1	H112	—	—	—
ISO-MgAl9Ca1Zn1	F	—	—	—
ISO-MgAl9Ca2Zn1	F	—	—	—
ISO-MgGd6Y4	F	—	—	—
ISO-MgGd7Y5RE1	T5	—	—	6 to 12 h at 200 °C to 230 °C
ISO-MgGd7Y6	T5A	—	—	16 h at 250 °C
ISO-MgGd7Y6	T5B	—	—	16 h at 225 °C
ISO-MgGd8Y3	F	—	—	—

Alloy	Condition	Solution treatment	Quench	Age
ISO-MgGd8Y3	T5	—	—	16 h at 225 °C
ISO-MgGd8Y4Zn2	F	—	—	—
ISO-MgGd8Y4Zn2	T6	4 h at 540 °C	Furnace cool to 300 °C	100 h at 200 °C
ISO-MgGd4Zr1	F	—	—	—
ISO-MgLi9Zn1	F	—	—	—
ISO-MgLi9Zn1	O	—	—	—
ISO-MgLi4Al3Zn3	F	—	—	—
ISO-MgLi10Al3Zn3	F	—	—	—
ISO-MgMn2	F	—	—	—
ISO-MgY4RE3Zr1(B)	T5	—	—	16 h at 250 °C
ISO-MgY4RE3Zr1(B)	T6	8 h at 525 °C	Alr cool or hot water	16 h at 250 °C
ISO-MgY4RE3Zr1(C)	T5	—	—	24 h at 225 °C
ISO-MgY5RE4Zr1	T5	—	—	16 h at 250 °C
ISO-MgY5RE4Zr1	T6	8 h at 525 °C	Alr cool or hot water	16 h at 250 °C
ISO-MgY7RE1Zr1	T5	—	—	26 to 32 h at 1 95 °C to 210 °C
ISO-MgY9RE1Zr1	T5	—	—	20 to 24 h at 210 °C to 230 °C
ISO-MgY7Zn3	F	—	—	—
ISO-MgY7Zn3	H112	—	—	—
ISO-MgY7Zn5	F	—	—	—
ISO-MgY7Zn5	H112	—	—	—
ISO-MgZn8Al1Cu1	T6	1 h at 365 °C	Hot water (80 °C)	32 h at 75 °C 8 h at 180 °C
ISO-MgZn2Cu	F	—	—	—
ISO-MgZn7Cu1Mn1	F	—	—	—
ISO-MgZn7Cu1Mn1	T6	4 to 8 h at 430 °C	Hot water	16 h at 180 °C
ISO-MgZn2Mn1	F	—	—	—
ISO-MgZn2Mn1RE	F	—	—	—
ISO-MgZn5Mn1	F	—	—	—
ISO-MgZn5Mn1	T5	—	—	30 to 40 h at 170 °C to 180 °C
ISO-MgZn3Zr	F	—	—	—
ISO-MgZn3Zr	T5	—	—	24 h at 150 °C
ISO-MnZn6Zr	F	—	—	—
ISO-MnZn6Zr	T5	—	—	24 h at 150 °C
ISO-MnZn6Zr	T6	2 h at 500 °C	As required	24 h at 150 °C

Bibliography

- [1] ISO 2092,¹⁾*Light metals and their alloys — Code of designation based on chemical symbols*

1) Withdrawn document.

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK