



BSI Standards Publication

Binders for paints and varnishes — Determination of hydroxyl value

Part 3: Rapid test

National foreword

This British Standard is the UK implementation of [ISO 4629-3:2018](#).

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 52120 1

ICS 87.060.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2018.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

BS ISO
4629-3:2018

ISO
4629-3

First edition
2018-10-26

Binders for paints and varnishes — Determination of hydroxyl value —

Part 3: Rapid test

*Liants pour peintures et vernis — Détermination de l'indice
d'hydroxyle —*

Partie 3: Méthode rapide



Reference number
ISO 4629-3:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP
401
CH-1214 Vernier, Geneva,
Switzerland
Tel. +41 22 749 01 11 Fax
+41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus	2
7 Sampling	2
8 Procedure	2
9 Expression of results	3
10 Precision	3
11 Test report	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.


This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

A list of all parts in the ISO 4629 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction


The most frequently described method for determining the hydroxyl number is conversion with acetic anhydride in pyridine with subsequent titration of the released acetic acid.



However, this method suffers from the following disadvantages:

- the sample is boiled under reflux for 1 h;
- the method cannot be automated;
- small hydroxyl numbers cannot be determined exactly;
- unpleasant and toxic pyridine is used.

For these reasons, a far simpler method was selected for automation. The (primary and secondary) hydroxyl groups are converted to acidic carbamate groups using toluene-4-sulfonyl-isocyanate.



The carbamate can then be titrated with the strong base tetrabutylammonium hydroxide (TBAOH) under non-aqueous conditions, i.e. in an organic solvent.

Binders for paints and varnishes — Determination of hydroxyl value —

Part 3: Rapid test

1 Scope

This document specifies a titrimetric method for determining the hydroxyl groups in resins and binders for paints and varnishes.

This method is primarily suitable for neutral media. Acidic products provide higher values; neutral products provide, through neutralization of the acidic carbamates, lower values. For these products, preliminary tests are performed to ensure the applicability of the method.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 4618](#), *Paints and varnishes — Terms and definitions*

[ISO 3696](#), *Water for analytical laboratory use — Specification and test methods*

[ISO 15528](#), *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in [ISO 4618](#) and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

hydroxyl value

number of milligrams of potassium hydroxide (KOH) corresponding to hydroxyl groups that have been acetylated under specified test conditions in 1 g of the product tested

[SOURCE: ISO 4629-1:2016, 3.1]

4 Principle

The primary and secondary hydroxyl groups of the sample are converted to acidic carbamate groups using toluene-4-sulfonyl-isocyanate. The carbamate can then be titrated with the strong base tetrabutylammonium hydroxide (TBAOH) under non-aqueous conditions, i.e. in an organic solvent.

5 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as specified in [ISO 3696](#).

5.1 Solution of tetrabutylammonium hydroxide (TBAOH) in isopropanol/methanol, $c(\text{TBAOH}) = 1,0 \text{ mol/l}$.

5.2 Reaction solution.

Place approximately 250 ml acetonitrile in a 500 ml volumetric flask and titrate with 20 ml toluene-4-sulfonyl-isocyanate. Make up the solution to the mark with acetonitrile and mix thoroughly. The reaction solution has a shelf life of approximately 1 month.

5.3 Acetonitrile, HPLC-Grade.

5.4 Toluene, analytical grade.

6 Apparatus

Ordinary laboratory equipment and glassware, together with the following.

6.1 Conical flask, capacity about 250 ml.

6.2 Watch glass.

6.3 Burette.

6.4 Potentiometric titration apparatus.

7 Sampling

Take a representative sample of the product to be tested, as specified in [ISO 15528](#).

8 Procedure

Depending on the expected hydroxyl number, weigh out 1 g to 15 g¹⁾ of the product under test in the conical flask ([6.1](#)), dissolve with 3 ml toluene and 7 ml acetonitrile and heat to 30 °C to 35 °C.

Add 10 ml reaction solution ([5.2](#)) and cover the flask with the watch glass ([6.2](#)). Allow the reaction to proceed for 5 min under gentle stirring. Then add 1,5 ml distilled water (to hydrolyse the excess reaction solution) and stir for an additional 3 min.

Add 30 ml acetonitrile ([5.3](#)) and titrate the mixture with the tetrabutylammonium hydroxide solution ([5.1](#)) until after the second point of change.

The electrode should be immersed in the solution immediately before the measurement. The electrode and burette shall be rinsed with acetone before each use.

After each titration rinse the electrode and burette tip with acetone followed by distilled water. Then place the electrode in distilled water for 1 min.

1) The optimum sample mass, in grams, can be calculated as follows: $40/\text{expected hydroxyl number}$ (numerical value equation).

9 Expression of results

Calculate the hydroxyl value, HV, in milligrams of KOH per gram, of the product using [Formula \(1\)](#):

$$HV = \frac{(V_2 - V_1) \cdot c \cdot 56,1}{m} \quad (1)$$

where

- V_1 is the volume, in millilitres, of tetrabutylammonium hydroxide solution ([5.1](#)) at the first point of change;
 V_2 is the volume, in millilitres, of tetrabutylammonium hydroxide solution ([5.1](#)) at the second point of change;
 c is the actual concentration, in moles per litre, of the tetrabutylammonium hydroxide solution ([5.1](#));
56,1 is the factor for the conversion of millilitres of potassium hydroxide, $c(\text{KOH}) = 1 \text{ mol/l}$, to milligrams of potassium hydroxide;
 m is the mass, in grams, of the test portion.

10 Precision

No precision data are currently available.

11 Test report

The test report shall contain at least the following information:

- all details necessary to identify the product tested;
- a reference to this document, i.e. [ISO 4629-3:2018](#);
- the result of the test as indicated in [Clause 9](#);
- any deviation (by agreement or otherwise) from the test method specified;
- any unusual features (anomalies) observed during the test;
- the date of the test.

Bibliography

- [1] [ISO 4629-1:2016](#), *Binders for paints and varnishes — Determination of hydroxyl value — Part 1: Titrimetric method without using a catalyst*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
 - A British Standard purchased in hard copy format is for personal or internal company use only.
 - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions. With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member. PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision. We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services
Tel: +44 345 086 9001
Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions
Tel: +44 345 086 9001
Email: subscriptions@bsigroup.com

Knowledge Centre
Tel: +44 20 8996 7004
Email: knowledgecentre@bsigroup.com

Copyright & Licensing
Tel: +44 20 8996 7070
Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

This page deliberately left blank