



BSI Standards Publication

**Rubber, vulcanized — Determination of static
adhesion to textile cord — H-pull test**

National foreword

This British Standard is the UK implementation of [ISO 4647:2021](#). It supersedes [BS ISO 4647:2010](#), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/22, Testing and analysis of rubber.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2021
Published by BSI Standards Limited 2021

ISBN 978 0 539 16792 4

ICS 83.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2021.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
4647

Third edition
2021-08-02

**Rubber, vulcanized — Determination
of static adhesion to textile cord
— H-pull test**

*Caoutchouc vulcanisé — Détermination de l'adhérence statique au
câblé textile — Essai d'arrachement en H*



Reference number
ISO 4647:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Materials	2
6 Apparatus	2
6.1 Mould.....	2
7 Calibration	5
8 Test piece	5
8.1 Dimensions.....	5
8.2 Preparation.....	5
8.3 Number of test pieces.....	8
9 Time interval between vulcanization and testing	8
10 Conditioning of test pieces	8
11 Test temperature	8
12 Procedure	8
12.1 Testing at standard laboratory temperature.....	8
12.2 Testing at elevated temperature.....	9
13 Expression of results	9
14 Test report	9
Annex A (informative) Preparation of silicone-rubber-faced bars	10
Annex B (normative) Calibration schedule	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This third edition cancels and replaces the second edition ([ISO 4647:2010](http://www.iso.org/iso/4647:2010)), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- The Normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber, vulcanized — Determination of static adhesion to textile cord — H-pull test

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies a method for the determination of the static adhesion of textile cord to vulcanized rubber using the H-pull test. It is applicable to cords made from natural or man-made fibres.

The property levels obtained with this method are affected considerably by the history of the cord and the rubber compound. The method yields data, however, on which a judgement as to the service quality of the material can be based.

The method is primarily intended for use with tyre cord. However, it can be applied, if desired, to similar cords for use in other rubber products, but it is limited to cords of linear density not exceeding 800 mg/m (tex).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 5893](#), *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

[ISO 18899:2013](#), *Rubber — Guide to the calibration of test equipment*

[ISO 23529](#), *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>


4 Principle

The adhesion between a rubber and textile cord is assessed by measuring the force required to pull a single cord from a block of vulcanized rubber, the force being applied along the longitudinal axis of the cord and the length of cord embedded in the rubber being fixed (see [Figure 1](#)).

Cords are stretched over and perpendicular to the rubber strips, with a distance L between each cord. Two further strips of rubber are applied above the cord, the mould closed and put into a press, and the test pieces vulcanized.

It is common practice to use moulds which allow many identical test pieces to be produced simultaneously as a test pad.

One example of a suitable mould is shown in [Figure 2](#). It is recommended that the width of the cord groove be 0,8 mm for cords of linear density 560 mg/m (tex) or less, and 1,2 mm for cords of linear density more than 560 mg/m (tex) and up to 800 mg/m (tex). Although this form of mould is simple to use, the moulding pressure tends to force excess rubber down the cord groove between the rubber strips, particularly when the cord is much narrower than the groove. This “flash” shall be removed from the cord by careful cutting before the test to improve the reproducibility of the results. The formation of this rubber flash can be almost completely eliminated by using a mould of the form shown in [Figure 3](#), which shows two methods for preparing test pieces. The technique requires the cord length between the rubber strips to be held in position during vulcanization by a deformable surface, rather than a groove, so that there are no voids into which excess rubber can flow.



Key


1 four slots 0,8 mm or 1,2 mm wide and 3,0 mm deep, with all burrs removed

The mould shown will produce 16 test pieces. It may be fabricated to produce a larger or smaller number, but the dimensions that govern the size of the test pieces may not be altered.

a Material: hot-rolled steel.

Figure 2 — Suitable mould for H-pull test

Dimensions in millimetres



Key

- 1 mould frame
- 2 mould top plate
- 3 mould base plate
- 4 cord grooves, width 0,8 mm or 1,2 mm (see 6.1)
- 5 locating grooves for spacer bars
- R rubber cavity, width X and depth Y (see 6.1 and 8.1)
- S silicone-rubber-faced bar
- P plain spacer bar

Figure 3 — Methods of preparation of test pieces

In method A, the cord between the rubber strips R_1 and R_2 , and between R_3 and R_4 , is held between specially prepared silicone-rubber-faced bars. A suitable method for the preparation of such bars is described in [Annex A](#).

In method B, the upper strip of rubber is made sufficiently wide to cover the whole distance R_5 to R_6 (and R_7 to R_8), with the addition of a thin cellophane or polyester strip applied to the central portion of the rubber, which contacts the cords, to prevent the adherence of rubber to the cord in this region.

6.2 Tensioning device, capable of providing a tensioning force of $0,49\text{ N} \pm 0,1\text{ N}$. This can be achieved, for example, by suspending a mass of $50\text{ g} \pm 1\text{ g}$ on one end of each cord during assembly of the test piece and removing it prior to placing the mould in the vulcanizing press. The masses can be of the hook type or designed in such a manner that they can be clamped to the cord. In any event, the total mass shall be $50\text{ g} \pm 1\text{ g}$.

6.3 Tensile-testing machine, complying with the requirements of [ISO 5893](#), capable of measuring force with an accuracy corresponding to class 1 and with a rate of traverse of the moving grip of $100\text{ mm/min} \pm 10\text{ mm/min}$.

6.4 Test piece grips, of a design as shown in [Figure 4](#) or [Figure 5](#). Two grips are required.

NOTE The two types of grip do not necessarily give the same results.

7 Calibration

The requirements for calibration of the test apparatus are given in [Annex B](#).

8 Test piece

8.1 Dimensions

The standard test piece shall be a length of cord embedded in rubber strips, nominally 6,4 mm wide and 3,2 mm thick (see [6.1](#)).

Although this method specifies that the rubber strips shall be 3,2 mm thick, an interlaboratory test gave equivalent values for 3,2 mm-thick and 6,4 mm-thick test pieces. The embedded length of cord may be reduced to 5 mm or increased to 10 mm where the adhesion is very high or very low respectively, but the results obtained using different embedded lengths are not comparable.

8.2 Preparation

8.2.1 Cut the rubber compound into strips, 6 mm wide and of a suitable length, leaving the protective film attached. This can be done with scissors or with a clicker die cutter.


8.2.2 Cut strips of cotton fabric to the same dimensions as those of the rubber compound. (If the rubber compound is calendered onto the fabric, do not carry out this step.)

8.2.3 If necessary, place the bottom spacer bars in the mould ([Figure 3](#) type mould).

8.2.4 Using a mould at room temperature, place the fabric strips in the bottom of the mould cavities (see [8.2.11](#), second paragraph).

8.2.5 Place the rubber strips in the mould cavities with the protective-film side on top. (If the rubber is calendered onto the fabric, the fabric side shall be on the bottom.)

Dimensions in millimetres



Dimension	Value in mm
<i>A</i>	1,6
<i>B</i>	12,5
<i>C^a</i>	25,0
<i>D</i>	40,0
<i>E</i>	7,0
<i>F</i>	14,0
<i>G</i>	4,0
<i>H</i>	2,0


^a This dimension is the most important one and shall not be altered. All other dimensions are included for guidance and may be altered if desired.

Break all sharp edges and corners with slight radii.

The threaded hole is drilled and tapped to facilitate attaching the grip to the tester.

Figure 4 — Test piece grip

Dimensions in millimetres



NOTE The lower part of the grip is spring loaded with a spring tension of between 5 N and 15 N to minimize deformation of the rubber.

Figure 5 — Alternative test piece grip

8.2.6 Remove the protective film from the rubber strips and immediately place the cords in the cord slots. The portion of the cord to be embedded in the rubber shall not be touched with bare hands. The procedure for handling calendered cords shall be agreed upon by the purchaser and the supplier. Knot each cord at one end so that it is secured firmly against the cord slot on one side of the mould. Take care to prevent the loss of cord twist. Attach a tensioning device to the other end of the cord.

8.2.7 If required, place the upper spacer bars in the mould.

8.2.8 Remove the protective film from additional strips of rubber and place them in the mould cavities on top of the cords. The side from which the protective film was removed shall be facing down. When preparing test pieces by method B, these additional strips of rubber shall be 22 mm wide, with a strip of protective film or similar material replaced over the central 10 mm-wide area.

8.2.9 Place strips of fabric on top of the rubber strips. (If the rubber is calendered onto the fabric, eliminate this step.)

8.2.10 Identify the test pieces in the mould and cover the mould with a smooth metal plate if the upper press platen is not smooth.

8.2.11 Remove the tensioning devices from the cords and place the mould in a press which has been preheated to the vulcanizing temperature. Adjust the pressure to a minimum of 3,5 MPa with reference to the mould surface. After vulcanizing for the specified time, immediately remove the test pad from the mould and allow to cool at room temperature.

A preheated mould may be used, but this will alter the vulcanizing conditions (time and temperature) of the rubber. If a preheated mould is used, the materials should exhibit sufficient tack to permit the pad to be prefabricated in a cold mould and then transferred to the preheated mould.

8.2.12 Cut the pads using scissors, a sharp knife or a clicker die cutter to produce "H" pieces consisting of a single cord with each end embedded in the centre of a rubber tab approximately 25 mm in length. If necessary, trim off all excess rubber flash. When using method B, the trimming shall be carried out with great care to avoid cutting into the test piece.

8.3 Number of test pieces

At least eight test pieces shall be used.

9 Time interval between vulcanization and testing

Unless otherwise specified for technical reasons, the following requirements for time intervals shall be observed.

For all test purposes, the minimum time between vulcanization and testing shall be 16 h.

The maximum time between vulcanization and testing shall be 4 weeks and, for evaluations intended to be comparable, the tests shall, as far as possible, be carried out after the same time interval.

10 Conditioning of test pieces

10.1 When tests are performed at a standard laboratory temperature, the test piece shall be maintained at the conditions of test for at least 16 h immediately before testing.

10.2 When tests are made at higher or lower temperatures, the test pieces shall be maintained at the conditions of test for a period of time sufficient to reach temperature equilibrium with the test environment, or for the period of time required by the specification covering the material or product being tested, and shall then be tested immediately.

11 Test temperature

The test shall normally be carried out at a standard laboratory temperature specified in [ISO 23529](#). When other temperatures are used, they shall be selected from those given in [ISO 23529](#).

The same temperature shall be used throughout any one test or throughout a series of tests intended to be comparable.

12 Procedure

12.1 Testing at standard laboratory temperature

Attach the test piece grips to the tensile machine and set them 1 mm apart. Take care to ensure axial alignment.

Adjust the speed of the movable grip to 100 mm/min \pm 10 mm/min. Insert the test piece in the grips and start the machine. Record, to the nearest 1,0 N, the maximum force required to separate the cord from the rubber.

12.2 Testing at elevated temperature

Proceed as described in [12.1](#), but enclose the test piece grips in a temperature-controlled chamber attached to the tensile-testing machine. Heat the test pieces in the chamber, controlled at the test temperature, for not less than 15 min and not more than 60 min total elapsed time for testing of any one test piece. (Alternatively, a less precise procedure may be used whereby the test pieces are heated in an oven adjacent to the tensile-testing machine and then removed, one at a time, and tested within 15 s of removal.)

13 Expression of results

Record the cord adhesion value, in newtons, and calculate the arithmetic mean of the results. Describe the appearance of the cord, indicating whether the rubber has remained adhered to it or not.

14 Test report

The test report shall include the following information:

- a) sample details:
 - 1) a full description of the sample and its origin, including complete identification of the cord and rubber,
 - 2) the method of preparation of the test pieces from the sample, including the date of moulding;
- b) test method:
 - 1) a full reference to the test method used, i.e. the number of this document,
 - 2) the test procedure used (testing at standard laboratory temperature or testing at elevated temperature),
 - 3) the type of test piece used;
- c) test details:
 - 1) the time and temperature of conditioning prior to testing,
 - 2) the test temperature,
 - 3) the type of grip used,
 - 4) details of any procedures not specified in this document;
- d) test results:
 - 1) the number of test pieces used,
 - 2) the individual cord adhesion values and the arithmetic mean of these values,
 - 3) the appearance of the cord after each test;
- e) the date(s) of testing.

Annex A (informative)

Preparation of silicone-rubber-faced bars

A.1 Silicone compound preparation

A.1.1 A self-bonding grade of silicone rubber of hardness about 60 IRHD has been found suitable.

A.1.2 Depending on the mould plate size available, press out, between sheets of polyester, a 50 g to 60 g piece of the compound, using two flat mould plates to obtain a thickness of 1,5 mm which is as even as possible. The pressing is best done in a hydraulic press at very low pressure (less than 175 kPa). A hand-pump press is preferable. The platens may be heated to 50 °C to 70 °C, if preferred.

A.1.3 After pressing for 2 min to 3 min, examine the silicone rubber to see if the required thickness has been reached. It may not be possible to attain 1,5 mm, but up to 2 mm is permissible.

A.1.4 Remove the sheet of silicone rubber and store it on a cool, flat surface, still protected by the polyester film.

A.2 Bar preparation

A.2.1 Remove as much old silicone rubber as possible from any previously used bars by scraping, mechanical wire-brushing of the bars, or similar means.

A.2.2 Degrease the bars in a vapour degreasing bath, using trichloroethylene or perchloroethylene, for 30 min to 60 min.

A.2.3 Abrade the bars on the bonding surfaces only, using fine emery cloth. Light shot or vapour blasting may also be used, but it is advisable to protect the non-bonding surfaces to prevent unnecessary roughening.

A.2.4 Finally, clean the bars by wiping liberally with a clean cloth soaked in a petroleum solvent, the solvent being allowed to evaporate. Apply the strip of silicone rubber (see [A.3.1](#)) as soon as possible after cleaning.

A.3 Bonding procedure

A.3.1 Cut 10 mm-wide strips from the polyester-film-protected silicone rubber to fit the bonding areas on the bars. If the silicone rubber is unavoidably thick, the width of the strips may be reduced by between 1 mm and 2 mm to prevent excessive spew.

A.3.2 Peel the polyester film from one face of the strip, place the exposed face on the freshly cleaned bonding area and, manually, lightly press into contact. Avoid contact with the exposed silicone rubber surface and the prepared bar surface to prevent contamination and hence poor bonding.

A.3.3 Prepare two bars at a time. These should be used as a pair, and preferably marked for easy identification.

A.3.4 Place the bars in a suitable mould, side by side, with the silicone rubber faces uppermost. The top layers of polyester film may now be removed if preferred, but to facilitate easy demoulding a piece of polyester film, sufficient to cover the mould cavity, should be inserted. Alternatively, the mould lid should be sprayed with a PTFE aerosol mould lubricant.

A.3.5 With the lid located by the matching holes and pegs of the bars, place the mould in a press while the platens are warming up and use a low pressure to spread the silicone rubber. When the full curing temperature of 160 °C is reached, apply the highest possible safe pressure and vulcanize for 15 min.

A.3.6 Cool the bars, preferably in the mould in the press still under pressure. If this is not possible, allow the complete mould to cool outside the press as at this stage (i.e. when hot) the silicone rubber is still weak and prone to damage.

A.3.7 When cool, carefully remove the faced bars from the mould. This may be facilitated by removing one of the screwed-in mould end stops, allowing a thin lever to be inserted under the bars.

A.3.8 Excess silicone spew, etc., may then be trimmed off, or this may be deferred until after the oven cure.

A.3.9 When all the bars to be re-faced have been press-cured, store them for 18 h to 24 h at 200 °C. Remove excess spew, etc., if this was not carried out at the previous stage.

NOTE 1 During use, the silicone rubber may protrude beyond the edge of the bar. If a trial pull-through test piece is moulded, the amount of excess silicone can be measured by examining the test piece cross-section, which will be an H-section if the silicone protrudes. The edge of the silicone can then be trimmed back from the edge of each bar by slightly less than the depth of the indentation caused in the pull-through test piece.

NOTE 2 With normal usage, a minimum of 500 test mouldings can be expected before the bars need to be refaced.

Annex B (normative)

Calibration schedule

B.1 Inspection

Before any calibration is undertaken, the condition of the items to be calibrated shall be ascertained by inspection and recorded in any calibration report or certificate. It shall be reported whether calibration is made in the “as-received” condition or after rectification of any abnormality or fault.

It shall be ascertained that the apparatus is generally fit for the intended purpose, including any parameters specified as approximate and for which the apparatus does not therefore need to be formally calibrated. If such parameters are liable to change, then the need for periodic checks shall be written into the detailed calibration procedures.

B.2 Schedule

Verification/calibration of the test apparatus is a normative part of this document. The frequency of calibration and the procedures used are, unless otherwise stated, at the discretion of the individual laboratory, using [ISO 18899](#) for guidance.

The calibration schedule given in [Table B.1](#) has been compiled by listing all of the parameters specified in the test method, together with the specified requirement. A parameter and requirement can relate to the main test apparatus, to part of that apparatus or to an ancillary apparatus necessary for the test.

For each parameter, a calibration procedure is indicated by reference to [ISO 18899](#), to another publication or to a procedure particular to the test method which is detailed (whenever a calibration procedure which is more specific or more detailed than that in [ISO 18899](#) is available, it shall be used in preference).

The verification frequency for each parameter is given by the code-letter “S”, i.e. the standard interval as given in [ISO 18899](#).

In addition to the items listed, some standards assume the use of “normal” laboratory apparatus, e.g. timers, beakers, etc. These may need calibrating in accordance with the appropriate procedure given in [ISO 18899](#). Also, there may be items specified in the relevant cited standard which have a dimension, for example a 250 ml flask. Where the size has no particular significance, other than convenience of use, these items will not need to be calibrated.

Most standards for the testing of materials require the test piece to be conditioned. This implies the use of a thermometer and, possibly, a hygrometer, both of which will require calibration. Standard conditioning and test temperatures and humidities cited in the relevant standard have not been repeated in the schedule.

Test piece dimensions are usually specified. This implies the use of dimension-measuring instruments which will require calibration. Test piece dimensions cited in the relevant standard have not been repeated in the schedule.

Table B.1 — Calibration schedule

Parameter	Requirement	Clause or subclause in ISO 18899:2013	Verification frequency guide	Notes
Recommended mould	As in Figure 2 or Figure 3	15.2	S	
Cord groove width for linear densities ≤ 560 tex ≥ 560 tex up to 800 tex	0,8 mm	15.2	S	
	1,2 mm	15.2	S	
Tensioning force	0,49 N ± 0,1 N	21.2	S	e.g. 50 g ± 1 g on each cord
Tensioning machine	As in ISO 5893			
Force accuracy	Class 1	21.1	S	Low-inertia dynamometer preferred
Rate of separation of jaws	100 mm/min ± 10 mm/min	23.4	S	
Test piece grips	As in Figure 4 or Figure 5	15.2	S	The two types give the same result
Press	Preheated to vulcanization temperature	Clause 18	S	
Pressure	≥3,5 MPa	16.6	S	
Materials	Trichloroethylene or perchloroethylene for degreasing Fine emery cloth, or materials for shot or vapour blasting Petroleum solvent			

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK