



BSI Standards Publication

Rubber, vulcanized — Preparation of samples and test pieces

Part 2: Chemical tests

National foreword

This British Standard is the UK implementation of [ISO 4661-2:2018](#). It supersedes [BS 7164-2.2:1990](#), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/22, Testing and analysis of rubber.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 52196 6

ICS 83.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2018.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

INTERNATIONAL STANDARD

BS ISO
4661-2:2018

ISO
4661-2

Second edition
2018-09-28

Rubber, vulcanized — Preparation of samples and test pieces —

Part 2: Chemical tests

*Caoutchouc vulcanisé — Préparation des échantillons et
éprouvettes —*

Partie 2: Essais chimiques



Reference number
ISO 4661-2:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP
401
CH-1214 Vernier, Geneva,
Switzerland
Tel. +41 22 749 01 11 Fax
+41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Preparation of samples	1
4.1 Soft vulcanized rubber	1
4.2 Ebonite	1
4.3 Rubberized composites	1

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition ([ISO 4661-2:1987](http://www.iso.org/iso/4661-2:1987)), which has been technically revised.

The main changes compared to the previous edition are as follows:

- updating of the format of the document in regard to [Clauses 2](#) and [3](#);
- replacement of chlorinated solvents with less hazardous solvents in [4.3](#).

A list of all parts in the ISO 4661 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

When preparing samples of vulcanized rubber for chemical testing, care should be taken that any test portion is representative of the sample with respect to the property or constituent to be determined. Thus, if it is desired to deduce the composition of the original mix, any surface bloom should be incorporated, but if the final bulk composition is required, bloom should be removed preferably by using mechanical means. In the case of tests carried out with test pieces taken from a manufacturer's product, it might be necessary first to separate the desired vulcanized rubber from other possible components of the manufactured products, such as adjacent rubber compounds of different composition, metals, threads, tapes, and fabrics as well as coatings or veneers that cover it. This separation should be made using, whenever possible, mechanical means — blades, abrasive wheels, files, etc. — and avoiding any heat generation.

Rubber, vulcanized — Preparation of samples and test pieces —

Part 2: Chemical tests

1 Scope

This document specifies a method of preparing samples from vulcanized rubber for use in chemical tests.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 1407:2011](#), *Rubber — Determination of solvent extract*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Preparation of samples

4.1 Soft vulcanized rubber

The sample shall be comminuted with scissors, a rotating rasp, a suitable grinder or by cryogenic crushing to pass a sieve with an approximately 1,7 mm opening. Alternatively, it shall be sheeted to a thickness not exceeding 0,5 mm by passing between cold, tightly closed rolls of a laboratory mill. The type of grinder or mill used is immaterial, provided that the sample does not become contaminated or unduly heated.

4.2 Ebonite

The sample shall be rasped to powder which will pass a sieve with an approximately 400 µm opening. The powder shall be treated with a magnet to remove any iron particles.

4.3 Rubberized composites

Where it is not possible to separate the rubber mechanically, the following procedure shall be carried out.

The rubber shall be separated by exposing it to the vapour only of a suitable solvent. For composites based on NR, SBR and BR, acetone or ETA (ethanol-toluene azeotrope) will be suitable solvents. For other types of rubber, refer to [ISO 1407:2011](#) (Annex A) for suitable solvents.

The time of exposure should be kept as short as possible to avoid any possibility of extracting plasticizers from the rubber compound.

Afterwards, the swollen rubber shall have the solvent completely removed in air at room temperature and treated as described in [4.1](#).

In cases where the rubber is chemically bonded to the substrate, it should be noted that the composition of the rubber in the region of the bond can be substantially different from that in the bulk of the material.

In all cases, sampling shall be appropriate to the test being carried out. Even if the substrate can be removed "clean", the remaining rubber might consist of more than one formulation, and the blending carried out subsequently in accordance with [4.1](#) can result in a sample for analysis which is not representative of any one original formulation. Such composite layers can be revealed by microscopic examination of a series of cross-sections of the material.

It will then be possible, by careful buffing or cutting, to produce a sample of one or more rubber components for individual analysis.

Where it is impossible to separate the rubber from the substrate, the material shall be cut into small cubes to pass a sieve with 2 mm openings, and analysed as a whole.

In this case, the proportion by mass of rubber in the composite can be determined by disintegration of the rubber in a hot high boiling solvent, and weighing before and after the treatment. It should be noted that there might be partial dissolution of any organic material in the composite (for example, fabric), and the results should be interpreted with caution.

Where available, a sample of the non-rubber portion of the composite should also be analysed similarly.

In reporting the results of any analysis, the method of separation used shall be specified. If separation was impossible, it shall be made clear that the sample analysed was a heterogeneous blend of rubber and substrate and the possibility of error due to inhomogeneity or inadequate separation of materials should be pointed out.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions. With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member. PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

This page deliberately left blank