



BSI Standards Publication

Steel castings — Liquid penetrant testing

**INTERNATIONAL
STANDARD**

**ISO
4987**

Third edition
2020-01

**Steel castings — Liquid penetrant
testing**

Pièces moulées en acier — Contrôle par ressuage



Reference number
ISO 4987:2020(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Ordering information	1
5 Testing	2
5.1 Operating mode.....	2
5.2 Qualification of the operators.....	2
5.3 Surface preparation.....	2
5.4 Conditions of testing.....	2
6 Acceptance criteria	2
6.1 Definition of liquid penetrant indications.....	2
6.1.1 General.....	2
6.1.2 Non-linear indications (SP).....	2
6.1.3 Linear indication (LP).....	3
6.2 Severity levels.....	4
6.2.1 General.....	4
6.2.2 Non-linear indications.....	4
6.2.3 Linear indications.....	4
6.2.4 Selection of the severity level.....	4
6.2.5 Designation of severity levels.....	5
7 Classification of the indications and interpretation of results	5
7.1 Classification of the indications using Tables 1 and 2	5
7.1.1 General.....	5
7.1.2 Non-linear indications.....	5
7.1.3 Linear indications.....	5
7.2 Interpretation of results.....	5
8 Retesting	5
9 Post-examination cleaning procedures	6
10 Test report	6
Annex A (informative) Recommended surface finish for liquid penetrant testing	7
Annex B (informative) Reference figures — Non-linear isolated indications (SP)	8
Annex C (informative) Reference figures — Linear indications (LP)	13
Annex D (informative) Model of a liquid penetrant test report	28
Bibliography	30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 11, *Steel castings*.

This third edition cancels and replaces the second edition (ISO 4987:2010), which has been technically revised. The main changes compared to the previous edition are as follows:

- isolated non-linear indications are defined in [6.1.2](#);
- definition of aligned linear indications in [6.1.3](#) is corrected

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document complements the general principles of liquid penetrant testing described in ISO 3452-1 with additional requirements of the steel foundry industry.

Liquid penetrant testing, as well as any other non-destructive testing, is part of a general or specific assessment of the quality of a casting to be agreed between the purchaser and the manufacturer at the time of acceptance of the order.

Steel castings — Liquid penetrant testing

1 Scope

This document specifies a method for the liquid penetrant testing of steel castings.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3059, *Non-destructive testing — Penetrant testing and magnetic particle testing — Viewing conditions*

ISO 3452-1, *Non-destructive testing — Penetrant testing — Part 1: General principles*

ISO 4990, *Steel castings — General technical delivery requirements*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Ordering information

Subject to agreement between the manufacturer and the purchaser, enquiries and purchase orders for castings requiring liquid penetrant testing should include the following information:

- a) the area of the casting to be tested;
- b) the qualification of the operators who will carry out the testing (see 5.2) or interpretation (see 7.2);
- c) the frequency/number of castings to be tested;
- d) the manufacturing stage, when liquid penetrant testing is to be performed;
- e) the required surface finish of the areas to be tested;
- f) the type of discontinuity;
- g) the severity level.

The sensitivity can differ depending on the method of liquid penetrant testing selected. Therefore, the severity levels required shall be selected as a function of the liquid penetrants used and the method agreed between the manufacturer and the purchaser.

The severity level can vary depending on the area of the casting tested (see [Tables 1](#) and [2](#)).

5 Testing

5.1 Operating mode

Testing shall be carried out as specified in ISO 3452-1.

5.2 Qualification of the operators

Testing shall be performed by personnel qualified in accordance with ISO 9712 or equivalent recognised standards. The qualification level of the personnel shall be agreed between the manufacturer and purchaser by the time of the acceptance of the order.

5.3 Surface preparation

The surface to be tested shall be clean and free from oil, grease, moulding and coating residues, or any other contaminant which could interfere with the correct implementation and interpretation of the penetrant testing results. For small indications, it may be necessary to improve the surface condition. [Annex A](#) provides guidance on recommended surface finish for testing based on indication allowed.

Surface treatment or cleaning techniques which may seal or close discontinuities are not allowed.

5.4 Conditions of testing

The testing shall be carried out unaided or at a maximum magnification of 3× under viewing conditions in accordance with ISO 3059.

6 Acceptance criteria

6.1 Definition of liquid penetrant indications

6.1.1 General

Indications revealed by the liquid penetrant testing can have different shapes and sizes. The distinction between the indications is made depending on the ratio of the length L of the indication to its width W , in the manner described in [6.1.2](#) and [6.1.3](#).

6.1.2 Non-linear indications (SP)

Indications are considered to be non-linear when the length L is smaller than three times the width W . Indications are considered to be aligned when the distance between non-linear indications is less than 2 mm and at least three indications are aligned. An alignment of indications is considered to be a unique non-linear indication and its length is equal to the overall length L of the alignment specified in [Table 1](#). Non-linear indications that are not aligned are considered to be isolated.

NOTE The symbol for non-linear indications is SP (S for surface and P for liquid penetrant).

Table 1 — Severity levels for liquid penetrant testing — Non-linear (SP) indications (isolated)

Characteristic	Severity levels						
	SP 001	SP 01	SP 1	SP 2	SP 3	SP 4	SP 5
Testing means	Magnifying glass or eye		Eye				
Magnification for observation of penetrant indication	≤3		1				
Length L_1 of the smallest indication to be considered, in millimetres	0,3	0,5	1,5	2	3	5	5
Maximum number of non-linear indications allowed	5	6	8	8	12	20	32
Maximum individual length L_2 allowed, in millimetres	1	2	3 ^a	6 ^a	9 ^a	14 ^a	21 ^a
^a A maximum number of two indications of the designated dimension are permitted.							

6.1.3 Linear indication (LP)

The indications are considered to be linear when the length L is greater than or equal to three times the width W .

The lengths of the linear indications greater than the minimum length shall be added together and the result shall be compared to the total (T) length specified in [Table 2](#).

Table 2 — Severity levels for liquid penetrant testing — Linear (LP) indications

Characteristic	Severity levels													
	LP 001	LP 01	LP 1		LP 2		LP 3		LP 4		LP 5			
Testing means	Magnifying glass or eye		Eye											
Magnification for observation of penetrant indication	≤3		1											
Length L_1 of smallest indication to be considered, in millimetres	0,3		1,5	2	3	5	5							
Acceptable indications Individual (I) or Total (T) length	I or T		I	T	I	T	I	T	I	T	I	T		
Maximum length L_2 of linear (LP) indications allowed depending on the section thickness t , in millimetres ^a	section thickness type a $t \leq 16$ mm		0	1	2	4	4	6	6	10	10	18	18	25
	section thickness type b $16 \text{ mm} < t \leq 50$ mm		0	1	3	6	6	12	9	18	18	27	27	40
	section thickness type c $t > 50$ mm		0	2	5	10	10	20	15	30	30	45	45	70
^a No functional relationship exists between each type of section thickness and maximum crack length, relative to a fracture-mechanics study. However, this table is a useful guide where no relevant fracture-mechanics parameters currently exist.														

Indications are considered to be aligned when the distance between two indications is smaller than the length L of the longest indication. An alignment of indications is considered to be a unique indication and its length is equal to the overall length L of the alignment.

NOTE The symbol for linear indications is LP (L for linear and P for liquid penetrant).

6.2 Severity levels

6.2.1 General

The severity levels are a reference scale, each level depends on the types of indications.

6.2.2 Non-linear indications

For the non-linear indications, the severity levels (see [Table 1](#)) are defined by:

- a) the length (largest dimension) L_1 of the smallest indication to be considered, and
- b) the maximum length L_2 of the indications.

6.2.3 Linear indications

6.2.3.1 General

The severity levels for linear indications (see [Table 2](#)) are defined by:

- a) the length (largest dimension) L_1 of the smallest indication to be considered,
- b) the maximum length L_2 of the linear individual (I) indications, and
- c) the total (T) of the lengths of the linear indications exceeding the length L_1 in a frame measuring 105 mm × 148 mm.

6.2.3.2 Section thickness type

Three section thickness types are specified (see [Table 2](#)):

- a) $t \leq 16$ mm;
- b) $16 \text{ mm} < t \leq 50$ mm;
- c) $t > 50$ mm;

where t is the section thickness.

6.2.4 Selection of the severity level

The severity levels shall be selected from [Tables 1](#) and/or [2](#) as seen in, if necessary, the reference figures given in [Annexes B](#) and [C](#). The reference figures are drawn to a scale of 1:1 and are given as examples. The largest non-relevant indication is shown in a 26 mm × 37 mm frame corresponding to the ISO format A10.

[Table 1](#) and [Annex B](#) correspond to non-linear (SP) indications (isolated).

[Table 2](#) and [Annex C](#) correspond to linear (LP) indications.

NOTE Note that several equivalent severity levels defined in [Table 2](#) are represented by the same reference figure. In certain cases, the equivalence of the figure is only approximate because of slight differences in the parameters in [Table 2](#).

The severity levels cannot be considered in the same progression from [Table 1](#) to [Table 2](#). They should not be considered equivalent as regards severity. The severity criteria and the severity levels can differ from one part of a casting to another.

6.2.5 Designation of severity levels

The requirements in the order or in the specifications shall conform to the terminology used in this document.

Examples of correct terminology are given below:

- SP 2 for non-linear indications with a maximum of 8 non-linear indications, L_1 of 2 mm and L_2 of 6 mm (see [6.1.2](#), [6.2](#), and [Table 1](#));
- LP 5c for linear indications and $t > 50$ mm with L_1 of 5 mm and L_2 of 45 mm for Individual indications or 70 mm for Total indications (see [6.1.3](#), [6.2](#), and [Table 2](#)).

7 Classification of the indications and interpretation of results

7.1 Classification of the indications using [Tables 1](#) and [2](#)

7.1.1 General

In order to classify an indication, it is necessary to place a 105 mm × 148 mm frame in the most unfavourable location, i.e. showing the greatest severity for discontinuities.

7.1.2 Non-linear indications

Only those indications with a length greater than L_1 shall be considered (see [Table 1](#)).

The length of these indications shall be measured.

The severity level of the SP indications shall be established using [Table 1](#).

7.1.3 Linear indications

Only the indications with a length greater than L_1 shall be considered. The length L of the isolated indications greater than the minimum length taken into account, defined by the required severity level, shall be measured. The sum of the indications included in a 105 mm × 148 mm frame shall be calculated.

The section thickness t at the testing location shall be measured.

The level of the LP indications shall be established using [Table 2](#).

The lengths of the linear indications greater than the minimum length shall be summated and the result shall be compared to the total (T) length specified in [Table 2](#).

7.2 Interpretation of results

The casting shall be considered to conform with this document when the observed severity level is equal to or better than that specified in the order. If, for any indication type, the observed severity level is worse than that specified in the order, the casting shall be considered not to conform with this document.

NOTE Non-linear indications and linear indications can appear on the same part of the casting.

8 Retesting

Retesting shall be in accordance ISO 3452-1.

9 Post-examination cleaning procedures

Post-examination cleaning procedures shall be in accordance with ISO 3452-1.

10 Test report

When a test report is specified in the enquiry and the order, it shall contain at least the following information:

- a) the manufacturer;
- b) the purchaser (including the order number);
- c) the casting designation;
- d) the date and place of the test;
- e) the traceability identification;

and, as applicable, any of the following:

- a reference to this document for the acceptance criteria;
- the position of the testing stage in the manufacturing process;
- the surface finish;
- the test method;
- the equipment used;
- the testing materials used;
- the criteria required in accordance with this document;
- the reference to a specification;
- the results (description and location);
- the cartography of the significant indications;
- the decision taken after the interpretation of results;
- the elements required in ISO 4990 (type of document, signature(s) of the authorized persons according to the type of document);
- the certification/qualification, name and the signature of the non-destructive testing operator.

A model of a bilingual test report is shown in [Annex D](#).

Annex A (informative)

Recommended surface finish for liquid penetrant testing

Table A.1 — Recommended surface finish for liquid penetrant testing

Length L_1 of smallest indication to be considered mm	Visual/tactile comparators ^a	
	BNIF	SCRATA
0,3	2/0S1 - 1/0S1 1 S2 - 2 S2	—
1,5	1 S1 - 2 S1 3 S2 - 4 S2	A 1 H 1
2	2 S1 - 3 S1 4 S2 - 5 S2	A 2 H 2
≥3	unspecified (rough surface)	A 3 - A 4 H 3

^a Two visual/tactile comparators are currently used (see ISO 11971):

— *SCRATA comparators for the definition of surface quality of steel castings*, available from Castings Technology International, Advanced Manufacturing Park, Brunel Way, Rotherham, S60 5WG, United Kingdom; info@castingstechnology.com

— *BNIF 359 - Recommandation technique du Bureau de Normalisation des Industries de la Fonderie - Caractérisation d'états de surface des pièces moulées - Utilisation des échantillons types de 110 × 160 mm*, available from CTIF, 44 avenue de la Division Leclerc, 92310 Sèvres, France, www.ctif-editions.com.

NOTE These products are examples of suitable products available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of these products.

Annex B (informative)

Reference figures — Non-linear isolated indications (SP)

All reference figures shown in this annex are for guidance only. They are drawn and shall be used at a scale of 1:1.



a) Maximum size allowed for a non-relevant indication for severity level SP 1



b) Severity level SP 1

Figure B.1 — Severity level SP 1




a) Maximum size allowed for a non-relevant indication for severity level SP 2




b) Severity level SP 2

Figure B.2 — Severity level SP 2




a) Maximum size allowed for a non-relevant indication for severity level SP 3




b) Severity level SP 3

Figure B.3 — Severity level SP 3



a) Maximum size allowed for a non-relevant indication for severity level SP 4




b) Severity level SP 4

Figure B.4 — Severity level SP 4



a) Maximum size allowed for a non-relevant indication for severity level SP 5



b) Severity level SP 5

Figure B.5 — Severity level SP 5


Annex C (informative)

Reference figures — Linear indications (LP)

All reference figures shown in this annex are for guidance only. They are drawn and shall be used at a scale of 1:1.



a) Maximum size allowed for a non-relevant indication for severity level LP 1a




b) Severity level LP 1a

Figure C.1 — Severity level LP 1a



a) Maximum size allowed for a non-relevant indication for severity level LP2a




b) Severity level LP 2a

Figure C.2 — Severity level LP 2a



a) Maximum size allowed for a non-relevant indication for severity level LP 3a



b) Severity level LP 3a

Figure C.3 — Severity level LP 3a



a) Maximum size allowed for a non-relevant indication for severity level LP 4a




b) Severity level LP 4a

Figure C.4 — Severity level LP 4a



a) Maximum size allowed for a non-relevant indication for severity level LP 5a



b) Severity level LP 5a

Figure C.5 — Severity level LP 5a



a) Maximum size allowed for a non-relevant indication for severity level LP 1b



b) Severity level LP 1b

Figure C.6 — Severity level LP 1b



a) Maximum size allowed for a non-relevant indication for severity level LP 2b



b) Severity level LP 2b

Figure C.7 — Severity level LP 2b



a) Maximum size allowed for a non-relevant indication for severity level LP 3b



b) Severity level LP 3b

Figure C.8 — Severity level LP 3b



a) Maximum size allowed for a non-relevant indication for severity level LP 4b




b) Severity level LP 4b

Figure C.9 — Severity level LP 4b



a) Maximum size allowed for a non-relevant indication for severity level LP 5b



b) Severity level LP 5b

Figure C.10 — Severity level LP 5b



a) Maximum size allowed for a non-relevant indication for severity level LP 1c




b) Severity level LP 1c

Figure C.11 — Severity level LP 1c



a) Maximum size allowed for a non-relevant indication for severity level LP 2c



b) Severity level LP 2c

Figure C.12 — Severity level LP 2c



a) Maximum size allowed for a non-relevant indication for severity level LP 3c




b) Severity level LP 3c

Figure C.13 — Severity level LP 3c



a) Maximum size allowed for a non-relevant indication for severity level LP 4c




b) Severity level LP 4c

Figure C.14 — Severity level LP 4c



a) Maximum size allowed for a non-relevant indication for severity level LP 5c



b) Severity level LP 5c

Figure C.15 — Severity level LP 5c

Annex D (informative)

Model of a liquid penetrant test report

Company <i>Société</i>	Liquid penetrant test report <i>Contrôle par ressuage - Rapport d'essais</i>		No. <i>N°</i>		
			Sheet <i>Page</i>		
			According to <i>Conforme à</i>		
Customer <i>Client</i>		Order No. <i>Commande n°</i>			
Specification <i>Spécification</i>		Material <i>Nuance</i>	Heat No. <i>Coulée n°</i>		
Identification <i>Marquage</i>	Quantity <i>Quantité</i>	Casting designation <i>Désignation des pièces</i>	Lot No. <i>N° du lot</i>	Drawing No. <i>Plan n°</i>	
Area examined – <i>Zone contrôlée</i> <input type="checkbox"/> 100 % <input type="checkbox"/> testing scheme – <i>plan de contrôle</i> <input type="checkbox"/> cavity root – <i>fonds affouillements</i>					
Stage – <i>Stade</i> <input type="checkbox"/> after heat treatment – <i>après traitement thermique</i> <input type="checkbox"/> before stress relieving – <i>avant détensionnement</i>					
Dye penetrant – <i>Pénétrant</i>					
Trademark – <i>Marque</i>					
Dye penetrant remover – <i>Produit de nettoyage</i>					
Developer – <i>Révéléateur</i>					
Trademark – <i>Marque</i>					
Testing conditions – <i>Conditions d'examen</i>					
Surface condition – <i>État de surface</i> <input type="checkbox"/> shot-blasted – <i>grenillé</i> <input type="checkbox"/> ground – <i>meulé</i> <input type="checkbox"/> machined – <i>usiné</i>					

Bibliography

- [1] ISO 11971, *Steel and iron castings — Visual testing of surface quality*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK