

BS ISO 562:2010



BSI Standards Publication

Hard coal and coke — Determination of volatile matter

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 562:2010. It supersedes BS 1016-104.3:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/16, Solid mineral fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 70435 2

ICS 73.040; 75.160.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2010.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 562:2010

ISO
562

Third edition
2010-06-15

**Hard coal and coke — Determination of
volatile matter**

Houille et coke — Détermination des matières volatiles



Reference number
ISO 562:2010(E)

© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Principle.....	1
4	Reagents and materials	1
5	Apparatus	1
6	Preparation of the test sample	6
7	Procedure	6
8	Expression of results	6
9	Precision.....	7
10	Test report.....	7
Bibliography.....		8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 562 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 562:1998), of which it constitutes a minor revision.

Introduction

In this International Standard the volatile matter is determined as the loss in mass, less that due to moisture, when coal or coke is heated out of contact with air under standardized conditions. The test is empirical and, in order to ensure reproducible results, it is essential that the rate of heating, the final temperature and the overall duration of the test be carefully controlled. It is also essential to exclude air from the coal or coke during heating to prevent oxidation. The fit of the crucible lid is, therefore, critical. The moisture content of the sample is determined at the same time as the volatile matter so that the appropriate correction can be made.

Mineral matter associated with the sample can also lose mass under the conditions of the test, the magnitude of the loss being dependent on both the nature and the quantity of the minerals present.

NOTE When applying this International Standard for classification purposes, to samples obtained directly from coal seams, it is required to give special care to the ash.

The apparatus and procedure are specified so that one or more determinations can be performed simultaneously in the furnace.

Hard coal and coke — Determination of volatile matter

1 Scope

This International Standard specifies a method of determining the volatile matter of hard coal and of coke. It is not applicable to brown coals and lignites.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 687, *Solid mineral fuels — Coke — Determination of moisture in the general analysis test sample*

ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*

3 Principle

A portion of the sample is heated out of contact with air at 900 °C for 7 min. The percentage mass fraction of volatile matter is calculated from the loss in mass of the test portion after deducting the loss in mass due to moisture.

4 Reagents and materials

4.1 **Cyclohexane**, of recognized analytical grade.

5 Apparatus

5.1 **Furnace**, heated by electricity, in which a zone of uniform temperature of 900 °C ± 5 °C can be maintained.

It may be of the stop-ended type or fitted at the back with a flue approximately 25 mm in diameter and 150 mm long (see Figure 1).

It is important for furnaces with flues that the furnace door seal well. The flue should not reach far out of the oven and should be fitted with a butterfly valve to restrict airflow through the furnace.

Its heat capacity shall be such that, with an initial temperature of 900 °C, the temperature is regained within 4 min after insertion of a cold stand and its crucibles. The temperature is measured with a thermocouple (5.2).

Normally, the furnace is designed specifically either for multiple determinations using a number of crucibles in one stand or for receiving one crucible and its stand. In the first case, the zone of uniform temperature shall be at least 160 mm × 100 mm; in the latter case, a zone with a diameter of 40 mm is sufficient.

A position for the crucible stand shall be chosen within the zone of uniform temperature and this position shall be used for all determinations. The temperature of 900 °C shall be attained as closely as possible with a specified tolerance of ± 5 °C in order to compensate for inherent errors in the temperature measurement and lack of uniformity in the temperature distribution.

5.2 Thermocouple, unsheathed, of wire no thicker than 1 mm.

It should be long enough to reach the centre of the underside of each crucible when placed in the zone of uniform temperature on being inserted through the front or rear of the furnace. The thermojunction shall be placed midway between the base of the crucible in its stand and the floor of the furnace. If the stand holds more than one crucible, the temperature under each crucible shall be checked in the same manner.

If desired, a sheathed thermocouple may be permanently installed in the furnace (see Figure 1) with its thermojunction as close as possible to the centre of the zone of uniform temperature; in this case furnace temperature readings shall be correlated at frequent intervals with those of the unsheathed thermocouple, which is thus inserted only when necessary.

NOTE The temperature/electromotive force relationship of a thermojunction maintained at elevated temperatures gradually changes with time.

5.3 Crucible, cylindrical, with a well-fitting lid, both of fused silica.

The crucible with lid shall have a mass between 10 g and 14 g and dimensions approximating to those shown in Figure 2. The fit of the lid on the crucible is critical to the determination and a lid shall be selected to match the crucible so that the horizontal clearance between them is no greater than 0,5 mm. After selection, the crucible and the lid shall be ground together to give smooth surfaces and then be given a common distinguishing mark.

When performing multiple determinations on highly swelling coals, it can be necessary to use taller crucibles. These may be up to 45 mm in height without affecting the determined volatile matter, provided that the specified rate of temperature recovery be maintained.


5.4 Crucible stand, on which the crucible is placed in the furnace, such that the appropriate rate of heating can be achieved.

For example, it may consist of the following:

- a) for single determinations, a ring of heat-resistant steel wire as shown in Figure 3 a) with ceramic discs, 25 mm in diameter and 2 mm thick, resting on the inner projection of its legs; or
- b) for multiple determinations, a tray of heat-resistant steel wire as shown in Figure 3 b), of appropriate size, with ceramic plates 2 mm thick supporting the crucibles.

5.5 Balance, capable of reading to the nearest 0,1 mg.

Dimensions in millimetres



Key

- 1 zone of uniform temperature
- 2 check thermocouple
- 3 chamber (width 200 mm)
- 4 heating system
- 5 flue
- 6 valve
- 7 thermocouple

Figure 1 — Example of a suitable furnace

Dimensions in millimetres






Figure 2 — Silica crucible and lid

Dimensions in millimetres



a) Suitable for a single determination



b) Suitable for multiple determinations

Key

- | | |
|--------------------------------|------------------|
| 1 three legs separated by 120° | 3 handle |
| 2 ring | 4 ceramic plates |

Figure 3 — Crucible stands

6 Preparation of the test sample

The coal or coke used for the determination of volatile matter is the general analysis test sample (ground to pass a sieve of 212 µm aperture).

The sample shall be well mixed and in moisture equilibrium with the laboratory atmosphere.

A test portion from the same test sample is separated for determination of moisture in parallel with the determination of volatile matter.

7 Procedure

7.1 Furnace temperature checking

Adjust the temperature of the zone in the furnace (5.1), containing either a stand with one crucible and lid [Figure 3 a)] or a stand with the requisite number of crucibles and lids [Figure 3 b)], to $900\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$ as indicated by the correctly located thermocouple (5.2). Check that the temperature under each crucible, at the same height, lies within the temperature tolerance of the uniform zone.

Temperature checking should be made before starting determinations. However, in routine operation when several analyses are performed per day, a monthly temperature check is sufficient. The check of the temperature recovery criterion (5.1) should be dealt with in a similar way.

7.2 Volatile matter determination

Fill either a stand with one empty crucible and lid [Figure 3 a)] or a stand with the requisite number of empty crucibles and lids [Figure 3 b)] and insert in the oven. Maintain at $900\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$ for 7 min. Remove the crucible(s) from the furnace and allow to cool to room temperature on a thick metal plate.

As soon as they are cool, weigh each empty crucible and lid and weigh into each crucible, to the nearest 0,1 mg, $1\text{ g} \pm 0,1\text{ g}$ of test sample. Replace the lid and tap each crucible on a clean hard surface until the test portion forms a layer of even thickness on the bottom of the crucible. If the sample is coke, remove the lid of the charged crucible, add 2 drops to 4 drops of cyclohexane (4.1) and replace the lid.

NOTE 1 The addition of cyclohexane prevents the oxidation of the coke but does not prevent adsorption of gases, e.g. nitrogen.

Place the charged crucible(s) in a cold stand, transfer to the furnace, close the door and leave for $7\text{ min} \pm 5\text{ s}$. If multiple determinations are being made, any vacant places in the stand should be filled with empty crucibles.

Remove and allow to cool to room temperature. When cool, weigh the crucible(s) to the nearest 0,1 mg in the same manner as for the empty crucible(s).

NOTE 2 The same treatment of the crucible before and after the determination minimizes the effect of any film of water adsorbed on its surface, while the rapid cooling reduces absorption of moisture by the coal or coke residue.

8 Expression of results

The volatile matter, V , in the sample as analysed, expressed as a percentage mass fraction, is given by Equation (1):

$$V = \frac{100(m_2 - m_3)}{m_2 - m_1} - \omega_{\text{H}_2\text{O}} \quad (1)$$

where

- m_1 is the mass, expressed in grams, of the empty crucible and lid;
- m_2 is the mass, expressed in grams, of the crucible and lid and test portion before heating;
- m_3 is the mass, expressed in grams, of the crucible and lid and contents after heating;
- $\omega_{\text{H}_2\text{O}}$ is the moisture, expressed as a percentage mass fraction, in the sample as analysed, determined in accordance with the method specified in ISO 11722 for coal or ISO 687 for coke.

Report the result, as the mean of duplicate determinations, to the nearest 0,1 % mass fraction. The results of the determination described in this International Standard are reported on the “air-dried” basis. Calculation of the results to other bases is dealt with in ISO 1170.

9 Precision

9.1 Repeatability limit

The results of the duplicate determinations (performed within a short period of time, but not simultaneously) in the same laboratory by the same operator using the same apparatus on two representative test portions taken from the same general analysis test sample, shall not differ by more than the values given in Table 1.

Table 1 — Repeatability and reproducibility limits for volatile matter

Type of sample	Maximum acceptable differences between results obtained for volatile matter (calculated to the same moisture content)	
	Repeatability limit	Reproducibility limit
Hard coal < 10 %	0,3 % absolute	0,5 % absolute
Hard coal > 10 %	3 % of the mean result	0,5 % absolute or 4 % of the mean result, whichever is greater
Coke	0,2 % absolute	0,3 % absolute

9.2 Reproducibility limit

The means of the results of duplicate determinations, performed in each of two different laboratories on representative test portions taken from the same general analysis test sample shall not differ by more than the values given in Table 1.

10 Test report

The test report shall include the following information:

- a) reference to this International Standard, i.e. ISO 562;
- b) identification of the sample tested;
- c) date of the determination;
- d) results of the determination performed, together with the relevant analysis basis (e.g. air dry).

Bibliography

[1] ISO 1170, *Coal and coke — Calculation of analyses to different bases*

[2] ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™