



BSI Standards Publication

Lubricants, industrial oils and related products (Class L) — Family D (compressors)

Part 1: Specifications of categories DAA and DAB (lubricants
for reciprocating and drip feed rotary air compressors)

National foreword

This British Standard is the UK implementation of [ISO 6521-1:2019](#).

The UK participation in its preparation was entrusted to Technical Committee PT1/2, Liquid Fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 539 00435 9

ICS 75.100

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**INTERNATIONAL
STANDARD**

**ISO
6521-1**

First edition
2019-06-07

**Lubricants, industrial oils and
related products (Class L) — Family D
(compressors) —**

Part 1:

**Specifications of categories DAA and
DAB (lubricants for reciprocating and
drip feed rotary air compressors)**

*Lubrifiants, huiles industrielles et produits connexes (classe L) —
Famille D (compresseurs) —*

*Partie 1: Spécifications pour les catégories DAA et DAB (lubrifiants
pour compresseurs alternatifs et compresseurs rotatifs alimentés au
goutte à goutte)*



Reference number
ISO 6521-1:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Sampling	2
5 Requirements	2
6 Specifications	3
6.1 Specifications for ISO-L-DAA air compressor oils.....	3
6.2 Specifications for ISO-L-DAB air compressor oils.....	3
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 28, *Petroleum and related products, fuels and lubricants from natural or synthetic sources*, Subcommittee SC 4, *Classifications and specifications*.

A list of all parts in the [ISO 6521](#) series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Lubricants for compressors are used in various compressor designs. The lubricants for these applications can vary in composition, from straight mineral oils to more complex blends, based on mineral oils, synthetic oils (e.g. poly α -olefins, esters, poly-glycols), and additives. The additives most currently used are antioxidants, rust and copper corrosion inhibitors. They can be supplemented by detergents and dispersing additives to improving the cleanliness of the hottest parts of the compressors, e.g. the inlet and the exhaust valves in reciprocating compressors.

These lubricants are also able to lubricate the mechanical parts of the compressors (crankshaft and connecting rods bearings, crossheads, rolling bearings).

Lubricants, industrial oils and related products (Class L) — Family D (compressors) —

Part 1:

Specifications of categories DAA and DAB (lubricants for reciprocating and drip feed rotary air compressors)

1 Scope

This document specifies the minimum requirements for mineral or synthetic based lubricants intended for use in reciprocating and drip feed rotary air compressors (vane compressors) with the compression chamber(s)/cylinders lubricated by direct lubricant injection.

NOTE This document can be read in conjunction with [ISO 6743-3^{\[1\]}](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 2160](#), *Petroleum products — Corrosiveness to copper — Copper strip test*

[ISO 2592](#), *Petroleum and related products — Determination of flash and fire points — Cleveland open cup method*

[ISO 2719](#), *Determination of flash point — Pensky-Martens closed cup method*

[ISO 2909](#), *Petroleum products — Calculation of viscosity index from kinematic viscosity*

ISO 3016, *Petroleum and related products from natural or synthetic sources — Determination of pour point*

[ISO 3104](#), *Petroleum products — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity*

[ISO 3170](#), *Petroleum liquids — Manual sampling*

[ISO 3448](#), *Industrial liquid lubricants — ISO viscosity classification*

[ISO 3675](#), *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method*

[ISO 3987](#), *Petroleum products — Determination of sulfated ash in lubricating oils and additives*

ISO 4259 (all parts), *Petroleum and related products — Precision of measurement methods and results*

[ISO 6245](#), *Petroleum products — Determination of ash*

ISO 6247, *Petroleum products — Determination of foaming characteristics of lubricating oils*

[ISO 6296](#), *Petroleum products — Determination of water — Potentiometric Karl Fischer titration method*

[ISO 6614](#), *Petroleum products — Determination of water separability of petroleum oils and synthetic fluids*

[ISO 6615](#), *Petroleum products — Determination of carbon residue — Conradson method*

ISO 6617, *Petroleum-based lubricating oils — Aging characteristics — Determination of change in Conradson carbon residue after oxidation*

[ISO 6618](#), *Petroleum products and lubricants — Determination of acid or base number — Colour-indicator titration method*

ISO 6619, *Petroleum products and lubricants — Neutralization number — Potentiometric titration method*

ISO 7120, *Petroleum products and lubricants — Petroleum oils and other fluids — Determination of rust-preventing characteristics in the presence of water*

[ISO 12185](#), *Crude petroleum and petroleum products — Determination of density — Oscillating U-tube method*

[ISO 12937](#), *Petroleum products — Determination of water — Coulometric Karl Fischer titration method*

[ISO 20764](#), *Petroleum and related products — Preparation of a test portion of high-boiling liquids for the determination of water content — Nitrogen purge method*

ASTM D1160, *Standard Test Method for Distillation of Petroleum Products at Reduced Pressure*

DIN 51352-2, *Testing of lubricants; determination of ageing characteristics of lubricating oils; Conradson carbon residue after ageing by passing air through the lubricating oil in the presence of iron(III) oxide*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Sampling

Sampling of compressor oils for the purpose of this document, unless otherwise specified, shall be carried out in accordance with the relevant procedure described in [ISO 3170](#). The sample shall be evaluated on a representative portion. Any drum, barrel, tanker compartment or any type of container delivered to the end user may be sampled and analysed at the discretion of the purchaser.

5 Requirements

Compressor oil samples, when tested under the prescribed methods, shall be in accordance with the limits set out in [Tables 1](#) and [2](#).

The aspect of the delivered oil shall be clear and bright and free of any visible particulate matter, under visible light at ambient temperature.

Most of the test methods specified in [Tables 1](#) and [2](#) contain a precision statement. In cases of dispute, the procedure described in the [ISO 4259](#) series shall apply.

NOTE 1 Some equipment manufacturers or customers can have additional requirements covering e.g. characteristics such as elastomer and materials compatibility, anti-wear behaviour, detergent properties.

NOTE 2 These lubricants can also be used to lubricate the other mechanical parts of the compressors (crankshaft and connecting rod bearings, crossheads, rolling bearings). They might be also able to fulfil the required properties.

6 Specifications

6.1 Specifications for ISO-L-DAA air compressor oils

These lubricants are refined mineral oils with suitable oxidation and corrosion inhibitors; they can also contain some additional detergent additives to improve the cleanliness of the exhaust valve systems in reciprocating compressors. They are intended to lubricate reciprocating and rotary air compressors operating within the parameters of a normal duty cycle as defined in [ISO 6743-3](#)^[1].

These lubricants shall be in accordance with the specifications given in [Table 1](#).

6.2 Specifications for ISO-L-DAB air compressor oils

These lubricants are either refined mineral oils, part-synthetic or synthetic oils with suitable oxidation and corrosion inhibitors; they may also contain some additional detergent additives to improve the cleanliness of the exhaust valve systems in reciprocating compressors. They are intended to lubricate reciprocating and rotary air compressors operating within the parameters of a severe duty cycle as defined in [ISO 6743-3](#)^[1].

These lubricants shall be in accordance with the specifications given in [Table 2](#).

Table 1 — Specifications of ISO-L-DAA category

Characteristics	Unit	Test method	ISO — L- DAA				
			32	46	68	100	150
Viscosity grade		ISO 3448	32	46	68	100	150
Viscosity at 40 °C	mm ² /s	ISO 3104	28,8	41,4	61,2	90	135
— minimum			35,2	50,6	74,8	110	165
— maximum							
Viscosity at 100 °C	mm ² /s	ISO 3104	Report				
Viscosity index		ISO 2909	Report				
Density	kg/m ³	ISO 12185 or ISO 3675	Report				
Pour point (minimum)	°C	ISO 3016	-18	-15	-12	-9	-9
Flash point (Cleveland open cup) (minimum)	°C	ISO 2592	175	195	195	205	210
Flash point (Closed cup) (minimum)	°C	ISO 2719	162	182	182	192	198
Copper corrosiveness (maximum)	rating	ISO 2160	1	1	1	1	1
Acid number	mg KOH/g	ISO 6618 or ISO 6619	Report				
Water content (maximum) ^a	% m/m	ISO 6296 or ISO 12937	0,02				
Sulfated ash or oxide ash	% m/m	ISO 6245 or ISO 3987	Report				
Rust preventing characteristics	rating	ISO 7120 B	Shall pass				
Demulsibility ^b : maximum time to reach an emulsion volume of 3 ml	min	ISO 6614	30 at 54 °C			30 at 82 °C	
Foaming		ISO 6247					
Sequence I at 24 °C	ml/ml		150/0	150/0	150/0	150/0	150/0
Sequence II at 93 °C	ml/ml		50/0	50/0	50/0	50/0	50/0
Sequence III at 24 °C after 93 °C	ml/ml		150/0	150/0	150/0	150/0	150/0
Oxidation stability:		ISO 6617					
Carbon Conradson residue increase ^c	%		2,0				2,5
Evaporation losses	%		Report				

^a In case of dispute, use [ISO 20764](#).

^b This property does not apply to products containing detergents and dispersing additives.

^c [ISO 10370](#)[2] can be used as an alternative method to [ISO 6615](#) for the determination of the Conradson residue.

Table 2 — Specifications of ISO-L-DAB category

Characteristics	Unit	Test method	ISO — L — DAB				
			32	46	68	100	150
Viscosity grade		ISO 3448	32	46	68	100	150
Viscosity at 40 °C	mm ² /s	ISO 3104					
— minimum			28,8	41,4	61,2	90	135
— maximum			35,2	50,6	74,8	110	165
Viscosity at 100 °C	mm ² /s	ISO 3104	Report				
Viscosity index		ISO 2909	Report				
Density	kg/m ³	ISO 12185 or ISO 3675	Report				
Pour point (minimum)	°C	ISO 3016	-18	-15	-12	-9	-9
Flash point (Cleveland open cup) (minimum)	°C	ISO 2592	175	195	195	205	210
Flash point (Closed cup) (minimum)	°C	ISO 2719	162	182	182	192	198
Copper corrosiveness (maximum)	rating	ISO 2160	1	1	1	1	1
Acid number	mg KOH/g	ISO 6618	Report				
Water content (maximum) ^a	% m/m	ISO 6296 or ISO 12937	0,02				
Sulfated ash or oxide ash	% m/m	ISO 6245 or ISO 3987	Report				
Rust preventing characteristics	rating	ISO 7120 B	Shall pass				
Demulsibility ^b : maximum time to reach an emulsion volume of 3 ml	min	ISO 6614	30 at 54 °C			30 at 82 °C	
Foaming		ISO 6247					
Sequence I at 24 °C	ml/ml		150/0	150/0	150/0	150/0	150/0
Sequence II at 93 °C	ml/ml		50/0	50/0	50/0	50/0	50/0
Sequence III at 24 °C after 93 °C	ml/ml		150/0	150/0	150/0	150/0	150/0
Characteristics of the 20 % distillation residue obtained by distillation under reduced pressure:		ASTM D1160					
Carbon Conradson residue	% m/m	ISO 6615 or ISO 10370	0,3	0,3	0,3	0,3	0,6
Maximum viscosity at 40 °C of the residue	mm ² /s	ISO 3104	5 times of the viscosity of the new oil				
Oxidation stability		DIN 51352-2					
Carbon Conradson residue after aging ^c	%		2,5		3,0		
Evaporation losses	%		Report				

^a In case of dispute, use [ISO 20764](#).

^b This property does not apply to products containing detergents and dispersing additives.

^c [ISO 10370](#)[2] can be used as an alternative method to DIN 51551-1[3] for the determination of the Conradson residue.

Bibliography

- [1] [ISO 6743-3](#), *Lubricants, industrial oils and related products (class L) — Classification — Part 3: Family D (Compressors)*
- [2] [ISO 10370](#), *Petroleum products — Determination of carbon residue — Micro method*
- [3] DIN 51551-1, *Testing of lubricants and liquid fuels — Determination of the carbon residue — Part 1: Conradson method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
 - The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
 - A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
 - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK