



BSI Standards Publication

**Paper, board and pulps — Determination
of conductivity of aqueous extracts**

**INTERNATIONAL
STANDARD**

**ISO
6587**

Third edition
2021-11

**Paper, board and pulps —
Determination of conductivity of
aqueous extracts**

*Papier, carton et pâtes — Détermination de la conductivité des
extraits aqueux*



Reference number
ISO 6587:2021(E)

© ISO 2021

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		1
5 Reagents		2
5.1 Distilled or deionized water.....		2
5.2 Potassium chloride, standard solutions.....		2
5.2.1 0,01 mol/l solution.....		2
5.2.2 0,001 mol/l solution.....		2
6 Apparatus		2
7 Sampling and sample preparation		3
7.1 Sampling.....		3
7.2 Sample preparation.....		3
7.3 Determination of dry matter content.....		3
8 Procedure		3
8.1 Determination of cell constant.....		3
8.2 Preparation of the aqueous extract.....		4
8.2.1 Weighing of sample.....		4
8.2.2 Hot extraction method.....		4
8.2.3 Cold extraction method.....		4
8.3 Determination of conductivity.....		4
8.4 Blank test.....		4
9 Calculation and expression of results		4
9.1 If the meter gives conductance.....		4
9.2 If the meter gives resistance.....		5
9.3 Expression of results.....		5
10 Test report		5
Bibliography		6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 6587:1992), which has been technically revised.

The main changes are as follows:

- editorial updates;
- requirement added to [7.1](#);
- bibliography update.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Conductivity measurement provides an indication of the level of residual ionic impurities in pulp. It can thus be used, for example, to assess the effectiveness of washing in the pulp and paper manufacturing process.

Paper, board and pulps — Determination of conductivity of aqueous extracts

1 Scope

This document specifies a method for the determination of the conductivity of aqueous extracts of paper, board or pulp, these extracts having been prepared by a hot or cold method.

The method is applicable to all kinds of paper, board and pulps, except for papers used for electrical purposes. For high purity papers used for electrical purposes, see method given in EN 60554-2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

ISO 638-1, *Paper, board, pulps and cellulosic nanomaterials — Determination of dry matter content by oven-drying method — Part 1: Materials in solid form*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

conductivity

measure of the effect of the presence of dissolved substances in a solution to conduct electricity

Note 1 to entry: Conductivity does not measure the same solution properties as either osmolality or osmolarity and does not produce equivalent results. Conductivity only measures those substances that produce ions and does not measure dissolved substances that do not produce ions.

[SOURCE: ISO 18369-1:2017, 3.1.6.7]

4 Principle

A 2 g sample is extracted for 1 h with 100 ml of boiling or cold, distilled or deionized water. Measurement of the conductivity of the extract at 25 °C by means of a conductivity meter or resistance bridge, using alternating current.

5 Reagents

5.1 Distilled or deionized water

Distilled or deionized water shall be used throughout the test. The conductivity of the water shall not exceed 0,2 mS/m after boiling and cooling as specified in [8.2.2](#).

NOTE Usually, both distillation and deionization are required. Unless great care is exercised when distilling, and with the materials employed in the condenser and subsequent surfaces with which the condensed vapour would possibly come in contact, the distillate can fail to reach the required level of conductivity.

When it is not possible to obtain water of the specified purity, water with a higher conductivity may be used, but the conductivity of the water used should be stated in the test report.

5.2 Potassium chloride, standard solutions

Use potassium chloride (KCl) of recognized analytical reagent grade, powdered, or fine crystals. Dry for 2 h at $105\text{ °C} \pm 2\text{ °C}$ and immediately prepare the following two solutions.

5.2.1 0,01 mol/l solution

Dissolve 0,745 g of the potassium chloride in water having a conductivity not greater than 0,2 mS/m, and dilute to 1 000 ml.

5.2.2 0,001 mol/l solution

Dilute 100 ml of the 0,01 mol/l solution ([5.2.1](#)) to 1 000 ml.

Store the solutions in waxed glass bottles with ground glass stoppers. The conductivity values, in millisiemens per meter, of the two solutions, are given in [Table 1](#).

Table 1 — Conductivity of potassium chloride standard solutions

Concentration mol/l	Temperature °C	Conductivity mS/m
0,01	18	122,05
	20	127,80
	25	140,88
0,001	25	14,693

6 Apparatus

The usual laboratory apparatus and, in particular, the following shall be used.

6.1 Flasks of chemically resistant glass, with ground glass joints, stoppers and efficient water-cooled reflux condensers made of the same quality of glass. All glassware shall be carefully rinsed with boiling distilled or deionized water ([5.1](#)).

6.2 Electric heater, adjustable at least to 200 W.

6.3 Conductivity meter or resistance bridge, with measuring cells provided with black platinum electrodes of area approximately 1 cm^2 , and capable of indicating the conductance of an aqueous extract with an error of less than $\pm 5\%$ in the frequency range of 50 Hz to 3 000 Hz.

6.4 Constant-temperature bath, capable of maintaining a temperature of $25\text{ °C} \pm 0,5\text{ °C}$.

7 Sampling and sample preparation

7.1 Sampling

Sampling of paper or board shall be carried out in accordance with ISO 186. If the testing is done on another type of sample, report the origin of the sample, and if possible, the sampling procedure.

Sampling of pulp shall be carried out in accordance with ISO 7213. If the testing is done on another type of sample, report the origin of the sample, and if possible, the sampling procedure.

7.2 Sample preparation

Cut or tear the sample into pieces approximately 5 mm x 5 mm in size from portions that have not been touched by bare hands. Mix the pieces thoroughly. The sample shall not be touched at any time with bare hands. Clean protective gloves shall be worn at all times to protect the sample and the pieces prepared from it. Store the prepared samples in clean, covered containers.

7.3 Determination of dry matter content

Determine the dry matter content in accordance with ISO 287 for paper or board and ISO 638-1 for pulp.

8 Procedure

8.1 Determination of cell constant

Wash the measuring cell (see [6.3](#)) several times with water ([5.1](#)), and then at least twice with the potassium chloride standard solution ([5.2.1](#) or [5.2.2](#)) the conductivity of which is nearest to that of the extract being measured.

Measure the conductance or resistance of the cell by means of the conductivity meter or resistance bridge ([6.3](#)), with a fresh portion of the same potassium chloride standard solution.

Calculate the cell constant using the appropriate formula between [Formula \(1\)](#) and [\(2\)](#):

$$J = \frac{\gamma_{\text{KCl}}}{G_{\text{KCl}}} \quad (1)$$

or

$$J = \frac{R_{\text{KCl}} \cdot \gamma_{\text{KCl}}}{1\,000} \quad (2)$$

where

J is the cell constant

G_{KCl} is the conductance, in millisiemens, of the potassium chloride standard solution;

R_{KCl} is the resistance, in ohms, of the potassium chloride standard solution;

γ_{KCl} is the conductivity, in millisiemens per meter, of the potassium chloride standard (see [Table 1](#)).

NOTE The conductance G (in siemens) is equal to $1/R$, where R is the resistance (in ohms).

8.2 Preparation of the aqueous extract

8.2.1 Weighing of sample

Weigh $2 \text{ g} \pm 0,002 \text{ g}$ (oven-dry basis) of the sample (7.2) into a flask of suitable size (6.1) that has been carefully washed with boiling water (5.1).

8.2.2 Hot extraction method

With the aid of a pipette, measure 100 ml of water (5.1) into a separate flask (6.1). Attach the reflux condenser (see 6.1) and heat the water to almost boiling. Remove the condenser and add the water to the flask containing the sample (8.2.1). Replace the reflux condenser then boil gently for 1 h on the electric heater (6.2). Cool rapidly, with the condenser still fitted, to about 25 °C. Let the fibres settle and then decant the extract. Prepare the extract in duplicate.

Using the constant temperature bath (6.4), adjust the temperature of the extract to $25 \text{ °C} \pm 0,5 \text{ °C}$ and maintain that temperature throughout the test.

8.2.3 Cold extraction method

With the aid of a pipette, measure 100 ml of water (5.1) into the flask containing the sample (8.2.1). Seal the flask with a ground glass stopper and leave to stand at room temperature (20 °C to 25 °C) for 1 h. Shake the flask at least once during this time. Decant the extract. Prepare the extract in duplicate.

Using the constant temperature bath (6.4), adjust the temperature of the extract to $25 \text{ °C} \pm 0,5 \text{ °C}$ and maintain that temperature throughout the test.

8.3 Determination of conductivity

Rinse the measuring cell (see 6.3) carefully, several times with the water (5.1), and then twice more with the extract from 8.2.2 or 8.2.3. Measure the conductance or resistance with fresh portions of the extract until a constant value is obtained.

Repeat the determination with the duplicate extract.

8.4 Blank test

Carry out a blank test following the same procedure as for the determination, but omitting the sample.

9 Calculation and expression of results

9.1 If the meter gives conductance

The conductivity, γ , of the extract is given, in millisiemens per metre, by Formula (3):

$$\gamma = J(G_x - G_o) \quad (3)$$

where

J is the cell constant, determined as specified in 8.1;

G_x is the conductance, in millisiemens, of the extract;

G_o is the conductance, in millisiemens, corresponding to the blank test.

9.2 If the meter gives resistance

The conductivity, γ , of the extract is given, in millisiemens per metre, by [Formula \(4\)](#):

$$\gamma = 1\,000 \times J \left(\frac{1}{R_x} - \frac{1}{R_0} \right) \quad (4)$$

where

J is the cell constant, determined as specified in [8.1](#);

R_x is the resistance, in ohms, of the extract;

R_0 is the resistance, in ohms, corresponding to the blank test.

9.3 Expression of results

Report the conductivity of the extract, in millisiemens per meter, as the mean of two determination to the nearest 1 mS/m. The individual results should not differ by more than 10 % or 2 mS/m, whichever is the greater; if they do, repeat the determination on two additional extracts and report the mean and range of all measurements.

10 Test report

The test report shall include the following particulars:

- a) all the information necessary for complete identification of the sample;
- b) reference to this document, i.e. ISO 6587:2021;
- c) the extraction procedure used, i.e. hot or cold;
- d) the results expressed in millisiemens per meter;
- e) the conductivity of the water used, where this is greater than 0,2 mS/m;
- f) any unusual features observed in the course of the test;
- g) any operations not specified in the International Standard(s) to which reference is made, or are regarded as optional, which can have affected the results.

Bibliography

- [1] ISO 18369-1:2017, *Ophthalmic optics — Contact lenses — Part 1: Vocabulary, classification system and recommendations for labelling specifications*
- [2] EN 60554-2, Cellulosic papers for electrical purposes — Part 2: Methods of test
- [3] TAPPI test method T252, “pH and electrical conductivity of hot water extracts of pulp, paper, and paperboard”

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK