



BSI Standards Publication

Textiles — Methods for analysis of woven fabrics construction

Part 6: Determination of the mass of warp and weft per unit area of fabric

National foreword

This British Standard is the UK implementation of [ISO 7211-6:2020](#).

The UK participation in its preparation was entrusted to Technical Committee TCI/24, Physical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 580 52105 8

ICS 59.080.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
7211-6

Second edition
2020-04-01

**Textiles — Methods for analysis of
woven fabrics construction —**

Part 6:

**Determination of the mass of warp
and weft per unit area of fabric**

Textiles — Méthodes d'analyse de la construction des tissus —

*Partie 6: Détermination de la masse des fils de chaîne et de trame par
unité de surface d'un tissu*



Reference number
ISO 7211-6:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		1
5 Apparatus		1
6 Conditioning and testing atmosphere		2
7 Test specimens		2
7.1 Conditioning.....		2
7.2 Method A.....		2
7.3 Method B.....		2
8 Procedure		2
8.1 Method A.....		2
8.2 Method B.....		3
9 Calculation and expression of results		3
10 Test report		3
Bibliography		4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 24, *Conditioning atmospheres and physical tests for textile fabrics*.

This second edition cancels and replaces the first edition ([ISO 7211-6:1984](http://www.iso.org/iso/7211-6:1984)), of which it constitutes a minor revision.

The main changes compared to the previous edition are as follows:

- the normative reference to ISO/TR 5090 (withdrawn) has been replaced by [ISO 1833-1](http://www.iso.org/iso/1833-1);
- a [Clause 3](#), Terms and definitions has been added.

A list of all parts in the ISO 7211 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

It is common practice to describe fabrics by the mass per unit area (see [ISO 3801](#)) and the ends and picks per centimetre, but this leaves the proportions of warp and weft in the fabric uncertain. Any desired balance of cover between warp and weft can be stated without specifying the yarn linear densities by giving separate values for the masses of warp and weft per unit area of the fabric.

Textiles — Methods for analysis of woven fabrics construction —

Part 6:

Determination of the mass of warp and weft per unit area of fabric

1 Scope

This document specifies methods for determining the mass of the warp and weft threads per unit area of fabric after the removal of any non-fibrous matter.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 139](#), *Textiles — Standard atmospheres for conditioning and testing*

[ISO 1833-1](#), *Textiles — Quantitative chemical analysis — Part 1: General principles of testing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Method A: The outline of the fabric specimen to be dissected is marked in the form of a square or rectangle, and the nonfibrous matter is removed while the marked area still forms part of a larger sample and the threads cannot, therefore, be lost from it. If the amount of non-fibrous matter is to be determined, it is stipulated that the larger sample shall be a square cut with its diagonals parallel to the directions of the threads in the fabric. If the amount of non-fibrous matter has not to be determined, the larger sample may be of any shape or size.

Method B: A specimen of known area is dissected and the non-fibrous matter is removed from the warp and weft threads.

5 Apparatus

5.1 Indelible marking ink.

5.2 Scissors.

Determine the mass of the marked area to an accuracy of 0,1 %.

Working over paper of a colour suitable for showing up fragments of the yarn and fibre from the fabric being tested, fray out from one edge of the square or rectangle, and collect together the threads more easily removed from the fabric.

From time to time, cut off the fringe of threads remaining in the other direction of the fabric and collect the short lengths together, keeping them separate from the more easily removed threads. When the whole of the marked area has been dissected into warp and weft threads, determine the mass of the two sets of threads separately to an accuracy of 0,1 %. The sum of these two masses shall not differ from the mass of the fabric before dissection by more than 1 %. Where the sum of the masses of warp and weft threads differs by more than 1 % from the mass of the fabric specimen, the procedure has not been followed with sufficient accuracy. Repeat the procedure in order to achieve the required accuracy.

Long rectangular specimens are easier to dissect than squares, but the dissection of the latter may be facilitated by cutting into several rectangles with their lengths in the direction of the threads more easily removed from the fabric.

8.2 Method B

Dissect the specimen of known area into warp and weft threads over paper of a colour suitable for showing up fragments of yarn from the fabric being tested. When the dissection of the specimen has been completed, remove the non-fibrous matter from the two sets of threads separately by a method described in [ISO 1833-1](#), taking care that no loss of fibre occurs during the process.

Dry the threads and bring them into equilibrium with the standard atmosphere for testing, from the dry side by exposing them freely to that atmosphere. Determine the mass of the two sets of threads separately to an accuracy of 0,1 %.

9 Calculation and expression of results

From the conditioned masses of warp and weft, free from added matter, and the known area of the specimens dissected, calculate the mass per unit area of warp, weft and fabric and express each in grams per square metre.

10 Test report

The test report shall include at least the following particulars:

- a) a reference to this document (i.e. [ISO 7211-6:2020](#));
- b) atmosphere used (standard or one of the alternative atmospheres);
- c) actual method used, i.e. method A or method B;
- d) method used for removal of non-fibrous matter, if carried out;
- e) the mass of warp and weft per unit area of each specimen and, if required, the mass per unit area of the fabric, all expressed in grams per square metre;
- f) details of any deviation from the given procedure;
- g) any unusual features observed;
- h) date of the test.

Bibliography

- [1] [ISO 3801](#), *Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area*

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK