



BSI Standards Publication

Methods for the petrographic analysis of coals

Part 4: Method of determining microlithotype,
carbominerite and minerite composition

National foreword

This British Standard is the UK implementation of ISO 7404-4:2017. It supersedes BS 6127-4:1990, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/16, Solid mineral fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017
Published by BSI Standards Limited 2017

ISBN 978 0 580 92330 2

ICS 75.160.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
7404-4

Second edition
2017-08

**Methods for the petrographic analysis
of coals —**

Part 4:
**Method of determining
microlithotype, carbominerite and
minerite composition**

Méthodes d'analyse pétrographique des charbons —

*Partie 4: Détermination de la composition en microlithotypes,
carbominérites et minérites*



Reference number
ISO 7404-4:2017(E)

© ISO 2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		1
5 Material		2
6 Apparatus		2
7 Procedure		3
8 Expressions of results		5
9 Precision		7
9.1 Repeatability limit.....		7
9.2 Reproducibility limit.....		7
10 Test report		8
Bibliography		9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This second edition cancels and replaces the first edition (ISO 7404-4:1988), which has been technically revised.

A list of all the parts in the ISO 7404 series can be found on the ISO website.

Introduction

Petrographic analyses have been recognized internationally as important in the context of the genesis, vertical and lateral variation, continuity, metamorphism and usage of coal. The International Committee for Coal Petrology (ICCP) has made recommendations concerning nomenclature and analytical methods and has published and described in detail the characteristics of a wide range of coals. This document agrees substantially with the text of relevant ICCP publications and incorporates many useful comments made by members of the ICCP and by member bodies of ISO/TC 27.

Petrographic analyses of a single coal provide information about the rank, the maceral and microlithotype compositions and the distribution of mineral matter in the coal. The reflectance of vitrinite is a useful measure of coal rank and the distribution of the reflectance of vitrinite in a coal blend, together with a maceral group analysis, can provide information about some important chemical and technological properties of the blend.

The ISO 7404 series is concerned with the methods of petrographic analysis currently employed in characterizing coal in the context of its technological and/or geological use. It establishes a system for petrographic analysis and comprises five parts, see ISO website:

Microlithotypes are the naturally occurring associations of macerals which characterize the microscopically visible different types of coal. By convention, the identity of a microlithotype is determined by the maceral group or groups occurring within an area of at least $50\ \mu\text{m} \times 50\ \mu\text{m}$ and which are present in amounts equal to or exceeding 5 % by volume. Hence, they can comprise a single maceral or maceral group if it exceeds these dimensions. Microlithotypes may include up to 20 % by volume of minerals such as clay, quartz and carbonates or up to 5 % by volume of sulfide minerals. If the content of mineral matter exceeds these amounts, the material is designated as minerite or carbominerite depending on the proportions of coal and mineral matter.

Carbominerites can be subdivided according to the type of mineral matter.

Microlithotypes contribute information on the genesis of coal seams and can assist in solving problems of seam correlation. Because they determine, together with rank and mineral matter, the hardness and density of the bulk coal substance, microlithotypes affect the behaviour of coal in mining and coal preparation processes. The different microlithotypes determine, under given geological conditions, the distribution of micro-cracks and to some extent the cleat in the coal. The results of maceral analyses can be interpreted more meaningfully from a knowledge of microlithotype composition. Such information can assist in explaining the behaviour of coal in commercial and experimental utilization processes where the association of macerals is known to be important.

NOTE The percentage volume of carbonate, clay and quartz minerals on the one hand and sulfide minerals on the other, which define the carbominerites and minerites, correspond to the densities which separate acceptable coal from middlings ($1,5\ \text{g/cm}^3$) and from rejects in coal preparation.

Methods for the petrographic analysis of coals —

Part 4:

Method of determining microlithotype, carbominerite and minerite composition

1 Scope

This document specifies a method, using a graticule with 20 crossline intersections, for determining the proportions of microlithotypes, carbominerite and minerite in coals. It applies only to determinations made on polished particulate blocks using reflected white light (about 400 nm to 700 nm). Additional blue, blue-violet or UV light excitation (365 nm to 440 nm) for better identification of liptinite in fluorescence may be used especially at low rank coals.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7404-1, *Methods for the petrographic analysis of coals — Part 1: Vocabulary*

ISO 7404-2, *Methods for the petrographic analysis of coals — Part 2: Methods of preparing coal samples*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 7404-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <http://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

point

observation of a portion of the particulate block through the eyepiece graticule made during the analysis

Note 1 to entry: The allocation of a point to a particular microlithotype, or to carbominerite or minerite, is determined by the macerals and/or mineral matter present at the 20 intersections of the graticule. A point is only counted if at least 10 intersections fall on a particle.

4 Principle

Examination by using a reflected light microscope and point count procedure of a representative sample of coal prepared as a particulate block as described in ISO 7404-2. Identification under an immersion medium of the microlithotypes from their maceral composition. The proportions of the macerals are determined using a graticule having a grid with 20 points of intersection spaced to define a distance of 50 µm on the specimen between extreme intersections in the x (abscissa) and y (ordinate) directions, respectively. The use of such a graticule allows the analyst to comply with the 5 % minimum content and 50 µm minimum size stipulation.

5 Material


Immersion medium, having a suitable refractive index and compatible with the microscope objective.

NOTE If reflectance measurements are required on the same particulate block, an immersion oil as specified in ISO 7404-5 is used.

6 Apparatus

6.1 Reflected light microscope, having an immersion objective of magnification between $\times 25$ and $\times 60$ and eyepiece of magnification between $\times 8$ and $\times 12$. The eyepiece shall have the facility for inserting a graticule.

6.2 Graticule, inscribed with a grid having 20 crossline intersections according to the pattern shown in [Figure 1](#). The effective distance between extreme intersections in the x- and y-directions, respectively, is $50\ \mu\text{m}$.



Key

1 $50\ \mu\text{m}$ on the specimen

Figure 1 — Design of grid for microlithotype analysis

NOTE 1 With a total number of 20 cross line intersections, a maceral appearing beneath a single intersection can be assumed to occupy 5 % by volume of the area covered by the grid.

NOTE 2 The graticule is designed for use with a particular combination of objective and eyepiece. Change in either objective or eyepiece will necessitate the use of a grid of different dimensions.

6.3 Mechanical or scanning stage, capable of advancing the specimen in the x-direction by equal steps of such length that only a negligibly small proportion of the particles examined receives more than one count on the same particle. The step-length is equal to half the maximum particle diameter, i.e. $0,5\ \text{mm}$ to $0,6\ \text{mm}$ for samples with a standard top particle size of $1\ \text{mm}$. The stage also permits a similar stepped advance in the y-direction. The stage movement may be actuated manually, by the counter mechanism or a computer attached to the stage.

6.4 Counter/computer, capable of registering the points in each category and preferably the grand total of points counted.

6.5 Sample mounting equipment, comprising slides, modelling clay and levelling press.

7 Procedure

Insert the graticule (6.2) into the eyepiece of the adjusted microscope (6.1).

Place the levelled particulate block, prepared in accordance with ISO 7404-2, on the stage. Add the immersion medium to the surface of the block, focus and observe the image in the microscope.

Assess the number of crossline intersections lying on the particle in order to decide whether the point should be recorded in the counting procedure and, if so, whether it should be assigned to the category of a microlithotype, carbominerite or minerite. If the number of intersections on one particle is 10 or more the point shall be accepted for analysis. If there are no intersections on coal or mineral matter, the point is ignored (i.e. it is not recorded). If the number is less than 10 it shall be recorded as a rejected category and the stage shall be advanced by one step. The number of such rejected points shall not exceed 10 % of the total accepted and rejected points. If the proportion exceeds 10 %, excessive fines may have been produced during preparation and a fresh sample should be prepared if material is available. If this is not possible the fact shall be recorded in the test report. For identifying the material under the individual crosslines, apply the procedure described in ISO 7404-3. The criteria for determining accepted and rejected points are shown in [Figure 2](#).

If the particle is accepted for analysis, assess the number of intersections lying on mineral matter. If the number of crossline intersections on mineral matter exceeds the number shown in [Table 1](#) for a given number of intersections lying within the particle, the material is either carbominerite or minerite.

Table 1 — Maximum permissible number of intersections falling on mineral matter for the point to be classified as a microlithotype

No. of intersections lying within the particle	Number of intersections on	
	carbonate, clay, quartz	sulfide
16 to 20	3	0
11 to 15	2	0
10	1	0

If the particle is a microlithotype, it is identified according to the criteria shown in [Table 2](#) ignoring any intersections on carbonate, clay or quartz.

Table 2 — Delimitation of microlithotypes

Microlithotype	Location of the crossline intersections lying in the coal
Vitrite	All intersections in the vitrinite
Liptite	All intersections in the liptinite
Inertite	All intersections in the inertinite
Clarite	All intersections in the vitrinite and liptinite, at least one intersection in each of the two maceral groups
Durite	All intersections in the inertinite and liptinite, at least one intersection in each of the two maceral groups
Vitrinertite	All intersections in the vitrinite and inertinite, at least one intersection in each of the two maceral groups
Trimacerite	At least one intersection in each of the three maceral groups

These criteria are applicable to microlithotypes containing mineral matter not exceeding the limits given in [Table 1](#).

If the intersections on mineral matter exceed the limits given in [Table 1](#), determine whether the particle is minerite or a carbominerite according to the criteria given in [Table 3](#) and [Table 4](#), if necessary. In using [Table 3](#) to identify carbominerite or minerite, the minerals appearing under the intersections shall be either sulfide or other minerals, but not both. The carbominerite may be named carbankerite, carbargilite, carbosilicite, carbopyrite or carbopolyminerite, according to the mineral matter appearing under the intersections.

Table 3 — Delimitation of carbominerite (excluding carbopolyminerite with sulfide) and minerite

No. of intersections lying within particle	Intersections falling on specified minerals			
	Carbominerite		Minerite	
	Carbonate, clay, quartz	Sulfide	Carbonate, clay, quartz	Sulfide
19 or 20	4 to 11	1 to 3	>11	>3
17 or 18	4 to 10	1 to 3	>10	>3
16	4 to 9	1 to 3	>9	>3
14 or 15	3 to 8	1 or 2	>8	>2
12 or 13	3 to 7	1 or 2	>7	>2
11	3 to 6	1 or 2	>6	>2
10	2 to 5	1	>5	>1

If both sulfide and other minerals occur under intersections of the grid, within the limits given in [Table 4](#), the carbominerite is named carbopolyminerite, otherwise the particle is again assigned to minerite.

Table 4 — Delimitation of carbopolyminerite with sulfide

No. of intersections lying within the particle	Carbopolyminerite	
	Intersection falling on specified minerals	
	Carbonate, clay, quartz	Sulfide
16 to 20	1 to 3	1 to 3
11 to 15	1 or 2	1 or 2
10	1	1

The maceral group or groups associated with the mineral matter and appearing under the residual intersections of the grid may be recorded to further characterize the carbominerite.

Having identified the point, advance the particulate block by one step along the x-axis, and continue counting and traversing the specimen. At the end of a traverse, advance the block by a step of at least equal length along the y-axis to start the next parallel traverse. The step length shall be chosen to ensure a uniform counting of points over the surface of the particulate block.

The total number of accepted points shall be at least 500.

NOTE For the assignment of a microlithotype, only the maceral group or groups appearing under the crossline intersections are considered. If a natural boundary between the two different microlithotypes lies under the grid, the assessment is made as if there were no boundary. The analysis, as described in this document, is traditionally applied to hard coals; there is, however, no reason, why it cannot be applied to lignite.

8 Expressions of results

Report the number of accepted points per microlithotype, per carbominerite and per minerite as the percentage of total number of accepted points. Express the values obtained as percentages by volume to the nearest integer.

The number of accepted points and the percentage of rejected points shall be indicated in the test report. An example of a suitable method of expressing results is shown in [Table 5](#).

The nature of coal associated with carbominerite and minerite, if determined, expressed as

- a) general qualitative observations, or
- b) quantitative record of maceral groups under residual intersections

may be recorded as shown in [Table 6](#).

Table 5 — An example of a method of expressing the results

Sample No.	Date:	
Microlithotype	Number of accepted points	Volume %
Vitrite	101	20
Liptite		
Inertite	64	13
Clarite	57	11
Durite	115	23
Vitrinertite		
Trimacerite	141	28
Total microlithotypes		95
Carbominerite	Number of accepted points	Volume %
Carbargilite	13	3
Carbankerite		
Carbosilicite		
Carbopyrite	5	1
Carbopolyminerite		
Total carbominerite		4
Minerite	Number of accepted points	Volume %
	4	1
Grand total		100

Total number of accepted points 500

Percentage of rejected points 7

Table 6 — Nature of coal associated with carbominerite and minerite (example)

Carbominerite/minerite (specify)	Associated maceral group(s) observed ^a	Number of accepted points	Accepted points as a percentage of carbominerite/minerite
Carbargilite	V	3	20
	V + L	12	80
Carbopyrite	V	1	20
	V + L	3	60
	V + L + I	1	20
Minerite	V + I	5	100
^a L = liptinite I = inertinite V = vitrinite			

9 Precision

9.1 Repeatability limit

The repeatability of the determination of the volume percentage of a component is the difference between two single determinations each based on the same number of point counts carried out by the same operator on the same sample, using the same apparatus, below which 95 % of such differences would be expected to lie. The repeatability may be calculated using [Formula \(1\)](#):

$$r = (2\sqrt{2})\sigma_t \quad (1)$$

where σ_t is the theoretical standard deviation.

Provided that the operator makes negligible errors in classifying the microlithotypes, the results of an analysis will be subject to standard deviations calculable on the basis of the binomial distribution. Where p % of the total number of counts, N , is registered for a given microlithotype, the standard deviation, σ_t , of p is given by the [Formula \(2\)](#):

$$\sigma_t = \sqrt{\frac{p(N-p)}{N}} \quad (2)$$

Values for the theoretical standard deviation and repeatability calculated for a range of volume percentages of a component are given in [Table 7](#) based on 500 point counts.

Table 7 — Theoretical standard deviation and repeatability of the percentage of a component based on 500 point counts

Volume percentage p	Standard deviation, σ_t of the volume percentage	Repeatability $r = (2\sqrt{2})\sigma_t$
5	1,0	2,8
20	1,8	5,1
50	2,2	6,3
80	1,8	5,1
95	1,0	2,8

9.2 Reproducibility limit

The reproducibility of the determination of the volume percentage of a component is the difference between two single determinations each based on the same number of point counts, carried out by two different operators on two separate sub-samples taken from the same sample, using different equipment, below which 95 % of such differences would be expected to lie. The reproducibility is given by the [Formula \(3\)](#):

$$R = (2\sqrt{2})\sigma_o \quad (3)$$

where σ_o is the observed standard deviation.


Values of the observed standard deviation normally exceed those of the theoretical values given in [Table 7](#) due to misidentification of the microlithotypes or minerals by different operators and to variation between sub-samples. There is, at present, insufficient evidence from collaborative analyses to estimate the effect of misidentification.

ISO 7404-4:2017(E)

10 Test report

The test report shall include the following information:

- a reference to this document, i.e. ISO 7404-4;
- all details necessary for identification of the sample;
- number of accepted points analysed and the percentage of rejected points;
- the results obtained;
- the nature of coal associated with the carbominerite and minerite if determined.



Key

- inertinite
- liptinite
- vitrinite
- immersion medium

NOTE The count of intersections is made on a single particle.

Figure 2 — Criteria used to determine the categories of accepted and rejected points

Bibliography

- [1] ISO 7404-3, *Methods for the petrographic analysis of coals — Part 3: Method of determining maceral group composition*
- [2] ISO 7404-5, *Methods for the petrographic analysis of coals — Part 5: Method of determining microscopically the reflectance of vitrinite*
- [3] Taylor G.H., Teichmüller M., Davis A., Diessel C.F.K., Littke R., Robert P. *Organic petrology*. Borntraeger, Berlin, Stuttgart, 1998, 704 p.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK